

INTERNATIONAL STANDARD

**Electrical installations in ships –
Part 376: Cables for control and instrumentation circuits 150/250 V (300 V)**

IECNORM.COM : Click to view the full PDF of IEC 60092-376:2017



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2017 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

IECNORM.COM : Click to view the full text of IEC 6002-316:2017

INTERNATIONAL STANDARD

**Electrical installations in ships –
Part 376: Cables for control and instrumentation circuits 150/250 V (300 V)**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 47.020.60

ISBN 978-2-8322-4321-3

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	4
1 Scope and object	6
2 Normative references	6
3 Terms and definitions	7
4 General requirements	7
4.1 Rated voltage	7
4.2 Markings	8
4.2.1 Indication of origin and voltage identification	8
4.2.2 Continuity of marking	8
4.2.3 Core identification	8
5 Constructional requirements	8
5.1 General description	8
5.1.1 Overview	8
5.1.2 Unarmoured single- or double-sheathed cable	9
5.1.3 Armoured single-sheathed cable with outer sheath only	9
5.1.4 Armoured double-sheathed cable with inner and outer sheath only	9
5.1.5 Armoured single-sheathed cable with inner sheath only	9
5.2 Conductors	10
5.3 Insulation	10
5.3.1 Material	10
5.3.2 Application	10
5.3.3 Thickness of insulation	10
5.4 Cabling	11
5.4.1 General	11
5.4.2 Core assembly	11
5.4.3 Forming pair, triple or quad units	11
5.4.4 Fillers	11
5.4.5 Number of cores, pair, triple or quad units	12
5.5 Inner covering	12
5.5.1 General	12
5.5.2 Thickness of inner covering	12
5.6 Screen	12
5.6.1 Individual screen	12
5.6.2 Collective electrostatic screen	13
5.7 Inner sheath	14
5.7.1 Material	14
5.7.2 Application	14
5.7.3 Thickness of inner sheath	14
5.8 Braid armour	15
5.8.1 General	15
5.8.2 Braid wire diameter	15
5.8.3 Coverage density	15
5.8.4 Application of the armour	15
5.9 Outer sheath	15
5.9.1 Material	15
5.9.2 Application	16

5.9.3	Thickness of outer sheath	16
5.9.4	Colour of outer sheath	16
6	Tests – methods and requirements	16
Annex A (informative)	Core identification	20
Annex B (informative)	Identification of cores of multicore cables	21
B.1	Inscription	21
B.2	Arrangement of the marks	21
B.3	Spacing and dimensions of the marks	21
B.4	Appearance of inscription	22
Annex C (informative)	Number of cores, pair, triple or quad units	23
C.1	Number of cores	23
C.2	Number of pair, triple or quad units	23
Bibliography		24
Figure B.1	– Arrangement of the marks	21
Table 1	– Electrical resistance of conductors	10
Table 2	– Insulation thickness	11
Table 3	– Thickness of inner covering	12
Table 4	– Requirements of drain wire	13
Table 5	– Tests applicable to all cables	17
Table 6	– Additional tests required for halogen-free cables	18
Table 7	– Additional test required for low smoke cables	19
Table 8	– Additional tests required for fire resistant cables	19
Table 9	– Additional tests required for specific performances	19
Table A.1	– Preferred colour code for single unit cables	20
Table B.1	– Dimensions of the marks	22

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ELECTRICAL INSTALLATIONS IN SHIPS –**Part 376: Cables for control and instrumentation
circuits 150/250 V (300 V)****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60092-376 has been prepared by subcommittee 18A: Electric cables for ships and mobile and fixed offshore units, of IEC technical committee 18: Electrical installations of ships and of mobile and fixed offshore units.

This third edition of IEC 60092-376 cancels and replaces the second edition published in 2003, of which it constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) new structure in line with IEC 60092-353 and IEC 60092-354;
- b) requirements and test methods have been divided in several tables for clarification (enhanced cold properties, oil resistance or resistance to drilling fluids) and have been aligned to IEC 60092-350;

c) the new testing methods for fire resistant cables are referenced in this document.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
18A/404/FDIS	18A/409/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60092 series, published under the general title *Electrical installations in ships*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IECNORM.COM : Click to view the full PDF of IEC 60092-376:2017

ELECTRICAL INSTALLATIONS IN SHIPS –

Part 376: Cables for control and instrumentation circuits 150/250 V (300 V)

1 Scope and object

This part of IEC 60092 is applicable to screened and unscreened cables for control and instrumentation circuits on ships and offshore units. The cables have extruded solid insulation with a voltage rating of 150/250V (300V) (see Clause 4) and are intended for fixed installations.

The various types of cables are given in Clause 5. The constructional requirements and test methods are aligned with those indicated in IEC 60092-350, unless otherwise specified in this document.

The object of this document is

- to standardise cables whose safety and reliability are ensured when they are installed in accordance with the requirements of IEC 60092-352,
- to lay down standard manufacturing requirements and characteristics of such cables directly or indirectly bearing on safety, and
- to specify test methods for checking conformity with those requirements.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-461, *International Electrotechnical Vocabulary – Part 461: Electric cables*

IEC 60092-350:2014, *Electrical installations in ships – Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications*

IEC 60092-352, *Electrical installations in ships – Part 352: Choice and installation of electrical cables*

IEC 60092-360:2014, *Electrical installations in ships – Part 360: Insulating and sheathing materials for shipboard and offshore units, power, control, instrumentation and telecommunication cables*

IEC 60331-1, *Tests for electric cables under fire conditions – Circuit integrity – Part 1: Test method for fire with shock at a temperature of at least 830 °C for cables of rated voltage up to and including 0,6/1,0 kV and with an overall diameter exceeding 20 mm*

IEC 60331-2, *Tests for electric cables under fire conditions – Circuit integrity – Part 2: Test method for fire with shock at a temperature of at least 830 °C for cables of rated voltage up to and including 0,6/1,0 kV and with an overall diameter not exceeding 20 mm*

IEC 60331-21, *Tests for electric cables under fire conditions – Circuit integrity – Part 21: Procedures and requirements – Cables of rated voltage up to and including 0,6/1,0 kV*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60332-3-22, *Tests on electric cables under fire conditions – Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category A*

IEC 60445, *Basic and safety principles for man-machine interface, marking and identification – Identification of equipment terminals, conductor terminations and conductors*

IEC 60684-2, *Flexible insulating sleeving – Part 2: Methods of test*

IEC 60754-1, *Test on gases evolved during combustion of materials from cables – Part 1: Determination of the halogen acid gas content*

IEC 60754-2, *Test on gases evolved during combustion of materials from cables – Part 2: Determination of acidity (by pH measurement) and conductivity*

IEC 61034-2, *Measurement of smoke density of cables burning under defined conditions – Part 2: Test procedure and requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60092-350 and IEC 60050-461 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 General requirements

4.1 Rated voltage

The standard method of designating the rated voltages of cables covered by this document shall take the form $U_o/U (U_m)$,

where

- U_o is the rated power-frequency voltage between phase conductor and earth or metallic screen, for which the cable is designed;
- U is the rated power-frequency voltage between phase conductors for which the cable is designed;
- U_m is the maximum value of the "highest system voltage" for which the equipment (including cable) may be used (see IEC 60038).

All voltages are given as RMS values.

The standard rated voltages $U_o/U (U_m)$ of the cables considered in this document are:

$$U_o/U (U_m) = 150 \text{ V}/250 \text{ V} (300 \text{ V}) \text{ AC}$$

For 150/250 (300) V cables, DC voltage up to a maximum of 1,5 times the AC voltage may be used provided that the voltage to earth does not exceed 250 V.

NOTE When circuits are to be supplied from a low impedance source, attention is drawn to IEC 60092-353 for 600/1000 V cables having a minimum conductor size of 1,5 mm².

4.2 Markings

4.2.1 Indication of origin and voltage identification

Cables shall comply with 4.1.3 of IEC 60092-350:2014 with respect to:

- indication of origin;
- rated voltage and cable construction (number of cores and cross sectional area of the construction);
- continuity of marking;
- durability/legibility.

4.2.2 Continuity of marking

The marking is deemed to be continuous if the distance between the end of any marking and the beginning of the next does not exceed

- 550 mm if the marking is on the outer surface of the cable, and
- 275 mm in all other cases.

4.2.3 Core identification

4.2.3.1 General

Cable cores shall be clearly identified by either colours or numbers.

4.2.3.2 Coloured cores

The core colours shall be in accordance with IEC 60445.

NOTE Annex A gives details of preferred colour code.

4.2.3.3 Numbered cores – multicore cables

Identification should be made by inscription of numbers on each core starting from the centre beginning with 1 in accordance with Annex B.

4.2.3.4 Unit identification

When requested by the purchaser, identification of the individual units of multiunit cables is permitted by the use of tape(s) marked with numbers.

5 Constructional requirements

5.1 General description

5.1.1 Overview

Shipboard and offshore cables for fixed installations shall be single or multicore cables generally constructed as follows.

5.1.2 Unarmoured single- or double-sheathed cable

- copper conductor, see 5.2;
- insulation, see 5.3;
- cabling (for multicore cables), see 5.4;
- inner covering (optional, but mandatory when a braided electrostatic screening is applied over the core lay-up), see 5.5;
- electrostatic screening (optional), see 5.6;
- inner sheath (optional), see 5.7;
- outer sheath applied as either one or two layer systems, see 5.9.

5.1.3 Armoured single-sheathed cable with outer sheath only

- copper conductor, see 5.2;
- insulation, see 5.3;
- cabling (for multicore cables), see 5.4;
- inner covering below electrostatic screening (optional, but mandatory when a braided electrostatic screening is applied over the core lay-up), see 5.5;
- electrostatic screening (optional), see 5.6;
- inner covering (optional, but mandatory in case of a braid armour of galvanised steel wires in which case the inner covering shall be extruded), see 5.5;
- braid armour, see 5.8;
- outer sheath applied as either one or two layer systems, see 5.9.

5.1.4 Armoured double-sheathed cable with inner and outer sheath only

- copper conductor, see 5.2;
- insulation, see 5.3;
- cabling (for multicore cables), see 5.4;
- inner covering (optional, but mandatory when a braided electrostatic screening is applied over the core lay-up), see 5.5;
- electrostatic screening (optional), see 5.6;
- inner sheath, see 5.7;
- braid armour, see 5.8;
- outer sheath applied as either one or two layer systems, see 5.9.

5.1.5 Armoured single-sheathed cable with inner sheath only

- copper conductor, see 5.2;
- insulation, see 5.3;
- cabling (for multicore cables), see 5.4;
- inner covering (optional, but mandatory when a braided electrostatic screening is applied over the core lay-up), see 5.5;
- electrostatic screening (optional), see 5.6;
- inner sheath, see 5.7;
- braid armour, see 5.8.

Cables for installation in spaces where corrosion can occur, for example weather decks, wet locations, battery compartments, refrigeration rooms, should have an outer sheath over the braid, unless the braid itself is corrosion-resistant.

5.2 Conductors

The material, metal coating, separator, class and form of the conductors shall be in accordance with IEC 60092-350 and shall be circular Class 2 or Class 5 constructions of cross-sectional area 0,50 mm², 0,75 mm², 1,0 mm², 1,5 mm² or 2,5 mm².

NOTE The preferred conductor sizes are 0,75 mm² and 1,5 mm².

Conductor resistance shall be in accordance with Table 1.

Table 1 – Electrical resistance of conductors

Nominal cross-section mm ²	Maximum DC resistance for class 2 stranding		Maximum DC resistance for class 5 stranding	
	of plain copper conductors Ω/km at 20°C	of tinned copper conductors Ω/km at 20°C	of plain copper conductors Ω/km at 20°C	of tinned copper conductors Ω/km at 20°C
0,50	40,4	41,6	41,4	42,5
0,75	26,0	26,3	27,6	28,3
1,00	19,2	19,3	20,7	21,2
1,50	12,8	12,9	14,1	14,5
2,50	7,86	8,02	8,47	8,71

5.3 Insulation

5.3.1 Material

The insulating compounds and their designations shall be as given in IEC 60092-360, thus types EPR, HEPR, XLPE, HF 90 or S 95 shall be used.

The insulation system shall consist of one of the options (a) to (c) as listed in IEC 60092-350:2014, 4.3.1.

5.3.2 Application

The application shall be as detailed in IEC 60092-350:2014, 4.3.2.

5.3.3 Thickness of insulation

The thickness of the insulation shall be as specified in Table 2 hereinafter and meet the requirements of IEC 60092-350:2014, 4.3.3.

Table 2 – Insulation thickness

Nominal cross-sectional area of conductor	EPR HF 90 S 95	XLPE HEPR
mm ²	mm	mm
0,50	0,6	0,4
0,75	0,6	0,5
1,0	0,6	0,5
1,5	0,7	0,6
2,5	0,7	0,6

For cables which include inorganic tape(s) or varnished glass braid to confer fire resistance (limited circuit integrity), all the values of insulation given in this table shall be increased by 0,20 mm for subsequent consideration in the calculation of fictitious diameters.

NOTE For the calculation of fictitious diameters, see method outlined in Annex A and Annex B of IEC 60092-350.

5.4 Cabling

5.4.1 General

Cores of a multicore cable shall be laid up, and the interstices filled if necessary with fillers, inner covering or inner sheath (outer sheath in the case of unarmoured cables) according to IEC 60092-350:2014, 4.5.

5.4.2 Core assembly

- Cores laid up in concentric layers, unscreened, provided with an optional tape wrapping, finished to one of the constructions detailed in 5.1.2.
- Cores laid up in concentric layers, with an overall collective screen with drain wire, with an optional tape wrapping, finished to one of the constructions detailed in 5.1.3, 5.1.4 and 5.1.5.
- Cores twisted together to form a pair, triple or quad unit each unit being individually screened with drain wire, then cabled together, provided with an optional tape wrapping or optional tape screen, finished to one of the constructions detailed in 5.1.3, 5.1.4 and 5.1.5.
- Cores twisted to form a pair, triple or quad unit, these unscreened units cabled together with an overall collective screen with drain wire, provided with an optional tape wrapping, finished to one of the constructions detailed in 5.1.3, 5.1.4 and 5.1.5.

NOTE A non-hygroscopic binder tape or tapes can be applied over each layer.

5.4.3 Forming pair, triple or quad units

If the pair, triple or quad units are not individually screened then the lay length of the cores, in adjacent units, shall be selected so as to reduce inductive effects and cross-talk to a minimum and ensure that the cores of the pair, triple or quad units do not become disassociated by normal handling. The lay length of the cores individually or collectively screened shall not exceed 120 mm for sizes below 1,5 mm² and 150 mm for sizes 1,5 mm² and above.

NOTE A non-hygroscopic binder tape or tapes can be applied over each layer.

5.4.4 Fillers

Use of fillers is permitted, as necessary, to give the completed cable a substantially circular cross section. When used, they shall be composed of a crosslinked or non crosslinked elastomeric compound, a thermoplastic compound or natural or synthetic textiles. The fillers shall be non-hygroscopic and there shall be no harmful interactions between the constituents

of the filler and the insulation and/or the sheath and they shall be capable of being removed without damaging any other component in the cable. Alternatively, interstitial fillers may be applied integrally with the sheath of unarmoured cables or the inner sheath or inner covering of metal armoured cables.

5.4.5 Number of cores, pair, triple or quad units

Within practical physical limits any number of cores, pairs, triples or quads can be laid up to form a cable assembly, however Annex C gives recommended cable assemblies.

5.5 Inner covering

5.5.1 General

The inner covering, if any, may be extruded (mandatory below galvanized steel wire braid) or lapped. The relevant material and characteristics shall be in accordance with 4.6 of IEC 60092-350:2014.

5.5.2 Thickness of inner covering

The values of the (approximate) thickness of extruded inner covering for the calculation of fictitious diameters are given in Table 3.

Table 3 – Thickness of inner covering

Fictitious diameter over laid-up cores		Thickness of inner covering (approximate value)	
Above mm	Up to and including mm	Extruded mm	Lapped mm
-	25	1,0	0,1
25	35	1,2	0,1
35	45	1,4	0,1
45	60	1,6	0,1
60	-	1,8	0,1

NOTE For the calculation of fictitious diameter, see Annex A and Annex C of IEC 60092-350.

5.6 Screen

5.6.1 Individual screen

5.6.1.1 General

The screen, if any, shall be individually metallic screen of pair, triple or quad. It shall be in accordance with IEC 60092-350:2014, 4.4.2, and shall consist of one or more tapes, a braid or a combination of a braid with tape.

5.6.1.2 Metal/polymer tape

The laminated electrostatic screening tape shall be applied with the metallic side in electrical contact with a drain wire. The minimum overlap of the laminated tape shall be 25 % of its total width, to ensure coverage in case of bending the cable. The laminated tape shall be either aluminium bonded to polymeric material having a minimum thickness of aluminium of 0,008 mm and a minimum thickness of polymer of 0,010 mm, or copper bonded to polymer having a minimum thickness of copper of 0,018 mm and a minimum thickness of polymer of 0,023 mm.

The drain wire shall be composed of a number of strands of tinned annealed copper wires in the case of aluminium laminate tape and either plain or tinned annealed copper wires in the case of copper laminate tape. The drain wire shall have a maximum resistance in accordance with Table 4.

5.6.1.3 Braided screen

When an individual braided screened pair, triple or quad construction is required, each pair, triple or quad shall have a non-hygroscopic separator tape applied over the cores and under the braid. The nominal overlap shall not be less than 25 %.

The braid shall be either plain or metal coated copper wires; the minimum diameter of the braid wire shall be

- 0,15 mm for fictitious cable diameters under the braid less than or equal to 9 mm, and
- 0,2 mm for fictitious cable diameters under the braid greater than 9 mm.

Joints in the braiding wires shall be soldered, twisted or woven in and the complete braid shall not be welded. The braid shall be evenly applied.

The "filling factor" F of the braid shall be not less than 0,6 when calculated in accordance with the alternative method given in IEC 60092-350.

NOTE The percent coverage $K = (2F - F^2) \times 100$

The fictitious diameter under the braid is calculated by the method described in Annex A of IEC 60092-350:2014.

When required, to aid termination, a drain wire may be applied under and in direct contact with the braid screen. The drain wire shall be composed of a number of strands of tinned or plain annealed copper wires. The drain wire shall have a maximum resistance in accordance with Table 4.

Table 4 – Requirements of drain wire

Nominal area of core conductor mm ²	Maximum drain wire resistance Ω/km
0,50	61,2
0,75	42,5
1,0	28,3
1,5	28,3
2,5	21,2

Polymer tape of either 0,023 mm or 0,050 mm nominal thickness shall be applied over the screen with a minimum overlap of 20 % of its total width.

5.6.2 Collective electrostatic screen

5.6.2.1 Metal/polymer tape

When collectively screened constructions are required, a laminated electrostatic screening tape shall be applied with the metallic side in electrical contact with the drain wire. The minimum overlap of the laminated tape shall be 25 % of its total width.

The laminated tape shall be either aluminium bonded to polymer having a minimum thickness of aluminium of 0,008 mm and a minimum thickness of polymer of 0,010 mm, or copper

bonded to polymer having a minimum thickness of copper of 0,018 mm and a minimum thickness of polymer of 0,023 mm.

The drain wire shall be composed of a number of strands of tinned annealed copper wires in the case of aluminium laminate tape and either plain or tinned annealed copper wires in the case of copper laminate tape. The drain wire shall have a maximum resistance in accordance with Table 4.

Alternatively a braid screen may be applied.

5.6.2.2 Braided screen

The braid shall be either plain or metal coated copper wires; the nominal diameter of the braid wire shall be

- 0,15 mm for fictitious cable diameters under the braid less than or equal to 9 mm, and
- 0,2 mm for fictitious cable diameters under the braid greater than 9 mm.

Joints in the braiding wires shall be soldered, twisted or woven in and the complete braid shall not be welded. The braid shall be evenly applied.

The "filling factor" F of the braid shall be not less than 0,6 when calculated in accordance with the alternative method given in IEC 60092-350.

NOTE The percent coverage $K = (2F - F^2) \times 100$

The fictitious diameter under the braid is calculated by the method described in Annex A of IEC 60092-350.

When required to aid termination, a drain wire may be applied under and in direct contact with the braid screen. The drain wire shall be composed of a number of strands of tinned or plain annealed copper wires. The drain wire shall have a maximum resistance in accordance with Table 4.

In the case of metal armour consisting of copper braid metal armour, this may also provide the function of a collective screen.

5.6.2.3 Application

The screen, if any, shall be applied over the inner covering in case of a braided or a metal/polymer tape screen (see 5.1.3, 5.1.4 and 5.1.5).

5.7 Inner sheath

5.7.1 Material

The inner sheathing compound and its designation shall be one of those given in Tables 5 or 7 of IEC 60092-360.

5.7.2 Application

The application shall be as detailed in IEC 60092-350:2014, 4.7.2.

5.7.3 Thickness of inner sheath

The thickness of the inner sheath is given as a function of the internal diameter of the sheath under consideration, the fictitious diameter being calculated by the method in IEC 60092-350:2014, Annex A and Annex C.

The formula is the following:

a) for unarmoured double sheathed cables (see 5.1.2):

$t_1 = 0,025 D + 0,6$ mm with a minimum thickness of 0,8 mm;

– where D is the fictitious diameter under the inner sheath

b) for armoured cables (see 5.1.4 and 5.1.5):

$t_1 = 0,04 D + 0,8$ mm with a minimum thickness of 1,0 mm;

– where D is the fictitious diameter under the inner sheath.

The thickness at any point shall satisfy the prescriptions given in 4.7.3 of IEC 60092-350:2014.

5.8 Braid armour

5.8.1 General

In this document, only metal braid armours are specified, the braid wires being of copper (plain or tinned), copper alloy (plain or tinned) or zinc coated (galvanized) steel.

Joints in the braiding wires shall be soldered, twisted or woven in and the complete braid shall not be jointed. The braid shall be evenly applied.

The armour may serve as a collective metallic screen (see 5.6).

NOTE In some countries, the use of an armour as an earthing collective metallic screen is prohibited for legal reasons.

5.8.2 Braid wire diameter

Irrespective of the metal used, the nominal diameter of the braid wire shall be

- 0,2 mm, as a minimum, for cables having fictitious diameter under the braid less than or equal to 10 mm,
- 0,3 mm, as a minimum, for cables having fictitious diameter under the braid larger than 10 mm and less than or equal to 30 mm, and
- 0,4 mm, as a minimum, for cables having fictitious diameter under the braid larger than 30 mm.

5.8.3 Coverage density

The coverage density of the braid shall be in accordance with IEC 60092-350:2014, 4.8.2.

NOTE In case the alternative method in accordance with IEC 60092-350:2014, 4.8.2 is used to evaluate the coverage density, the mean diameter of the braid to be used is the fictitious diameter under the braid plus two times the nominal diameter of the braiding wires.

5.8.4 Application of the armour

The armour shall be applied in such a way that it shall neither adhere to the inner covering or inner sheath nor to the outer sheath.

5.9 Outer sheath

5.9.1 Material

The outer sheathing compound and its designation shall be one of those given in IEC 60092-360.

5.9.2 Application

The application shall be as detailed in IEC 60092-350:2014, 4.9.2.

5.9.3 Thickness of outer sheath

The thickness of outer sheath is given as a function of the internal diameter of the sheath under consideration, the fictitious diameter being calculated by the method in IEC 60092-350:2014, Annex A and Annex C.

The formula is the following:

- c) for unarmoured or armoured single-sheathed cables (see 5.1.2 and 5.1.3):

$$t_1 = 0,04 D + 0,8 \text{ mm with a minimum thickness of } 1,0 \text{ mm}$$

where D is the fictitious diameter under the sheath

- d) for unarmoured double-sheathed cables (see 5.1.2):

$$t_2 = 0,025 D + 0,9 \text{ mm, with a minimum thickness of } 1,0 \text{ mm}$$

- e) for armoured double-sheathed cables (see 5.1.4):

$$t_2 = 0,025 D + 0,6 \text{ mm, with a minimum thickness of } 0,8 \text{ mm}$$

The thickness at any point shall satisfy the prescriptions given in 4.9.3 of IEC 60092-350:2014.

5.9.4 Colour of outer sheath

The outer sheath shall be coloured black or grey, or, for fire resistant cables orange, unless otherwise specified by the purchaser at the time of ordering.

6 Tests – methods and requirements

The tests shall be carried out according to Table 5 to Table 9 where applicable.

Table 5 – Tests applicable to all cables

Test	Applicability – all types of cable unless otherwise stated	Status	Method – clause number given in IEC 60092-350:2014	Requirement – as in IEC 60092-350 unless otherwise stated
Measurement of electrical resistance of conductors and drain wires		Routine	5.2.2	Table 1
Voltage test		Routine	5.2.3	-
Voltage test on sheath	Armoured cables	Routine	5.2.3.4	-
Insulation resistance test		Sample	6.9	-
Insulation resistance constant test		Type	7.2.1	IEC 60092-360:2014, Table 3
Screen insulation resistance, the insulation resistance between individually screened pair triple or quad units and any collective screening		Sample	6.9	$\geq 1 \text{ M}\Omega \cdot \text{km}$
The insulation resistance between any screen and the armour for armoured cables		Sample	6.9	$\geq 0,25 \text{ M}\Omega \cdot \text{km}$
Conductor examination		Sample and Type	6.4	-
Check of cable dimensions		Sample and Type		
– Thickness of insulation			6.5 and 8.2	-
– Thickness of non-metallic sheaths (excluding inner coverings)			6.6 and 8.3	-
– External diameter			6.7	-
Hot set test	HEPR, EPR, XLPE, HF 90, S 95 insulations and SH, SE, SHF2 sheaths	Sample	6.8	IEC 60092-360
Coverage density of braid	Braid armoured cables and/or braid screened cable	Type	4.8.2	
Insulation resistance measurement at maximum rated temperature		Type	7.2.2	IEC 60092-360
Mutual capacitance		Type	7.5	-
Inductance to resistance ratio		Type	7.6	-
Mechanical properties of insulation before and after ageing		Type	8.4	IEC 60092-360
Mechanical properties of sheath before and after ageing		Type	8.5	IEC 60092-360

Test	Applicability – all types of cable unless otherwise stated	Status	Method – clause number given in IEC 60092-350:2014	Requirement – as in IEC 60092-350 unless otherwise stated
Additional ageing compatibility test		Type	8.6	IEC 60092-360
Loss of mass test	PVC ST2 sheath	Type	8.7	IEC 60092-360
Behaviour at high temperature	PVC ST2 and SHF1 sheaths	Type	8.8	IEC 60092-360
Behaviour at low temperatures	PVC ST2, SHF1 and SHF2 sheaths	Type	8.9	IEC 60092-360
Test for coating of copper wires		Type	8.11	
Galvanizing test		Type	8.12	
Resistance to cracking heat shock	PVC ST2 and SHF1 sheaths	Type	8.13	IEC 60092-360
Ozone resistance	HEPR, EPR, HF90 insulations and SH, SE, SHF2 sheaths	Type	8.14	IEC 60092-360
Hot oil immersion	SE, SH and SHF2 sheaths	Type	8.15.1	IEC 60092-360
Fire-retardant tests: IEC 60332-1-2 and IEC 60332-3-22		Type	8.17.1 8.17.2	IEC 60332-1-2 and IEC 60332-3-22 in which case cables shall be installed in touching configuration on the front of the ladder.
Determination of hardness	HEPR insulation	Type	8.18	IEC 60092-360
Determination of modulus of elasticity	HEPR insulation	Type	8.19	IEC 60092-360
Durability of marking		Type	8.20	The marking shall remain legible following the test as given in 8.20 of IEC 60092-350:2014.

Table 6 – Additional tests required for halogen-free cables

Test	Status	Method – clause number given in IEC 60092-350:2014	Requirement – as in IEC 60092-350 unless otherwise stated
Acid gas emission	Type	8.17.4	IEC 60754-1
pH and conductivity	Type	8.17.5	IEC 60754-2
Fluorine content test	Type	8.17.6	IEC 60684-2

Table 7 – Additional test required for low smoke cables

Test	Status	Method – clause number given in IEC 60092-350:2014	Requirement – as in IEC 60092-350 unless otherwise stated
Smoke emission test for cables insulated and sheathed with halogen-free materials. When tested according to IEC 61034-2	Type	8.17.3	The test is satisfactory for the finished cables if the levels of light transmittance exceeds 60 % throughout the test
NOTE The smoke emission test is in general applicable to halogen-free cables. See also Table 6.			

Table 8 – Additional tests required for fire resistant cables

Test	Status	Method – clause number given in IEC 60092-350:2014	Requirement – as in IEC 60092-350 unless otherwise stated
Test for fire resistance (limited circuit integrity)	Type	8.17.7	The test shall be carried out in accordance with IEC 60331-21 or IEC 60331-1 or IEC 60331-2 and the minimum time to failure shall be 90 min
NOTE The test apparatus for the test procedure defined in IEC 60331-21 is detailed in IEC 60331-11.			

Table 9 – Additional tests required for specific performances

Test	Status	Method – clause number given in IEC 60092-350:2014	Requirement – as in IEC 60092-350 unless otherwise stated
Special test for low temperature behaviour	Type	8.10	
Enhanced hot oil immersion	Type	8.15.2	IEC 60092-360
Drilling fluid test	Type	8.16	IEC 60092-360

Annex A

(informative)

Core identification

An example of the preferred colour code for single unit cables is given in Table A.1. In the case of multiunit cables, the additional identification of the same number printed on the insulation of each core within the same unit is also required.

For arrangement, appearance, spacing and dimensions of the marks, see Annex B.

Table A.1 – Preferred colour code for single unit cables

Unit element	Wire a	Wire b	Wire c	Wire d
Pair unit	Black or blue	White	-	-
Triple unit	Black or blue	White	Red	-
Quad unit	Black or blue	White	Red	Blue or black
Other suitable colour codes may be supplied by agreement between the purchaser and supplier.				