

INTERNATIONAL STANDARD

**Polyvinyl chloride insulated cables of rated voltages up to and including
450/750 V –
Part 1: General requirements**

IECNORM.COM : Click to view the full PDF of IEC 60227-1:2024



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2024 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IECNORM.COM : Click to view the full text of IEC 60027-1:2024

INTERNATIONAL STANDARD

**Polyvinyl chloride insulated cables of rated voltages up to and including
450/750 V –
Part 1: General requirements**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.060.20

ISBN 978-2-8322-8245-8

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	8
4 Marking	9
4.1 Indication of origin and cable identification.....	9
4.1.1 General	9
4.1.2 Continuity of marks.....	9
4.2 Durability	10
4.3 Legibility	10
5 Core identification	10
5.1 General.....	10
5.2 Core identification by colours	10
5.2.1 General requirements	10
5.2.2 Colour scheme	10
5.2.3 Colour combination green-and-yellow	10
5.3 Core identification by numbers.....	11
5.3.1 General requirements	11
5.3.2 Preferred arrangement of marking	11
5.3.3 Durability	11
6 General requirements for the construction of cables	11
6.1 Conductors	11
6.1.1 Material	11
6.1.2 Construction	12
6.1.3 Check on construction	12
6.1.4 Electrical resistance	12
6.2 Insulation	12
6.2.1 Material	12
6.2.2 Application to the conductor	12
6.2.3 Thickness	12
6.2.4 Mechanical properties before and after ageing	13
6.3 Filler	15
6.3.1 Material	15
6.3.2 Application.....	15
6.4 Extruded inner covering	15
6.4.1 Material	15
6.4.2 Application.....	16
6.4.3 Thickness	16
6.5 Sheath	16
6.5.1 Material	16
6.5.2 Application.....	16
6.5.3 Thickness	16
6.5.4 Mechanical properties before and after ageing	16
6.6 Tests on completed cables.....	19
6.6.1 Electrical properties.....	19

6.6.2	Overall dimensions	20
6.6.3	Mechanical strength of flexible cables	20
6.6.4	Flame retardance	21
7	Guidance on the use of cables.....	21
Annex A (normative)	Code designations	22
Bibliography		23
Figure 1	– Arrangement of marking by numbers	11
Table 1	– Requirements for the non-electrical tests for polyvinyl chloride (PVC) insulation	13
Table 2	– Requirements for the non-electrical test for polyvinyl chloride (PVC) sheaths	17
Table 3	– Requirements for electrical tests for PVC insulated cables	19

IECNORM.COM : Click to view the full PDF of IEC 60227-1:2024

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**POLYVINYL CHLORIDE INSULATED CABLES OF
RATED VOLTAGES UP TO AND INCLUDING 450/750 V –****Part 1: General requirements****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 60227-1 has been prepared by IEC technical committee 20: Electric cables. It is an International Standard.

This fourth edition cancels and replaces the third edition published in 2007. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the reference to tests according to IEC 60227-2 has been withdrawn and replaced with a reference to IEC 63294;
- b) normative references have been updated.

The text of this International Standard is based on the following documents:

Draft	Report on voting
20/2145/FDIS	20/2153/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 60227 series, published under the general title *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IECNORM.COM : Click to view the full PDF of IEC 60227-1:2024

INTRODUCTION

The IEC 60227 series, published under the general title *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V*, consists of the following parts:

IEC 60227-1: General requirements;

IEC 60227-2: Test methods (withdrawn and replaced by IEC 63294);

IEC 60227-3: Non-sheathed cables for fixed wiring;

IEC 60227-4: Sheathed cables for fixed wiring;

IEC 60227-5: Flexible cables (cords);

IEC 60227-6: Lift cables and cables for flexible connections;

IEC 60227-7: Flexible cables screened and unscreened with two or more conductors and of rated voltages up to and including 300/500 V.

This part of IEC 60227, when used in conjunction with each of the other parts of the IEC 60227 series, forms the complete standard for the type of cable specified in the specific part.

IECNORM.COM : Click to view the full PDF of IEC 60227-1:2024

POLYVINYL CHLORIDE INSULATED CABLES OF RATED VOLTAGES UP TO AND INCLUDING 450/750 V –

Part 1: General requirements

1 Scope

This part of IEC 60227 applies to rigid and flexible cables with insulation, and sheath if any, based on polyvinyl chloride, of rated voltages U_o/U up to and including 450/750 V used in power installations of nominal voltage not exceeding 450/750 V AC.

NOTE For some types of flexible cables the term "cord" is used.

The particular types of cables are specified in IEC 60227-3, IEC 60227-4, IEC 60227-5, IEC 60227-6 and IEC 60227-7. The code designations of these types of cables are provided in this document.

The test methods specified in this document, IEC 60227-3, IEC 60227-4, IEC 60227-5, IEC 60227-6 and IEC 60227-7 are given in IEC 63294, IEC 60332-1-2 and in the relevant parts of the IEC 60811 series.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60227-3, *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 3: Non-sheathed cables for fixed wiring*

IEC 60227-4, *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 4: Sheathed cables for fixed wiring*

IEC 60227-5, *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 5: Flexible cables (cords)*

IEC 60227-6, *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 6: Lift cables and cables for flexible connections*

IEC 60227-7, *Polyvinyl chloride insulated cables of rated voltages up to and including 450/750 V – Part 7: Flexible cables screened and unscreened with two or more conductors and of rated voltages up to and including 300/500 V*

IEC 60228, *Conductors of insulated cables*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60811-401:2012, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 401: Miscellaneous tests – Thermal ageing methods – Ageing in an air oven*
IEC 60811-401:2012/AMD1:2017

IEC 60811-404, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 404: Miscellaneous tests – Mineral oil immersion tests for sheaths*

IEC 60811-405, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 405: Miscellaneous tests – Thermal stability test for PVC insulations and PVC sheaths*

IEC 60811-409, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 409: Miscellaneous tests – Loss of mass test for thermoplastic insulations and sheaths*

IEC 60811-501, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 501: Mechanical tests – Tests for determining the mechanical properties of insulating and sheathing compounds*

IEC 60811-504, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 504: Mechanical tests – Bending tests at low temperature for insulation and sheaths*

IEC 60811-505, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Elongation at low temperature for insulations and sheaths*

IEC 60811-506, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 506: Mechanical tests – Impact test at low temperature for insulations and sheaths*

IEC 60811-508, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 508: Mechanical tests – Pressure test at high temperature for insulation and sheaths*

IEC 60811-509, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 509: Mechanical tests – Test for resistance of insulations and sheaths to cracking (heat shock test)*

IEC 62440, *Electric cables with a rated voltage not exceeding 450/750 V – Guide to use*

IEC 63294:2021, *Test methods for electric cables with rated voltages up to and including 450/750 V*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

polyvinyl chloride compound

PVC

combination of materials suitably selected, proportioned and treated, of which the characteristic constituent is the plastomer polyvinyl chloride or one of its copolymers

Note 1 to entry: PVC also designates compounds containing both polyvinyl chloride and certain of its polymers.

3.2

type of compound

category in which a compound is placed according to its properties, as determined by specific tests

Note 1 to entry: The type designation is not directly related to the composition of the compound.

3.3

rated voltage

reference voltage for which the cable is designed and which serves to define the electrical tests

Note 1 to entry: The rated voltage is expressed by the combination of two values U_0/U , expressed in volts:

U_0 being the RMS value between any insulated conductor and "earth" (metal covering of the cable or the surrounding medium);

U being the RMS value between any two-phase conductors of a multicore cable or of a system of single-core cables.

In an alternating current system, the rated voltage of a cable shall be at least equal to the nominal voltage of the system for which it is intended.

This condition applies both to the value U_0 and to the value U .

In a direct current system, the rated nominal voltage between conductor and "earth" shall be not higher than 1,5 times the rated AC value of U_0 .

Note 2 to entry: The operating voltage of a system can permanently exceed the nominal voltage of such a system by 10 %. A cable can be used at a 10 % higher operating voltage than its rated voltage if the latter is at least equal to the nominal voltage of the system.

3.4

code designation

code used to designate a specific type of cable

Note 1 to entry: The code designations for the cables specified in the IEC 60227 series are listed in Annex A.

4 Marking

4.1 Indication of origin and cable identification

4.1.1 General

Cables shall be provided with an indication of the manufacturer, which shall be either an identification thread or a repetitive marking of the manufacturer's name or trademark.

Cables for use at a conductor temperature exceeding 70 °C shall also be marked either with the code designation according to Annex A or with the maximum conductor temperature.

Marking may be by printing or by reproduction in relief on or in the insulation or sheath.

4.1.2 Continuity of marks

Each specified mark shall be regarded as continuous if the distance between the end of the mark and the beginning of the next identical mark does not exceed

- 550 mm if the marking is on the outer sheath of the cable;
- 275 mm if the marking is
 - a) on the insulation of an unsheathed cable;
 - b) on the insulation of a sheathed cable;
 - c) on a tape within a sheathed cable.

4.2 Durability

Printed markings shall be durable. Compliance with this requirement shall be checked by the test given in IEC 63294:2021, 6.1.

4.3 Legibility

All markings shall be legible.

The colours of the identification threads shall be easy to recognize or easily made recognizable, if necessary, by cleaning with petrol or other suitable solvent.

5 Core identification

5.1 General

Each core shall be identified as follows:

- in cables having up to and including five cores by colour, see 5.2;
- in cables having more than five cores by number, see 5.3.

NOTE The colour scheme, and in particular the scheme for rigid multicore cables, is under consideration.

5.2 Core identification by colours

5.2.1 General requirements

Identification of the cores of a cable shall be achieved by the use of coloured insulation or other suitable method.

Each core of a cable shall have only one colour, except the core identified by the colour combination green-and-yellow.

The colours green and yellow, when not in combination, shall not be used for any multicore cable.

NOTE The colours red and white are preferably avoided.

5.2.2 Colour scheme

The preferred colour scheme for flexible cables and single-core cables is:

- single-core cable: no preferred colour scheme;
- two-core cable: no preferred colour scheme;
- three-core cable: either green-and-yellow, blue, brown, or, brown, black, grey;
- four-core cable: either green-and-yellow, brown, black, grey, or blue, brown, black, grey;
- five-core cable: either green-and-yellow, blue, brown, black, grey, or blue, brown, black, grey, black.

The colours shall be clearly identifiable and durable. Durability shall be checked by the test given in IEC 63294:2021, 6.1.

5.2.3 Colour combination green-and-yellow

The distribution of the colours for the core coloured green-and-yellow shall comply with the following condition: for every 15 mm length of core, either one of the colours green and yellow shall cover at least 30 % and not more than 70 % of the surface of the core, the other colour covering the remainder.

NOTE Information on the use of the colours green-and-yellow and blue: It is understood that the colours green and yellow, when they are combined as specified above, are recognized exclusively as a means of identification of the core intended for use as earth connection or similar protection, and that the colour blue is intended for the identification of the core intended to be connected to neutral. If, however, there is no neutral, blue can be used to identify any core except the earthing or protective conductor.

5.3 Core identification by numbers

5.3.1 General requirements

The insulation of the cores shall be of the same colour and numbered sequentially, except for the core coloured green-and-yellow, if one is included.

The green-and-yellow core, if any, shall comply with the requirement of 5.2.3 and shall be in the outer layer.

The numbering shall start with number 1 in the inner layer.

The numbers shall be printed in Arabic numerals on the outer surfaces of the cores. All the numbers shall be of the same colour, which shall contrast with the colour of the insulation. The numerals shall be legible.

5.3.2 Preferred arrangement of marking

The numbers shall be repeated, at regular intervals along the core, consecutive numbers being inverted in relation to each other.

When the number is a single numeral, a dash shall be placed underneath it. If the number consists of two numerals, these shall be positioned one below the other and a dash placed below the lower numeral. The spacing d between consecutive numbers shall not exceed 50 mm.

The arrangement of the marks is shown in Figure 1 below.




Figure 1 – Arrangement of marking by numbers

5.3.3 Durability

Printed numerals shall be durable. Compliance with this requirement shall be checked by the test given in IEC 63294:2021, 6.1.

6 General requirements for the construction of cables

6.1 Conductors

6.1.1 Material

The conductors shall consist of annealed copper, except for the wires of tinsel cords, for which a copper alloy may be used. The wires may be plain or tinned.

6.1.2 Construction

The maximum diameters of the wires of flexible conductors – other than the conductors of tinsel cords – and the minimum number of the wires of rigid conductors shall be in accordance with IEC 60228.

The classes of the conductors relevant to the various types of cables are given in the particular standards (see IEC 60227-3, IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7).

Conductors of cables for fixed installations shall be circular solid, circular stranded or compacted circular stranded conductors.

For tinsel cords each conductor shall comprise a number of strands or groups of strands, twisted together, each strand being composed of one or more flattened wires of copper or copper alloy, helically wound on a thread of cotton, polyamide or similar material.

6.1.3 Check on construction

Compliance with the requirements of 6.1.1 and 6.1.2, including the requirements of IEC 60228, shall be checked by inspection and by measurement.

6.1.4 Electrical resistance

For cables – other than tinsel cords – the resistance of each conductor at 20 °C shall be in accordance with the requirements of IEC 60228 for the given class of the conductor.

Compliance shall be checked by the test given in IEC 63294:2021, 5.1.

6.2 Insulation

6.2.1 Material

The insulation shall be polyvinyl chloride compound of the type specified for each type of cable in the particular standards (see IEC 60227-3, IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7):

- type PVC/C in the case of cables for fixed installation;
- type PVC/D in the case of flexible cables;
- type PVC/E in the case of heat-resistant cables for internal wiring.

The test requirements for these compounds are specified in Table 1.

The maximum operating temperatures for cables insulated with any of the above types of compound and covered by the particular standards (see IEC 60227-3, IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7) are given in those publications.

6.2.2 Application to the conductor

The insulation shall be so applied that it fits closely on the conductor, but for cables other than tinsel cords, it shall be possible to remove it without damage to the insulation itself, to the conductor or to the tin coating if any. Compliance shall be checked by inspection and by manual test.

6.2.3 Thickness

The mean value of the thickness of insulation shall be not less than the specified value for each type and size of cable shown in the tables of the particular standards (IEC 60227-3, IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7).

However, the thickness at any point may be less than the specified value provided that the difference does not exceed 0,1 mm + 10 % of the specified value.

Compliance shall be checked by the test given in IEC 63294:2021, 6.2.

6.2.4 Mechanical properties before and after ageing

The insulation shall have adequate mechanical strength and elasticity within the temperature limits to which it may be exposed in normal use.

Compliance shall be checked by carrying out the tests specified in Table 1.

The applicable test methods and the results to be obtained are specified in Table 1.

Table 1 – Requirements for the non-electrical tests for polyvinyl chloride (PVC) insulation

1	2	3	4	5	6	7
Reference No.	Test	Unit	Type of component			Test method described in
			PVC/C	PVC/D	PVC/E	
1	Tensile strength and elongation at break					IEC 60811-501
1.1	Properties in the state as delivered					
1.1.1	Values to be obtained for the tensile strength:					
	– median, min.	N/mm ²	12,5	10	15	
1.1.2	Values to be obtained for the elongation at break:					
	– median, min.	%	125	150	150	
1.2	Properties after ageing in air oven					IEC 60811-401 and IEC 60811-501
1.2.1	Ageing conditions:					
	– temperature	°C	80 ± 2	80 ± 2	135 ± 2	
	– duration of treatment	h	7 × 24	7 × 24	10 × 24	
1.2.2	Values to be obtained for the tensile strength:					
	– median, min.	N/mm ²	12,5	10	15	
	– variation ^a , max.	%	±20	±20	±25	
1.2.3	Values to be obtained for the elongation at break:					
	– median, min.	%	125	150	150	
	– variation ^a , max.	%	±20	±20	±25	
2	Loss of mass test					IEC 60811-409
2.1	Ageing conditions:					
	– temperature	°C	80 ± 2	80 ± 2	115 ± 2	
	– duration of treatment	h	7 × 24	7 × 24	10 × 24	
2.2	Values to be obtained for the loss of mass, max.	mg/cm ²	2	2	2	

1	2	3	4	5	6	7
Reference No.	Test	Unit	Type of component			Test method described in
			PVC/C	PVC/D	PVC/E	
3	Compatibility test ^b					IEC 60811-401
3.1	Ageing conditions	°C	80 ± 2	80 ± 2	100 ± 2	
		h	7 × 24	7 × 24	10 × 24	
3.2	Mechanical properties after ageing Values to be obtained		As in reference Nos. 1.2.2 and 1.2.3			
4	Heat shock test					IEC 60811-509
4.1	Test conditions:					
	– temperature	°C	150 ± 2	150 ± 2	150 ± 2	
	– duration of treatment	h	1	1	1	
4.2	Results to be obtained		Absence of cracks			
5	Pressure test at high temperature					IEC 60811-508
5.1	Test conditions:					
	– force exercised by the blade		See IEC 60811-508			
	– duration of heating under load		See IEC 60811-508			
	– temperature	°C	80 ± 2	70 ± 2	90 ± 2	
5.2	Results to be obtained:					
	– median of the depth of penetration, max.	%	50	50	50	
6	Bending test at low temperature					IEC 60811-504
6.1	Test conditions:					
	– temperature	°C	–15 ± 2	–15 ± 2	–15 ± 2	
	– period of application of low temperature		See IEC 60811-504			
6.2	Results to be obtained		Absence of cracks			
7	Elongation test at low temperature					IEC 60811-505
7.1	Test conditions:					
	– temperature	°C	–15 ± 2	–15 ± 2	–	
	– period of application of low temperature		See IEC 60811-505			
7.2	Result to be obtained:					
	– elongation without break, min.	%	20	20	–	
8	Impact test at low temperature ^c					IEC 60811-506
8.1	Test conditions:					
	– temperature	°C	–15 ± 2	–15 ± 2	–	
	– period of application of low temperature		See IEC 60811-506			
	– mass of hammer		See IEC 60811-506			
8.2	Results to be obtained		See IEC 60811-506			

6.4.2 Application

The extruded inner covering shall surround the cores and may penetrate the spaces between them giving the assembly a practical circular shape. The extruded inner covering shall not adhere to the cores.

For each type of cable, the particular standards (IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7) indicate whether that cable includes an extruded inner covering or not, or whether the outer sheath may penetrate between the cores, thus forming a filling.

6.4.3 Thickness

No measurement is required for the extruded inner covering, unless otherwise specified in the particular standards (IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7).

6.5 Sheath

6.5.1 Material

The sheath shall be polyvinyl chloride compound of the type specified for each type of cable in the particular standards (see IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7):

- type PVC/ST4 in the case of cables for fixed installations;
- type PVC/ST5 in the case of flexible cables;
- type PVC/ST9 in the case of oil-resistant flexible cables;
- type PVC/ST10 in the case of cables sheathed with a 90 °C polyvinyl chloride compound.

The test requirements for these compounds are specified in Table 2.

6.5.2 Application

The sheath shall be extruded in a single layer:

- a) on the core, in the case of single-core cables;
- b) on the assembly of cores and fillers or inner covering, if any, in the case of other cables.

The sheath shall not adhere to the cores. A separator, consisting of a film or tape, may be placed under the sheath.

In certain cases, indicated in the particular standards (IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7), the sheath may penetrate into the spaces between the cores, thus forming a filling (see 6.4.2).

6.5.3 Thickness

The mean value of the thickness shall not be less than the specified value for each type and size of cable shown in the tables of the particular standards (IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7).

However, the thickness at any place may be less than the specified value provided that the difference does not exceed 0,1 mm + 15 % of the specified value, unless otherwise specified.

Compliance shall be checked by the test given in IEC 63294:2021, 6.3.

6.5.4 Mechanical properties before and after ageing

The sheath shall have adequate mechanical strength and elasticity within the temperature limits to which it can be exposed in normal use.

Compliance shall be checked by carrying out the tests specified in Table 2.

The applicable test values and the results to be obtained are specified in Table 2.

Table 2 – Requirements for the non-electrical test for polyvinyl chloride (PVC) sheaths

1	2	3	4	5	6	7	8
Reference No.	Test	Unit	Type of compound				Test method described in
			PVC/ST4	PVC/ST5	PVC/ST9	PVC/ST10	
1	Tensile strength and elongation at break						IEC 60811-501
1.1	Properties in the state as delivered						
1.1.1	Values to be obtained for the tensile strength:						
	– median, min.	N/mm ²	12,5	10	10	10	
1.1.2	Values to be obtained for the elongation at break						
	– median, min.	%	125	150	150	150	
1.2	Properties after ageing in the air oven						
1.2.1	Ageing conditions:						IEC 60811-401
	– temperature	°C	80 ± 2	80 ± 2	80 ± 2	135 ± 2	
	– duration of treatment	h	7 × 24	7 × 24	7 × 24	7 × 24	
1.2.2	Values to be obtained for the tensile strength:						
	– median, min.	N/mm ²	12,5	10	10	10	
	– variation ^a , max.	%	±20	±20	±20	±25	
1.2.3	Values to be obtained for the elongation at break:						
	– median, min.	%	125	150	150	150	
	– variation ^a , max.	%	±20	±20	±20	±25	
2	Loss of mass test						IEC 60811-409
2.1	Ageing conditions:						
	– temperature	°C	As in reference No. 1.2.1				115 ± 2
	– duration of treatment	h					10 × 24
2.2	Values to be obtained for the loss of mass, max.	mg/cm ²	2	2	2	2	
3	Compatibility test ^b						IEC 60811-401
3.1	Ageing conditions:						
	– temperature	°C	As in reference No. 1.2.1				100 ± 2
	– duration of treatment	h					10 × 24
3.2	Mechanical properties after ageing		As in reference Nos. 1.2.2 and 1.2.3				
	Values to be obtained						
4	Heat shock test						IEC 60811-509
4.1	Test conditions:						
	– temperature	°C	150 ± 2	150 ± 2	150 ± 2	150 ± 2	
	– duration of treatment	h	1	1	1	1	
4.2	Results to be obtained		Absence of cracks				

6.6 Tests on completed cables

6.6.1 Electrical properties

The cables shall have adequate dielectric strength and insulation resistance.

Compliance shall be checked by carrying out the tests specified in Table 3.

The test methods and the results to be obtained are specified in Table 3.

Table 3 – Requirements for electrical tests for PVC insulated cables

1	2	3	4	5	6	7
Reference No.	Test	Unit	Rated voltage of cables			Test method described in
			300/ 300 V	300/ 500 V	450/ 750 V	
1	Measurement of the resistance of conductors					IEC 63294:2021, 5.1
1.1	Values to be obtained, max.		See IEC 60228 and particular standards (IEC 60227-3, IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7)			
2	Voltage test on completed cables					IEC 63294:2021, 5.2
2.1	Test conditions:					
	– minimum length of the sample	m	10	10	10	
	– minimum period of immersion in water	h	1	1	1	
	– temperature of the water	°C	20 ± 5	20 ± 5	20 ± 5	
2.2	Voltage applied (AC)	V	2 000	2 000	2 500	
2.3	Duration of each application of voltage, min.	min	5	5	5	
2.4	Results to be obtained		No breakdown			
3	Voltage test on cores					IEC 63294:2021, 5.3
3.1	Test conditions:					
	– length of sample	m	5	5	5	
	– minimum period of immersion in water	h	1	1	1	
	– temperature of the water	°C	20 ± 5	20 ± 5	20 ± 5	
3.2	Applied voltage (AC) according to specified thickness of insulation:					
	– up to and including 0,6 mm	V	1 500	1 500	–	
	– exceeding 0,6 mm	V	2 000	2 000	2 500	
3.3	Duration of each application of voltage, min.	min	5	5	5	
3.4	Results to be obtained		No breakdown			

1	2	3	4	5	6	7
Reference No.	Test	Unit	Rated voltage of cables			Test method described in
			300/ 300 V	300/ 500 V	450/ 750 V	
4	Measurement of insulation resistance					IEC 63294:2021, 5.4
4.1	Test conditions:					
	– length of sample	m	5	5	5	
	– previous voltage test as in Ref. Nos. 2 or 3					
	– minimum period of immersion in hot water	h	2	2	2	
	– temperature of water		See tables in the particular standards			
4.2	Results to be obtained		(IEC 60227-3, IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7)			

6.6.2 Overall dimensions

The mean overall dimensions of the cables shall be within the limits specified in the tables in the particular standards (see IEC 60227-3, IEC 60227-4, IEC 60227-5, IEC 60227-6, IEC 60227-7).

Ovality compliance shall be checked by the tests given in IEC 63294:2021, 6.4.

6.6.3 Mechanical strength of flexible cables

6.6.3.1 General

The flexible cables shall be capable of withstanding bending and other mechanical stresses occurring in normal use.

When specified in the particular standards (see IEC 60227-5, IEC 60227-6, IEC 60227-7), compliance shall be checked by the test given in IEC 63294:2021, Clause 6.

6.6.3.2 Flexing test for flexible cables

See IEC 63294:2021, 6.6.

During the test with 15 000 backward and forward movements, i.e. 30 000 single strokes, neither interruption of the current nor short circuit between the conductors shall occur.

After the test, the sample shall withstand the voltage test carried out in accordance with IEC 63294:2021, 5.2.

6.6.3.3 Bending test for tinsel cord

See IEC 63294:2021, 6.8.

During the test with 60 000 bending cycles, i.e. 120 000 single strokes, interruption of the current shall not occur.

After the test, the sample shall withstand the voltage test carried out in accordance with IEC 63294:2021, 5.2, the voltage, however, being 1 500 V and applied only between the conductors connected together and the water.