

INTERNATIONAL STANDARD

**Specifications for particular types of winding wires –
Part 67: Polyvinyl acetal enamelled rectangular aluminium wire, class 105**

IECNORM.COM : Click to view the full PDF of IEC 60317-67:2017



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2017 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

IECNORM.COM : Click to view the full text of IEC 6017-87:2017

INTERNATIONAL STANDARD

**Specifications for particular types of winding wires –
Part 67: Polyvinyl acetal enamelled rectangular aluminium wire, class 105**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.060.10

ISBN 978-2-8322-3839-4

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms, definitions, general notes and appearance	6
3.1 Terms and definitions.....	6
3.2 General notes	7
3.2.1 Methods of test.....	7
3.2.2 Winding wire.....	7
3.3 Appearance	7
4 Dimensions.....	7
5 Electrical resistance	7
6 Elongation	7
7 Springiness	7
8 Flexibility and adherence	7
8.1 Mandrel winding test.....	7
8.2 Adherence test.....	8
9 Heat shock	8
10 Cut-through	8
11 Resistance to abrasion	8
12 Resistance to solvents.....	8
13 Breakdown voltage	8
14 Continuity of insulation	8
15 Temperature index	8
16 Resistance to refrigerants.....	8
17 Solderability	8
18 Heat or solvent bonding.....	8
19 Dielectric dissipation factor.....	8
20 Resistance to transformer oil	9
21 Loss of mass	9
23 Pin hole test	9
30 Packaging	9
Bibliography.....	10
Table 1 – Mandrel winding	7

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 67: Polyvinyl acetal enamelled rectangular aluminium wire, class 105

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-67 has been prepared by IEC technical committee 55: Winding wires.

The text of this standard is based on the following documents:

CDV	Report on voting
55/1569/CDV	55/1590/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

This International Standard is to be read in conjunction with IEC 60317-0-9:2015.

A list of all parts in the IEC 60317, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The numbering of clauses in this standard is not continuous from Clauses 21 through 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IECNORM.COM : Click to view the full PDF of IEC 60317-67:2017

INTRODUCTION

This part of IEC 60317 forms an element of a series of standards which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) *Winding wires – Test methods* (IEC 60851 series);
- 2) *Specifications for particular types of winding wires* (IEC 60317 series);
- 3) *Packaging of winding wires* (IEC 60264 series).

IECNORM.COM : Click to view the full PDF of IEC 60317-67:2017

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 67: Polyvinyl acetal enamelled rectangular aluminium wire, class 105

1 Scope

This part of IEC 60317 specifies the requirements of enamelled rectangular aluminium winding wire of class 105 with a sole coating based on polyvinyl acetal resin, which may be modified providing it retains the chemical identity of the original resin and meets all specified wire requirements.

NOTE A modified resin is a resin that has undergone a chemical change, or contains one or more additives to enhance certain performance of application characteristics.

The range of nominal conductor dimensions covered by this standard is:

	Minimum	Maximum
Width	2,0 mm	16,0 mm
Thickness	0,80 mm	5,60 mm

Wires of grade 1 and grade 2 are included in this part of IEC 60317 and apply to the complete range of conductors.

The specified combinations of width and thickness as well as the specific ratio width/thickness are given in IEC 60317-0-9.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60317-0-9:2015, *Specifications for particular types of winding wires – Part 0-9: General requirements – Enamelled rectangular aluminium wire*

IEC 60851-4:2016, *Winding wires – Test methods – Part 4: Chemical properties*

3 Terms, definitions, general notes and appearance

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60317-0-9:2015 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.2 General notes

3.2.1 Methods of test

Subclause 3.2 of IEC 60317-0-9:2015 applies. In case of inconsistencies between IEC 60317-0-9 and this part of IEC 60317, the latter shall prevail.

3.2.2 Winding wire

Class 105 is a thermal class that requires a minimum temperature index of 105 and a heat shock resistance of at least 155 °C.

The temperature in degrees Celsius corresponding to the temperature index is not necessarily that at which it is recommended that the wire be operated and this will depend on many factors, including the type of equipment involved.

3.3 Appearance

See 3.3 of IEC 60317-0-9:2015.

4 Dimensions

Clause 4 of IEC 60317-0-9:2015 applies.

5 Electrical resistance

Clause 5 of IEC 60317-0-9:2015 applies.

6 Elongation

Clause 6 of IEC 60317-0-9:2015 applies.

7 Springiness

Test appropriate but no requirements specified.

8 Flexibility and adherence

8.1 Mandrel winding test

The coating shall show no crack after the wire has been bent flatwise and edgewise on a mandrel with a diameter as specified in Table 1.

Table 1 – Mandrel winding

Wire bent on		Mandrel diameter
Width	Sizes up to and including 10 mm	2 × width
	Sizes over 10 mm	3 × width
Thickness	All sizes	2 × thickness

8.2 Adherence test

The wire shall be stretched by 15 %. The distance of loss of adhesion shall be less than $1 \times$ width.

9 Heat shock

Clause 9 of IEC 60317-0-9:2015 applies. The minimum heat shock temperature shall be 155 °C.

10 Cut-through

Test inappropriate

11 Resistance to abrasion

Test inappropriate

12 Resistance to solvents

Clause 12 of IEC 60317-0-9:2015 applies.

13 Breakdown voltage

Clause 13 of IEC 60317-0-9:2015 applies. The elevated temperature shall be 105 °C.

14 Continuity of insulation

Test inappropriate

15 Temperature index

Clause 15 of IEC 60317-0-9:2015 applies. The minimum temperature index shall be 105.

16 Resistance to refrigerants

Test inappropriate

17 Solderability

Test inappropriate

18 Heat or solvent bonding

Test inappropriate

19 Dielectric dissipation factor

Test inappropriate

20 Resistance to transformer oil

Test according to Clause 6 of IEC 60851-4:2016 appropriate. Test requirements are under consideration.

21 Loss of mass

Test inappropriate

23 Pin hole test

Test inappropriate

30 Packaging

Clause 30 of IEC 60317-0-9:2015 applies.

IECNORM.COM : Click to view the full PDF of IEC 60317-67:2017