

INTERNATIONAL STANDARD



**Terms and nomenclature for cores made of magnetically soft ferrites –
Part 1: Terms used for physical irregularities and reference of dimensions**

IECNORM.COM : Click to view the full PDF of IEC 60401-1:2020 RLV



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2020 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IECNORM.COM : Click to view the full text of IEC 60364-1:2020 RVV

INTERNATIONAL STANDARD



**Terms and nomenclature for cores made of magnetically soft ferrites –
Part 1: Terms used for physical irregularities and reference of dimensions**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.100.10

ISBN 978-2-8322-8218-2

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	5
1 Scope	7
2 Normative references	7
3 Terms and definitions	7
4 Physical irregularities	7
4.1 General overview	7
4.2 General terms for physical irregularities	8
4.3 Surface irregularities	9
4.3.1 Chip irregularities	9
4.3.2 Protruding (convex) irregularities	10
4.3.3 Edge irregularities	11
4.3.4 Crack irregularities	12
4.3.5 Colour irregularities	14
4.3.6 Machining-related irregularities	15
4.4 Interior irregularities	16
4.5 Shape irregularities (deformations)	17
4.5.1 Non-flat irregularities	17
4.5.2 Simple geometry irregularities	19
4.5.3 Grinding related irregularities	22
4.5.4 Other shape irregularities	22
5 Bulk irregularities	23
5 Reference of dimensions	23
5.1 General specifications	23
5.2 Dimension descriptions	23
5.3 Core illustrations	24
Annex A (informative) Location related terms	28
A.1 General	28
A.2 Surfaces	28
A.3 Shape	29
A.4 Specific parts location qualifiers	29
Figure 1 – Surface chip	9
Figure 2 – Edge chip	9
Figure 3 – Corner chip	9
Figure 4 – Pull-out	10
Figure 5 – Pores	10
Figure 6 – Hump	11
Figure 7 – Attached particle	11
Figure 8 – Ragged edge	11
Figure 9 – Flash	11
Figure 10 – Single-surface narrow crack	12
Figure 11 – Single-surface broad crack	12
Figure 12 – Edge narrow crack	12
Figure 13 – Edge broad crack	13

Figure 14 – Inner channel crack	13
Figure 15 – Lamination	13
Figure 16 – Crazing	14
Figure 17 – Difference in colour tones.....	14
Figure 18 – Discoloration	14
Figure 19 – Stain	15
Figure 20 – Crystallite	15
Figure 21 – Roughness	15
Figure 22 – Short-ground surface.....	16
Figure 23 – Scratch	16
Figure 24 – Convexity	17
Figure 25 – Concavity	18
Figure 26 – Warping	18
Figure 27 – Deflection-out.....	18
Figure 28 – Deflection-in.....	19
Figure 29 – Transverse deflection	19
Figure 30 – Undulation.....	19
Figure 31 – Non-parallelism	19
Figure 32 – Non-perpendicularity	20
Figure 33 – Non-coplanarity	20
Figure 34 – Non-circularity.....	20
Figure 35 – Ovality	21
Figure 36 – Non-concentricity of co-planar circles.....	21
Figure 37 – Non-concentricity of circles lying on two planes.....	21
Figure 38 – Steplike ground surface.....	22
Figure 39 – Uneven grinding slant.....	22
Figure 40 – Un-matching.....	22
Figure 41 – Profile deformation	23
Figure 42 – Ring-cores	24
Figure 43 – E-core.....	24
Figure 44 – ETD- or EER-core	25
Figure 45 – EC-core.....	25
Figure 46 – Planar E-core	25
Figure 47 – Planar EL-core	25
Figure 48 – Planar ER-core	25
Figure 49 – Plate-core mating planar cores.....	25
Figure 50 – EFD-core	26
Figure 51 – Drum-core	26
Figure 52 – EP-core.....	26
Figure 53 – PQ-core	26
Figure 54 – Pot-core and half pot-core for inductive proximity switches	26
Figure 55 – PM-core	26
Figure 56 – RM-core	27

Figure 57 – U-core	27
Figure 58 – UR-core	27
Figure 59 – Balun-core	27
Figure 60 – Multi hole bead.....	27
Figure A.1 – E-core.....	33
Figure A.2 – RM-core.....	33
Table 1 – Ring-core dimension designations	23
Table 2 – Other ferrite shape dimension designations	24

IECNORM.COM : Click to view the full PDF of IEC 60401-1:2020 RLV

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**TERMS AND NOMENCLATURE FOR CORES MADE
OF MAGNETICALLY SOFT FERRITES –****Part 1: Terms used for physical irregularities
and reference of dimensions**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60401-1 has been prepared by IEC technical committee 51: Magnetic components, ferrite and magnetic powder materials.

This second edition cancels and replaces the first edition of IEC 60401-1 published in 2002 and the second edition of IEC 60401-2 published in 2009. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous editions of IEC 60401-1 and IEC 60401-2:

- a) added the surface irregularity term “pores” in 4.3.1.6;
- b) added the surface irregularity term “scratch” in 4.3.6.3;
- c) removed the surface irregularity term “crater” in 4.1.5 of IEC 60401-1: 2002;
- d) removed the bulk irregularity terms “superpores” in 5.1, “inclusions” in 5.2, “internal stratification” in 5.3 and “internal crack” in 5.4 of IEC 60401-1: 2002;
- e) removed the contents related to “yoke ring cores” in 7.1.3 and 7.4 of IEC 60401-1:2002;
- f) replaced the surface irregularity term “stratification” with “lamination” in 4.3.4.7;
- g) replaced the location related terms “upper surface of back” with “bottom surface” and “lower surface of back” with “back surface” in Figure A.1;
- h) changed Clause 7 of IEC 60401-1:2002 into Annex A.

The text of this International Standard is based on the following documents:

CDV	Report on voting
51/1313/CDV	51/1332/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60401 series, published under the general title *Terms and nomenclature for cores made of magnetically soft ferrites* can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

TERMS AND NOMENCLATURE FOR CORES MADE OF MAGNETICALLY SOFT FERRITES –

Part 1: Terms used for physical irregularities and reference of dimensions

1 Scope

This part of IEC 60401 provides a nomenclature of the most frequent surface, bulk and shape irregularities relevant to cores made of soft ferrites (magnetic oxides). Most irregularities are graphically exemplified as visual aids. A general recommendation is also given in Annex A for a consistent scheme for specifying the exact location of the irregularity, combining a general name for the location with more detailed qualifiers of the specified location. This document can also be useful as a terminology reference when preparing technical documentation, irregularity inspection specifications, etc.

This document also presents a method for defining the designation nomenclature for the major physical attributes of soft ferrite core shapes. The purpose of this document is to facilitate uniform usage of dimensional characters by manufacturers, specifiers, and users when describing core dimensions on drawings, in tables, and on catalogue specification sheets.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the terms and definitions given in 4.2, 4.3, 4.5 and Annex A apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Physical irregularities

4.1 General overview

Physical irregularities mean here the surface irregularities, bulk irregularities and shape irregularities. The irregularity here stands for inconsistency of the state or quality of the part's surface, bulk or shape with its intended regularity. These irregularities are considered here in the macroscopic scale, i.e. within the range of linear dimensions of irregularities from one micrometre to tens of millimetres.

There is a great variety of surface, bulk and shape irregularities degrading the quality of parts made of ferrites. Different types of these irregularities ~~may~~ can often occur together and overlap one another.

Each type of irregularity is, in general, produced by one or more of the following: ~~an incorrectly or inaccurately performed process variability in a manufacturing step, or improper~~ handling, grinding, packing or transportation.

The extent of the quality degradation is dependent on the type, scale, and combination of irregularities being present as well as on their locations on the part. There are locations particularly sensitive to the degrading effect of the specific types of irregularities.

The irregularities ~~may~~ can in extreme cases ~~give~~ have a detrimental or critical effect ~~to~~ on magnetic, electric and mechanical performances of the part. Operations performed on the part, such as marking, winding, assembling and mounting, can also be adversely affected by the irregularities.

An ongoing tendency to upgrade the overall quality of the parts results in more stringent restrictions being imposed on the quantity of irregularities in these parts.

This brings about a need for a set of definitions, or nomenclature, which would be a primary basis for approaches to irregularities and their location issues.

Therefore, this nomenclature is intended to be used as a uniform reference when formulating more detailed descriptions of irregularities at specified locations, requirements and procedures related to the inspection and assessment of irregularities. This nomenclature can also be useful with regard to methods and tools used for detection, recognition and classification of irregularities.

4.2 General terms for physical irregularities

4.2.1

surface irregularity

unintentional state or appearance of the surfaces, edges and corners of the part

Note 1 to entry: Some surface irregularities, if excessive, can so deform contours and surfaces of the part, that they may also be classified as shape irregularities.

4.2.2

interior irregularity

unintentional inhomogeneity inside the part

4.2.3

shape irregularity

unintentional deformation of the contour lines or surfaces delimiting the shape of the part

Note 1 to entry: In some cases, shape irregularities smaller than quoted tolerances ~~may~~ can still disqualify the part.

3.3

bulk irregularity

~~unintentional inhomogeneity inside the part~~

4.2.4

tolerance

<dimensional> allowable difference between the nominal and permissible limit dimensions of the contour lines defining the part's shape

4.2.5

location

<of the irregularity> position on or within the part where the irregularity is present

4.3 Surface irregularities

4.3.1 Chip irregularities

4.3.1.1

chip

lack of surface material generally caused by mechanical impact during handling or ~~grinding~~ transportation

Note 1 to entry: In almost all cases, chips are located on the edges of surfaces.

~~According to specific locations, the chips are sub-classified:~~

4.3.1.2

surface chip

chip located only on the core surface

SEE: Figure 1.



Figure 1 – Surface chip

4.3.1.3

edge chip

chip located only on the core edge

SEE: Figure 2.




Figure 2 – Edge chip

4.3.1.4

corner chip

chip located only in a corner

SEE: Figure 3.




Figure 3 – Corner chip

4.3.1.5

pull-out

consequence of the removal of the surface layer of the core due to die “sticking”, which occurs on surfaces perpendicular to the direction of the pressing action

Note 1 to entry: A pull-out with a depth greater than 1 mm should be considered as a chip.

SEE: Figure 4.





Figure 4 – Pull-out

4.1.5

crater

blind hole with depth comparable to or greater than its diameter



4.3.1.6

pore

hole left on the surface of cores after sintering and surface finishing

SEE: Figure 5.




Figure 5 – Pores

4.3.2 Protruding (convex) irregularities

4.3.2.1

hump

elevation of a rounded contour on the relevant surface

SEE: Figure 6.




Figure 6 – Hump

4.3.2.2**attached particle**

any particle on the surface which cannot be removed by compressed-air, cleaning, washing or wiping

SEE: Figure 7.



Figure 7 – Attached particle

4.3.2.3**inclusion**

millimetre or sub-millimetre-sized foreign body located in the surface of the part ~~(refer to 5.2)~~

4.3.3 Edge irregularities**4.3.3.1****ragged edge**

edge affected by a series of small chips

SEE: Figure 8.




Figure 8 – Ragged edge

4.3.3.2**flash**

sharp feather-edge wall extending beyond the intended contour surface of the core

SEE: Figure 9.




Figure 9 – Flash

4.3.4 Crack irregularities

4.3.4.1

crack

surface irregularity which has a width much smaller than its length and penetrates into the core

~~Specific types of 'cracks' can be sub-classified:~~

4.3.4.2

single-surface narrow crack

crack located on a single surface, not going beyond its edges, and with a width not exceeding a specified limit (e.g. 0,1 mm) anywhere along the crack path on the surface

SEE. Figure 10.




Figure 10 – Single-surface narrow crack

4.3.4.3

single-surface broad crack

crack located on a single surface, not going beyond its edges, and with a width equal to or exceeding the limit specified for the narrow crack anywhere along the crack path on the surface

SEE. Figure 11.



Figure 11 – Single-surface broad crack

4.3.4.4

edge narrow crack

crack located on two adjacent surfaces and crossing their common edge, with a width not exceeding a specified limit (e.g. 0,1 mm) anywhere along the crack path on these surfaces

SEE: Figure 12.




Figure 12 – Edge narrow crack

4.3.4.5**edge broad crack**

crack located on two adjacent surfaces and crossing their common edge, with a width equal to or exceeding the limit specified for the narrow crack anywhere along the crack path on these surfaces

SEE: Figure 13.




Figure 13 – Edge broad crack

4.3.4.6**inner channel crack**

narrow or broad crack along an inner edge of the core

SEE: Figure 14.



Figure 14 – Inner channel crack

4.3.4.7**stratification lamination**

series of cracks located side by side which are more or less parallel, or single crack, which runs along a significant portion (e.g. 20 %) of the periphery of the part

Note 1 to entry: **Stratification Lamination** is usually positioned transversely to the direction of the pressing of the core.

SEE: Figure 15.





Figure 15 – Lamination

4.3.4.8**crazing**

grid-like pattern of superficial cracks of a depth not exceeding a specified limit (e.g. 0,3 mm)

SEE: Figure 16.



IEC

Figure 16 – Crazing


4.3.5 Colour irregularities

4.3.5.1

difference in colour tone

slight but visible local change(s) in the tint of the natural colour or shading of an area of a surface from the surrounding background

SEE: Figure 17.



IEC


Figure 17 – Difference in colour tones

4.3.5.2

discoloration

visible difference in the colours of an area of a surface from the normal uniform colour background

SEE: Figure 18.



IEC

Figure 18 – Discoloration

4.3.5.3

stain

smear of oil, grease, or other substance ~~etc.~~ or deposit (e.g. whitish or water marks) on the surface

SEE: Figure 19.




Figure 19 – Stain

4.3.5.4

crystallite

grain of abnormal size distinguishable on the surface, often with sparkling facets

SEE: Figure 20.





Figure 20 – Crystallite

4.5.5

oxidation of split surfaces

part of split (detached, crashed, etc.) surface which is oxidized



4.3.6 Machining-related irregularities

4.3.6.1

roughness

uneven, ~~not smooth~~ rough surface ~~including~~ which includes traces from grinding, abrasives, etc.

SEE: Figure 21.




Figure 21 – Roughness

4.3.6.2

short-ground surface

part of surface which unintentionally remains un-ground after grinding, with no steplike surface irregularities

Note 1 to entry: See 4.5.3.1.

SEE: Figure 22.




Figure 22 – Short-ground surface

4.3.6.3

scratch

one or more scrapes caused by the handling process

SEE: Figure 23.




Figure 23 – Scratch

4.4 Interior irregularities

Since inclusions, cracks or lamination that is confined to the inside of a part cannot be detected by direct inspection except with destructive or expensive procedures, control of bulk irregularities is maintained through break strength testing. Small sample sizes from production batches are destructively broken with M testing, W testing, or tensile pull testing. The yield strength is recorded and compared with specification limits or control limits. Further, internal irregularities that cause electrical performance to be impaired are detected by means of testing against the electrical specifications.

5 Bulk irregularities

5.1


superpores

pores being millimetre-sized voids

5.2

inclusions

millimetre or sub-millimetre-sized foreign bodies located inside cores



NOTE—An inclusion, if it appears on the surface of the part, is also considered as the surface irregularity (see 4.2.3).

5.3

internal stratification


~~stratum shaped material discontinuity located inside the core and not always extending to the surface; usually narrow but sometimes of an extensive area~~

NOTE—The internal stratification caused by the improper press of the material is usually positioned transversely to the direction of pressing.

5.4

internal crack

~~crack shaped material discontinuity inside the core not always extending to the surface; usually narrow but sometimes of an extensive length~~



4.5 Shape irregularities (deformations)

4.5.1 Non-flat irregularities

4.5.1.1

convexity

~~outwards~~ outwardly curved outline or surface

SEE: Figure 24.




Figure 24 – Convexity

4.5.1.2

concavity

~~inwards~~ inwardly curved outline or surface

SEE: Figure 25.



Figure 25 – Concavity

4.5.1.3

warping

state of a shape with twisted surface(s)

SEE: Figure 26.




Figure 26 – Warping

4.5.1.4

bending

deflection, curved or angular, from any direction that is regarded as the intended ~~one~~ deflection

~~Three different kind of deflections as follows:~~

4.5.1.4.1

deflection-out

state of being more or less inclined to the outside from the perpendicular or from another intended inclination

Note 1 to entry: This is also called "toe-out".

SEE: Figure 27.




Figure 27 – Deflection-out

4.5.1.4.2

deflection-in

state of being more or less inclined to the inside from the perpendicular or from another intended inclination

Note 1 to entry: This is also called "toe-in".

SEE: Figure 28.




Figure 28 – Deflection-in

4.5.1.4.3

transverse deflection

state of being more or less inclined or twisted transversely to the reference surface

SEE: Figure 29.




Figure 29 – Transverse deflection

4.5.1.5

undulation

upwards and downwards bending of the outline or surface

SEE: Figure 30.




Figure 30 – Undulation

4.5.2 Simple geometry irregularities

4.5.2.1

non-parallelism

deviation from being parallel of two or more lines, planes or surfaces including the deviation from their intended equidistance

SEE: Figure 31.



Figure 31 – Non-parallelism

4.5.2.2

non-perpendicularity

deviation from the right angle

SEE: Figure 32.



Figure 32 – Non-perpendicularity

4.5.2.3

non-coplanarity

deviation from belonging to the same plane

SEE: Figure 33.




Figure 33 – Non-coplanarity

4.5.2.4

non-circularity

deviation from the shape of a circle

SEE: Figure 34.




Figure 34 – Non-circularity

4.5.2.5

ovality

deviation from the shape of a circle to an oval or egg-shape

SEE: Figure 35.




Figure 35 – Ovality

4.5.2.6**non-concentricity**

shift between the centres of circles, arcs, or sectors, ~~etc. intended~~ which are supposed to have a common centre

~~One distinguishes the following:~~

4.5.2.6.1**non-concentricity of co-planar circles**

non-concentricity of circles lying on the same plane

Note 1 to entry: In such a case, the axes of circles are parallel.

SEE: Figure 36.





Figure 36 – Non-concentricity of co-planar circles

4.5.2.6.2**non-concentricity of circles lying on two planes**

non-concentricity of circles lying on two planes situated one above the other

SEE: Figure 37.



NOTE Planes A and B ~~may~~ can be non-parallel (see 4.5.2.1). In such a case, the axes of the circles are mutually twisted.

Figure 37 – Non-concentricity of circles lying on two planes

4.5.3 Grinding related irregularities

4.5.3.1

steplike ground surface

step caused by a partial grinding of the surface intended to be ground with no step remainder

SEE: Figure 38.




Figure 38 – Steplike ground surface

4.5.3.2

uneven grinding slant

non-coplanar ground surface

SEE: Figure 39.




Figure 39 – Uneven grinding slant

4.5.4 Other shape irregularities

4.5.4.1

un-matching

incomplete overlap or misalignment of mating parts, surfaces, dimensions, etc., in parts which have to be joined or paired

SEE: Figure 40.





Figure 40 – Un-matching

4.5.4.2

profile deformation

deformation from the intended profile outline

SEE: Figure 41.



IEC

Figure 41 – Profile deformation

5 Reference of dimensions

5.1 General specifications

Only upper case alphabetic character assignments shall be used.

Only one character per dimension and per ferrite piece shall be used.

Characters 2B and 2D shall be used for core sets such as EP, PQ, pot and RM.

Subscripts (e.g. F_1 and F_2 for planar EL- and EFD-cores) may be used.

5.2 Dimension descriptions

Table 1 and Table 2 describe the alphabetic character assignments for the major dimensions of ring-cores and other ferrite shapes, respectively. All other minor core dimensions designations are left to the discretion of the specifier.

Table 1 – Ring-core dimension designations



Letter	Dimension description
<i>A</i>	Ring outside diameter
<i>B</i>	Ring inside diameter
<i>C</i>	Ring height

Table 2 – Other ferrite shape dimension designations

Letter	Dimension description
<i>A</i>	Overall length of the core back or diameter
<i>B</i>	Outside leg length or height of core
<i>C</i>	Core width or floor width at wire aperture
<i>D</i>	Inside leg length or available bobbin depth
<i>E</i>	Window width or available bobbin width
<i>F</i>	Centre post thickness or diameter
<i>G</i>	Wire aperture or slot width
<i>H</i>	Centre post hole diameter
<i>J</i>	RM-core side-to-side parallel width or PQ floor angle opening
<i>K</i>	Centre post offset dimension
<i>L</i>	PQ floor angle separation
<i>S</i>	Slot width in outside legs
<i>T</i>	Distance between slot depths in outside legs

5.3 Core illustrations

Figure 42 through Figure 60 represent typical core geometries with the standard dimension nomenclature applied.

**Figure 42 – Ring-core****Figure 43 – E-core**




Figure 44 – ETD- or EER-core




Figure 45 – EC-core




Figure 46 – Planar E-core




Figure 47 – Planar EL-core




Figure 48 – Planar ER-core




Figure 49 – Plate-core mating planar cores




Figure 50 – EFD-core




Figure 51 – Drum-core




Figure 52 – EP-core




Figure 53 – PQ-core




Figure 54 – Pot-core and half pot-core for inductive proximity switches




Figure 55 – PM-core




Figure 56 – RM-core




Figure 57 – U-core




Figure 58 – UR-core




Figure 59 – Balun-core




Figure 60 – Multi hole bead

Annex A (informative)

Location related terms

A.1 General

Location is directly related to the shape geometry of the part by such shape determiners as surfaces, contours, edges, etc. However, a specific state or function (additional attributes) of some locations means that their names, in practical use, are not only related to the shape geometry but also to the additional attribute such as, for example, ground or un-ground (surface).

A.2 Surfaces

A.2.1

ground surface

surface which has been made smoother by grinding, polishing or lapping

A.2.2

un-ground surface

surface not subjected to any smoothing process(es)

A.2.3

mating surface

~~surface intended to be crossed by the main magnetic flux (leakage flux excluded) guided by the magnetic core~~

location where part halves meet (or nearly meet except for an intentional air gap) to form a part set (e.g. EI-core, E-core, U-core, pot-core), and where the main magnetic flux (leakage flux excluded) is guided by the magnetic core to cross the surfaces that so meet

Note 1 to entry: The mating surface is the magnetically active surface.

Note 2 to entry: The quality of the magnetically active surface is one of the crucial factors affecting locally the direction and value of the magnetic flux crossing that surface.

Note 23 to entry: Mating surfaces are usually ground, especially in cases where it is essential that the magnetic flux crossing these surfaces runs as intended.

Note 34 to entry: Magnetic cores forming a closed magnetic circuit with no air-gap (i.e. non-cut cores such as ring cores, non-cut E- or U-cores), being magnetized along that circuit, have no magnetically active surfaces. Nevertheless, irregularities ~~may~~ can also affect the performance of such cores (e.g. cracks ~~may~~ can extend the main magnetic flux beyond the core surface, contributing to flux leakage).

~~NOTE 4—Mating surfaces are adjacent parts or halves of a part which meet to form a part set (e.g. EI-core, pot-core, E-core, U-core, split halves of a yoke ring core, surfaces of air-gap).~~

A.2.4

magnetically passive surfaces

other surfaces than active surfaces

~~Within the passive surfaces one distinguishes the following ones:~~

A.2.4.1

wall

more or less vertical inner or outer surface, with sides from the top and bottom, back and front, between two ends

~~7.1.4.2~~

~~upper and lower, back and front surfaces
usually horizontal surfaces of a part~~

A.2.4.2

bottom surface

interior plane of the back wall, facing the coil

A.2.4.3

back surface

lower base surface which serves as a reference plane for grinding the mating surface

Note 1 to entry: Irregularities on magnetically passive surfaces can also affect performance of the magnetic cores.

A.3 Shape

A.3.1

profile

line or surface outlining the shape, usually projected on a plane, if not specified otherwise

A.3.2

edge

line between two adjacent surfaces (outer or inner) where a sudden change of slope occurs

A.3.3

corner

point at which three or more surfaces (outer or inner) meet

A.3.4

ridge

elevation on a surface of a recess groove (used to fix a clip) ~~etc.~~

~~7.3 Inside~~

~~7.3.1~~

~~inside~~

~~the bulk within the interior of the part~~

~~NOTE Term related only to the bulk irregularities.~~

A.4 Specific parts location qualifiers


As a rule, the shape determiners such as the surfaces, contours, edges, etc., are further qualified by adding more precise qualifying words, usually related to a specific geometry (shape) of the part and/or with the location where the specified irregularity has to be examined. Often these surfaces, walls and their qualifiers are termed according to custom. Nevertheless, it is recommended to follow, as far as possible, the terminology proposed here which is aimed at a more precise and unified classification linking the irregularities with their locations in specific types of parts. Moreover, to avoid any ambiguity, the given locations should be distinctly indicated on a relevant drawing of the concerned part.

~~Examples of such more precise terminology are:~~

~~upper surface of back (of U-core); lateral wall of outer leg (of E-core); outer circular wall (of pot-core...); back flange wall (of yoke-ring core), foot, bevelled wall, end wall (in segment) etc.~~


~~Examples of the use of location qualifiers for the case of E-core, yoke ring core and RM-core are given below.~~

~~EXAMPLE 1 — E-core~~



IEC 3188/02

~~NOTE — The term “centre pole” shall be used when the cross-section of the centre leg is round.~~


EXAMPLE 2 – Yoke ring core

IEC 3189/02

NOTE This example illustrates the case of a complicated shape (yoke ring core) when the recommended (in 7.1 and 7.2) and accustomed (in *italics*) location qualifiers are both in alternative use.

¹⁾ Upper edge can be rounded, bevelled or softly pointed.

Example 3 – RM-core




IEC 3190/02

NOTE The term “centre leg” shall be used when cross-section of centre leg is square.

Examples of such more precise terminology are:

- bottom surface (of U-core);
- lateral wall of outer leg (of E-core);
- outer circular wall (of pot-core), etc.

Examples of the use of location qualifiers for the cases of an E-core and an RM-core are given in Figure A.1 and Figure A.2.




IEC

The term “centre pole” shall be used when the cross-section of the centre post is round.

The term “back” means the three-dimensional area enclosed with the bottom surface, back surface and two back walls.

Figure A.1 – E-core



IEC

The term “centre leg” shall be used when cross-section of centre post is square.

The term “back” means the three-dimensional area enclosed with the bottom surface, back surface and two back walls.

Figure A.2 – RM-core

IECNORM.COM : Click to view the full PDF of IEC 60401-1:2020 RLV

INTERNATIONAL STANDARD

**Terms and nomenclature for cores made of magnetically soft ferrites –
Part 1: Terms used for physical irregularities and reference of dimensions**

IECNORM.COM : Click to view the full PDF of IEC 60401-1:2020 RLV

CONTENTS

FOREWORD	5
1 Scope	7
2 Normative references	7
3 Terms and definitions	7
4 Physical irregularities	7
4.1 General overview	7
4.2 General terms for physical irregularities	8
4.3 Surface irregularities	8
4.3.1 Chip irregularities	8
4.3.2 Protruding (convex) irregularities	10
4.3.3 Edge irregularities	11
4.3.4 Crack irregularities	11
4.3.5 Colour irregularities	13
4.3.6 Machining-related irregularities	15
4.4 Interior irregularities	16
4.5 Shape irregularities (deformations)	16
4.5.1 Non-flat irregularities	16
4.5.2 Simple geometry irregularities	18
4.5.3 Grinding related irregularities	20
4.5.4 Other shape irregularities	20
5 Reference of dimensions	21
5.1 General specifications	21
5.2 Dimension descriptions	21
5.3 Core illustrations	22
Annex A (informative) Location related terms	26
A.1 General	26
A.2 Surfaces	26
A.3 Shape	27
A.4 Specific parts location qualifiers	27
Figure 1 – Surface chip	9
Figure 2 – Edge chip	9
Figure 3 – Corner chip	9
Figure 4 – Pull-out	10
Figure 5 – Pores	10
Figure 6 – Hump	10
Figure 7 – Attached particle	10
Figure 8 – Ragged edge	11
Figure 9 – Flash	11
Figure 10 – Single-surface narrow crack	11
Figure 11 – Single-surface broad crack	12
Figure 12 – Edge narrow crack	12
Figure 13 – Edge broad crack	12
Figure 14 – Inner channel crack	13

Figure 15 – Lamination	13
Figure 16 – Crazing	13
Figure 17 – Difference in colour tones.....	14
Figure 18 – Discoloration	14
Figure 19 – Stain	14
Figure 20 – Crystallite.....	14
Figure 21 – Roughness	15
Figure 22 – Short-ground surface.....	15
Figure 23 – Scratch	15
Figure 24 – Convexity	16
Figure 25 – Concavity	16
Figure 26 – Warping	16
Figure 27 – Deflection-out.....	17
Figure 28 – Deflection-in.....	17
Figure 29 – Transverse deflection	17
Figure 30 – Undulation.....	18
Figure 31 – Non-parallelism	18
Figure 32 – Non-perpendicularity	18
Figure 33 – Non-coplanarity.....	18
Figure 34 – Non-circularity.....	19
Figure 35 – Ovality	19
Figure 36 – Non-concentricity of co-planar circles.....	19
Figure 37 – Non-concentricity of circles lying on two planes.....	20
Figure 38 – Steplike ground surface.....	20
Figure 39 – Uneven grinding slant.....	20
Figure 40 – Un-matching.....	21
Figure 41 – Profile deformation.....	21
Figure 42 – Ring-cores	22
Figure 43 – E-core.....	22
Figure 44 – ETD- or EER-core	23
Figure 45 – EC-core.....	23
Figure 46 – Planar E-core	23
Figure 47 – Planar EL-core	23
Figure 48 – Planar ER-core	23
Figure 49 – Plate-core mating planar cores.....	23
Figure 50 – EFD-core	24
Figure 51 – Drum-core	24
Figure 52 – EP-core.....	24
Figure 53 – PQ-core	24
Figure 54 – Pot-core and half pot-core for inductive proximity switches	24
Figure 55 – PM-core	24
Figure 56 – RM-core	25
Figure 57 – U-core.....	25

Figure 58 – UR-core	25
Figure 59 – Balun-core	25
Figure 60 – Multi hole bead.....	25
Figure A.1 – E-core.....	28
Figure A.2 – RM-core.....	28
Table 1 – Ring-core dimension designations	21
Table 2 – Other ferrite shape dimension designations	22

IECNORM.COM : Click to view the full PDF of IEC 60401-1:2020 RLV

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**TERMS AND NOMENCLATURE FOR CORES MADE
OF MAGNETICALLY SOFT FERRITES –****Part 1: Terms used for physical irregularities
and reference of dimensions**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60401-1 has been prepared by IEC technical committee 51: Magnetic components, ferrite and magnetic powder materials.

This second edition cancels and replaces the first edition of IEC 60401-1 published in 2002 and the second edition of IEC 60401-2 published in 2009. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous editions of IEC 60401-1 and IEC 60401-2:

- a) added the surface irregularity term "pores" in 4.3.1.6;
- b) added the surface irregularity term "scratch" in 4.3.6.3;
- c) removed the surface irregularity term "crater" in 4.1.5 of IEC 60401-1: 2002;

- d) removed the bulk irregularity terms “superpores” in 5.1, “inclusions” in 5.2, “internal stratification” in 5.3 and “internal crack” in 5.4 of IEC 60401-1: 2002;
- e) removed the contents related to “yoke ring cores” in 7.1.3 and 7.4 of IEC 60401-1:2002;
- f) replaced the surface irregularity term “stratification” with “lamination” in 4.3.4.7;
- g) replaced the location related terms “upper surface of back” with “bottom surface” and “lower surface of back” with “back surface” in Figure A.1;
- h) changed Clause 7 of IEC 60401-1:2002 into Annex A.

The text of this International Standard is based on the following documents:

CDV	Report on voting
51/1313/CDV	51/1332/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60401 series, published under the general title *Terms and nomenclature for cores made of magnetically soft ferrites* can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IECNORM.COM : Click to view the full text of IEC 60401-1:2020 RLV

TERMS AND NOMENCLATURE FOR CORES MADE OF MAGNETICALLY SOFT FERRITES –

Part 1: Terms used for physical irregularities and reference of dimensions

1 Scope

This part of IEC 60401 provides a nomenclature of the most frequent surface, bulk and shape irregularities relevant to cores made of soft ferrites (magnetic oxides). Most irregularities are graphically exemplified as visual aids. A general recommendation is also given in Annex A for a consistent scheme for specifying the exact location of the irregularity, combining a general name for the location with more detailed qualifiers of the specified location. This document can also be useful as a terminology reference when preparing technical documentation, irregularity inspection specifications, etc.

This document also presents a method for defining the designation nomenclature for the major physical attributes of soft ferrite core shapes. The purpose of this document is to facilitate uniform usage of dimensional characters by manufacturers, specifiers, and users when describing core dimensions on drawings, in tables, and on catalogue specification sheets.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the terms and definitions given in 4.2, 4.3, 4.5 and Annex A apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Physical irregularities

4.1 General overview

Physical irregularities mean here the surface irregularities, bulk irregularities and shape irregularities. The irregularity here stands for inconsistency of the state or quality of the part's surface, bulk or shape with its intended regularity. These irregularities are considered here in the macroscopic scale, i.e. within the range of linear dimensions of irregularities from one micrometre to tens of millimetres.

There is a great variety of surface, bulk and shape irregularities degrading the quality of parts made of ferrites. Different types of these irregularities can often occur together and overlap one another.

Each type of irregularity is, in general, produced by one or more of the following: process variability in a manufacturing step, handling, grinding, packing or transportation.

The extent of the quality degradation is dependent on the type, scale, and combination of irregularities being present as well as on their locations on the part. There are locations particularly sensitive to the degrading effect of the specific types of irregularities.

The irregularities can in extreme cases have a detrimental or critical effect on magnetic, electric and mechanical performances of the part. Operations performed on the part, such as marking, winding, assembling and mounting, can also be adversely affected by the irregularities.

An ongoing tendency to upgrade the overall quality of the parts results in more stringent restrictions being imposed on the quantity of irregularities in these parts.

This brings about a need for a set of definitions, or nomenclature, which would be a primary basis for approaches to irregularities and their location issues.

Therefore, this nomenclature is intended to be used as a uniform reference when formulating more detailed descriptions of irregularities at specified locations, requirements and procedures related to the inspection and assessment of irregularities. This nomenclature can also be useful with regard to methods and tools used for detection, recognition and classification of irregularities.

4.2 General terms for physical irregularities

4.2.1

surface irregularity

unintentional state or appearance of the surfaces, edges and corners of the part

Note 1 to entry: Some surface irregularities, if excessive, can so deform contours and surfaces of the part, that they may also be classified as shape irregularities.

4.2.2

interior irregularity

unintentional inhomogeneity inside the part

4.2.3

shape irregularity

unintentional deformation of the contour lines or surfaces delimiting the shape of the part

Note 1 to entry: In some cases, shape irregularities smaller than quoted tolerances can still disqualify the part.

4.2.4

tolerance

<dimensional> allowable difference between the nominal and permissible limit dimensions of the contour lines defining the part's shape

4.2.5

location

<of the irregularity> position on or within the part where the irregularity is present

4.3 Surface irregularities

4.3.1 Chip irregularities

4.3.1.1

chip

lack of surface material generally caused by mechanical impact during handling or transportation

Note 1 to entry: In almost all cases, chips are located on the edges of surfaces.

4.3.1.2

surface chip

chip located only on the core surface

SEE: Figure 1.



Figure 1 – Surface chip

4.3.1.3

edge chip

chip located only on the core edge

SEE: Figure 2.




Figure 2 – Edge chip

4.3.1.4

corner chip

chip located only in a corner

SEE: Figure 3.




Figure 3 – Corner chip

4.3.1.5

pull-out

consequence of the removal of the surface layer of the core due to die “sticking”, which occurs on surfaces perpendicular to the direction of the pressing action

Note 1 to entry: A pull-out with a depth greater than 1 mm should be considered as a chip.

SEE: Figure 4.




Figure 4 – Pull-out

4.3.1.6

pore

hole left on the surface of cores after sintering and surface finishing

SEE: Figure 5.




Figure 5 – Pores

4.3.2 Protruding (convex) irregularities

4.3.2.1

hump

elevation of a rounded contour on the relevant surface

SEE: Figure 6.



Figure 6 – Hump

4.3.2.2

attached particle

any particle on the surface which cannot be removed by compressed-air, cleaning, washing or wiping

SEE: Figure 7.



Figure 7 – Attached particle

4.3.2.3**inclusion**

millimetre or sub-millimetre-sized foreign body located in the surface of the part

4.3.3 Edge irregularities**4.3.3.1****ragged edge**

edge affected by a series of small chips

SEE: Figure 8.




Figure 8 – Ragged edge

4.3.3.2**flash**

sharp feather-edge wall extending beyond the intended contour surface of the core

SEE: Figure 9.



Figure 9 – Flash

4.3.4 Crack irregularities**4.3.4.1****crack**

surface irregularity which has a width much smaller than its length and penetrates into the core

4.3.4.2**single-surface narrow crack**

crack located on a single surface, not going beyond its edges, and with a width not exceeding a specified limit (e.g. 0,1 mm) anywhere along the crack path on the surface

SEE: Figure 10.




Figure 10 – Single-surface narrow crack

4.3.4.3

single-surface broad crack

crack located on a single surface, not going beyond its edges, and with a width equal to or exceeding the limit specified for the narrow crack anywhere along the crack path on the surface

SEE: Figure 11.



Figure 11 – Single-surface broad crack

4.3.4.4

edge narrow crack

crack located on two adjacent surfaces and crossing their common edge, with a width not exceeding a specified limit (e.g. 0,1 mm) anywhere along the crack path on these surfaces

SEE: Figure 12.



Figure 12 – Edge narrow crack

4.3.4.5

edge broad crack

crack located on two adjacent surfaces and crossing their common edge, with a width equal to or exceeding the limit specified for the narrow crack anywhere along the crack path on these surfaces

SEE: Figure 13.




Figure 13 – Edge broad crack

4.3.4.6

inner channel crack

narrow or broad crack along an inner edge of the core

SEE: Figure 14.




Figure 14 – Inner channel crack

4.3.4.7

lamination

series of cracks located side by side which are more or less parallel, or single crack, which runs along a significant portion (e.g. 20 %) of the periphery of the part

Note 1 to entry: Lamination is usually positioned transversely to the direction of the pressing of the core.

SEE: Figure 15.




Figure 15 – Lamination

4.3.4.8

crazing

grid-like pattern of superficial cracks of a depth not exceeding a specified limit (e.g. 0,3 mm)

SEE: Figure 16.




Figure 16 – Crazing

4.3.5 Colour irregularities

4.3.5.1

difference in colour tone

slight but visible local change(s) in the tint of the natural colour or shading of an area of a surface from the surrounding background

SEE: Figure 17.




Figure 17 – Difference in colour tones

4.3.5.2 discoloration

visible difference in the colours of an area of a surface from the normal uniform colour background

SEE: Figure 18.




Figure 18 – Discoloration

4.3.5.3 stain

smear of oil, grease, or other substance, or deposit (e.g. whitish or water marks) on the surface

SEE: Figure 19.




Figure 19 – Stain

4.3.5.4 crystallite

grain of abnormal size distinguishable on the surface, often with sparkling facets

SEE: Figure 20.



Figure 20 – Crystallite

4.3.6 Machining-related irregularities

4.3.6.1

roughness

uneven, rough surface which includes traces from grinding, abrasives, etc.

SEE: Figure 21.




Figure 21 – Roughness

4.3.6.2

short-ground surface

part of surface which unintentionally remains un-ground after grinding, with no steplike surface irregularities

Note 1 to entry: See 4.5.3.1.

SEE: Figure 22.




Figure 22 – Short-ground surface

4.3.6.3

scratch

one or more scrapes caused by the handling process

SEE: Figure 23.




Figure 23 – Scratch

4.4 Interior irregularities

Since inclusions, cracks or lamination that is confined to the inside of a part cannot be detected by direct inspection except with destructive or expensive procedures, control of bulk irregularities is maintained through break strength testing. Small sample sizes from production batches are destructively broken with M testing, W testing, or tensile pull testing. The yield strength is recorded and compared with specification limits or control limits. Further, internal irregularities that cause electrical performance to be impaired are detected by means of testing against the electrical specifications.

4.5 Shape irregularities (deformations)

4.5.1 Non-flat irregularities

4.5.1.1

convexity

outwardly curved outline or surface

SEE: Figure 24.



Figure 24 – Convexity

4.5.1.2

concavity

inwardly curved outline or surface

SEE: Figure 25.



Figure 25 – Concavity

4.5.1.3

warping

state of a shape with twisted surface(s)

SEE: Figure 26.




Figure 26 – Warping

4.5.1.4

bending

deflection, curved or angular, from any direction that is regarded as the intended deflection