

INTERNATIONAL STANDARD

IEC
60684-3-214

Second edition
2005-11

Flexible insulating sleeving –

Part 3:

Specifications for individual types of sleeving –

Sheet 214: Heat-shrinkable, polyolefin sleeving, not flame retarded, shrink ratio 3:1 –

Thick and medium wall



Reference number
IEC 60684-3-214:2005(E)

Publication numbering

As from 1 January 1997 all IEC publications are issued with a designation in the 60000 series. For example, IEC 34-1 is now referred to as IEC 60034-1.

Consolidated editions

The IEC is now publishing consolidated versions of its publications. For example, edition numbers 1.0, 1.1 and 1.2 refer, respectively, to the base publication, the base publication incorporating amendment 1 and the base publication incorporating amendments 1 and 2.

Further information on IEC publications

The technical content of IEC publications is kept under constant review by the IEC, thus ensuring that the content reflects current technology. Information relating to this publication, including its validity, is available in the IEC Catalogue of publications (see below) in addition to new editions, amendments and corrigenda. Information on the subjects under consideration and work in progress undertaken by the technical committee which has prepared this publication, as well as the list of publications issued, is also available from the following:

- **IEC Web Site** (www.iec.ch)

- **Catalogue of IEC publications**

The on-line catalogue on the IEC web site (www.iec.ch/searchpub) enables you to search by a variety of criteria including text searches, technical committees and date of publication. On-line information is also available on recently issued publications, withdrawn and replaced publications, as well as corrigenda.

- **IEC Just Published**

This summary of recently issued publications (www.iec.ch/online_news/justpub) is also available by email. Please contact the Customer Service Centre (see below) for further information.

- **Customer Service Centre**

If you have any questions regarding this publication or need further assistance, please contact the Customer Service Centre:

Email: custserv@iec.ch
Tel: +41 22 919 02 11
Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

IEC
60684-3-214

Second edition
2005-11

Flexible insulating sleeving –

Part 3:

Specifications for individual types of sleeving –

Sheet 214: Heat-shrinkable, polyolefin sleeving, not flame retarded, shrink ratio 3:1 –

Thick and medium wall

© IEC 2005 — Copyright - all rights reserved

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Electrotechnical Commission, 3, rue de Varembé, PO Box 131, CH-1211 Geneva 20, Switzerland
Telephone: +41 22 919 02 11 Telefax: +41 22 919 03 00 E-mail: inmail@iec.ch Web: www.iec.ch



Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

PRICE CODE

L

For price, see current catalogue

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Designation	7
4 Conditions of test	7
5 Requirements	7
6 Sleeving conformance	7
Table 1 – Dimensional and mass requirements – Type A	8
Table 2 – Dimensional and mass requirements – Type B	8
Table 3 – Property requirements	9
Table 4 – Requirements for breakdown voltage	10
Table 5 – Resistance to selected fluids	11
Table 6 – Additional property requirements	11

IECNORM.COM : Click to view the full PDF of IEC 60684-3-214:2005

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

**Part 3: Specifications for individual types of sleeving –
Sheet 214: Heat-shrinkable, polyolefin sleeving,
not flame retarded, shrink ratio 3:1 – Thick and medium wall**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60684-3-214 has been prepared by IEC technical committee 15: Standards on specifications for electrical Insulating materials.

This second edition replaces the first edition (2001) and constitutes a technical revision.

The main change with respect to the previous edition is as follows:

The thermal endurance test method according to IEC 60216 has been replaced with a long term ageing test i.e. 3 000 h (see Amendment 1 to IEC 60684-2), at the recommended maximum temperature found suitable for use, to provide safe thermal test data within a workable time scale.

The text of this standard is based on the following documents:

FDIS	Report on voting
15/230/FDIS	15/248/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

INTRODUCTION

This International Standard is one of a series which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

- Part 1: Definitions and general requirements (IEC 60684-1)
- Part 2: Methods of test (IEC 60684-2)
- Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This standard comprises one of the sheets of Part 3 as follows:

Sheet 214: Heat-shrinkable, polyolefin sleeving, not flame retarded, shrink ratio 3:1 – Thick and medium wall

Withdrawing
IECNORM.COM: Click to view the full PDF of IEC 60684-3-214:2005

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 214: Heat-shrinkable, polyolefin sleeving, not flame retarded, shrink ratio 3:1 – Thick and medium wall

1 Scope

This standard gives the requirements for two types of heat-shrinkable, not flame retarded, polyolefin sleeving with a nominal shrink ratio of 3:1 and with thick and medium wall. This sleeving has been found suitable at temperatures up to 135 °C.

- Type A: Medium wall – internal diameter of up to 180,0 mm.
- Type B: Thick wall – internal diameter of up to 160,0 mm.

These sleeveings are normally supplied in black.

Sizes or colours other than those specifically listed in this standard may be available as custom items. These items are in compliance with this standard if they comply with the property requirements listed in Tables 3, 4, 5 and 6 except for dimensions and mass.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60296:2003, *Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear*
Amendment 1 (2003)

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:1997, *Flexible insulating sleeving – Part 2: Methods of test*
Amendment 1 (2003)

IEC 60757:1983, *Code for designation of colours*

ISO 846:1997, *Plastics – Evaluation of the action of microorganisms*

3 Designation

This sleeving shall be identified by the following designation:

Description	IEC publication number	IEC Part number	IEC Sheet number	Type	Size (expanded/ recovered internal diameter, in mm)	Colour
↓	↓	↓	↓	↓	↓	↓
Sleeving	IEC 60684	-3	-214	B	- 85,0/25,0	- BK

Any colour abbreviation shall comply with IEC 60757, where applicable. Where no abbreviation is given, the colour shall be written in full.

4 Conditions of test

Unless otherwise specified, the sleeving shall be shrunk in a forced air circulation oven for (10 ± 1) min at $150 \text{ }^{\circ}\text{C} \pm 3 \text{ K}$ prior to testing.

5 Requirements

In addition to the general requirements given in IEC 60684-1, the sleeving shall comply with the requirements in Tables 1 to 6.

6 Sleeving conformance

Conformance to the requirements of this specification shall normally be based on the results obtained for black sleeveings of the following sizes:

- Type A: 85,0 mm/25,0 mm,
- Type B: 85,0 mm/25,0 mm.

The colour fastness to light shall be determined for all colours.

Table 1 – Dimensional and mass requirements – Type A

Size code	Internal diameter mm		Recovered wall thickness mm	Mass per unit length g/m Max.
	Expanded Min.	Recovered Max.		
10,0/3,0	10,0	3,0	1,20 ± 0,20	21,4
16,0/5,0	16,0	5,0	1,70 ± 0,30	53,7
25,0/8,0	25,0	8,0	2,30 ± 0,30	106
35,0/12,0	35,0	12,0	2,30 ± 0,30	147
50,0/16,0	50,0	16,0	2,30 ± 0,30	196
63,0/19,0	63,0	19,0	2,80 ± 0,40	285
75,0/22,0	75,0	22,0	3,20 ± 0,50	385
85,0/25,0	85,0	25,0	3,30 ± 0,50	430
95,0/29,0	95,0	29,0	3,60 ± 0,50	552
115,0/34,0	115,0	34,0	3,70 ± 0,60	636
140,0/42,0	140,0	42,0	3,70 ± 0,60	716
160,0/50,0	160,0	50,0	3,80 ± 0,60	894
180,0/60,0	180,0	60,0	3,80 ± 0,60	1 072

Table 2 – Dimensional and mass requirements – Type B

Size code	Internal diameter mm		Recovered wall thickness mm	Mass per unit length g/m Max.
	Expanded Min.	Recovered Max.		
9,0/3,0	9,0	3,0	2,30 ± 0,30	55,0
13,0/4,0	13,0	4,0	2,80 ± 0,40	87,0
20,0/6,0	20,0	6,0	2,90 ± 0,40	115
33,0/8,0	33,0	8,0	3,75 ± 0,55	210
43,0/12,0	43,0	12,0	4,90 ± 0,60	360
51,0/16,0	51,0	16,0	5,00 ± 0,65	466
70,0/21,0	70,0	21,0	5,00 ± 0,65	572
85,0/25,0	85,0	25,0	5,00 ± 0,65	691
90,0/30,0	90,0	30,0	5,00 ± 0,65	815
130,0/36,0	130,0	36,0	5,00 ± 0,70	986
160,0/50,0	160,0	50,0	5,00 ± 0,70	1 307

Table 3 – Property requirements

Property	IEC 60684-2 Clause or subclause	Units	Max. or Min.	Requirements	Remarks
Dimensions	3				
– Internal diameter	3.1.2	mm		Tables 1 and 2	
– Wall thickness	3.3.2	mm		Tables 1 and 2	
– Concentricity	3.3.3	%			
• Expanded			Min.	50	
• Recovered			Min.	85	
Heat shock	6				Heat at 200 °C ± 5 K
Tensile strength	19.1 and 19.2	MPa	Min.	10	
Elongation at break	19.1 and 19.2	%	Min.	200	
Longitudinal change	9	%	Max.	–15 +5	Heat expanded sleeving at 150 °C ± 3 K for (10 ± 1) min
Bending at low temperature	14	–	–	No cracking shall be visible	Test at –40 °C after conditioning at the same temperature for 4 h For strips, the mandrel shall be between 20 and 22 times the wall thickness Full section sleeving is tested unfilled, and the mandrel shall be between 20 and 22 times the outer diameter
Dimensional stability on storage	16	–	–	The dimensions shall be as specified in Tables 1 and 2	
Tensile strength	19.1 and 19.2	MPa	Min.	13	Use a jaw separation rate of 100 mm/min. For internal diameters of <6,5 mm, use sleeving samples for testing. For diameters of 6,5 mm and more, use dumb-bell samples cut from sleeving
Elongation at break	19.1 and 19.2	%	Min.	350	
Secant modulus at 2 % elongation	19.4	MPa	Min.	80	
		MPa	Max.	160	
Volume resistivity	23				
– at room temperature	23.4.2	Ωm	Min.	10 ¹²	
– after damp heat	23.4.4	Ωm	Min.	10 ¹¹	
Copper corrosion	33	%	Max.	None above the allowable 8 %	Heat the specimens for (16 ± 0,5) h at 150 °C ± 3 K