

INTERNATIONAL STANDARD

IEC
60684-3-233

Second edition
2006-01

Flexible insulating sleeving –

Part 3:

**Specifications for individual types of sleeving –
Sheet 233: Heat-shrinkable fluoroelastomer
sleeving, flame retarded, fluid resistant, shrink
ratio 2:1**



Reference number
IEC 60684-3-233:2006(E)

Publication numbering

As from 1 January 1997 all IEC publications are issued with a designation in the 60000 series. For example, IEC 34-1 is now referred to as IEC 60034-1.

Consolidated editions

The IEC is now publishing consolidated versions of its publications. For example, edition numbers 1.0, 1.1 and 1.2 refer, respectively, to the base publication, the base publication incorporating amendment 1 and the base publication incorporating amendments 1 and 2.

Further information on IEC publications

The technical content of IEC publications is kept under constant review by the IEC, thus ensuring that the content reflects current technology. Information relating to this publication, including its validity, is available in the IEC Catalogue of publications (see below) in addition to new editions, amendments and corrigenda. Information on the subjects under consideration and work in progress undertaken by the technical committee which has prepared this publication, as well as the list of publications issued, is also available from the following:

- **IEC Web Site** (www.iec.ch)

- **Catalogue of IEC publications**

The on-line catalogue on the IEC web site (www.iec.ch/searchpub) enables you to search by a variety of criteria including text searches, technical committees and date of publication. On-line information is also available on recently issued publications, withdrawn and replaced publications, as well as corrigenda.

- **IEC Just Published**

This summary of recently issued publications (www.iec.ch/online_news/justpub) is also available by email. Please contact the Customer Service Centre (see below) for further information.

- **Customer Service Centre**

If you have any questions regarding this publication or need further assistance, please contact the Customer Service Centre:

Email: custserv@iec.ch
Tel: +41 22 919 02 11
Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

IEC
60684-3-233

Second edition
2006-01

Flexible insulating sleeving –

Part 3:

**Specifications for individual types of sleeving –
Sheet 233: Heat-shrinkable fluoroelastomer
sleeving, flame retarded, fluid resistant, shrink
ratio 2:1**

© IEC 2006 — Copyright - all rights reserved

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Electrotechnical Commission, 3, rue de Varembé, PO Box 131, CH-1211 Geneva 20, Switzerland
Telephone: +41 22 919 02 11 Telefax: +41 22 919 03 00 E-mail: inmail@iec.ch Web: www.iec.ch



Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

PRICE CODE

M

For price, see current catalogue

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Designation	7
4 Conditions of test.....	7
5 Requirements	7
6 Sleeving conformance.....	7
7 Breakdown voltage	11
Table 1 – Type A Dimensional and mass requirements	8
Table 2 – Type B Dimensional and mass requirements	8
Table 3 – Property requirements	9
Table 4 – Requirements for breakdown voltage	12
Table 5 – Resistance to selected fluids.....	12
Table 6 – Additional property requirements.....	12

IECNORM.COM : Click to view the full PDF of IEC 60684-3-233:2006

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

**Part 3: Specifications for individual types of sleeving –
Sheet 233: Heat-shrinkable fluoroelastomer sleeving,
flame retarded, fluid resistant, shrink ratio 2:1**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60684-3-233 has been prepared by IEC technical committee 15: Standards on specifications for electrical Insulating materials.

This second edition cancels and replaces the first edition, published in 1998, and constitutes a technical revision.

The main change with regard to the previous edition concerns the replacement of the thermal endurance test, according to IEC 60216, by a long-term ageing test, i.e. 3 000 h, at the maximum recommended temperature for such use, in order to furnish thermal test data within a workable time frame.

The text of this standard is based on the following documents:

FDIS	Report on voting
15/231/FDIS	15/249/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IECNORM.COM : Click to view the full PDF of IEC 60684-3-233:2006

INTRODUCTION

This International Standard is one of a series which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60684-1)

Part 2: Methods of test (IEC 60684-2)

Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This standard gives one of the sheets comprising part 3 as follows:

Sheet 233: Heat-shrinkable fluoroelastomer sleeving, flame retarded, fluid resistant, shrink ratio 2:1.

IECNORM.COM : Click to view the full PDF of IEC 60684-3-233:2006

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 233: Heat-shrinkable fluoroelastomer sleeving, flame retarded, fluid resistant, shrink ratio 2:1

1 Scope

This standard gives the requirements for two types of heat-shrinkable, flame retarded, fluid resistant¹⁾, nominal shrink ratio 2:1, fluoroelastomer sleeving for use at temperatures up to 200 °C:

- Type A: thick wall;
- Type B: thin wall.

These sleeveings are normally supplied with internal diameters up to 51 mm, and the standard colour is black.

Sizes or colours other than those specifically listed in this standard may be available as custom items. These items shall be considered to comply with this standard if they comply with the property requirements listed in Tables 3, 4, 5 and 6 except for dimensions and mass

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:1997, *Flexible insulating sleeving – Part 2: Methods of test*

Amendment (2003)

IEC 60757:1983, *Code for designation of colours*

ISO 846:1997, *Plastics – Evaluation of the action of micr-organisms*

ISO 1817:1999, *Rubber, vulcanized – Determination of the effect of liquids*

¹⁾ Except to phosphate ester-based hydraulic fluids.

3 Designation

The sleeving shall be identified by the following designation:

Description	IEC publication number	IEC Part number	IEC sheet number	Type	Size (expanded and recovered internal diameter in mm)	Colour
↓	↓	↓	↓	↓	↓	↓
Sleeving	IEC 60684	- 3	-233	-A	- 12,7/6,4	- BK

Any colour abbreviation shall comply with IEC 60757, where applicable. Non-standard colours shall be written out in full.

4 Conditions of test

Unless otherwise specified, the sleeving shall be shrunk in a forced air circulation oven for (5 ± 1) min at $200\text{ °C} \pm 5\text{ K}$ prior to testing.

5 Requirements

In addition to the general requirements given in IEC 60684-1, the sleeving shall comply with the requirements of Tables 1, 2, 3, 4, 5 and 6.

6 Sleeving conformance

Product conformance shall normally be based on the results from size 12,7/6,4 mm black sleeving. The colour fastness to light shall be qualified for all colours.

Table 1 – Type A dimensional and mass requirements

Size code	Internal diameter mm		Recovered wall thickness mm	Mass per unit length g/m Max.
	Expanded min.	Recovered max.		
3,2 / 1,6	3,2	1,6	$0,75 \pm 0,15$	13,8
4,8 / 2,4	4,8	2,4	$0,85 \pm 0,20$	22,2
6,4 / 3,2	6,4	3,2	$0,90 \pm 0,20$	29,0
9,5 / 4,8	9,5	4,8	$1,00 \pm 0,20$	44,1
12,7 / 6,4	12,7	6,4	$1,20 \pm 0,30$	72,6
19,0 / 9,5	19,0	9,5	$1,45 \pm 0,35$	125
25,4 / 12,7	25,4	12,7	$1,80 \pm 0,45$	206
38,0 / 19,0	38,0	19,0	$2,40 \pm 0,50$	389
51,0 / 25,4	51,0	25,4	$2,80 \pm 0,50$	580

Table 2 – Type B dimensional and mass requirements

Size code	Internal diameter mm		Recovered wall thickness mm	Mass per unit length g/m Max.
	Expanded min.	Recovered max.		
3,2 / 1,6	3,2	1,6	$0,90 \pm 0,20$	20,5
4,8 / 2,4	4,8	2,4	$0,90 \pm 0,20$	26,6
6,4 / 3,2	6,4	3,2	$0,90 \pm 0,20$	32,7
9,5 / 4,8	9,5	4,8	$0,90 \pm 0,20$	44,8
12,7 / 6,4	12,7	6,4	$0,90 \pm 0,20$	57,0
19,0 / 9,5	19,0	9,5	$1,10 \pm 0,20$	97,0
25,4 / 12,7	25,4	12,7	$1,20 \pm 0,30$	147
38,0 / 19,0	38,0	19,0	$1,40 \pm 0,40$	259
51,0 / 25,4	51,0	25,4	$1,70 \pm 0,40$	409
76,2/38,1	76,2	38,1	$1,70 \pm 0,40$	600

Table 3 – Property requirements

Property	IEC 60684-2 Clause or subclause	Units	Max. or min.	Requirements	Remarks
Dimensions	3				
– internal diameter	3.1.2	mm		Tables 1 and 2	
– wall thickness	3.3.2	mm	Min.	Tables 1 and 2	
– concentricity	3.3.3	%			
• expanded				65	
• recovered				85	
Heat shock	6				Heat at 300 °C ± 5 K
Tensile strength	19.1 and 19.2	MPa	Min.	8	
Elongation at break	19.1 and 19.2	%	Min.	150	
Longitudinal change	9	%	Max.	± 20	Heat the expanded sleeving at 200 °C ± 5 K for (15 ± 1) min
Bending at low temperature	14	–	–	There shall be no signs of cracking	Test temperature –55 °C ± 3 K. For strips, the mandrel shall be no more than 20 times the wall thickness. Full section sleeving is tested unfilled and the mandrel shall be no more than 20 times the outer diameter
Dimensional stability on storage	16	–	–	The dimensions shall be as specified in Tables 1 and 2	
Tensile strength	19.1 and 19.2	MPa	Min.	8,2	Rate of jaw separation 100 mm/min.
Elongation at break	19.1 and 19.2	%	Min.	250	Below 6,5 mm diameter as sleeving; at 6,5 mm diameter and above as dumb-bells
Secant modulus at 2 % elongation	19.4	MPa MPa	Min. Max.	30 100	
Breakdown voltage	21	kV	Min.	Table 4	
Volume resistivity	23				
– at room temperature	23.4.2	Ω m	Min.	10 ¹⁰	
– after damp heat	23.4.4	Ω m	Min.	10 ⁹	
Flame propagation	26				
Time of burning	Method C	s	Max.	30	
Length burned		mm	Max.	75	

Table 3 (continued)

Property	IEC 60684-2 Clause or subclause	Units	Max. or min.	Requirements	Remarks
Copper corrosion	33	%	Max.	None above the allowable 8 %	Heat for (16 ± 0,5) h at 175 °C ± 3 K
Colour fastness to light	34			The colour contrast between the exposed and unexposed parts of the specimens shall be equal to or less than that of the fastness standard	Fastness standard No. 5
Resistance to selected fluids	36				Use the fluids and test temperatures specified in Table 5
Tensile strength	19.1 and 19.2	MPa	Min.	8	
Elongation at break	19.1 and 19.2	%	Min.	200	
Mass per unit length	38	g/m	Max.	Tables 1 and 2	
Heat ageing	39				Heat at 250 °C ± 5 K
Tensile strength	19.1 and 19.2	MPa	Min.	8,2	
Elongation at break	19.1 and 19.2	%	Min.	150	
Water absorption	40	%	Max.	1,0	
Long term ageing	50				; The ageing temperature shall be 200 °C ± 5K
Elongation	19.1 and 19.2	%	Min	125	

IECNORM.COM : Click to view the full PDF of IEC 60684-3-233:2006