

INTERNATIONAL STANDARD



**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IECNORM.COM : Click to view the full text of IEC publications
IEC 61851-2:2019 RLV

INTERNATIONAL STANDARD



**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.035.20

ISBN 978-2-8322-7327-2

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	3
INTRODUCTION	2
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Designation	7
5 Conditions of test	7
6 Requirements	7
7 Sleeving conformance	7
Annex A (informative) Guidance to the available sizes and wall thicknesses	12
Bibliography	13
Table 1 – Property requirements	8
Table 2 – Requirements for dielectric strength	10
Table 3 – Resistance to selected fluids	10
Table 4 – Additional property requirements	11
Table A.1 – Type A, medium wall	12
Table A.2 – Type B, thick wall	12

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60684-3-283 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 2010 and Amendment 1:2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) change of moulded plaque thickness for resistance to tracking and weathering tests to $(6 \pm 0,5)$ mm.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
15/892/FDIS	15/901/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60684 series, published under the general title *Flexible insulating sleeving*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

This document is one of a series of standards which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60684-1)

Part 2: Methods of test (IEC 60684-2)

Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This document comprises one of the sheets of Part 3 as follows:

Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation.

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 RLV

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation

1 Scope

This part of IEC 60684 gives the requirements for two types of heat-shrinkable, polyolefin sleeving for bus-bar insulation, with a nominal shrink ratio of 2,5:1.

This sleeving has been found suitable up to temperatures of 100 °C.

- Type A: Medium wall – internal diameter up to 170,0 mm typically
- Type B: Thick wall – internal diameter up to 165,0 mm typically

These sleeveings are normally supplied in colour, red or brown.

Since these types of sleeveings cover a significantly large range of sizes and wall thicknesses, Annex A (Tables A.1 and A.2) provides guidance to the range of sizes available. The actual size and wall thickness shall will be agreed between the user and supplier depending on the electric strength of the installed tubing offered and the requirements of the user.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should will be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60296:2003/2012, *Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear*

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:1997/2011, *Flexible insulating sleeving – Part 2: Methods of test*
~~Amendment 1 (2003)~~
~~Amendment 2 (2005)~~

IEC 60757:1983, *Code for designation of colours*

ISO 846:1997/2019, *Plastics – Evaluation of the action of microorganisms*

ISO 4892-3:2006/2016, *Plastics – Methods of exposure to laboratory light sources – Part 3: Fluorescent UV lamps*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Designation

The sleeving shall be identified by the following designation:

Description	IEC publication number	IEC part number	IEC sheet number	Type	Size (expanded and recovered internal diameter in millimetres)	Colour	Table 4 ^a code
↓	↓	↓	↓	↓	↓	↓	↓
Sleeving	IEC 60684	- 3	-283	A	- 75,0/30,0	-Red	X

^a **NOTE 1** The addition of "X" at the end of the designation indicates that the properties contained in Table 4 have been agreed upon between the user and the supplier.

Any colour abbreviation shall comply with IEC 60757, where applicable. Non-standard colours shall be written out in full.

NOTE 2 This is for package labelling only in accordance with IEC 60684-1.

5 Conditions of test

Unless otherwise specified, the sleeving shall be shrunk in a forced air circulation oven for (10 ± 1) min at $200 \text{ }^{\circ}\text{C} \pm 3 \text{ K}$ prior to testing.

6 Requirements

In addition to the general requirements given in IEC 60684-1, the sleeving shall comply with the requirements of Tables 1, 2, 3, and 4 where applicable.

7 Sleeving conformance

Conformance to the requirements of this specification shall normally be based on the results from typical sizes:

- Type A: Recovered ID 25 mm to 30 mm
- Type B: Recovered ID 25 mm to 40 mm

Table 1 – Property requirements

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Dimensions Internal diameter Wall thickness Concentricity – expanded – recovered	3 3.1.2 3.3.2 3.3.3	mm mm %	Min. Min.	To be agreed between the purchaser and the supplier 60 85	
Heat shock Tensile strength Elongation at break	6 19.42 and 19.23 19.42 and 19.23	MPa %	Min. Min.	5 200	Heat at 150 °C ± 5 K Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Longitudinal change	9	%	Max.	–10 +5	
Bending at low temperature	14	–	–	No cracking shall be visible.	Test at –40 °C For strips, the mandrel shall be between 20 times and 22 times the wall thickness. Full section sleeving is tested unfilled and the mandrel shall be between 20 times and 22 times the outer diameter.
Dimensional stability on storage	16		–	The dimensions shall remain as agreed	See Clause 1
Tensile strength Elongation at break	19.42 and 19.23 19.42 and 19.23	MPa %	Min. Min.	8 400	Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Secant modulus at 2 % elongation	19.45	MPa	Max.	160	
Dielectric strength	24	kV/mm	Min.	See Table 2.	
Breakdown voltage	21.2	kV/mm	Min.	See Table 2	
Volume resistivity at room temperature	23 23.45.2	Ω·m	Min.	10 ¹¹	

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Flame propagation	26 Method C	s mm	Max. Max.	60 100	Burning includes flaming and glowing
Corrosion resistance Elongation	32 19.42 and 19.23	%	Min.	No chemical interaction	Heat at 150 °C ± 3 K Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Resistance to selected fluids Tensile strength Elongation at break	36 19.42 and 19.23 19.42 and 19.23	MPa %	Min. Min.	5 200	Use the fluids and test temperatures specified in Table 3 Immersion (24 ± 1) h Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Heat ageing Tensile strength Elongation at break	39 19.42 and 19.23 19.42 and 19.23	MPa %	Min. Min.	5 200	Heat at 150 °C ± 3 K Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Long term ageing Elongation at break	50 19.2 and 19.3	%	Min.	150	The ageing temperature shall be 100 °C ± 3 K Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving

Table 2 – Requirements for dielectric strength

Expanded wall thickness mm	Dielectric strength ^a	
	Min.	
All dimensions	Expanded ID Types A+B All sizes	Dielectric strength kV/mm 12
NOTE Care should be taken on selection of sizes based on these values. Refer to the manufacturer for actual values on installed conditions.		
^a Measure the expanded wall thickness and calculate the electric strength by dividing the breakdown voltage by this value.		

~~The breakdown voltage shall be determined by the method described in 21 of IEC 60684-2. All values shall comply with the minimum value in this table.~~

The sleeving shall be tested in the expanded condition.

The rate of application of the voltage shall be 500 V/s.

Table 3 – Resistance to selected fluids

Test fluid No.	Fluids	Type	Standard or symbol	Immersion temperature °C ± 2 K
1	Insulating oil	Mineral based	IEC 60296	23
2	Cleaning fluid	Solvent	Isopropyl alcohol	23
3	-	Water	De-ionized	85

Other fluids and/or temperatures may be specified for customers with specific needs. These additional fluids and/or temperatures shall be applicable when incorporated into agreements between the supplier and the customer.

Table 4 – Additional property requirements

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirement	Remarks
Fungus resistance Tensile strength Elongation	19.12 and 19.23	MPa %	Min. Min.	7 350	The test method shall be ISO 846 Method B 56 days exposure Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Resistance to weathering	ISO 4892-3 Method C After 5 000 h Test to 19.1 19.2 and 19.3 19.2 and 19.3 25	MPa %	Min. Min. Min.	8 200 2,5 kV for 20 min	Test method to ISO 4892-3 Samples for test 19.12 and 19.23 should be taken from recovered sleeving which is flattened. Use a jaw separation rate of 100 mm/min Samples for Test 25 should be taken from specially prepared test sheets (6 ± 0,1 0,5) mm thick. All samples should be cut to the appropriate size to fit the sample holders. Intermediate tests may also be done at 1 000 h intervals as an intermediate check on performance.
Resistance to tracking	25	–	Min.	Class 2A 2,5 kV for 1 h	Specimens shall be prepared from cross-linked moulded plaques of thickness (6 ± 0,1 0,5) mm Specimens shall not be abraded but cleaned with an appropriate solvent. The method of cleaning shall be recorded.

Annex A (informative)

Guidance to the available sizes and wall thicknesses

Table A.1 – Type A, medium wall

Internal diameter		Wall
Expanded Min. mm	Recovered Max. mm	Recovered wall thickness ± 20 %
15,0	6,0	2,0
30,0	12,0	2,3
50,0	20,0	2,5
70,0	25,0	3,0
75,0	30,0	2,5
90,0	30,0	3,0
100,0	40,0	2,5
120,0	50,0	3,0
170,0	60,0	3,0

Table A.2 – Type B, thick wall

Internal diameter		Wall
Expanded Min. mm	Recovered Max. mm	Recovered wall thickness ± 20 %
25,0	10,0	4,0
40,0	16,0	4,0
65,0	25,0	4,0
100,0	40,0	4,0
165,0	60,0	4,0

Bibliography

IEC 60684-3 (all sheets), *Flexible insulating sleeving – Part 3: Specifications for individual types of sleeving*

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 RLV

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 RLV

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation**

**Gaines isolantes souples –
Partie 3: Spécifications pour types particuliers de gaines –
Feuille 283: Gaines thermorétractables en polyoléfine pour isolation de barres
omnibus**

CONTENTS

FOREWORD	3
INTRODUCTION	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Designation	7
5 Conditions of test	7
6 Requirements	7
7 Sleeving conformance	7
Annex A (informative) Guidance to the available sizes and wall thicknesses	12
Bibliography	13
Table 1 – Property requirements	8
Table 2 – Requirements for dielectric strength	10
Table 3 – Resistance to selected fluids	10
Table 4 – Additional property requirements	11
Table A.1 – Type A, medium wall	12
Table A.2 – Type B, thick wall	12

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 RLV

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

**Part 3: Specifications for individual types of sleeving –
Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60684-3-283 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 2010 and Amendment 1:2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) change of moulded plaque thickness for resistance to tracking and weathering tests to $(6 \pm 0,5)$ mm.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
15/892/FDIS	15/901/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60684 series, published under the general title *Flexible insulating sleeving*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 REV

INTRODUCTION

This document is one of a series of standards which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60684-1)

Part 2: Methods of test (IEC 60684-2)

Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This document comprises one of the sheets of Part 3 as follows:

Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation.

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 RLV

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation

1 Scope

This part of IEC 60684 gives the requirements for two types of heat-shrinkable, polyolefin sleeving for bus-bar insulation, with a nominal shrink ratio of 2,5:1.

This sleeving has been found suitable up to temperatures of 100 °C.

- Type A: Medium wall – internal diameter up to 170,0 mm typically
- Type B: Thick wall – internal diameter up to 165,0 mm typically

These sleeveings are normally supplied in colour, red or brown.

Since these types of sleeving cover a significantly large range of sizes and wall thicknesses, Annex A (Tables A.1 and A.2) provides guidance to the range of sizes available. The actual size and wall thickness will be agreed between the user and supplier depending on the electric strength of the installed tubing offered and the requirements of the user.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application will be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60296:2012, *Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear*

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:2011, *Flexible insulating sleeving – Part 2: Methods of test*

IEC 60757:1983, *Code for designation of colours*

ISO 846:2019, *Plastics – Evaluation of the action of microorganisms*

ISO 4892-3:2016, *Plastics – Methods of exposure to laboratory light sources – Part 3: Fluorescent UV lamps*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Designation

The sleeving shall be identified by the following designation:

Description	IEC publication number	IEC part number	IEC sheet number	Type	Size (expanded and recovered internal diameter in millimetres)	Colour	Table 4 code
↓	↓	↓	↓	↓	↓	↓	↓
Sleeving	IEC 60684	- 3	-283	A	- 75,0/30,0	-Red	X

NOTE 1 The addition of "X" at the end of the designation indicates that the properties contained in Table 4 have been agreed upon between the user and the supplier.

Any colour abbreviation shall comply with IEC 60757, where applicable. Non-standard colours shall be written out in full.

NOTE 2 This is for package labelling only in accordance with IEC 60684-1.

5 Conditions of test

Unless otherwise specified, the sleeving shall be shrunk in a forced air circulation oven for (10 ± 1) min at $200 \text{ }^{\circ}\text{C} \pm 3 \text{ K}$ prior to testing.

6 Requirements

In addition to the general requirements given in IEC 60684-1, the sleeving shall comply with the requirements of Tables 1, 2, 3, and 4 where applicable.

7 Sleeving conformance

Conformance to the requirements of this specification shall normally be based on the results from typical sizes:

- Type A: Recovered ID 25 mm to 30 mm
- Type B: Recovered ID 25 mm to 40 mm

Table 1 – Property requirements

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Dimensions Internal diameter Wall thickness Concentricity – expanded – recovered	3 3.1.2 3.3.2 3.3.3	mm mm %	Min. Min.	To be agreed between the purchaser and the supplier 60 85	
Heat shock Tensile strength Elongation at break	6 19.2 and 19.3 19.2 and 19.3	MPa %	Min. Min.	5 200	Heat at 150 °C ± 5 K Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Longitudinal change	9	%	Max.	–10 +5	
Bending at low temperature	14	–	–	No cracking shall be visible.	Test at –40 °C For strips, the mandrel shall be between 20 times and 22 times the wall thickness. Full section sleeving is tested unfilled and the mandrel shall be between 20 times and 22 times the outer diameter.
Dimensional stability on storage	16		–	The dimensions shall remain as agreed	See Clause 1
Tensile strength Elongation at break	19.2 and 19.3 19.2 and 19.3	MPa %	Min. Min.	8 400	Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Secant modulus at 2 % elongation	19.5	MPa	Max.	160	
Breakdown voltage	21.2	kV/mm	Min.	See Table 2	
Volume resistivity at room temperature	23 23.5.2	Ω·m	Min.	10 ¹¹	

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Flame propagation	26 Method C	s mm	Max. Max.	60 100	Burning includes flaming and glowing
Corrosion resistance Elongation	32 19.2 and 19.3	%	Min.	No chemical interaction	Heat at 150 °C ± 3 K Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Resistance to selected fluids Tensile strength Elongation at break	36 19.2 and 19.3 19.2 and 19.3	MPa %	Min. Min.	5 200	Use the fluids and test temperatures specified in Table 3 Immersion (24 ± 1) h Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Heat ageing Tensile strength Elongation at break	39 19.2 and 19.3 19.2 and 19.3	MPa %	Min. Min.	5 200	Heat at 150 °C ± 3 K Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Long term ageing Elongation at break	50 19.2 and 19.3	%	Min.	150	The ageing temperature shall be 100 °C ± 3 K Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving

Table 2 – Requirements for dielectric strength

Expanded wall thickness mm	Dielectric strength ^a	
	Min.	
All dimensions	Expanded ID Types A+B All sizes	Dielectric strength kV/mm 12
Care should be taken on selection of sizes based on these values. Refer to the manufacturer for actual values on installed conditions.		
^a Measure the expanded wall thickness and calculate the electric strength by dividing the breakdown voltage by this value.		

The sleeving shall be tested in the expanded condition.

The rate of application of the voltage shall be 500 V/s.

Table 3 – Resistance to selected fluids

Test fluid No.	Fluids	Type	Standard or symbol	Immersion temperature °C ± 2 K
1	Insulating oil	Mineral based	IEC 60296	23
2	Cleaning fluid	Solvent	Isopropyl alcohol	23
3	-	Water	De-ionized	85

Other fluids and/or temperatures may be specified for customers with specific needs. These additional fluids and/or temperatures shall be applicable when incorporated into agreements between the supplier and the customer.

Table 4 – Additional property requirements

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirement	Remarks
Fungus resistance Tensile strength Elongation	19.2 and 19.3	MPa %	Min. Min.	7 350	The test method shall be ISO 846 Method B 56 days exposure Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Resistance to weathering	ISO 4892-3 Method C After 3 000 h Test to 19.2 and 19.3 19.2 and 19.3 25	MPa %	Min. Min. Min.	8 200 2,5 kV for 20 min	Test method to ISO 4892-3 Samples for test 19.2 and 19.3 should be taken from recovered sleeving which is flattened. Use a jaw separation rate of 100 mm/min Samples for Test 25 should be taken from specially prepared test sheets (6 ± 0,5) mm thick. All samples should be cut to the appropriate size to fit the sample holders. Intermediate tests may also be done at 1 000 h intervals as an intermediate check on performance.
Resistance to tracking	25	–	Min.	Class 2A 2,5 kV for 1 h	Specimens shall be prepared from cross-linked moulded plaques of thickness (6 ± 0,5) mm Specimens shall not be abraded but cleaned with an appropriate solvent. The method of cleaning shall be recorded.

Annex A (informative)

Guidance to the available sizes and wall thicknesses

Table A.1 – Type A, medium wall

Internal diameter		Wall
Expanded Min. mm	Recovered Max. mm	Recovered wall thickness ± 20 %
15,0	6,0	2,0
30,0	12,0	2,3
50,0	20,0	2,5
70,0	25,0	3,0
75,0	30,0	2,5
90,0	30,0	3,0
100,0	40,0	2,5
120,0	50,0	3,0
170,0	60,0	3,0

Table A.2 – Type B, thick wall

Internal diameter		Wall
Expanded Min. mm	Recovered Max. mm	Recovered wall thickness ± 20 %
25,0	10,0	4,0
40,0	16,0	4,0
65,0	25,0	4,0
100,0	40,0	4,0
165,0	60,0	4,0

Bibliography

IEC 60684-3 (all sheets), *Flexible insulating sleeving – Part 3: Specifications for individual types of sleeving*

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 RLV

SOMMAIRE

AVANT-PROPOS	15
INTRODUCTION.....	17
1 Domaine d'application	18
2 Références normatives	18
3 Termes et définitions	19
4 Désignation	19
5 Conditions d'essai	19
6 Exigences.....	19
7 Conformité des gaines	19
Annexe A (informative) Guide des tailles épaisseurs de paroi disponibles.....	24
Bibliographie.....	25
Tableau 1 – Exigences relatives aux propriétés	20
Tableau 2 – Exigences relative à la rigidité diélectrique	22
Tableau 3 – Résistance aux fluides choisis	22
Tableau 4 – Exigences complémentaires relatives aux propriétés	23
Tableau A.1 – Type A, paroi moyenne	24
Tableau A.2 – Type B, paroi épaisse.....	24

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 RLV

COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

GAINES ISOLANTES SOUPLES –

**Partie 3: Spécifications pour types particuliers de gaines –
Feuille 283: Gainés thermorétractables en polyoléfine
pour isolation de barres omnibus**

AVANT-PROPOS

- 1) La Commission Electrotechnique Internationale (IEC) est une organisation mondiale de normalisation composée de l'ensemble des comités électrotechniques nationaux (Comités nationaux de l'IEC). L'IEC a pour objet de favoriser la coopération internationale pour toutes les questions de normalisation dans les domaines de l'électricité et de l'électronique. A cet effet, l'IEC – entre autres activités – publie des Normes internationales, des Spécifications techniques, des Rapports techniques, des Spécifications accessibles au public (PAS) et des Guides (ci-après dénommés "Publication(s) de l'IEC"). Leur élaboration est confiée à des comités d'études, aux travaux desquels tout Comité national intéressé par le sujet traité peut participer. Les organisations internationales, gouvernementales et non gouvernementales, en liaison avec l'IEC, participent également aux travaux. L'IEC collabore étroitement avec l'Organisation Internationale de Normalisation (ISO), selon des conditions fixées par accord entre les deux organisations.
- 2) Les décisions ou accords officiels de l'IEC concernant les questions techniques représentent, dans la mesure du possible, un accord international sur les sujets étudiés, étant donné que les Comités nationaux de l'IEC intéressés sont représentés dans chaque comité d'études.
- 3) Les Publications de l'IEC se présentent sous la forme de recommandations internationales et sont agréées comme telles par les Comités nationaux de l'IEC. Tous les efforts raisonnables sont entrepris afin que l'IEC s'assure de l'exactitude du contenu technique de ses publications; l'IEC ne peut pas être tenue responsable de l'éventuelle mauvaise utilisation ou interprétation qui en est faite par un quelconque utilisateur final.
- 4) Dans le but d'encourager l'uniformité internationale, les Comités nationaux de l'IEC s'engagent, dans toute la mesure possible, à appliquer de façon transparente les Publications de l'IEC dans leurs publications nationales et régionales. Toutes divergences entre toutes Publications de l'IEC et toutes publications nationales ou régionales correspondantes doivent être indiquées en termes clairs dans ces dernières.
- 5) L'IEC elle-même ne fournit aucune attestation de conformité. Des organismes de certification indépendants fournissent des services d'évaluation de conformité et, dans certains secteurs, accèdent aux marques de conformité de l'IEC. L'IEC n'est responsable d'aucun des services effectués par les organismes de certification indépendants.
- 6) Tous les utilisateurs doivent s'assurer qu'ils sont en possession de la dernière édition de cette publication.
- 7) Aucune responsabilité ne doit être imputée à l'IEC, à ses administrateurs, employés, auxiliaires ou mandataires, y compris ses experts particuliers et les membres de ses comités d'études et des Comités nationaux de l'IEC, pour tout préjudice causé en cas de dommages corporels et matériels, ou de tout autre dommage de quelque nature que ce soit, directe ou indirecte, ou pour supporter les coûts (y compris les frais de justice) et les dépenses découlant de la publication ou de l'utilisation de cette Publication de l'IEC ou de toute autre Publication de l'IEC, ou au crédit qui lui est accordé.
- 8) L'attention est attirée sur les références normatives citées dans cette publication. L'utilisation de publications référencées est obligatoire pour une application correcte de la présente publication.
- 9) L'attention est attirée sur le fait que certains des éléments de la présente Publication de l'IEC peuvent faire l'objet de droits de brevet. L'IEC ne saurait être tenue pour responsable de ne pas avoir identifié de tels droits de brevets et de ne pas avoir signalé leur existence.

La Norme internationale IEC 60684-3-283 a été établie par le comité d'études 15 de l'IEC: Matériaux isolants électriques solides.

Cette deuxième édition annule et remplace la première édition parue en 2010 et l'Amendement 1:2013. Cette édition constitue une révision technique.

Cette édition inclut la modification technique majeure suivante par rapport à l'édition précédente:

- a) modification de l'épaisseur des plaques moulées pour les essais de résistance aux courants de cheminement et les essais de résistance aux intempéries qui devient $(6 \pm 0,5)$ mm.

Le texte de cette Norme internationale est issu des documents suivants:

FDIS	Rapport de vote
15/892/FDIS	15/901/RVD

Le rapport de vote indiqué dans le tableau ci-dessus donne toute information sur le vote ayant abouti à l'approbation de cette Norme internationale.

Ce document a été rédigé selon les Directives ISO/IEC, Partie 2.

Une liste de toutes les parties de la série IEC 60684, publiées sous le titre général *Gaines isolantes souples*, peut être consultée sur le site web de l'IEC.

Le comité a décidé que le contenu de ce document ne sera pas modifié avant la date de stabilité indiquée sur le site web de l'IEC sous "<http://webstore.iec.ch>" dans les données relatives au document recherché. A cette date, le document sera

- reconduit,
- supprimé,
- remplacé par une édition révisée, ou
- amendé.

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 REV

INTRODUCTION

Le présent document fait partie d'une série de normes traitant des gaines isolantes souples à usages électriques.

Cette série est constituée de trois parties:

Partie 1: Définitions et exigences générales (IEC 60684-1)

Partie 2: Méthodes d'essai (IEC 60684-2)

Partie 3: Spécifications pour types particuliers de gaines (IEC 60684-3)

Le présent document contient l'une des feuilles qui composent la Partie 3, comme suit:

Feuille 283: Gains thermorétractables en polyoléfine pour isolation de barre omnibus.

IECNORM.COM : Click to view the full PDF of IEC 60684-3-283:2019 RLV

GAINES ISOLANTES SOUPLES –

Partie 3: Spécifications pour types particuliers de gaines – Feuille 283: Gainses thermorétractables en polyoléfine pour isolation de barres omnibus

1 Domaine d'application

La présente partie de l'IEC 60684 donne les exigences relatives à deux types de gaines thermorétractables, en polyoléfine, pour isolation des barres omnibus dont le rapport de rétreint nominal est 2,5:1.

Ces gaines se sont avérées appropriées pour une utilisation à des températures allant jusqu'à 100 °C.

- Type A: Paroi moyenne – diamètre intérieur généralement jusqu'à 170,0 mm
- Type B: Paroi épaisse – diamètre intérieur généralement jusqu'à 165,0 mm

Ces gaines sont normalement disponibles en rouge ou en brun.

Comme ces types de gaines couvrent une plage très étendue de tailles et d'épaisseurs de paroi, l'Annexe A (Tableaux A.1 et A.2) fournit un guide des tailles disponibles dans cette plage. La taille réelle et l'épaisseur de la paroi font l'objet d'un accord entre l'utilisateur et le fournisseur en fonction de la rigidité diélectrique du tube installé et des exigences de l'utilisateur.

Les matériaux conformes à la présente spécification satisfont à des niveaux de performances établis. Cependant, le choix d'un matériau par un utilisateur, pour une application spécifique, est fondé sur les exigences réelles nécessaires pour obtenir des performances adéquates pour l'application concernée, et n'est pas fondé sur cette seule spécification.

2 Références normatives

Les documents suivants cités dans le texte constituent, pour tout ou partie de leur contenu, des exigences du présent document. Pour les références datées, seule l'édition citée s'applique. Pour les références non datées, la dernière édition du document de référence s'applique (y compris les éventuels amendements).

IEC 60296:2012, *Fluides pour applications électrotechniques – Huiles minérales isolantes neuves pour transformateurs et appareillages de connexion*

IEC 60684-1:2003, *Gaines isolantes souples – Partie 1: Définitions et exigences générales*

IEC 60684-2:2011, *Gaines isolantes souples – Partie 2: Méthodes d'essai*

IEC 60757:1983, *Code de désignation de couleurs*

ISO 846:2019, *Plastiques – Évaluation de l'action des micro-organismes*

ISO 4892-3:2016, *Plastiques – Méthodes d'exposition à des sources lumineuses de laboratoire – Partie 3: Lampes fluorescentes UV*

3 Termes et définitions

Aucun terme n'est défini dans le présent document.

L'ISO et l'IEC tiennent à jour des bases de données terminologiques destinées à être utilisées en normalisation, consultables aux adresses suivantes:

- IEC Electropedia: disponible à l'adresse <http://www.electropedia.org/>
- ISO Online browsing platform: disponible à l'adresse <http://www.iso.org/obp>

4 Désignation

Les gaines doivent être identifiées par la désignation suivante:

Description	Numéro de la publication IEC	Numéro de partie IEC	Numéro de la feuille IEC	Type	Taille (diamètre intérieur à l'état expansé et rétreint en mm)	Couleur	Tableau 4 code
↓	↓	↓	↓	↓	↓	↓	↓
Gaine	IEC 60684	- 3	-283	A	- 75,0/30,0	-Rouge	X

NOTE 1 L'ajout de "X" à la fin de la désignation indique que les propriétés contenues dans le Tableau 4 ont fait l'objet d'un accord entre l'utilisateur et le fournisseur.

Toutes les abréviations relatives aux couleurs doivent être conformes à l'IEC 60757, lorsque cela est applicable. Les couleurs non normalisées doivent être indiquées en toutes lettres.

NOTE 2 Cette information est réservée uniquement à l'étiquetage de l'emballage, conformément à l'IEC 60684-1.

5 Conditions d'essai

Sauf spécification contraire, les gaines doivent être rétreintes dans une étuve à circulation d'air forcée pendant (10 ± 1) mm à $200\text{ °C} \pm 3\text{ K}$, avant l'essai.

6 Exigences

Outre les exigences générales données dans l'IEC 60684-1, les gaines doivent être conformes aux exigences données dans les Tableaux 1, 2, 3 et 4, lorsque cela est applicable.

7 Conformité des gaines

La conformité aux exigences de la présente spécification doit normalement être fondée sur les résultats de tailles typiques:

- Type A: Diamètre intérieur rétreint de 25 mm à 30 mm
- Type B: Diamètre intérieur rétreint de 25 mm à 40 mm