

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Optical fibres –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

Fibres optiques –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2022 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, ...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 300 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 19 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Optical fibres –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

Fibres optiques –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 33.180.10

ISBN 978-2-8322-1075-0

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

REDLINE VERSION

VERSION REDLINE



Optical fibres –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

Fibres optiques –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1

CONTENTS

FOREWORD	5
1 Scope	7
2 Normative references	8
3 Terms and definitions	9
4 Abbreviated terms	10
5 Specifications	10
5.1 General	10
5.2 Dimensional requirements	10
5.3 Mechanical requirements	12
5.4 Transmission requirements	12
5.5 Environmental requirements	14
5.5.1 General	14
5.5.2 Mechanical environmental requirements (common to all fibres in category A1)	15
5.5.3 Transmission environmental requirements	16
Annex A (normative) Specifications for sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 multimode fibres	17
A.1 General	17
A.2 Dimensional requirements	17
A.3 Mechanical requirements	18
A.4 Transmission requirements	18
A.5 Environmental requirements	20
Annex B (normative) Specifications for sub-category A1-OM1 multimode fibres	21
B.1 General	21
B.2 Dimensional requirements	21
B.3 Mechanical requirements	21
B.4 Transmission requirements	22
B.5 Environmental requirements	22
Annex C (normative) Specifications for sub-category A1d multimode fibres	23
C.1 General	23
C.2 Dimensional requirements	23
C.3 Mechanical requirements	23
C.4 Transmission requirements	24
C.5 Environmental requirements	24
Annex D (normative) Fibre differential mode delay (DMD), calculated effective modal bandwidth (EMB _c) and calculated overfilled modal bandwidth (OMB _c) requirements	25
D.1 A1-OM3 fibre DMD requirements	25
D.1.1 General	25
D.1.2 DMD templates	25
D.1.3 DMD interval masks	26
D.2 A1-OM3 fibre EMB _c requirements	27
D.2.1 General	27
D.2.2 Calculated effective bandwidth	27
D.3 A1-OM4 DMD requirements	29
D.3.1 General	29

D.3.2	DMD templates	29
D.3.3	DMD interval masks	30
D.4	A1-OM4 fibre EMB _C requirements	30
D.4.1	General	30
D.4.2	Calculated effective bandwidth	30
D.5	A1-OM5 fibre modal bandwidth requirements	30
D.5.1	General	30
D.5.2	Calculated effective modal bandwidth	31
D.6	A1-OM2, A1-OM3, A1-OM4 and A1-OM5 calculated overfilled modal bandwidth	31
Annex E (informative)	System, modal bandwidth, and transmitter considerations	33
E.1	Background	33
E.2	System considerations	33
E.2.1	A1-OM3 and A1-OM4 fibres	33
E.2.2	A1-OM5 fibre	33
E.3	Effective modal bandwidth (EMB)	34
E.4	Transmitter encircled flux (EF) and centre wavelength requirements	37
E.4.1	Encircled flux	37
E.4.2	Centre wavelength for A1-OM3 and A1-OM4 fibres	38
E.4.3	Centre wavelength for A1-OM5 fibre	38
Annex F (informative)	Bandwidth nomenclature explanation	40
Annex G (informative)	Preliminary indications for items needing further study	41
G.1	Effective modal bandwidth (EMB) at 1 300 nm	41
G.2	Scaling of EMB with DMD	41
Annex H (informative)	Applications and cabling categories supported by A1 fibres	43
Annex I (informative)	1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit and 100-Gigabit Ethernet applications	44
Bibliography		50
Figure 1	– Relation between bandwidths at 850 nm and 1 300 nm	14
Figure D.1	– DMD template requirements	26
Figure E.1	– Estimated minimum wide band EMB versus wavelength for A1-OM3	35
Figure E.2	– Estimated minimum wide band EMB versus wavelength for A1-OM4	36
Figure E.3	– Estimated minimum wide band EMB versus wavelength for A1-OM5	37
Figure E.4	– Approximate position of DMD weightings relative to the EF boundaries of Equations (E.10) and (E.11)	38
Table 1	– Cross reference IEC A1 multimode fibre designations to IEC 60793-2-10:2017	8
Table 2	– Dimensional attributes and measurement methods	11
Table 3	– Dimensional requirements common to category A1 fibres	11
Table 4	– Additional dimensional attributes required in sub-category specifications	11
Table 5	– Mechanical attributes and measurement methods	12
Table 6	– Mechanical requirements common to category A1 fibres	12
Table 7	– Transmission attributes and measurement methods	13
Table 8	– Additional transmission attributes required in sub-category specifications	13
Table 9	– Environmental exposure tests	15

Table 10 – Attributes measured for environmental tests	15
Table 11 – Strip force for environmental tests	15
Table 12 – Tensile strength for environmental tests	16
Table 13 – Stress corrosion susceptibility for environmental tests	16
Table 14 – Change in attenuation for environmental tests	16
Table A.1 – Dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres	18
Table A.2 – Mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres	18
Table A.3 – Transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres	19
Table B.1 – Dimensional requirements specific to A1-OM1 fibres	21
Table B.2 – Mechanical requirements specific to A1-OM1 fibres	21
Table B.3 – Transmission requirements specific to A1-OM1 fibres	22
Table C.1 – Dimensional requirements specific to A1d fibres	23
Table C.2 – Mechanical requirements specific to A1d fibres	23
Table C.3 – Transmission requirements specific to A1d fibres	24
Table D.1 – DMD templates for A1-OM3 fibres	25
Table D.2 – DMD interval masks for A1-OM3 fibres	27
Table D.3 – DMD weightings	28
Table D.4 – DMD templates for A1-OM4 fibres	30
Table D.5 – DMD interval masks for A1-OM4 fibres	30
Table D.6 – DMD weighting for OMB _C	32
Table F.1 – Bandwidth nomenclature explanation	40
Table H.1 – Some standardised applications supported by A1-OM2, A1-OM3, A1-OM4, A1-OM5 fibres and in some cases A1-OM1 fibres	43
Table I.1 – Summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities	45

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 60793-2-10 edition 7.1 contains the seventh edition (2019-05) [documents 86A/1932/FDIS and 86A/1939/RVD] and its amendment 1 (2022-01) [documents 86A/2121/CDV and 86A/2140/RVC].

In this Redline version, a vertical line in the margin shows where the technical content is modified by amendment 1. Additions are in green text, deletions are in strikethrough red text. A separate Final version with all changes accepted is available in this publication.

International Standard IEC 60793-2-10 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This seventh edition constitutes a technical revision.

This edition includes the following significant change with respect to the previous edition: revision of the naming convention for A1 multimode fibres, which better matches with those found in ISO/IEC standards. These changes are outlined in the scope of this document along with a cross reference table for the new names.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60793 series, published under the general title *Optical fibres*, can be found on the IEC website.

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under webstore.iec.ch in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

OPTICAL FIBRES –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

1 Scope

This part of IEC 60793 is applicable to optical fibre sub-categories A1-OM1, A1-OM2, A1-OM3, A1-OM4, A1-OM5, and A1d. These fibres are used or can be incorporated in information transmission equipment and optical fibre cables.

Sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 apply to 50/125 μm graded index fibre in four bandwidth grades. Each of these bandwidth grades is defined for two levels of macrobend loss performance that are distinguished by "a" or "b" suffix. Those sub-categories with suffix "a" are specified to meet traditional macrobend loss performance levels. Those sub-categories with suffix "b" are specified to meet enhanced macrobend loss (i.e. lower loss) performance levels.

Sub-category A1-OM5 is specified to support single wavelength or multi-wavelength transmission systems in the vicinity of 850 nm to 950 nm. Although not normatively specified, bandwidth information covering this wavelength range is also included for A1-OM3 and A1-OM4.

Sub-category A1-OM1 applies to 62,5/125 μm graded index fibre and sub-category A1d applies to 100/140 μm graded index fibre.

Other applications include, but are not restricted to, the following: short reach, high bit-rate systems in telephony, distribution and local networks carrying data, voice and/or video services; on-premises intra-building and inter-building fibre installations including data centres, local area networks (LANs), storage area networks (SANs), private branch exchanges (PBXs), video, various multiplexing uses, outside telephone cable plant use, and miscellaneous related uses.

Three types of requirements apply to these fibres:

- general requirements, as defined in IEC 60793-2;
- specific requirements common to the category A1 multimode fibres covered in this document and which are given in Clause 5;
- particular requirements applicable to individual fibre sub-categories and models, or specific applications, which are defined in the normative specification Annexes A to D.

Table 1 shows the cross reference between the IEC A1 multimode optical fibre designations used in this document compared to those used in IEC 60793-2-10:2017. The table also refers to the normative annexes A, B and C for the A1 sub-category multimode fibres in this document that contains the detailed specification.

Table 1 – Cross reference IEC A1 multimode fibre designations to IEC 60793-2-10:2017

Annex	Sub-category	Sub-category/Model	Core diameter (nominal)	ISO/IEC 11801-1:2017
	This document designations	IEC 60793-2-10:2017 designations		Usage of cabled OMx fibres
A	A1-OM2	A1a.1	50 µm ^a	OM2 ^b
	A1-OM3	A1a.2	50 µm	OM3
	A1-OM4	A1a.3	50 µm	OM4
	A1-OM5	A1a.4	50 µm	OM5
B	A1-OM1	A1b	62,5 µm ^c	OM1 ^d
C	A1d	A1d	100 µm	
^a Historically, ISO/IEC 11801:2002 also defined OM2 cables made with 62,5/125 µm fibres having a minimum overfilled launch bandwidth of 500 MHz·km at 850 nm and 500 MHz·km at 1 300 nm. This specific bandwidth combination of 62,5/125 µm fibre is not part of this document. ^b OM2 cables are not supported for new installations within ISO/IEC 11801-1:2017. ^c Historically, ISO/IEC 11801:2002 also defined OM1 cables made with 50/125 µm fibres having a minimum overfilled launch bandwidth of 200 MHz·km at 850 nm and 500 MHz·km at 1 300 nm. This specific bandwidth combination of 50/125 µm fibre is not part of this document. ^d OM1 cables are not supported for new installations within ISO/IEC 11801-1:2017.				

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-21, *Optical fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*

IEC 60793-1-30, *Optical fibres – Part 1-30: Measurement methods and test procedures – Fibre proof test*

IEC 60793-1-31, *Optical fibres – Part 1-31: Measurement methods and test procedures – Tensile strength*

IEC 60793-1-32, *Optical fibres – Part 1-32: Measurement methods and test procedures – Coating strippability*

IEC 60793-1-33, *Optical fibres – Part 1-33: Measurement methods and test procedures – Stress corrosion susceptibility*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-41, *Optical fibres – Part 1-41: Measurement methods and test procedures – Bandwidth*

IEC 60793-1-42, *Optical fibres – Part 1-42: Measurement methods and test procedures – Chromatic dispersion*

IEC 60793-1-43, *Optical fibres – Part 1-43: Measurement methods and test procedures – Numerical aperture measurement*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-1-47, *Optical fibres – Part 1-47: Measurement methods and test procedures – Macrobending loss*

IEC 60793-1-49, *Optical fibres – Part 1-49: Measurement methods and test procedures – Differential mode delay*

IEC 60793-1-50, *Optical fibres – Part 1-50: Measurement methods and test procedures – Damp heat (steady state) tests*

IEC 60793-1-51, *Optical fibres – Part 1-51: Measurement methods and test procedures – Dry heat (steady state) tests*

IEC 60793-1-52, *Optical fibres – Part 1-52: Measurement methods and test procedures – Change of temperature tests*

IEC 60793-1-53, *Optical fibres – Part 1-53: Measurement methods and test procedures – Water immersion tests*

IEC 60793-2, *Optical fibres – Part 2: Product specifications – General*

IEC 61280-4-1:2009, *Fibre-optic communication subsystem test procedures – Part 4-1: Installed cable plant – Multimode attenuation measurement*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Abbreviated terms

CPR	coupled power ratio
DMD	differential mode delay
EF	encircled flux
EMB	effective modal bandwidth
EMB _c	calculated effective modal bandwidth
LAN	local area network
MMF	multimode fibre
NA	numerical aperture
OFL	overfilled launch
OMB _c	overfilled launch modal bandwidth calculated from differential mode delay (also known as OFL _c)
PBX	private branch exchange
PMD	physical medium dependent
ROFL	radial overfilled launch
SAN	storage area network

5 Specifications

5.1 General

The fibre consists of a glass core with a graded index profile and a glass cladding in accordance with IEC 60793-2.

The term "glass" usually refers to material consisting of non-metallic oxides.

5.2 Dimensional requirements

Dimensional attributes and measurement methods are given in Table 2.

Requirements common to all fibres in category A1 are indicated in Table 3.

Table 4 lists additional attributes that shall be specified by each sub-category specification.

Table 2 – Dimensional attributes and measurement methods

Attributes	Measurement methods
Cladding diameter	IEC 60793-1-20
Core diameter ^{a, b}	IEC 60793-1-20
Cladding non-circularity	IEC 60793-1-20
Core non-circularity	IEC 60793-1-20
Core-cladding concentricity error	IEC 60793-1-20
Primary coating diameter	IEC 60793-1-21
Primary coating non-circularity	IEC 60793-1-21
Primary coating-cladding concentricity error	IEC 60793-1-21
Fibre length	IEC 60793-1-22
^a Core diameter is specified at $850 \text{ nm} \pm 10 \text{ nm}$ with a test specimen length of $2,0 \text{ m} \pm 0,2 \text{ m}$ and a threshold value, k_{CORE} , of 0,025 for A1 fibres except A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres. ^b Core diameter is specified at $850 \text{ nm} \pm 10 \text{ nm}$ with a test specimen length of $100 \text{ m} \pm 5 \%$ and a threshold value, k_{CORE} , of 0,025 for A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres.	

Table 3 – Dimensional requirements common to category A1 fibres

Attributes	Unit	Limits
Core non-circularity	%	≤ 6
Primary coating diameter – uncoloured ^a	μm	245 ± 10
Primary coating diameter – coloured ^a	μm	250 ± 15
Primary coating-cladding concentricity error	μm	$\leq 12,5$
Fibre length	km	^b
^a The limits on primary coating diameter are most commonly used in telecommunications cables. There are other applications, which use other primary coating diameters, several of which are listed below. Alternative nominal primary coating diameters and tolerance (μm): 400 ± 40 500 ± 50 700 ± 100 900 ± 100		
^b Length requirements vary and should be agreed between supplier and customer.		

Table 4 – Additional dimensional attributes required in sub-category specifications

Attributes
Cladding diameter
Cladding non-circularity
Core diameter
Core-cladding concentricity error

5.3 Mechanical requirements

Mechanical attributes and measurement methods are given in Table 5.

Requirements common to all fibres in category A1 are in Table 6.

Table 5 – Mechanical attributes and measurement methods

Attributes	Test methods
Proof test	IEC 60793-1-30
Tensile strength	IEC 60793-1-31
Primary coating strippability	IEC 60793-1-32
Stress corrosion susceptibility	IEC 60793-1-33

Table 6 – Mechanical requirements common to category A1 fibres

Attributes	Unit	Limits
Proof stress level	GPa	$\geq 0,69^a$
Average strip force ^b	N	$1,0 \leq F_{\text{avg}} \leq 5,0$
Peak strip force ^b	N	$1,0 \leq F_{\text{peak}} \leq 8,9$
Tensile strength (median) for 0,5 m specimen length	GPa	$\geq 3,8$
Stress corrosion susceptibility constant, n_d	-	≥ 18
^a The proof test value of 0,69 GPa equals about 1 % strain or about 8,8 N force, for A1-OM1 to A1-OM5 fibres. For the relation between these different units, see IEC TR 62048:2014, 8.4. ^b Either average strip force or peak strip force, which are defined in the test procedure, may be specified by agreement between supplier and customer.		

5.4 Transmission requirements

Transmission attributes and measurement methods are given in Table 7.

Table 8 lists additional attributes that shall be specified by each sub-category specification.

Table 7 – Transmission attributes and measurement methods

Attributes	Measurement methods
Attenuation coefficient	IEC 60793-1-40
Modal bandwidth ^{a,b}	IEC 60793-1-41
Numerical aperture ^{c,d}	IEC 60793-1-43
Chromatic dispersion	IEC 60793-1-42
Change of optical transmission	IEC 60793-1-46
Macrobending loss	IEC 60793-1-47
Differential mode delay ^e	IEC 60793-1-49
^a For modal bandwidth, either overfilled launch (OFL) or overfilled launch modal bandwidth calculated from differential mode delay (OMB_c) can be used. OMB_c is the reference test method for A1-OM2, A1-OM3 and A1-OM4 fibres at 850 nm and is the required method for A1-OM5 fibres at 850 nm and 953 nm. ^b 850 nm modal bandwidth is specified with a test specimen length of 1 000 m ± 5 % for A1-OM3 to A1-OM5 fibres. For A1-OM3 fibres, the 850 nm modal bandwidth is measured at 850 nm ± 10 nm. For A1-OM4 and A1-OM5 fibres, the 850 nm modal bandwidth is measured at 850 nm ± 2 nm. For A1-OM5 fibre, the modal bandwidth is also measured at 953 nm ± 6 nm. ^c Numerical aperture is specified at 850 nm ± 10 nm with a test specimen length of 2 m ± 0,2 m and a threshold value, k_{NA}, of 0,05 for A1 fibres except A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres. ^d Numerical aperture is specified at 850 nm ± 10 nm with a test specimen length of 100 m ± 5 % and a threshold value, k_{NA}, of 0,05 for A1-OM2b, A1-OM3b, A1-OM4b and A1-OM5b fibres. ^e Differential mode delay is specified with a test specimen length of 1 000 m ± 5 % for A1-OM3, A1-OM4 and A1-OM5 fibres. For A1-OM3 fibres, the DMD is measured at 850 nm ± 10 nm. For A1-OM4 and A1-OM5 fibres, the DMD is measured at 850 nm ± 2 nm. For A1-OM5 fibre, the DMD is also measured at 953 nm ± 6 nm.	

Specification compliance of chromatic dispersion can be assured by compliance to the numerical aperture (NA) specification for A1 fibre.

Table 8 – Additional transmission attributes required in sub-category specifications

Attributes
Attenuation coefficient
Modal bandwidth
Chromatic dispersion
Numerical aperture
Macrobending loss

For attenuation coefficient and modal bandwidth, the sub-category specifications may contain ranges of specifiable values instead of fixed limits. In this case, the actual values of the maximum attenuation coefficient and minimum modal bandwidth, at both 850 nm and 1 300 nm (or just at one of these wavelengths) shall be agreed between supplier and customer. For commercial purposes, the modal bandwidth is linearly normalized to 1 km.

For guidance purposes, Annex H shows a number of standardised applications supported by A1 fibres and Annex I shows transmission capabilities for these fibres.

The indicated maximum attenuation coefficients apply to uncabled optical fibres; for the maximum cabled attenuation coefficients, reference is made to IEC 60794-1-1, which can be used in conjunction with this document. Tighter specifications for the fibre may be requested to account for added attenuation in the cabling process.

Remarks on the specification of modal bandwidth:

Care should be taken in writing dual wavelength bandwidth specifications. It is understood that for category A1 fibres, the bandwidth at 850 nm may be related to the bandwidth at 1 300 nm in a way shown in Figure 1, depending on the refractive index parameter, g (see IEC 60793-2). See [1]¹, page 50, and [2], page 255, for similar figures. The shaded region under the curve of Figure 1 can be defined as the dual window area. In this area, regions X, Y, and Z are examples of where a fibre manufacturer may choose to optimise the process. That is, centre the production bandwidth peak at 850 nm, 1 300 nm, or between these two wavelengths.

Due to this optimisation of the manufacturing process, there will be combinations of bandwidth that are not possible (i.e., outside the shaded region).




Figure 1 – Relation between bandwidths at 850 nm and 1 300 nm

5.5 Environmental requirements

5.5.1 General

Environmental exposure tests and measurement methods are documented in two forms:

- relevant environmental attributes and test procedures are given in Table 9;
- measurements of a particular mechanical or transmission attribute that may change on the application of the environment are listed in Table 10.

¹ Numbers in square brackets refer to the Bibliography.

Table 9 – Environmental exposure tests

Environmental exposure	Test
Damp heat	IEC 60793-1-50
Dry heat	IEC 60793-1-51
Change of temperature	IEC 60793-1-52
Water immersion	IEC 60793-1-53

Table 10 – Attributes measured for environmental tests

Attribute	Measurement method
Change in optical transmission	IEC 60793-1-46
Attenuation	IEC 60793-1-40
Strip force	IEC 60793-1-32
Tensile strength	IEC 60793-1-31
Stress corrosion susceptibility	IEC 60793-1-33

These tests are normally conducted periodically as type-tests for a fibre and coating design. Unless otherwise indicated, the recovery period allowed between the completion of the environmental exposure and performing the attribute measurements shall be as stated in the particular environmental test method.

5.5.2 Mechanical environmental requirements (common to all fibres in category A1)

5.5.2.1 General

These tests are, in practice, the most severe requirements amongst the environments defined in Table 9.

Tables 11, 12, and 13 give the prescriptions for strip force, tensile strength and stress corrosion susceptibility respectively.

5.5.2.2 Strip force

The following attributes shall be verified following removal of the fibre from the particular environment.

Table 11 – Strip force for environmental tests

Environment	Average strip force N	Peak strip force N
Damp heat	$1,0 \leq F_{avg} \leq 5,0$	$1,0 \leq F_{peak} \leq 8,9$
Water immersion	$1,0 \leq F_{avg} \leq 5,0$	$1,0 \leq F_{peak} \leq 8,9$

5.5.2.3 Tensile strength

The following attribute shall be verified following removal of the fibre from the environment.

Table 12 – Tensile strength for environmental tests

Environment	Median tensile strength specimen length: 0,5 m GPa	15th percentile tensile strength specimen length: 0,5 m GPa
Damp heat	≥ 3,03	≥ 2,76
NOTE These requirements do not apply to hermetically coated fibre.		

5.5.2.4 Stress corrosion susceptibility

The following attribute shall be verified following removal of the fibre from the environment.

Table 13 – Stress corrosion susceptibility for environmental tests

Environment	Stress corrosion susceptibility constant, n_d
Damp heat	≥ 18
NOTE This requirement does not apply to hermetically coated fibre.	

5.5.3 Transmission environmental requirements

Change in attenuation from the initial value shall be less than the values in Table 14. Attenuation shall be measured periodically during the entire exposure to each environment and after removal.

Table 14 – Change in attenuation for environmental tests

Environment	Wavelength nm	Attenuation increase dB/km
Damp heat	850	≤ 0,20
	1 300	≤ 0,20
Dry heat	850	≤ 0,20
	1 300	≤ 0,20
Change of temperature	850	≤ 0,20
	1 300	≤ 0,20
Water immersion	850	≤ 0,20
	1 300	≤ 0,20

Annex A (normative)

Specifications for sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 multimode fibres

A.1 General

Annex A contains particular requirements applicable to sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres. Common requirements, repeated here for ease of reference from the main body of this document, are noted by a clause entry in the "Reference" column. The "Reference" column also refers to other annexes containing relevant information on the attribute. Relevant notes from the main body of this document are not repeated but indicated with a superscript "SS".

Sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 are 50/125 μm graded index multimode fibres in four bandwidth grades. All are specified using overfilled bandwidth metrics, while sub-categories A1-OM3, A1-OM4 and A1-OM5 also apply differential mode delay measurements to deliver laser-optimised performance near 850 nm. Sub-category A1-OM5 also specifies both overfilled and differential mode delay bandwidth metrics at 953 nm to deliver laser-optimized performance over a wavelength range in the vicinity of 850 nm to 950 nm. A1-OM3 complies with A1-OM2 specifications. A1-OM4 complies with A1-OM3 specifications. A1-OM5 complies with A1-OM4 specifications.

Sub-category A1-OM2, A1-OM3, A1-OM4 and A1-OM5 are also specified for two levels of macrobend loss performance that are distinguished by "a" or "b" suffix. Those with suffix "a" (i.e. models A1-OM2a, A1-OM3a, A1-OM4a and A1-OM5a) are specified to meet traditional macrobend loss performance levels. Those with suffix "b" (i.e. models A1-OM2b, A1-OM3b, A1-OM4b and A1-OM5b) are specified to meet enhanced macrobend loss (i.e. lower loss) performance levels, and thereby also comply with traditional macrobend loss performance.

The nomenclature for the A1-OM2, A1-OM3, A1-OM4 and A1-OM5 sub-categories establishes a coding hierarchy that permits designation of fibres with increasing specificity. For example, purchase orders for A1-OM3 may be filled by A1-OM3a or A1-OM3b. As a result, where specifications and descriptions apply to all models at lower hierarchical levels, only the common portion of the name is stated.

The dimensional, mechanical and environmental requirements are common to all and specified in Tables A.1 and A.2. The common and distinguishing transmission requirements are specified in Table A.3.

A.2 Dimensional requirements

Table A.1 contains dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres.

Table A.1 – Dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres

Attributes	Unit	Limits	Reference
Cladding diameter	μm	125 ± 1	
Cladding non-circularity	%	≤ 1	
Core diameter ^{SS}	μm	$50 \pm 2,5$	
Core-cladding concentricity error	μm	≤ 2	
Core non-circularity	%	≤ 6	5.2
Primary coating diameter – uncoloured ^{SS}	μm	245 ± 10	5.2
Primary coating diameter – coloured ^{SS}	μm	250 ± 15	5.2
Primary coating-cladding concentricity error	μm	$\leq 12,5$	5.2
Length	km	(see 5.2)	5.2
^{SS} See notes in the main body of this document.			

A.3 Mechanical requirements

Table A.2 contains the mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres.

Table A.2 – Mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres

Attributes	Unit	Limits	Reference
Proof stress level ^{SS}	GPa	$\geq 0,69$	5.3
Average strip force ^{SS}	N	$1,0 \leq F_{\text{avg}} \leq 5,0$	5.3
Peak strip force ^{SS}	N	$1,0 \leq F_{\text{peak}} \leq 8,9$	5.3
^{SS} See notes in the main body of this document..			

A.4 Transmission requirements

Table A.3 contains transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres.

Table A.3 – Transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres

Attributes		Unit	Limits				Reference
Fibre sub-category			A1-OM2	A1-OM3	A1-OM4	A1-OM5	
Targeted operational wavelength(s) ^a		nm	850				Annex E
Maximum attenuation coefficient at 850 nm		dB/km	2,5				
Maximum attenuation coefficient at 953 nm		dB/km	Not specified				1,8
Maximum attenuation coefficient at 1 300 nm		dB/km	0,8				
Minimum modal bandwidth-length product for overfilled launch at 850 nm ^{ss}		MHz·km	500	1 500	3 500	3 500	Clause D.6
Minimum modal bandwidth-length product for overfilled launch at 953 nm ^{ss}		MHz·km	Not specified				1 850 Clause D.6
Minimum modal bandwidth-length product for overfilled launch at 1 300 nm		MHz·km	500				
Minimum effective modal bandwidth-length product at 850 nm ^{ss e}		MHz·km	Not specified	2 000 Meet Clause D.1 or Clause D.2	4 700 Meet Clause D.3 or Clause D.4	4 700 Meet Clause D.5	Annexes D, E, F, G
Minimum effective modal bandwidth-length product at 953 nm ^{ss e}		MHz·km	Not specified				2 470 Meet Clause D.5 Annexes D, E, F, G
Numerical aperture ^{ss}		Dimensionless	0,200 ± 0,015				
Fibre model			A1-OM2a	A1-OM3a	A1-OM4a	A1-OM5a	
Maximum macro-bending loss ^b	Bending radius	Number of turns	Max at 850 nm / 1 300 nm				
	37,5 mm	100	0,5 / 0,5				
	15 mm	2	1,0 / 1,0				
Fibre model			A1-OM2b	A1-OM3b	A1-OM4b	A1-OM5b	
Maximum macro-bending loss ^b	Bending radius	Number of turns	Max at 850 nm / 1 300 nm				
	37,5 mm	100	0,5 / 0,5				
	15 mm	2	0,1 / 0,3				
	7,5 mm	2	0,2 / 0,5				

Zero dispersion wavelength, λ_0	nm	$1\,295 \leq \lambda_0 \leq 1\,340$ ^c	$1\,297 \leq \lambda_0 \leq 1\,328$ ^d
Zero dispersion slope, S_0 ^e	ps/(nm ² ·km)	$S_0 \leq 0,105$ from $1\,295 \text{ nm} \leq \lambda_0 \leq 1\,310 \text{ nm}$, and $\leq 0,000\,375 (1\,590 - \lambda_0)$ from $1\,310 \text{ nm} \leq \lambda_0 \leq 1\,340 \text{ nm}$ ^c	$S_0 \leq 4 (-103) / (840 (1 - (\lambda_0/840)^4))$ ^d
^a Targeted operational wavelength(s) is informative. ^b The launch condition for the macrobending loss measurement shall fulfil that described in IEC 61280-4-1. ^c The worst case chromatic dispersion coefficient at 850 nm (e.g. $S_0 = 0,093\,75 \text{ ps}/(\text{nm}^2 \cdot \text{km})$ at $\lambda_0 = 1\,340 \text{ nm}$ or $S_0 = 0,101\,25 \text{ ps}/(\text{nm}^2 \cdot \text{km})$ at $\lambda_0 = 1\,320 \text{ nm}$) is – 104 ps/(nm·km). ^d The coordinate that generates the worst-case dispersion for operating wavelengths from 840 nm to 1 000 nm is $\lambda_0 = 1\,328 \text{ nm}$, $S_0 = 0,093\,477 \text{ ps}/(\text{nm}^2 \cdot \text{km})$. The worst case chromatic dispersion coefficient at 850 nm is –98,5 ps/(nm·km) ^e When assessing system link performance at wavelengths from 840 nm to 953 nm, refer to the appropriate estimated minimum EMB equations found in Annex E in addition to the dispersion specifications for A1-OM3, A1-OM4, and A1-OM5 fibres. SS See notes in the main body of this document.			

A.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex B (normative)

Specifications for sub-category A1-OM1 multimode fibres

B.1 General

Annex B contains particular requirements applicable to A1-OM1 fibres. Common requirements, repeated here for ease of reference from the main body of this document, are noted by a clause entry in the "Reference" column. Relevant notes from the main body of this document are not repeated but indicated with a superscript "SS".

Sub-category A1-OM1 fibre is a 62,5/125 µm graded index fibre.

B.2 Dimensional requirements

Table B.1 contains dimensional requirements specific to A1-OM1 fibres.

Table B.1 – Dimensional requirements specific to A1-OM1 fibres

Attributes	Unit	Limits	Reference
Cladding diameter	µm	125 ± 2	
Cladding non-circularity	%	≤ 2	
Core diameter ^{SS}	µm	$62,5 \pm 3$	
Core-cladding concentricity error	µm	≤ 3	
Core non-circularity	%	≤ 6	5.2
Primary coating diameter – uncoloured ^{SS}	µm	245 ± 10	5.2
Primary coating diameter – coloured ^{SS}	µm	250 ± 15	5.2
Primary coating-cladding concentricity error	µm	$\leq 12,5$	5.2
Length ^{SS}	km	(see 5.2)	5.2
^{SS} See notes in the main body of this document.			

B.3 Mechanical requirements

Table B.2 contains the mechanical requirements specific to A1-OM1 fibres.

Table B.2 – Mechanical requirements specific to A1-OM1 fibres

Attributes	Unit	Limits	Reference
Proof stress level ^{SS}	GPa	$\geq 0,69$	5.3
Average strip force ^{SS}	N	$1,0 \leq F_{avg} \leq 5,0$	5.3
Peak strip force ^{SS}	N	$1,0 \leq F_{peak} \leq 8,9$	5.3
^{SS} See notes in the main body of this document.			

B.4 Transmission requirements

Table B.3 contains transmission requirements specific to A1-OM1 fibres.

Table B.3 – Transmission requirements specific to A1-OM1 fibres

Attributes	Unit	Limits	Reference
Maximum attenuation coefficient at 850 nm	dB/km	3,0	
Maximum attenuation coefficient at 1 300 nm	dB/km	1,0	
Minimum modal bandwidth-length product at 850 nm	MHz·km	200	
Minimum modal bandwidth-length product at 1 300 nm	MHz·km	500	
Numerical aperture ^{SS}	Dimensionless	$0,275 \pm 0,015$	
Maximum macrobending loss 100 turns on bending radius of 37,5 mm at wavelengths 850 nm and 1 300 nm ^a	dB	0,5	
Zero dispersion wavelength, λ_0	nm	$1\,320 \leq \lambda_0 \leq 1\,365$ ^b	
Zero dispersion slope S_0 – from $1\,320 \text{ nm} \leq \lambda_0 \leq 1\,348 \text{ nm}$ – from $1\,348 \text{ nm} \leq \lambda_0 \leq 1\,365 \text{ nm}$	ps/(nm ² ·km)	$\leq 0,11$ ^b $\leq 0,001 (1\,458 - \lambda_0)$ ^b	
^a The launch condition for the macrobending loss measurement shall fulfil that described in IEC 61280-4-1. ^b The worst case chromatic dispersion coefficient at 850 nm ($S_0 = 0,11 \text{ ps}/(\text{nm}^2 \cdot \text{km})$ at $\lambda_0 = 1\,348 \text{ nm}$) is $-125 \text{ ps}/(\text{nm} \cdot \text{km})$. ^{SS} See notes in the main body of this document.			

B.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex C (normative)

Specifications for sub-category A1d multimode fibres

C.1 General

Annex C contains particular requirements for A1d fibres. Common requirements, repeated here for ease of reference from this document, are noted by an entry in the "Reference" column. Relevant notes from the main body of this document are not repeated but indicated with a superscript "SS".

Sub-category A1d fibre is a 100/140 μm graded index fibre.

C.2 Dimensional requirements

Table C.1 contains dimensional requirements specific to A1d fibres.

Table C.1 – Dimensional requirements specific to A1d fibres

Attributes	Unit	Limits	Reference
Cladding diameter	μm	140 ± 4	
Cladding non-circularity	%	≤ 4	
Core diameter ^{SS}	μm	100 ± 5	
Core-cladding concentricity error	μm	≤ 6	
Core non-circularity	%	≤ 6	5.2
Primary coating diameter – uncoloured ^{SS}	μm	245 ± 10	5.2
Primary coating diameter – coloured ^{SS}	μm	250 ± 15	5.2
Primary coating-cladding concentricity error	μm	$\leq 12,5$	5.2
Length ^{SS}	km	(see 5.2)	5.2
^{SS} See notes in the main body of this document.			

C.3 Mechanical requirements

Table C.2 contains the mechanical requirements specific to A1d fibres.

Table C.2 – Mechanical requirements specific to A1d fibres

Attributes	Unit	Limits	Reference
Proof stress level ^{SS}	GPa	$\geq 0,69$	5.3
Average strip force ^{SS}	N	$1,0 \leq F_{\text{avg}} \leq 5,0$	5.3
Peak strip force ^{SS}	N	$1,0 \leq F_{\text{peak}} \leq 8,9$	5.3
^{SS} See notes in the main body of this document.			

C.4 Transmission requirements

Table C.3 contains transmission requirements specific to A1d fibres.

Table C.3 – Transmission requirements specific to A1d fibres

Attributes	Unit	Limits	Reference
Maximum attenuation coefficient at 850 nm ^a	dB/km	3,5 to 7,0	
Maximum attenuation coefficient at 1 300 nm ^a	dB/km	1,5 to 4,5	
Minimum modal bandwidth-length product at 850 nm ^a	MHz·km	10 to 200	
Minimum modal bandwidth-length product at 1 300 nm ^a	MHz·km	100 to 300	
Numerical aperture ^{ss}	Dimensionless	$0,26 \pm 0,03$ or $0,29 \pm 0,03$	
Maximum macrobending loss	dB	For further study	
Zero dispersion wavelength, λ_0	nm	$1\,330 \leq \lambda_0 \leq 1\,385$ ^b	
Zero dispersion slope S_0 – from $1\,330\text{ nm} \leq \lambda_0 \leq 1\,365\text{ nm}$ – from $1\,365\text{ nm} \leq \lambda_0 \leq 1\,385\text{ nm}$	ps/(nm ² ·km)	$\leq 0,105$ ^b $\leq 0,000,5 (1\,575 - \lambda_0)$ ^b	
^a The limit column forms a range of values that may be specified.			
^b The worst case chromatic dispersion coefficient at 850 nm ($S_0 = 0,105$ ps/(nm ² ·km) at $\lambda_0 = 1\,365$ nm) is –126 ps/(nm·km).			
^{ss} See notes in the main body of this document.			

C.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex D (normative)

Fibre differential mode delay (DMD), calculated effective modal bandwidth (EMB_c) and calculated overfilled modal bandwidth (OMB_c) requirements

D.1 A1-OM3 fibre DMD requirements

D.1.1 General

A1-OM3 fibres selected using the DMD mask method shall meet the requirements of D.1.2 and D.1.3. The radial limits, R_{INNER} and R_{OUTER} , were established for transmitters meeting the requirements of Clause E.4.

Refer to Annex E for information regarding effective modal bandwidth (EMB).

D.1.2 DMD templates

A1-OM3 fibres shall meet at least one of the six templates in Table D.1, each of which includes an inner and outer mask requirement, when measured according to IEC 60793-1-49.

Table D.1 – DMD templates for A1-OM3 fibres

Template number	Inner mask DMD (ps/m) for $R_{\text{INNER}} = 5 \mu\text{m}$ to $R_{\text{OUTER}} = 18 \mu\text{m}$	Outer mask DMD (ps/m) for $R_{\text{INNER}} = 0 \mu\text{m}$ to $R_{\text{OUTER}} = 23 \mu\text{m}$
1	$\leq 0,23$	$\leq 0,70$
2	$\leq 0,24$	$\leq 0,60$
3	$\leq 0,25$	$\leq 0,50$
4	$\leq 0,26$	$\leq 0,40$
5	$\leq 0,27$	$\leq 0,35$
6	$\leq 0,33$	$\leq 0,33$

The DMD requirements in Table D.1 are illustrated in Figure D.1. In this figure, the allowable DMD (as measured according to IEC 60793-1-49) is plotted versus the radial offset position of the single mode probe. There is a trade-off between the tightness of the inner mask and the outer mask to ensure a sufficient amount of the baud energy from a transmitter (meeting the launch specifications) arrives within the required time period (defined by the baud rate of the transmission system).




Figure D.1 – DMD template requirements

The "floating" characteristic of the inner mask is also illustrated in Figure D.1. In this figure, the inner mask (5 μm to 18 μm) may be positioned vertically (temporally) anywhere within the outer mask (0 μm to 23 μm). The DMD is more tightly constrained in the inner mask to allow for looser tolerances on the outer mask providing for improved ability to manufacture fibre conforming to this requirement. In the case of the 0,33 ps/m mask, the requirement is the same over the whole range from 0 μm to 23 μm creating a "flat" mask.

IEC 60793-1-49 can be used to ensure a minimum effective modal bandwidth-length product, when using sources meeting appropriate restrictions. When the launch condition requirements on the transmitters are coupled to the DMD requirements on the fibre, a balance can be achieved between fibre tolerance and transmitter tolerance. A careful study, using fibres contributed by several different fibre manufacturers and laser transmitters from several different source manufacturers, and including extensive and detailed simulations, shows that the above coupled specifications on fibre and sources will yield a minimum effective modal bandwidth-length product of 2 000 MHz·km [3] to [14].

The use of a template on the values of DMD achieves an effective trade-off between transmitter and fibre properties. The transmitter launch condition is bounded by encircled flux requirements at 4,5 μm and 19 μm as discussed in Clause E.4. The limitation on the transmitter encircled flux at the 4,5 μm radius assures that very little energy is carried by the lowest order modes of the fibre, allowing the relaxed tolerance on modal structure excited at small radii. The limitation on the transmitter encircled flux at the 19 μm radius assures that very little energy is carried by the highest order modes of the fibre, allowing the relaxed tolerance on modal structure excited at high radii.

D.1.3 DMD interval masks

The A1-OM3 fibre DMD shall not exceed 0,25 ps/m for any of the radial offset intervals given in Table D.2.

Table D.2 – DMD interval masks for A1-OM3 fibres

Interval number	R_{INNER} μm	R_{OUTER} μm
1	7	13
2	9	15
3	11	17
4	13	19

These interval masks screen out fibres having DMD that change too rapidly over short radial ranges. Fibres passing this screen have lower inter-symbol interference than those that do not.

D.2 A1-OM3 fibre EMB_c requirements

D.2.1 General

A1-OM3 fibres selected using the EMB_c method shall meet the requirements of D.2.2.

D.2.2 Calculated effective bandwidth

The DMD optical pulse shapes can be weighted by a set of launch distributions to determine a corresponding set of EMB_c values. The minimum EMB_c (minEMB_c) within this set shall meet the requirement of Equation (D.1):

$$\text{minEMB}_c \geq 1.770 \text{ MHz}\cdot\text{km} \quad (\text{D.1})$$

where

minEMB_c is determined from the complex transfer function as described in IEC 60793-1-49 using the weights defined in Table D.3.

NOTE 1 Minimum EMB_c is a fibre parameter, and it is possible that its value is not optimal for use in system models. Refer to Annex E for information regarding the corresponding system parameter called the "effective modal bandwidth" (EMB) and its relationship to EMB_c .

NOTE 2 Refer to Annex F for additional explanation of bandwidth nomenclature.

Weightings within Table D.3 are provided for DMD measured at $1 \mu\text{m}$ radial intervals starting from the centre of the core ($r = 0$) for ten simulated lasers with encircled flux (EF) metrics that correspond to those of ten actual lasers. The DMD weightings in Table D.3 are specific to sources meeting the specifications of Clause E.4.

Table D.3 – DMD weightings

Radial position	Laser ID				
r (μm)	1	2	3	4	5
0	0	0	0	0	0
1	0,033 023	0,023 504	0	0	0
2	0,262 463	0,188 044	0	0	0
3	0,884 923	0,634 634	0	0	0
4	2,009 102	1,447 235	0,007 414	0,005 637	0,003 034
5	3,231 216	2,376 616	0,072 928	0,055 488	0,029 856
6	3,961 956	3,052 908	0,262 906	0,200 05	0,107 634
7	3,694 686	3,150 634	0,637 117	0,483 667	0,258 329
8	2,644 369	2,732 324	1,197 628	0,896 95	0,458 494
9	1,397 552	2,060 241	1,916 841	1,402 833	0,661 247
10	0,511 827	1,388 339	2,755 231	1,957 805	0,826 035
11	0,110 549	0,834 722	3,514 797	2,433 247	1,000 204
12	0,004 097	0,419 715	3,883 317	2,639 299	1,294 439
13	0,000 048	0,160 282	3,561 955	2,397 238	1,813 982
14	0,001 111	0,047 143	2,617 093	1,816 953	2,506 95
15	0,005 094	0,044 691	1,480 325	1,296 977	3,164 213
16	0,013 918	0,116 152	0,593 724	1,240 553	3,572 113
17	0,026 32	0,219 802	0,153 006	1,700 02	3,618 037
18	0,036 799	0,307 088	0,012 051	2,240 664	3,329 662
19	0,039 465	0,329 314	0	2,394 077	2,745 395
20	0,032 152	0,268 541	0	1,952 429	1,953 241
21	0,019 992	0,166 97	0	1,213 833	1,137 762
22	0,008 832	0,073 514	0	0,534 474	0,494 404
23	0,002 612	0,021 793	0	0,158 314	0,146 517
24	0,000 282	0,002 679	0	0,019 738	0,018 328
25	0	0	0	0	0

Radial position	Laser ID				
r (μm)	6	7	8	9	10
0	0	0	0	0	0
1	0,015 199	0,016 253	0,022 057	0,010 43	0,015 681
2	0,120 91	0,129 011	0,176 39	0,083 496	0,124 978
3	0,407 702	0,434 844	0,595 248	0,281 802	0,421 548
4	0,925 664	0,987 184	1,351 845	0,650 28	0,957 203
5	1,488 762	1,587 6	2,174 399	1,130 599	1,539 535
6	1,825 448	1,94 661 4	2,666 278	1,627 046	1,887 747
7	1,702 306	1,815 285	2,486 564	2,044 326	1,762 955
8	1,218 378	1,299 241	1,780 897	2,291 72	1,292 184
9	0,643 911	0,686 635	0,945 412	2,280 813	0,790 844
10	0,238 557	0,255 85	0,360 494	1,937 545	0,559 38
11	0,098 956	0,131 429	0,163 923	1,383 006	0,673 655
12	0,204 274	0,327 091	0,318 712	0,878 798	1,047 689
13	0,529 982	0,848 323	0,778 983	0,679 756	1,589 037
14	1,024 948	1,567 513	1,383 174	0,812 36	2,138 626
15	1,611 695	2,224 027	1,853 992	1,074 702	2,470 827
16	2,210 689	2,555 06	1,914 123	1,257 323	2,361 764
17	2,707 415	2,464 566	1,511 827	1,255 967	1,798 213
18	2,938 8	2,087 879	0,908 33	1,112 456	1,059 264
19	2,739 32	1,577 111	0,386 991	0,879 309	0,444 481
20	2,090 874	1,056 343	0,111 76	0,608 183	0,123 304
21	1,261 564	0,595 102	0,014 829	0,348 921	0,012 552
22	0,552 14	0,256 718	0,001 818	0,151 12	0
23	0,163 627	0,076 096	0,000 54	0,044 757	0
24	0,020 443	0,009 446	0	0,005 639	0
25	0	0	0	0	0

D.3 A1-OM4 DMD requirements

D.3.1 General

A1-OM4 fibres selected using the DMD mask method shall meet the requirements of D.3.2 and D.3.3. See Clause D.1 for supporting information. The radial limits, R_{INNER} and R_{OUTER} , were established for transmitters meeting the requirements of Clause E.4.

Refer to Annex E for information regarding effective modal bandwidth (EMB).

D.3.2 DMD templates

A1-OM4 fibres shall meet at least one of the three templates in Table D.4, each of which includes an inner and outer mask requirement, when measured according to IEC 60793-1-49.

Table D.4 – DMD templates for A1-OM4 fibres

Template number	Inner mask DMD (ps/m) for $R_{\text{INNER}} = 5 \mu\text{m}$ to $R_{\text{OUTER}} = 18 \mu\text{m}$	Outer mask DMD (ps/m) for $R_{\text{INNER}} = 0 \mu\text{m}$ to $R_{\text{OUTER}} = 23 \mu\text{m}$
1	$\leq 0,10$	$\leq 0,30$
2	$\leq 0,11$	$\leq 0,17$
3	$\leq 0,14$	$\leq 0,14$

D.3.3 DMD interval masks

The A1-OM4 fibre DMD shall not exceed 0,11 ps/m for any of the radial offset intervals given in Table D.5 when measured according to IEC 60793-1-49.

Table D.5 – DMD interval masks for A1-OM4 fibres

Interval number	R_{INNER} μm	R_{OUTER} μm
1	7	13
2	9	15
3	11	17
4	13	19

D.4 A1-OM4 fibre EMB_c requirements

D.4.1 General

A1-OM4 fibres selected using the EMB_c method shall meet the requirements of D.4.2. See the introductory text for Table D.3 in D.2.2 for supporting information.

D.4.2 Calculated effective bandwidth

The DMD optical pulse shapes can be weighted by a set of launch distributions to determine a corresponding set of EMB_c values. The minimum EMB_c (minEMB_c) within this set shall meet the requirement of Equation (D.2):

$$\text{minEMB}_c \geq 4 \text{ 160 MHz} \cdot \text{km} \quad (\text{D.2})$$

where

minEMB_c is determined from the complex transfer function as described in IEC 60793-1-49 using the weights defined in Table D.3.

D.5 A1-OM5 fibre modal bandwidth requirements

D.5.1 General

A1-OM5 fibres shall meet the requirements of D.5.2 and D.6. See the introductory text for Table D.3 in D.2.2 for supporting information.

D.5.2 Calculated effective modal bandwidth

The DMD optical pulse shapes shall be weighted by a set of launch distributions to determine a corresponding set of EMB_c values. The minimum EMB_c ($minEMB_c$) within this set shall meet the requirement of Equations (D.3) and (D.4):

$$minEMB_c \geq 4\ 160\ \text{MHz}\cdot\text{km at 850 nm} \quad (\text{D.3})$$

$$minEMB_c \geq 2\ 190\ \text{MHz}\cdot\text{km at 953 nm} \quad (\text{D.4})$$

where

$minEMB_c$ is determined from the complex transfer function as described in IEC 60793-1-49 using the weights defined in Table D.3.

D.6 A1-OM2, A1-OM3, A1-OM4 and A1-OM5 calculated overfilled modal bandwidth

The DMD optical pulse shapes shall be weighted for A1-OM2, A1-OM3 and A1-OM4 fibres by the launch distribution of Table D.6 to determine a corresponding OMB_c value at 850 nm. For A1-OM5 fibres, the launch distribution of Table D.6 shall be used to determine a corresponding value at 850 nm and 953 nm. The weights of Table D.6 are the same as those in IEC 60793-1-41 for method C.

Table D.6 – DMD weighting for OMB_c

Radial position, r μm	OFL weighting
0	0
1	0,000 73
2	0,001 57
3	0,002 53
4	0,003 62
5	0,004 87
6	0,006 31
7	0,007 95
8	0,009 83
9	0,011 98
10	0,014 43
11	0,017 25
12	0,020 46
13	0,024 14
14	0,028 36
15	0,033 17
16	0,038 69
17	0,045 00
18	0,052 21
19	0,060 47
20	0,069 92
21	0,080 73
22	0,093 10
23	0,107 25
24	0,123 45
25	0,141 97

Annex E (informative)

System, modal bandwidth, and transmitter considerations

E.1 Background

When a multimode fibre is used with laser transmitters, the bandwidth of the combination may vary widely, depending on the details of the modal structure of the lasers, the modal delay structure of the fibre, and the coupling between the laser and the fibre modes. More precisely, modal bandwidth is the –3 dB bandwidth of the impulse response produced from the modal delays of a particular fibre weighted by the mode power distribution excited by a particular laser. To generate a robust bandwidth estimate when the impulse response is non-Gaussian, the 3 dB bandwidth is replaced by an extrapolation of the 1,5 dB bandwidth.

Knowledge of the modal structure of a fibre, as determined by IEC 60793-1-49, allows a lower limit to be placed on the range of bandwidths which will be experienced when using a given fibre with various laser transmitters. The minEMB_c technique reviewed in Clause E.3 screens the fibre with 10 simulated lasers that explore the observed mode power distribution; the set of 10 simulated lasers is believed to be conservative compared to commercially available lasers but narrower than the set of theoretical lasers in the original TIA model shown in Figure E.2 [13]. The chosen lasers exhibit a variety of coupled mode power distribution characteristics: some with power more concentrated in lower order modes, some with power more concentrated in higher order modes, and some with both low order and high order mode power concentrations.

By using lasers which couple primarily into modes with well bounded delays, minimum modal bandwidth can be ensured. IEC 61280-1-4 can be used to measure the launch condition of laser transmitters into multimode fibre [15]. Appropriately selected launch condition specifications can restrict the modes of the fibre used by the transmitters primarily to those with appropriately limited differential mode delays.

A minimum modal bandwidth-length product can be ensured by combining a transmitter meeting the specifications in Clause E.4 below with a 50 µm fibre meeting the specifications in Annex D.

E.2 System considerations

E.2.1 A1-OM3 and A1-OM4 fibres

Refer to Clause E.3.

E.2.2 A1-OM5 fibre

Fibre specifications for high data systems have been developed using link models [16]. The 10 Gb/s and 25 Gb/s models build on the 1 Gb/s link model [16] which includes both a requirement that the power penalty or margin be positive and that the inter-symbol interference (ISI) be less than 3,6 dB.

The A1-OM5 fibre specifications were developed using the Excel link models for IEEE 100GBASE-SR4 (Example MMF Link Model.xls [17]) and Fibre Channel 32GFC (T11-12-376v0.xlsx [18]). The link models were used to determine the bandwidth requirements over the wavelength range from 840 nm to 953 nm. The wavelengths were varied within this range in the models. In the link models, the dispersion parameters U_0 (zero dispersion wavelength) and S_0 (zero dispersion slope) were adjusted to new values of 1 328 nm and 0,093 477 ps/(nm²·km) based on round-robin results, and the cabled fibre attenuation was decreased from 3,5 dB/km to 3,0 dB/km. Both link models are margin-limited over the 840 nm to 953 nm wavelength range (unlike the IEEE P802.3ae 10GBASE-S model [19] used for OM3,

which is inter-symbol interference limited to less than or equal to 3,6 dB), and the EMB in the link model was adjusted to achieve a margin of 0,000 dB. For setting the EMB specification, it was agreed to use the 32GFC link model with zero margin because the EMB requirements are higher than for the 100GBASE-SR4 model (that is, bandwidth requirements were chosen that met requirements of both system link models). The normative EMB specifications are 4 700 MHz·km at 850 nm and 2 470 MHz·km at 953 nm. These are marked with circles in Figure E.1. With these requirements fulfilled, the expected worst-case EMB lies on or above the system requirements, as explained in Clause E.3.

E.3 Effective modal bandwidth (EMB)

During the development of fibre sub-category A1-OM3, a detailed time-domain Monte-Carlo simulation was used to assess the performance-screening ability of various DMD mask and DMD weighting proposals for transmitters meeting the specifications of Clause E.4 [3] to [14]. The proposals were judged based on their ability to pass fibres that did not cause inter-symbol interference (ISI) to exceed a specific value more often than a 0,5 % rate [13]. The specific ISI value was established via the IEEE 802.3ae link budget spreadsheet [19] for a channel that included the effects of transmitter rise time, receiver bandwidth, and a fibre with 2 000 MHz·km modal bandwidth. Thus, through the use of the Monte-Carlo simulation, fibres meeting the requirements of sub-category A1-OM3 provide a minimum EMB of 2 000 MHz·km.

The minimum EMB value is aligned with the assumptions of the IEEE 802.3ae link budget spreadsheet. Of particular relevance is the fact that, in the spreadsheet, the ISI impairment is modelled under Gaussian waveform assumptions for the transmitter and fibre outputs. According to the results of the Monte-Carlo simulation for fibres passing the requirements, the spreadsheet relationship between ISI and minimum fibre modal bandwidth is pessimistic. Therefore, the calculation of EMB from weighted DMD included a factor of 1,13 to align the fibre requirements developed with the time-domain Monte-Carlo simulation with the spreadsheet model as shown in Equation (E.1).

$$EMB = 1,13 \times \min EMB_c \quad (E.1)$$

The EMB derived by Equation (E.1) also applies to the Fibre Channel link models. If other models are used, then a different EMB may be appropriate.

Fibres passing the requirements of Clauses D.3 and D.4 (i.e. A1-OM4 fibres) provide a minimum modal bandwidth at 850 nm that is 2,35 times higher than the minimum modal bandwidth of those passing the requirements of Clauses D.1 and D.2 (i.e. A1-OM3 fibres). As such, their minimum EMB is also 2,35 times higher under the same link budget spreadsheet assumptions as stated by Equation (E.2).

$$EMB \geq 2,35 \times 2\,000 \text{ MHz}\cdot\text{km} \geq 4\,700 \text{ MHz}\cdot\text{km} \quad (E.2)$$

System performance studies with actual fibres and laser sources support this relationship [20] to [22]. Applications have emerged which will utilize multiple wavelengths in the vicinity of 850 nm to 950 nm. To support these applications, guidance which characterizes the minimum EMB for A1-OM3, A1-OM4, and A1-OM5 is provided in the form of Equations (E.3) through (E.9) and Figures E.1 through E.3. These equations should not be extrapolated without due consideration.

The population of A1-OM3 subcategory fibres generally exhibit estimated minimum EMB meeting Equations (E.3) and (E.4) which are depicted as two curves from (a) 840 nm to 850 nm and (b) 850 nm to 953 nm as depicted in Figure E.1. The unit of EMB in the two equations is MHz·km.

For $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:


$$\text{EMB} \geq 1\,826 + (2\,000 - 1\,826) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.3})$$

For $850 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 2\,000 \times (1,001\,0 - 0,980\,9x + 0,807\,3x^2 - 0,430\,4x^3 + 0,119\,4x^4) \quad (\text{E.4})$$

where

$$x = (\lambda_c - 850) / (953 - 850)$$



IEC

Figure E.1 – Estimated minimum wide band EMB versus wavelength for A1-OM3

The population of A1-OM4 subcategory fibres generally exhibit estimated minimum EMB meeting Equations (E.5) and (E.6) which are depicted as two curves from (a) 840 nm to 850 nm and (b) 850 nm to 953 nm in Figure E.2. The unit of EMB in the two equations is MHz.km.

For $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:

$$\text{EMB} \geq 3\,840 + (4\,700 - 3\,840) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.5})$$

For $850 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 4\,700 \times (1,000\,2 - 2,154\,9x + 3,270\,0x^2 - 2,732\,8x^3 + 0,928\,0x^4) \quad (\text{E.6})$$

where

$$x = (\lambda_c - 850) / (953 - 850)$$




Figure E.2 – Estimated minimum wide band EMB versus wavelength for A1-OM4

Fibres passing the requirements of Clause D.5 (i.e. A1-OM5 fibres) generally exhibit estimated EMB meeting Equations (E.7), (E.8) and (E.9), which are depicted as three straight-line segments from (a) 840 nm to 850 nm, (b) 850 nm to 930 nm, and (c) 930 nm to 953 nm in Figure E.3. The unit of EMB in all three equations is MHz.km.

For $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:

$$\text{EMB} \geq 3\,840 + (4\,700 - 3\,840) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.7})$$

For $850 \text{ nm} \leq \lambda_c \leq 930 \text{ nm}$:


$$\text{EMB} \geq 4\,700 + (2\,565 - 4\,700) \times (\lambda_c - 850) / (930 - 850) \quad (\text{E.8})$$

For $930 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 2\,565 + (2\,470 - 2\,565) \times (\lambda_c - 930) / (953 - 930) \quad (\text{E.9})$$

Equations (E.7), (E.8), and (E.9) describe three straight line segments between the minimum EMB indicated by the 32GFC link model at 840 nm and the two minimum EMBs at the nominal measurement wavelengths of 850 nm and 953 nm. Equations (E.7), (E.8) and (E.9) are plotted in Figure E.3 along with values of EMB that close the 32GFC link model. The straight line segments from 840 nm to 953 nm were carefully established as providing a minimum EMB

guidance over the wavelength range while not intentionally introducing special fibre design dependence.



IEC

Figure E.3 – Estimated minimum wide band EMB versus wavelength for A1-OM5

E.4 Transmitter encircled flux (EF) and centre wavelength requirements

E.4.1 Encircled flux

The DMD radial limits of the inner, outer and interval masks specified in Clauses D.1 and D.3, and the DMD weightings specified in Clauses D.2, D.4 and D.5, were established in conjunction with the particular bounded range of laser launch conditions specified in Equations (E.10) and (E.11). The minimum modal bandwidth for launch conditions outside of this range has not been determined, but will be lower than for launch conditions within this range.

The transmitter launch condition power distribution should meet the requirements of Equations (E.10) and (E.11) when measured according to IEC 61280-1-4 [15] with the transmitter coupled into a 50- μm fibre meeting the specifications of this document.

$$\text{EF at radius } 4,5 \mu\text{m} \leq 30 \% \quad (\text{E.10})$$

$$\text{EF at radius } 19 \mu\text{m} \geq 86 \% \quad (\text{E.11})$$

The approximate positions of the DMD weightings specified in Table D.3 are depicted in the Figure E.4 below, relative to the boundaries given in Equations (E.10) and (E.11) [2].




Figure E.4 – Approximate position of DMD weightings relative to the EF boundaries of Equations (E.10) and (E.11)

Several published application standards meet the requirements of E.4.1 and E.4.2 [23] to [26].

E.4.2 Centre wavelength for A1-OM3 and A1-OM4 fibres

Because the fibre's modal delays change with wavelength, the transmitter centre wavelength should be kept close to the nominal DMD measurement wavelength of 850 nm to achieve the highest modal bandwidth performance over the population of passing fibres. It may be appropriate to de-rate the modal bandwidth when the transmitter is not operating at 850 nm [8]. See [27] for an illustration of bandwidth roll-off for fibres with bandwidth similar to fibre model A1-OM4.

The laser transmitter centre wavelength (λ_c) should meet the requirements of Equation (E.12) when tested according to IEC 61280-1-3 [28].

$$840 \text{ nm} \leq \lambda_c \leq 860 \text{ nm} \quad (\text{E.12})$$

E.4.3 Centre wavelength for A1-OM5 fibre

Because the fibre's modal delays change with wavelength, the highest modal bandwidth performance is attained when the laser transmitter centre wavelength is between the DMD measurement wavelengths. When the laser transmitter's centre wavelength is outside this range, the modal bandwidth may degrade. See Equation (E.7), (E.8) and (E.9) for advice on bandwidth values between the DMD measurement wavelengths.

The laser transmitter centre wavelength (λ_c) should meet the requirements of Equation (E.13) when tested according to IEC 61280-1-3 [28].

$$840 \text{ nm} \leq \lambda_c \leq 953 \text{ nm} \quad (\text{E.13})$$

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

Annex F (informative)

Bandwidth nomenclature explanation

Table F.1 provides explanations of bandwidth parameters that have similar names and abbreviations.

Table F.1 – Bandwidth nomenclature explanation

Parameter name and abbreviation	Parameter description
Calculated effective modal bandwidth (EMB_c)	The calculated modal bandwidth resulting from a particular weighting of a particular DMD.
Minimum calculated effective modal bandwidth (minimum EMB_c or $minEMB_c$)	The minimum calculated modal bandwidth resulting from a particular set of weightings of a particular DMD.
Effective modal bandwidth (EMB)	The modal bandwidth that results from multiplying the minimum calculated effective modal bandwidth by 1,13 to arrive at a value aligned with the assumptions of the IEEE 802.3ae link model for transmitters compliant to Clause E.2.
Calculated overfilled modal bandwidth (OMB_c)	The calculated modal bandwidth resulting from weighting a particular DMD to simulate an overfilled launch condition.

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

Annex G (informative)

Preliminary indications for items needing further study

G.1 Effective modal bandwidth (EMB) at 1 300 nm

Chromatic dispersion properties allow DMD measured at one wavelength to be transformed to DMD at another wavelength. Thus, 850 nm DMD may be used to predict minimum effective modal bandwidth-length product at 1 300 nm. Preliminary engineering analysis indicates that fibres meeting the requirements of Annex D for $\geq 2\,000$ MHz·km EMB at 850 nm will also provide ≥ 500 MHz·km EMB at 1 300 nm.

Some 1 300 nm laser-based transmitters are defined to operate into both multimode fibre and single mode fibre. In order to provide better assurance that multimode fibres, with bandwidth performance specified only on the basis of overfilled launch conditions, deliver at least their minimum overfilled bandwidth-length product for 1 300 nm transmitters designed to launch into single mode fibre (e.g. 1000BASE-LX), IEEE Std 802.3™ specifies the use of offset-launch mode-conditioning patch cords when connecting such transmitters to this type of multimode fibre.

The offset-launch is implemented by joining a single mode fibre to a multimode fibre within the patch cord using a specified range of single mode-to-multimode radial offset. By launching significantly off-centre from the single mode fibre into the multimode fibre, many modes are excited that produce a mode power distribution closer to that of an overfilled launch than that of the native launch, which typically strongly excites only low-order modes.

Because overfilled-launch bandwidth measurements are heavily dominated by high-order mode behaviour, they are insensitive to the behaviour of low-order modes. Therefore, by avoiding strong excitation of the low-order modes, the offset-launch patch cord eliminates dependence on the behaviour of these poorly-characterized modes, and improves the correlation between minimum system bandwidth and the overfilled launch bandwidth-length measurement.

However, because the DMD test procedure does measure low-order mode behaviour, it is capable of bounding the lower limit of bandwidth-distance product for the native launches of these 1 300 nm transmitters. Fibres meeting A1-OM3 and A1-OM4 specifications are optimised for peak bandwidth at 850 nm, and have specifically limited low-order mode DMD.

Operating at wavelengths different from the peak wavelength introduces a systematic increase in DMD. The largest increase in DMD occurs for the highest order modes. Thus the overfilled bandwidth, which is dominated by high-order mode DMD, is a conservative indicator of lowest effective modal bandwidth for native 1 300 nm launches that concentrate power in the low order modes. Therefore, A1-OM3 and A1-OM4 fibres are expected to provide EMB at least as high as their 500 MHz·km minimum overfilled bandwidth-length product at 1 300 nm without the use of mode conditioning patch cords.

G.2 Scaling of EMB with DMD

Different effective modal bandwidth-length products can be derived from the templates and interval masks defined in Clauses D.1 and D.3 simply by scaling EMB in inverse proportion to DMD temporal width, provided the following three conditions are met:

- 1) the fibre is used with transmitters meeting the specifications in E.4.1;
- 2) the radial offset limits of the templates are not changed; and
- 3) the overfilled modal bandwidth-length product requirements are scaled in direct proportion to the EMB.

This scaling ability is substantiated by the following relationships. From the waveguide theory, the mode power distribution of the transmitter relates directly to the radial extents of the inner and outer DMD masks. The operating wavelength range constrains operation in close proximity to the nominal DMD measurement wavelength to minimise modal bandwidth changes due to wavelength. With the mode power distribution and the radial extent of the DMD masks fixed, and the operating wavelength range unchanged, scaling is supported by the inverse proportionality between RMS pulse width and bandwidth [29] [30]. In this case, the RMS pulse width equates to the DMD temporal width. Scaling the overfilled bandwidth in direct proportion to the desired EMB maintains the established proportionality between the DMD and overfilled bandwidth.

For example, an effective modal bandwidth-length product at 850 nm of $\geq 1\,000$ MHz·km (one-half of 2 000 MHz·km) can be provided with fibre meeting any of the six DMD templates given in Clause D.1, with each template having double the DMD temporal width in both the inner and outer masks, and an overfilled bandwidth-length product of ≥ 750 MHz·km.

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

Annex H (informative)

Applications and cabling categories supported by A1 fibres

Table H.1 shows various internationally standardised applications, as well as other recommended applications, which are supported by A1 fibres. It is not an exhaustive list, and many other applications not specifically listed may also be supported.

**Table H.1 – Some standardised applications supported by
A1-OM2, A1-OM3, A1-OM4, A1-OM5 fibres and in some cases A1-OM1 fibres**

Application	Source	Name
1GFC	ISO/IEC 14165-115	1-Gigabit Fibre Channel
2GFC	ISO/IEC 14165-115	2-Gigabit Fibre Channel
4GFC	ANSI/INCITS 479	4-Gigabit Fibre Channel
8GFC	ANSI/INCITS 479	8-Gigabit Fibre Channel
10GFC	ISO/IEC 14165-116	10-Gigabit Fibre Channel
16GFC	ANSI/INCITS 479	16-Gigabit Fibre Channel
32GFC	ANSI/INCITS 512	32-Gigabit Fibre Channel
1000BASE-SX	ISO/IEC/IEEE 8802-3	Gigabit Ethernet
1000BASE-LX	ISO/IEC/IEEE 8802-3	Gigabit Ethernet
10GBASE-S	ISO/IEC/IEEE 8802-3	10-Gigabit Ethernet
25GBASE-SR	ISO/IEC/IEEE 8802-3	25-Gigabit Ethernet
40GBASE-SR4	ISO/IEC/IEEE 8802-3	40-Gigabit Ethernet
100GBASE-SR10	ISO/IEC/IEEE 8802-3	100-Gigabit Ethernet
100GBASE-SR4	ISO/IEC/IEEE 8802-3	100-Gigabit Ethernet

Annex I (informative)

1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit and 100-Gigabit Ethernet applications

Annex I is intended to outline a summary of category A1-OM2, A1-OM3, A1-OM4, A1-OM5 and A1-OM1 fibre requirements and related transmission capabilities for the 1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit, and 100-Gigabit Ethernet application standards developed within IEEE 802.3. All the Ethernet applications at 1 Gb/s or higher are considered as "laser launch" applications.

Table I.1 shows a summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities. The rows of Table I.1 are grouped by fibre sub-category and model and listed by increasing data rate. For each line item, there is an indication of the application link length and the requirements on transmitter launch characteristics. The requirements of the transmitter launch characteristics are of three types

- Offset-launch mode-conditioning patch cord for 1 300 nm operations, defined in IEEE 802.3.
- Coupled power ratio (CPR) > 9 dB and avoidance of radial overfilled launch (ROFL) for 1 Gb/s 850 nm operations on fibres characterised solely by overfilled launch (OFL) bandwidth. CPR is defined in IEC 61280-4-1:2009; ROFL is defined in IEEE 802.3.
- Encircled Flux (EF) requirements for 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s 850 nm operation on fibre models A1-OM3, A1-OM4 and A1-OM5 with effective modal bandwidth ensured by DMD measurement. The EF requirements are: EF at 4,5 μm radius $\leq 30\%$ and EF at 19,0 μm radius $\geq 86\%$. For EF measurements, see IEC 61280-1-4.

Table I.1 – Summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength									
		850 nm					1 300 nm				
		Minimum modal bandwidth for indicated measurement launch condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Minimum modal bandwidth for indicated measurement launch condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m
A1-OM1	1	160 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	220	500 for OFL	n.s.	1000BASE-LX	Offset-launch patch cord	550
A1-OM1	1	200 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	275	500 for OFL	n.s.	1000BASE-LX	Offset-launch patch cord	550
A1-OM1	10	160 for OFL	n.s.	10GBASE-S	EF at 4,5 μm radius ≤ 30 %, EF at 19,0 μm radius ≥ 86 %	26	500 for OFL	n.s.	10GBASE-LX4	Offset-launch patch cord	300
A1-OM1	10	200 for OFL	n.s.	10GBASE-S	EF at 4,5 μm radius ≤ 30 %, EF at 19,0 μm radius ≥ 86 %	33	500 for OFL	n.s.	10GBASE-LX4	Offset-launch patch cord	300
A1-OM1	10	160 for OFL	n.s.	n.s.	n.s.	n.s.	500 for OFL	n.s.	10GBASE-LRM	Offset-launch patch cord or EF at 5 μm radius ≥ 30 %, EF at 11 μm radius ≥ 81 %	220

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength							
		850 nm				1 300 nm			
		Minimum modal bandwidth for indicated measurement condition MHz-km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz-km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Minimum modal bandwidth for indicated measurement condition MHz-km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz-km	IEEE 802.3 PMD ^a
A1-OM1	10	200 for OFL	n.s.	n.s.	n.s.	n.s.	500 for OFL	n.s.	10GBASE-LRM
A1-OM2	1	400 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	500	400 for OFL	n.s.	1000BASE-LX
A1-OM2	1	500 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	550	500 for OFL	n.s.	1000BASE-LX
A1-OM2	10	400 for OFL	n.s.	10GBASE-S	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	66	400 for OFL	n.s.	10GBASE-LX4
A1-OM2	10	500 for OFL	n.s.	10GBASE-S	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	82	500 for OFL	n.s.	10GBASE-LX4
A1-OM2	10	500 for OFL	n.s.	10GBASE-S	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	82	500 for OFL	n.s.	10GBASE-LX4

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength					
		850 nm			1 300 nm		
		Minimum modal bandwidth for indicated measurement launch condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Link length m
A1-OM2	10	400 for OFL	n.s.	n.s.	n.s.	500 for OFL	100
A1-OM2	10	500 for OFL	n.s.	n.s.	n.s.	500 for OFL	220
A1-OM3	10	1 500 for OFL	2 000	10GBASE-SR EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	300	500 for OFL	300
A1-OM3	10	1 500 for OFL	2 000	n.s.	n.s.	500 for OFL	220

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength							
		850 nm				1 300 nm			
		Minimum modal bandwidth for indicated measurement condition MHz-km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz-km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Minimum modal bandwidth for indicated measurement condition MHz-km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz-km	IEEE 802.3 PMD ^a
A1-OM3	25	1 500 for OFL	2 000	25GBASE-SR	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	70	500 for OFL	n.s.	n.s.
A1-OM3	40	1 500 for OFL	2 000	40GBASE-SR4	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	100	500 for OFL	n.s.	n.s.
A1-OM3	100	1 500 for OFL	2 000	100GBASE-SR10	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	100	500 for OFL	n.s.	n.s.
A1-OM3	100	1 500 for OFL	2 000	100GBASE-SR4	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	70	500 for OFL	n.s.	n.s.
A1-OM4 or A1-OM5	10	3 500 for OFL	4 700	10BASE-S	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	400	500 for OFL	n.s.	n.s.

--	--	--	--	--	--

enclosure for a device, such as a transceiver, that connects to the transmission medium.
 th maximum 1.0 dB connection and splice loss.

Bibliography

- [1] H. Murata, Handbook of Optical Fibers and Cables, 2nd Edition. New York: Marcel Dekker Inc., 1996, Figure 22
- [2] J. Abbott, S. Bickham, P. Dainese, M. Li, "Fibers for Short-Distance Applications", Chapter 7 in Optical Fiber Telecommunications VIA. New York: Elsevier, 2013, Figure 7.3
- [3] J. Ritger, J. Abbott, "New Delay Set for TIA Modelling", White paper, June 1, 2001. Available at: <http://www.tiaonline.org/>
- [4] J. Ritger, J. Abbott, "Fiber Delays for 10 Gb Risk Assessment", Presentation to FO2.2.1, June 25, 2001. Available at: <http://www.tiaonline.org/>
- [5] P. Kolesar, "Source Characteristics Development", Presentation to FO2.2.1, June 2001. Available at: <http://www.tiaonline.org/>
- [6] S. Golowich, J. Ritger, P. Kolesar, "Simulation of 50 μ m 10 Gb Links", Presentation to FO2.2.1, June 25, 2001. Available at: <http://www.tiaonline.org/>
- [7] S. Golowich, P. Kolesar, J. Ritger, G. Giaretta, "Modelling, Simulation, and Experimental Study of a 50 μ m Multimode Fiber Serial 10 Gb Link", Presentation to IEEE 802.3ae, May, 2000 [viewed 2019-01-30]. Available at: http://grouper.ieee.org/groups/802/3/ae/public/may00/golowich_1_0500.pdf
- [8] J. Ritger, "Risk Analysis: EF limits and Wavelength Dependence", Presentation to FO2.2.1, June 25, 2001. Available at: <http://www.tiaonline.org/>
- [9] S. Golowich, P. Kolesar, J. Ritger, P. Pepeljugoski, "Modelling and Simulations for 10 Gb Multimode Optical Fiber Link Component Specifications", OFC 2001, paper WDD57
- [10] P. Pepeljugoski, S. Golowich, "Measurements and simulations of intersymbol interference penalty in new high speed 50 μ m multimode fiber links operating at 10 Gb/s", OFC 2001, paper WDD40
- [11] J. Ritger, "Use of Differential Mode Delay in Qualifying Multi-Mode Optical Fiber for 10 Gbps Operation", OFMC 2001
- [12] M. Hackert, "ITA FO-2.2.1 March 12, 2001 Update", March 2001 IEEE Plenary [viewed 2019-01-30]. Available at: http://grouper.ieee.org/groups/802/3/ae/public/mar01/hackert_1_0301.pdf
- [13] P. Pepeljugoski, M. Hackert, J. Abbott, S. Swanson, S. Golowich, J. Ritger, P. Kolesar, C. Chen and P. Pleunis, "Development of System Specification for Laser Optimized 50 μ m Multimode Fiber for Multi-gigabit Short Wavelength LANs", J. Lightwave Tech., volume 21, No. 5, p. 1256-1275, May 2003
- [14] P. Pepeljugoski, S. Golowich, J. Ritger, P. Kolesar, A. Risteski, " Modeling and Simulation of Next-Generation Multimode Fiber Links", J. Lightwave Tech. Vol. 21, No. 5, p. 1242-1255, May 2003.
- [15] IEC 61280-1-4, *Fibre optic communication subsystem test procedures – Part 1-4: General communication subsystems – Light source encircled flux measurement method*

- [16] D. Cunningham and W. Lane, Gigabit Ethernet Networking. New York: Macmillan Technical Publishing, 1999 (Chapter 9 – The Gigabit Ethernet Optical Link Model)
- [17] IEEE 100G-SR4 Example MMF Link Model.xls, Petrilla [viewed 2019-01-30]. Available at: <http://www.ieee802.org/3/bm/public/may13/index.html>
- [18] 32G Fibre Channel Model T11-12-376v0, Cunningham 9/27/2012 [viewed 2019-02-25]. Available at: https://standards.incits.org/apps/group_public/document.php?document_id=105920&wg_abbrev=t11
- [19] IEEE P802.3ae 10Gb/s Ethernet Task Force Link Budget Spreadsheet (Version 3.1.16a) [viewed 2019-01-30]. Available at: <http://grouper.ieee.org/groups/802/3/ae/public/index.html>
- [20] C. Caspar, R. Freund, F. Achten, A. Gholami, G. Kuyt, P. Matthijsse and D. Molin "Impact of Transceiver Characteristics on the Performance of 10 GbE Links Applying OM-4 Multimode Fibers", Proceedings of the 57th IWCS Conference, p. 295-303, November 2008
- [21] A. Sengupta, "Simulation of 10GbE Multimode Optical Communications Systems", Proceedings of the 57th IWCS Conference, p. 320-326, November 2008
- [22] G. Oulundsen III, Y. Sun, D. Vaidya, R. Lingle, Jr., T. Irujo, D. Mazzaresse, "Important Performance Characteristics of Enhanced OM3 Fiber for 10 Gb/s Operation", Proceedings of the 57th IWCS Conference, p. 327-334, November 2008
- [23] IEEE Std 802.3TM-2015, *IEEE Standard for Ethernet*, Clause 52 for 10GBASE-S, Clause 86 for 40GBASE-SR4 and 100GBASE-SR10, Clause 95 for 100GBASE-SR4, Clause 112 for 25GBASE-SR2
- [24] ISO/IEC 14165-116, Information technology – *Fibre channel – Part 116: 10 Gigabit (10GFC)*
- [25] ANSI/INCITS 479-2011, Information Technology – *Fibre Channel – Physical Interface – 5 (FC-P1-5)*, for 400-SN (4GFC), 800-SN and 800-SA (8GFC), 1600-SN (16GFC)³
- [26] ANSI/INCITS 512-2015, Information Technology – *Fibre Channel – Physical Interface – 6 (FC-P1-6)*, for 3200-SN (32GFC)
- [27] OM3, OM4, OM5 Modal Bandwidth Over Wavelengths for WDM, IEEE 802.3 NGMMF Study Group, 01-2018 [viewed 2019-01-30]. Available at: http://grouper.ieee.org/groups/802/3/NGMMF/public/Jan18/kolesar_NGMMF_01_jan18.pdf
- [28] IEC 61280-1-3, *Fibre optic communication subsystem test procedures – Part 1-3: General communication subsystems – Central wavelength and spectral width measurement*

² This publication has been withdrawn and replaced by IEEE Std 802.3-2018, but for the purposes of this document, it is given as a reference.

³ This publication has been withdrawn, but for the purposes of this document, it is given as a reference.

- [29] R. G. Smith and S. D. Personick, Receiver design for optical communication systems. In Topics in Applied Physics, Vol. 39, *Semiconductor Devices for Optical Communications*, H. Kressel (ed.). Berlin: Springer-Verlag, 1982
- [30] Gair D. Brown, Bandwidth and rise time calculations for digital multimode fiber-optic data links. *JLT* 10, no. 5, p. 675-678, 1992 May

Non-numbered references

IEC 60793-2-10:2017, *Optical fibres – Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres*

IEC 60794-1-1, *Optical fibre cables – Part 1-1: Generic specification – General*

IEC TR 62048:2014, *Optical fibres – Reliability – Power law theory*

ISO/IEC 11801:2002, *Information technology – Generic cabling for customer premises*⁴

ISO/IEC 11801-1:2017, *Information technology – Generic cabling for customer premises – Part 1: General requirements*

ISO/IEC 14165-115, *Information technology – Fibre channel – Part 115: Physical interfaces (FC-PI)*

ISO/IEC/IEEE 8802-3, *Information technology – Telecommunications and information exchange between systems – Local and metropolitan area networks – Specific requirements – Part 3: Standard for Ethernet*

⁴ This publication has been withdrawn and replaced by ISO/IEC 11801-1:2017 and ISO/IEC 11801-2:2017, but for the purposes of this document, it is given as a reference.

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

SOMMAIRE

AVANT-PROPOS	57
1 Domaine d'application	59
2 Références normatives	60
3 Termes et définitions	61
4 Termes abrégés	62
5 Spécifications	62
5.1 Généralités	62
5.2 Exigences dimensionnelles	62
5.3 Exigences mécaniques	64
5.4 Exigences de transmission	64
5.5 Exigences environnementales	66
5.5.1 Généralités	66
5.5.2 Exigences liées à l'environnement mécanique (communes à toutes les fibres de catégorie A1)	67
5.5.3 Exigences d'environnement pour la transmission	68
Annexe A (normative) Spécifications pour les fibres multimodales de la sous-catégorie A1-OM2, A1-OM3, A1-OM4 et A1-OM5	69
A.1 Généralités	69
A.2 Exigences dimensionnelles	69
A.3 Exigences mécaniques	70
A.4 Exigences de transmission	70
A.5 Exigences environnementales	72
Annexe B (normative) Spécifications pour les fibres multimodales de la sous-catégorie A1-OM1	73
B.1 Généralités	73
B.2 Exigences dimensionnelles	73
B.3 Exigences mécaniques	73
B.4 Exigences de transmission	74
B.5 Exigences environnementales	74
Annexe C (normative) Spécifications pour les fibres multimodales de la sous-catégorie A1d	75
C.1 Généralités	75
C.2 Exigences dimensionnelles	75
C.3 Exigences mécaniques	75
C.4 Exigences de transmission	76
C.5 Exigences environnementales	76
Annexe D (normative) Exigences concernant le retard de mode différentiel (DMD) de la fibre, la largeur de bande modale effective calculée (EMB_C) et la largeur de bande modale saturée calculée (OMB_C)	77
D.1 Exigences relatives au DMD pour les fibres A1-OM3	77
D.1.1 Généralités	77
D.1.2 Gabarits de DMD	77
D.1.3 Masques d'intervalle de DMD	79
D.2 Exigences relatives au EMB_C pour les fibres A1-OM3	79
D.2.1 Généralités	79
D.2.2 Largeur de bande effective calculée	79

D.3	Exigences relative au DMD pour les fibres A1-OM4	81
D.3.1	Généralités	81
D.3.2	Gabarits de DMD	81
D.3.3	Masques d'intervalle de DMD	82
D.4	Exigences relatives au EMB _C pour les fibres A1-OM4	82
D.4.1	Généralités	82
D.4.2	Largeur de bande effective calculée	82
D.5	Exigences relatives à la largeur de bande modale des fibres A1-OM5.....	82
D.5.1	Généralités	82
D.5.2	Largeur de bande modale effective calculée	83
D.6	Largeur de bande modale saturée calculée A1-OM2, A1-OM3, A1-OM4 et A1-OM5	83
Annexe E (informative) Considérations sur les systèmes, la largeur de bande modale et les émetteurs		85
E.1	Contexte	85
E.2	Considérations sur les systèmes	85
E.2.1	Fibres A1-OM3 et A1-OM4.....	85
E.2.2	Fibre A1-OM5	85
E.3	Largeur de bande modale effective (EMB)	86
E.4	Exigences relatives au flux inscrit (EF) et à la longueur d'onde centrale pour l'émetteur.....	90
E.4.1	Flux inscrit.....	90
E.4.2	Longueur d'onde centrale pour les fibres A1-OM3 et A1-OM4.....	91
E.4.3	Longueur d'onde centrale pour une fibre A1-OM5	91
Annexe F (informative) Explication de la nomenclature des largeurs de bande		93
Annexe G (informative) Indications préliminaires pour les éléments qui nécessitent une étude supplémentaire		94
G.1	Largeur de bande modale effective (EMB) à 1 300 nm	94
G.2	Graduation de l'EMB avec le DMD	95
Annexe H (informative) Applications et catégories de câbles supportées par les fibres A1.....		96
Annexe I (informative) Applications Ethernet 1 gigabit, 10 gigabits, 25 gigabits, 40 gigabits et 100 gigabits		97
Bibliographie.....		105
Figure 1 – Relation entre les largeurs de bande à 850 nm et à 1 300 nm		66
Figure D.1 – Exigences relatives aux gabarits de DMD		78
Figure E.1 – EMB large bande minimale estimée en fonction de la longueur d'onde pour A1-OM3		88
Figure E.2 – EMB large bande minimale estimée en fonction de la longueur d'onde pour A1-OM4		89
Figure E.3 – EMB large bande minimale estimée en fonction de la longueur d'onde pour A1-OM5		90
Figure E.4 – Position approchée de pondérations de DMD par rapport aux limites de flux inscrit des Equations (E.10) et (E.11)		91
Tableau 1 – Correspondance entre les désignations de fibres optiques multimodales IEC A1 et l'IEC 60793-2-10:2017		60
Tableau 2 – Attributs dimensionnels et méthodes de mesure		63

Tableau 3 – Exigences dimensionnelles communes aux fibres de catégorie A1	63
Tableau 4 – Attributs dimensionnels supplémentaires exigés dans les spécifications de sous-catégories	63
Tableau 5 – Attributs mécaniques et méthodes de mesure.....	64
Tableau 6 – Exigences mécaniques communes aux fibres de catégorie A1	64
Tableau 7 – Attributs de transmission et méthodes de mesure	65
Tableau 8 – Attributs de transmission supplémentaires exigés dans les spécifications de sous-catégories	65
Tableau 9 – Essais d'exposition à l'environnement	67
Tableau 10 – Attributs mesurés pour les essais d'environnement.....	67
Tableau 11 – Force de dénudage pour les essais d'environnement.....	67
Tableau 12 – Résistance à la traction pour les essais d'environnement	68
Tableau 13 – Résistance à la corrosion sous contrainte pour les essais d'environnement	68
Tableau 14 – Variation de l'affaiblissement pour les essais d'environnement	68
Tableau A.1 – Exigences dimensionnelles spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5	70
Tableau A.2 – Exigences mécaniques spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5.....	70
Tableau A.3 – Exigences de transmission spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5	71
Tableau B.1 – Exigences dimensionnelles spécifiques aux fibres A1-OM1	73
Tableau B.2 – Exigences mécaniques spécifiques aux fibres A1-OM1	74
Tableau B.3 – Exigences de transmission spécifiques aux fibres A1-OM1	74
Tableau C.1 – Exigences dimensionnelles spécifiques aux fibres A1d	75
Tableau C.2 – Exigences mécaniques spécifiques aux fibres A1d.....	76
Tableau C.3 – Exigences de transmission spécifiques aux fibres A1d.....	76
Tableau D.1 – Gabarits de DMD pour les fibres A1-OM3.....	77
Tableau D.2 – Masques d'intervalles de DMD pour les fibres A1-OM3	79
Tableau D.3 – Pondérations de DMD	80
Tableau D.4 – Gabarits de DMD pour les fibres A1-OM4.....	82
Tableau D.5 – Masques d'intervalles de DMD pour les fibres A1-OM4	82
Tableau D.6 – Pondération de DMD pour OMB _C	84
Tableau F.1 – Explication de la nomenclature des largeurs de bande	93
Tableau H.1 – Exemples d'applications normalisées prises en charge par les fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5 et dans certains cas par les fibres A1-OM1	96
Tableau I.1 – Aperçu des exigences et des capacités de l'Ethernet 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s et 100 Gb/s.....	98

COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

FIBRES OPTIQUES –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1

AVANT-PROPOS

- 1) La Commission Electrotechnique Internationale (IEC) est une organisation mondiale de normalisation composée de l'ensemble des comités électrotechniques nationaux (Comités nationaux de l'IEC). L'IEC a pour objet de favoriser la coopération internationale pour toutes les questions de normalisation dans les domaines de l'électricité et de l'électronique. A cet effet, l'IEC – entre autres activités – publie des Normes internationales, des Spécifications techniques, des Rapports techniques, des Spécifications accessibles au public (PAS) et des Guides (ci-après dénommés "Publication(s) de l'IEC"). Leur élaboration est confiée à des comités d'études, aux travaux desquels tout Comité national intéressé par le sujet traité peut participer. Les organisations internationales, gouvernementales et non gouvernementales, en liaison avec l'IEC, participent également aux travaux. L'IEC collabore étroitement avec l'Organisation Internationale de Normalisation (ISO), selon des conditions fixées par accord entre les deux organisations.
- 2) Les décisions ou accords officiels de l'IEC concernant les questions techniques représentent, dans la mesure du possible, un accord international sur les sujets étudiés, étant donné que les Comités nationaux de l'IEC intéressés sont représentés dans chaque comité d'études.
- 3) Les Publications de l'IEC se présentent sous la forme de recommandations internationales et sont agréées comme telles par les Comités nationaux de l'IEC. Tous les efforts raisonnables sont entrepris afin que l'IEC s'assure de l'exactitude du contenu technique de ses publications; l'IEC ne peut pas être tenue responsable de l'éventuelle mauvaise utilisation ou interprétation qui en est faite par un quelconque utilisateur final.
- 4) Dans le but d'encourager l'uniformité internationale, les Comités nationaux de l'IEC s'engagent, dans toute la mesure possible, à appliquer de façon transparente les Publications de l'IEC dans leurs publications nationales et régionales. Toutes divergences entre toutes Publications de l'IEC et toutes publications nationales ou régionales correspondantes doivent être indiquées en termes clairs dans ces dernières.
- 5) L'IEC elle-même ne fournit aucune attestation de conformité. Des organismes de certification indépendants fournissent des services d'évaluation de conformité et, dans certains secteurs, accèdent aux marques de conformité de l'IEC. L'IEC n'est responsable d'aucun des services effectués par les organismes de certification indépendants.
- 6) Tous les utilisateurs doivent s'assurer qu'ils sont en possession de la dernière édition de cette publication.
- 7) Aucune responsabilité ne doit être imputée à l'IEC, à ses administrateurs, employés, auxiliaires ou mandataires, y compris ses experts particuliers et les membres de ses comités d'études et des Comités nationaux de l'IEC, pour tout préjudice causé en cas de dommages corporels et matériels, ou de tout autre dommage de quelque nature que ce soit, directe ou indirecte, ou pour supporter les coûts (y compris les frais de justice) et les dépenses découlant de la publication ou de l'utilisation de cette Publication de l'IEC ou de toute autre Publication de l'IEC, ou au crédit qui lui est accordé.
- 8) L'attention est attirée sur les références normatives citées dans cette publication. L'utilisation de publications référencées est obligatoire pour une application correcte de la présente publication.
- 9) L'attention est attirée sur le fait que certains des éléments de la présente Publication de l'IEC peuvent faire l'objet de droits de brevet. L'IEC ne saurait être tenue pour responsable de ne pas avoir identifié de tels droits de brevets et de ne pas avoir signalé leur existence.

Cette version consolidée de la Norme IEC officielle et de son amendement a été préparée pour la commodité de l'utilisateur.

L'IEC 60793-2-10 édition 7.1 contient la septième édition (2019-05) [documents 86A/1932/FDIS et 86A/1939/RVD] et son amendement 1 (2022-01) [documents 86A/2121/CDV et 86A/2140/RVC].

Dans cette version Redline, une ligne verticale dans la marge indique où le contenu technique est modifié par l'amendement 1. Les ajouts sont en vert, les suppressions sont en rouge, barrées. Une version Finale avec toutes les modifications acceptées est disponible dans cette publication.

La Norme internationale IEC 60793-2-10 a été établie par le sous-comité 86A: Fibres et câbles, du comité d'études 86 de l'IEC: Fibres optiques.

Cette septième édition constitue une révision technique.

La présente édition inclut les modifications majeures suivantes par rapport à l'édition précédente: révision de la convention de dénomination pour les fibres multimodales A1, correspondant mieux aux noms compris dans les normes ISO/IEC. Ces modifications sont indiquées dans le domaine d'application du présent document avec une table de correspondance pour les nouveaux noms.

Ce document a été rédigé selon les Directives ISO/IEC, Partie 2.

Une liste de toutes les parties de la série IEC 60793, publiées sous le titre général *Fibres optiques*, peut être consultée sur le site web de l'IEC.

Le comité a décidé que le contenu de la publication de base et de son amendement ne sera pas modifié avant la date de stabilité indiquée sur le site web de l'IEC sous webstore.iec.ch dans les données relatives à la publication recherchée. A cette date, la publication sera

- reconduite,
- supprimée,
- remplacée par une édition révisée, ou
- amendée.

IMPORTANT – Le logo "colour inside" qui se trouve sur la page de couverture de cette publication indique qu'elle contient des couleurs qui sont considérées comme utiles à une bonne compréhension de son contenu. Les utilisateurs devraient, par conséquent, imprimer cette publication en utilisant une imprimante couleur.

FIBRES OPTIQUES –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1

1 Domaine d'application

La présente partie de l'IEC 60793 est applicable aux fibres optiques des sous-catégories A1-OM1, A1-OM2, A1-OM3, A1-OM4, A1-OM5 et A1d. Ces fibres sont utilisées ou peuvent être intégrées dans des équipements destinés à la transmission de l'information et dans des câbles à fibres optiques.

Les sous-catégories A1-OM2, A1-OM3, A1-OM4 et A1-OM5 s'appliquent à la fibre à gradient d'indice de 50/125 μm dans quatre classes de largeur de bande. Chaque classe de largeur de bande est définie pour deux niveaux de performances en matière de pertes par macrocourbures, qui se distinguent par le suffixe "a" ou "b". Les sous-catégories qui comportent le suffixe "a" sont spécifiées de façon à satisfaire aux niveaux de performances classiques en matière de pertes par macrocourbures. Les sous-catégories qui comportent le suffixe "b" sont spécifiées de façon à satisfaire aux niveaux de performances avancées en matière de pertes par macrocourbures (c'est-à-dire des niveaux de pertes plus faibles).

La sous-catégorie A1-OM5 est spécifiée pour prendre en charge des systèmes de transmission à une seule ou plusieurs longueurs d'onde au voisinage de 850 nm à 950 nm. Bien qu'elles ne soient pas spécifiées sur le plan normatif, les informations de largeur de bande couvrant cette plage de longueurs d'onde sont également incluses pour A1-OM3 et A1-OM4.

La sous-catégorie A1-OM1 s'applique aux fibres à gradient d'indice de 62,5/125 μm et la sous-catégorie A1d à celles de gradient d'indice de 100/140 μm .

D'autres applications comprennent, mais sans s'y limiter, ce qui suit: les systèmes téléphoniques de courtes distances à haut débit, les réseaux de distribution et les réseaux locaux qui transportent des données, la voix et/ou des services vidéo; et les connexions par fibres intra ou inter bâtiment dans les locaux utilisateurs, englobant les centres de traitement de données, les réseaux locaux (LAN), les réseaux dédiés sauvegarde (SAN), les centraux téléphoniques privés (PABX), la vidéo, les différentes utilisations de multiplexage, l'utilisation d'une installation de câble du réseau téléphonique externe et les différentes utilisations associées.

Trois types d'exigences s'appliquent à ces fibres:

- les exigences générales, qui sont définies dans l'IEC 60793-2;
- des exigences spécifiques communes aux fibres multimodales de catégorie A1, couvertes par le présent document et qui sont données à l'Article 5;
- des exigences particulières applicables à des sous-catégories et des modèles particuliers de fibres ou à des applications spécifiques, qui sont définies dans les Annexes de spécifications normatives A à D.

Le Tableau 1 montre la correspondance entre les désignations de fibres optiques multimodales IEC A1 utilisées dans le présent document et celles utilisées dans l'IEC 60793-2-10:2017. Le tableau se réfère également aux Annexes normatives A, B et C pour les fibres multimodales de la sous-catégorie A1 dans le présent document contenant la spécification particulière.

Tableau 1 – Correspondance entre les désignations de fibres optiques multimodales IEC A1 et l'IEC 60793-2-10:2017

Annexe	Sous-catégorie	Sous-catégorie/ Modèle	Diamètre du noyau (nominal)	ISO/IEC 11801-1:2017
	Désignations du présent document	Désignations de l'IEC 60793-2-10:2017		Utilisation de fibres OMx câblées
A	A1-OM2	A1a.1	50 µm ^a	OM2 ^b
	A1-OM3	A1a.2	50 µm	OM3
	A1-OM4	A1a.3	50 µm	OM4
	A1-OM5	A1a.4	50 µm	OM5
B	A1-OM1	A1b	62,5 µm ^c	OM1 ^d
C	A1d	A1d	100 µm	
^a Historiquement, l'ISO/IEC 11801:2002 définissait également des câbles OM2 faits de fibres de 62,5/125 µm ayant une largeur de bande à injection saturée minimale de 500 MHz·km à 850 nm et 500 MHz·km à 1 300 nm. Cette combinaison de largeur de bande spécifique de fibres de 62,5/125 µm ne fait pas partie du présent document. ^b Les câbles OM2 ne sont pas pris en charge dans les nouvelles installations dans l'ISO/IEC 11801-1:2017. ^c Historiquement, l'ISO/IEC 11801:2002 définissait également des câbles OM1 faits de fibres de 50/125 µm ayant une largeur de bande à injection saturée minimale de 200 MHz·km à 850 nm et 500 MHz·km à 1 300 nm. Cette combinaison de largeur de bande spécifique de fibres de 50/125 µm ne fait pas partie du présent document. ^d Les câbles OM1 ne sont pas pris en charge dans les nouvelles installations dans l'ISO/IEC 11801-1:2017.				

2 Références normatives

Les documents suivants sont cités dans le texte de sorte qu'ils constituent, pour tout ou partie de leur contenu, des exigences du présent document. Pour les références datées, seule l'édition citée s'applique. Pour les références non datées, la dernière édition du document de référence s'applique (y compris les éventuels amendements).

IEC 60793-1-20, *Fibres optiques – Partie 1-20: Méthodes de mesure et procédures d'essai – Géométrie de la fibre*

IEC 60793-1-21, *Fibres optiques – Partie 1-21: Méthodes de mesure et procédures d'essai – Géométrie du revêtement*

IEC 60793-1-22, *Fibres optiques – Partie 1-22: Méthodes de mesure et procédures d'essai – Mesure de la longueur*

IEC 60793-1-30, *Fibres optiques – Partie 1-30: Méthodes de mesure et procédures d'essai – Essais de sélection*

IEC 60793-1-31, *Fibres optiques – Partie 1-31: Méthodes de mesure et procédures d'essai – Résistance à la traction*

IEC 60793-1-32, *Fibres optiques – Partie 1-32: Mesures de mesure et procédures d'essai – Dénudabilité du revêtement*

IEC 60793-1-33, *Fibres optiques – Partie 1-33: Méthodes de mesure et procédures d'essai – Résistance à la corrosion sous contrainte*

IEC 60793-1-40, *Fibres optiques – Partie 1-40: Méthodes de mesure et procédures d'essai – Affaiblissement*

IEC 60793-1-41, *Fibres optiques – Partie 1-41: Méthodes de mesure et procédures d'essai – Largeur de bande*

IEC 60793-1-42, *Fibres optiques – Partie 1-42: Méthodes de mesure et procédures d'essai – Dispersion chromatique*

IEC 60793-1-43, *Optical fibres – Part 1-43: Measurement methods and test procedures – Numerical aperture measurement* (disponible en anglais seulement)

IEC 60793-1-46, *Fibres optiques – Partie 1-46: Méthodes de mesure et procédures d'essai – Contrôle des variations du facteur de transmission optique*

IEC 60793-1-47, *Fibres optiques – Partie 1-47: Méthodes de mesure et procédures d'essai – Pertes par macrocourbures*

IEC 60793-1-49, *Fibres optiques – Partie 1-49: Méthodes de mesure et procédures d'essai – Retard différentiel de mode*

IEC 60793-1-50, *Fibres optiques – Partie 1-50: Méthodes de mesure et procédures d'essai – Essais de chaleur humide (état continu)*

IEC 60793-1-51, *Fibres optiques – Partie 1-51: Méthodes de mesure et procédures d'essai – Essais de chaleur sèche (état continu)*

IEC 60793-1-52, *Fibres optiques – Partie 1-52: Méthodes de mesure et procédures d'essai – Essais de variations de température*

IEC 60793-1-53, *Fibres optiques – Partie 1-53: Méthodes de mesure et procédures d'essai – Essais d'immersion dans l'eau*

IEC 60793-2, *Fibres optiques – Partie 2: Spécifications de produits – Généralités*

IEC 61280-4-1:2009, *Procédures d'essai des sous-systèmes de télécommunication à fibres optiques – Partie 4-1: Installation câblée – Mesure de l'affaiblissement en multimodal*

3 Termes et définitions

Aucun terme n'est défini dans le présent document.

L'ISO et l'IEC tiennent à jour des bases de données terminologiques destinées à être utilisées en normalisation, consultables aux adresses suivantes:

- IEC Electropedia: disponible à l'adresse <http://www.electropedia.org/>
- ISO Online browsing platform: disponible à l'adresse <http://www.iso.org/obp>

4 Termes abrégés

CPR	coupled power ratio (rapport de puissance couplé)
DMD	differential mode delay (retard de mode différentiel)
EF	encircled flux (flux inscrit)
EMB	effective modal bandwidth (largeur de bande modale effective)
EMB _c	calculated effective modal bandwidth (largeur de bande modale effective calculée)
LAN	local area network (réseau local)
MMF	multimode fibre (fibre multimodale)
NA	numerical aperture (ouverture numérique)
OFL	overfilled launch (injection saturée)
OMB _c	overfilled launch modal bandwidth calculated from differential mode delay (largeur de bande modale à injection saturée, calculée à partir du retard de mode différentiel) – également appelée OFL _c)
PBX	private branch exchange (central téléphonique privé)
PMD	physical medium dependent (dépendant du support physique)
ROFL	radial overfilled launch (injection saturée radiale)
SAN	storage area network (réseau dédié sauvegarde)

5 Spécifications

5.1 Généralités

La fibre est constituée d'un cœur de verre avec un profil à gradient d'indice et d'une gaine de verre conformément à l'IEC 60793-2.

Le terme "verre" se réfère habituellement à des matériaux constitués d'oxydes non métalliques.

5.2 Exigences dimensionnelles

Les attributs dimensionnels et les méthodes de mesure applicables sont donnés dans le Tableau 2.

Les exigences communes à toutes les fibres de catégorie A1 sont données dans le Tableau 3.

Le Tableau 4 énumère les attributs supplémentaires qui doivent être indiqués par chaque spécification de sous-catégorie.

Tableau 2 – Attributs dimensionnels et méthodes de mesure

Attributs	Méthodes de mesure
Diamètre de la gaine	IEC 60793-1-20
Diamètre du cœur ^{a, b}	IEC 60793-1-20
Non-circularité de la gaine	IEC 60793-1-20
Non-circularité du cœur	IEC 60793-1-20
Erreur de concentricité entre le cœur et la gaine	IEC 60793-1-20
Diamètre du revêtement primaire	IEC 60793-1-21
Non-circularité du revêtement primaire	IEC 60793-1-21
Erreur de concentricité gaine-revêtement primaire	IEC 60793-1-21
Longueur de fibre	IEC 60793-1-22
^a Le diamètre du cœur est spécifié à 850 nm ± 10 nm avec une longueur de spécimen d'essai de 2,0 m ± 0,2 m et une valeur de seuil, k_{CORE} , de 0,025 pour les fibres A1, à l'exception des fibres A1-OM2b, A1-OM3b, A1-OM4b et A1-OM5b. ^b Le diamètre du cœur est spécifié à 850 nm ± 10 nm avec une longueur de spécimen d'essai de 100 m ± 5 % et une valeur de seuil, k_{CORE} , de 0,025 pour les fibres A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b.	

Tableau 3 – Exigences dimensionnelles communes aux fibres de catégorie A1

Attributs	Unité	Limites
Non-circularité du cœur	%	≤ 6
Diamètre du revêtement primaire – incolore ^a	μm	245 ± 10
Diamètre du revêtement primaire – coloré ^a	μm	250 ± 15
Erreur de concentricité gaine-revêtement primaire	μm	≤ 12,5
Longueur de fibre	km	^b
^a Les limites sur le diamètre du revêtement primaire sont plus communément utilisées dans les câbles de télécommunications. Il existe d'autres applications qui utilisent d'autres diamètres de revêtement primaire; plusieurs d'entre eux sont donnés ci-dessous. Autres diamètres nominaux et tolérances pour le revêtement primaire (μm): 400 ± 40 500 ± 50 700 ± 100 900 ± 100 ^b Les exigences de longueurs varient et il convient qu'elles fassent l'objet d'un accord entre fournisseur et client.		

Tableau 4 – Attributs dimensionnels supplémentaires exigés dans les spécifications de sous-catégories

Attributs
Diamètre de la gaine
Non-circularité de la gaine
Diamètre du cœur
Erreur de concentricité entre le cœur et la gaine

5.3 Exigences mécaniques

Les attributs mécaniques et les méthodes de mesure applicables sont donnés dans le Tableau 5.

Les exigences communes à toutes les fibres de catégorie A1 sont données dans le Tableau 6.

Tableau 5 – Attributs mécaniques et méthodes de mesure

Attributs	Méthodes d'essais
Essai d'épreuve	IEC 60793-1-30
Résistance à la traction	IEC 60793-1-31
Dénudabilité du revêtement primaire	IEC 60793-1-32
Résistance à la corrosion sous contrainte	IEC 60793-1-33

Tableau 6 – Exigences mécaniques communes aux fibres de catégorie A1

Attributs	Unité	Limites
Niveau de contrainte d'épreuve	GPa	$\geq 0,69^a$
Force de dénudage moyenne ^b	N	$1,0 \leq F_{avg} \leq 5,0$
Force de dénudage de crête ^b	N	$1,0 \leq F_{peak} \leq 8,9$
Résistance à la traction (moyenne) pour une longueur de spécimen de 0,5 m	GPa	$\geq 3,8$
Constante de résistance à la corrosion sous contrainte, n_d	-	≥ 18
^a La valeur d'essai d'épreuve de 0,69 GPa est égale à une déformation d'environ 1 % ou une force d'environ 8,8 N, pour les fibres A1-OM1 à A1-OM5. Pour la relation entre ces différentes unités, voir l'IEC TR 62048:2014, 8.4. ^b Soit la force de dénudage moyenne, soit la force de dénudage de crête, qui sont toutes les deux définies dans la procédure d'essai, peut être spécifiée par accord entre fournisseur et client.		

5.4 Exigences de transmission

Les attributs de transmission et les méthodes de mesure applicables sont donnés dans le Tableau 7.

Le Tableau 8 énumère les attributs supplémentaires qui doivent être indiqués par chaque spécification de sous-catégorie.

Tableau 7 – Attributs de transmission et méthodes de mesure

Attributs	Méthodes de mesure
Affaiblissement linéique	IEC 60793-1-40
Largeur de bande modale ^{a,b}	IEC 60793-1-41
Ouverture numérique ^{c,d}	IEC 60793-1-43
Dispersion chromatique	IEC 60793-1-42
Variations du facteur de transmission optique	IEC 60793-1-46
Pertes par macrocourbures	IEC 60793-1-47
Retard de mode différentiel ^e	IEC 60793-1-49
^a Pour la largeur de bande modale, soit l'injection saturée (OFL), soit la largeur de bande modale à injection saturée calculée à partir du retard de mode différentiel (OMB_c) peut être utilisée. L'OMB_c est la méthode d'essai de référence pour les fibres A1-OM2, A1-OM3 et A1-OM4 à 850 nm et la méthode exigée pour les fibres A1-OM5 à 850 nm et 953 nm. ^b La largeur de bande modale 850 nm est spécifiée avec une longueur de spécimen d'essai de 1 000 m ± 5 % pour les fibres A1-OM3 à A1-OM5. Pour les fibres A1-OM3, la largeur de bande modale 850 nm est mesurée à 850 nm ± 10 nm. Pour les fibres A1-OM4 et A1-OM5, la largeur de bande modale 850 nm est mesurée à 850 nm ± 2 nm. Pour les fibres A1-OM5, la largeur de bande modale est également mesurée à 953 nm ± 6 nm. ^c L'ouverture numérique est spécifiée à 850 nm ± 10 nm avec une longueur de spécimen d'essai de 2 m ± 0,2 m et une valeur de seuil, k_{NA}, de 0,05 pour les fibres A1, à l'exception des fibres A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b. ^d L'ouverture numérique est spécifiée à 850 nm ± 10 nm avec une longueur de spécimen d'essai de 100 m ± 5 % et une valeur de seuil, k_{NA}, de 0,05 pour les fibres A1-OM2b, A1-OM3b, A1-OM4b et A1-OM5b. ^e Le retard de mode différentiel est spécifié avec une longueur de spécimen d'essai de 1 000 m ± 5 % pour les fibres A1-OM3, A1-OM4 et A1-OM5. Pour les fibres A1-OM3, le retard de mode différentiel est mesuré à 850 nm ± 10 nm. Pour les fibres A1-OM4 et A1-OM5, le retard de mode différentiel est mesuré à 850 nm ± 2 nm. Pour les fibres A1-OM5, le retard de mode différentiel est également mesuré à 953 nm ± 6 nm.	

La conformité à la spécification relative à la dispersion chromatique peut être assurée par la conformité à la spécification relative à l'ouverture numérique pour les fibres A1.

Tableau 8 – Attributs de transmission supplémentaires exigés dans les spécifications de sous-catégories

Attributs
Affaiblissement linéique
Largeur de bande modale
Dispersion chromatique
Ouverture numérique
Pertes par macrocourbures

Pour l'affaiblissement linéique et la largeur de bande modale, les spécifications de sous-catégories peuvent contenir des plages de valeurs qui peuvent être choisies par spécification au lieu des limites fixées. Dans ce cas, les valeurs réelles de l'affaiblissement linéique maximal et de la largeur de bande modale minimale, à 850 nm et à 1 300 nm (ou à une seule de ces longueurs d'onde) doivent faire l'objet d'un accord entre fournisseur et client. Dans un but commercial, la largeur de bande modale est normalisée linéairement à 1 km.

À des fins de recommandations, l'Annexe H montre plusieurs applications normalisées prises en charge par les fibres A1, et l'Annexe I des capacités de transmissions pour ces mêmes fibres.

Les coefficients d'affaiblissement maximal indiqués s'appliquent aux fibres optiques non câblées; pour les coefficients d'affaiblissement maximal des fibres câblées, il est fait référence à l'IEC 60794-1-1, utilisable conjointement avec le présent document. Des spécifications plus strictes pour la fibre peuvent être exigées pour prendre en compte l'affaiblissement ajouté dans le processus de câblage.

Remarques sur la spécification de largeur de bande modale:

Il convient d'être rigoureux lors de la rédaction des spécifications de largeurs de bandes doubles. Il est entendu que pour les fibres de catégorie A1, la largeur de bande à 850 nm peut être liée à la largeur de bande à 1 300 nm de la façon représentée à la Figure 1, en fonction du paramètre d'indice de réfraction, g (voir l'IEC 60793-2). Des figures similaires sont données dans les publications [1]¹, page 50, et [2], page 255. La région ombrée sous la courbe de la Figure 1 peut être définie comme la zone de fenêtre double. Dans cette zone, les régions X, Y et Z sont des exemples des endroits où un fabricant de fibres peut choisir d'optimiser le processus. C'est-à-dire, centrer la largeur de bande de production sur 850 nm, 1 300 nm, ou bien entre ces deux longueurs d'onde.

Du fait de l'optimisation du processus de fabrication, certaines combinaisons de largeurs de bandes sont impossibles (c'est-à-dire à l'extérieur de la région ombrée).




Figure 1 – Relation entre les largeurs de bande à 850 nm et à 1 300 nm

5.5 Exigences environnementales

5.5.1 Généralités

Les essais d'exposition à l'environnement et les méthodes de mesure correspondantes sont documentés sous deux formes:

¹ Les chiffres entre crochets se réfèrent à la Bibliographie.

- les attributs d'environnement et les procédures d'essai applicables sont donnés dans le Tableau 9;
- les mesures d'un attribut mécanique ou de transmission particulier qui peuvent varier lors de l'application de l'environnement sont données au Tableau 10.

Tableau 9 – Essais d'exposition à l'environnement

Exposition à l'environnement	Essai
Chaleur humide	IEC 60793-1-50
Chaleur sèche	IEC 60793-1-51
Variations de température	IEC 60793-1-52
Immersion dans l'eau	IEC 60793-1-53

Tableau 10 – Attributs mesurés pour les essais d'environnement

Attribut	Méthode de mesure
Variations du facteur de transmission optique	IEC 60793-1-46
Affaiblissement	IEC 60793-1-40
Force de dénudage	IEC 60793-1-32
Résistance à la traction	IEC 60793-1-31
Résistance à la corrosion sous contrainte	IEC 60793-1-33

Ces essais sont normalement effectués de manière périodique comme essais de type pour une conception de fibre et de revêtement donnée. Sauf indication contraire, la période de reprise autorisée entre la fin de l'exposition à l'environnement et la réalisation des mesures des attributs doit être celle spécifiée dans la méthode d'essai d'environnement spécifique.

5.5.2 Exigences liées à l'environnement mécanique (communes à toutes les fibres de catégorie A1)

5.5.2.1 Généralités

Ces essais correspondent, en pratique, aux exigences les plus sévères applicables aux essais d'exposition à l'environnement indiqués au Tableau 9.

Les Tableaux 11, 12 et 13 donnent, respectivement, la force de dénudage, la résistance à la traction et la résistance à la corrosion sous contrainte prescrites.

5.5.2.2 Force de dénudage

Les attributs suivants doivent être vérifiés dès que la fibre a été retirée de l'environnement.

Tableau 11 – Force de dénudage pour les essais d'environnement

Environnement	Force de dénudage moyenne N	Force de dénudage de crête N
Chaleur humide	$1,0 \leq F_{avg} \leq 5,0$	$1,0 \leq F_{peak} \leq 8,9$
Immersion dans l'eau	$1,0 \leq F_{avg} \leq 5,0$	$1,0 \leq F_{peak} \leq 8,9$

5.5.2.3 Résistance à la traction

Les attributs suivants doivent être vérifiés une fois la fibre retirée de l'environnement.

Tableau 12 – Résistance à la traction pour les essais d'environnement

Environnement	Longueur du spécimen pour la résistance à la traction médiane: 0,5 m GPa	Longueur de spécimen pour la résistance à la traction à 15 %: 0,5 m GPa
Chaleur humide	≥ 3,03	≥ 2,76
NOTE Ces exigences ne s'appliquent pas aux fibres sous revêtement hermétique.		

5.5.2.4 Résistance à la corrosion sous contrainte

Les attributs suivants doivent être vérifiés une fois la fibre retirée de l'environnement.

Tableau 13 – Résistance à la corrosion sous contrainte pour les essais d'environnement

Environnement	Constante de résistance à la corrosion sous contrainte, n_d
Chaleur humide	≥ 18
NOTE Cette exigence ne s'applique pas aux fibres sous revêtement hermétique.	

5.5.3 Exigences d'environnement pour la transmission

La variation d'affaiblissement par rapport à la valeur initiale doit être inférieure aux valeurs du Tableau 14. L'affaiblissement doit être mesuré de manière périodique au cours de toute la durée d'exposition, pour chaque environnement et après retrait de cet environnement.

Tableau 14 – Variation de l'affaiblissement pour les essais d'environnement

Environnement	Longueur d'onde nm	Augmentation de l'affaiblissement dB/km
Chaleur humide	850	≤ 0,20
	1 300	≤ 0,20
Chaleur sèche	850	≤ 0,20
	1 300	≤ 0,20
Variations de température	850	≤ 0,20
	1 300	≤ 0,20
Immersion dans l'eau	850	≤ 0,20
	1 300	≤ 0,20

Annexe A (normative)

Spécifications pour les fibres multimodales de la sous-catégorie A1-OM2, A1-OM3, A1-OM4 et A1-OM5

A.1 Généralités

L'Annexe A contient les exigences particulières applicables aux fibres de sous-catégories A1-OM2, A1-OM3, A1-OM4 et A1-OM5. Les exigences communes, rappelées pour faciliter la référence par rapport au corps du présent document, sont notées par une entrée dans la colonne "Référence". La colonne "Référence" contient également d'autres annexes présentant des informations applicables à l'attribut. Les notes correspondantes du corps du présent document ne sont pas répétées, mais indiquées à l'aide d'un exposant "SS".

Les sous-catégories A1-OM2, A1-OM3, A1-OM4 et A1-OM5 sont des fibres multimodales à gradient d'indice de 50/125 μm dans quatre classes de largeur de bande. Tous les modèles sont spécifiés en utilisant des valeurs de largeur de bande saturée, et les sous-catégories A1-OM3, A1-OM4 et A1-OM5 s'appliquent également aux mesures du retard de mode différentiel pour offrir des performances optimisées pour des lasers proches de 850 nm. En outre, la sous-catégorie A1-OM5 spécifie à la fois les valeurs de largeur de bande saturée et du retard de mode différentiel à 953 nm pour offrir des performances optimisées pour les lasers sur une plage de longueurs d'onde au voisinage de 850 nm à 950 nm. Le modèle A1-OM3 est conforme aux spécifications du modèle A1-OM2. Le modèle A1-OM4 est conforme aux spécifications du modèle A1-OM3. Le modèle A1-OM5 est conforme aux spécifications du modèle A1-OM4.

Les sous-catégories A1-OM2, A1-OM3, A1-OM4 et A1-OM5 sont également spécifiées pour deux niveaux de performances en matière de pertes par macrocourbures, qui se distinguent par le suffixe "a" ou "b". Ceux qui comportent le suffixe "a" (c'est-à-dire les modèles A1-OM2a, A1-OM3a, A1-OM4a et A1-OM5a) sont spécifiés de façon à satisfaire aux niveaux de performances classiques en matière de pertes par macrocourbures. Ceux qui comportent le suffixe "b" (c'est-à-dire A1-OM2b, A1-OM3b, A1-OM4b et A1-OM5b) sont spécifiés de façon à satisfaire aux niveaux de performances avancées en matière de pertes par macrocourbures (c'est-à-dire des niveaux de perte plus faibles) et sont donc conformes aux performances classiques en matière de pertes par macrocourbures.

La nomenclature utilisée pour les sous-catégories A1-OM2, A1-OM3, A1-OM4 et A1-OM5 établit une hiérarchie de codage qui permet de désigner des fibres de spécificité croissante. Par exemple, des boîs de commande de fibres A1-OM3 peuvent être rédigés en suivant la spécification A1-OM3a ou A1-OM3b. Par conséquent, lorsque les spécifications et les descriptions s'appliquent à tous les modèles à des niveaux hiérarchiques plus bas, seule la partie commune du nom est indiquée.

Les exigences dimensionnelles, mécaniques et environnementales sont communes à tous les types et sont spécifiées dans les Tableaux A.1 et A.2. Les exigences de transmission communes et particulières sont spécifiées dans le Tableau A.3.

A.2 Exigences dimensionnelles

Le Tableau A.1 contient les exigences dimensionnelles qui sont spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5.

**Tableau A.1 – Exigences dimensionnelles spécifiques
aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5**

Attributs	Unité	Limites	Référence
Diamètre de la gaine	μm	125 ± 1	
Non-circularité de la gaine	%	≤ 1	
Diamètre du noyau ^{SS}	μm	50 ± 2,5	
Erreur de concentricité entre le cœur et la gaine	μm	≤ 2	
Non-circularité du cœur	%	≤ 6	5.2
Diamètre du revêtement primaire – incolore ^{SS}	μm	245 ± 10	5.2
Diamètre du revêtement primaire – coloré ^{SS}	μm	250 ± 15	5.2
Erreur de concentricité gaine-revêtement primaire	μm	≤ 12,5	5.2
Longueur	km	(voir 5.2)	5.2
^{SS} Voir les notes du corps du présent document.			

A.3 Exigences mécaniques

Le Tableau A.2 contient les exigences mécaniques qui sont spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5.

**Tableau A.2 – Exigences mécaniques spécifiques
aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5**

Attributs	Unité	Limites	Référence
Niveau de contrainte d'épreuve ^{SS}	GPa	≥ 0,69	5.3
Force de dénudage moyenne ^{SS}	N	$1,0 \leq F_{\text{avg}} \leq 5,0$	5.3
Force de dénudage de crête ^{SS}	N	$1,0 \leq F_{\text{peak}} \leq 8,9$	5.3
^{SS} Voir les notes du corps du présent document.			

A.4 Exigences de transmission

Le Tableau A.3 contient les exigences de transmission qui sont spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5.

Tableau A.3 – Exigences de transmission spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5

Attributs		Unité	Limites				Référence
Sous-catégorie de fibre			A1-OM2	A1-OM3	A1-OM4	A1-OM5	
Longueur(s) d'onde de fonctionnement cible(s) ^a		nm	850			850 à 950	Annexe E
Affaiblissement linéique maximal à 850 nm		dB/km	2,5				
Affaiblissement linéique maximal à 953 nm		dB/km	Non spécifiées				1,8
Affaiblissement linéique maximal à 1 300 nm		dB/km	0,8				
Produit longueur-largeur de bande modale minimale pour injection saturée à 850 nm ^{ss}		MHz·km	500	1 500	3 500	3 500	Article D.6
Produit longueur-largeur de bande modale minimale pour injection saturée à 953 nm ^{ss}		MHz·km	Non spécifiées				Article D.6
Produit longueur-largeur de bande modale minimale pour injection saturée à 1 300 nm		MHz·km	500				
Produit longueur-largeur de bande modale effective minimale à 850 nm ^{ss e}		MHz·km	Non spécifiées	Conforme à l'Article D.1 ou à l'Article D.2	4 700 Conforme à l'Article D.3 ou à l'Article D.4	4 700 Conforme à l'Article D.5	Annexes D, E, F, G
Produit longueur-largeur de bande modale effective minimale à 953 nm ^{ss e}		MHz·km	Non spécifiées				Annexes D, E, F, G
Ouverture numérique ^{ss}		Sans dimension	0 200 ± 0 015				
Modèle de fibre			A1-OM2a	A1-OM3a	A1-OM4a	A1-OM5a	
Pertes maximales par macro-courbures ^b	Rayon de courbure	Nombre de tours	Max à 850 nm / 1 300 nm				
	37,5 mm	100	0,5 / 0,5				
	15 mm	2	1,0 / 1,0				
Modèle de fibre			A1-OM2b	A1-OM3b	A1-OM4b	A1-OM5b	
Pertes maximales par macro-courbures ^b	Rayon de courbure	Nombre de tours	Max à 850 nm / 1 300 nm				
	37,5 mm	100	0,5 / 0,5				
	15 mm	2	0,1 / 0,3				
	7,5 mm	2	0,2 / 0,5				

Longueur d'onde de dispersion nulle, λ_0	nm	$1\,295 \leq \lambda_0 \leq 1\,340$ ^c	$1\,297 \leq \lambda_0 \leq 1\,328$ ^d	
~~Longueur d'onde~~ Pente de dispersion nulle, S_0 ^e	ps/(nm ² ·km)	$S_0 \leq 0,105$ à partir de $1\,295 \text{ nm} \leq \lambda_0 \leq 1\,310 \text{ nm}$, et $\leq 0,000\,375 (1\,590 - \lambda_0)$ à partir de $1\,310 \text{ nm} \leq \lambda_0 \leq 1\,340 \text{ nm}$ ^c	$S_0 \leq 4 (-103) / (840 (1 - (\lambda_0/840)^4))$ ^d	
^a Les longueurs d'onde de fonctionnement cibles sont données à titre d'information uniquement. ^b La condition d'injection pour la mesure des pertes par macrocourbures doit satisfaire à celle décrite dans l'IEC 61280-4-1. ^c Le cas le plus défavorable pour le coefficient de dispersion chromatique à 850 nm (par exemple $S_0 = 0,093\,75 \text{ ps/nm}^2\cdot\text{km}$ à $\lambda_0 = 1\,340 \text{ nm}$ ou $S_0 = 0,101\,25 \text{ ps/nm}^2\cdot\text{km}$ à $\lambda_0 = 1\,320 \text{ nm}$) est de -104 ps/(nm km) . ^d Les coordonnées qui génèrent la dispersion la plus défavorable pour des longueurs d'onde de fonctionnement entre 840 nm et 1 000 nm sont $\lambda_0 = 1\,328 \text{ nm}$, $S_0 = 0,093\,477 \text{ ps/(nm}^2\cdot\text{km)}$. Le coefficient de dispersion chromatique le plus défavorable à 850 nm est $-98,5 \text{ ps/(nm km)}$. ^e Lors de l'évaluation des performances des liaisons des systèmes aux longueurs d'onde comprises entre 840 nm et 953 nm, se référer aux équations appropriées concernant la valeur minimale d'EMB estimée à l'Annexe E en plus des spécifications de dispersion pour les fibres A1-OM3, A1-OM4 et A1-OM5. SS Voir les notes du corps du présent document.				

A.5 Exigences environnementales

Les exigences de 5.5 doivent être satisfaites.

Annexe B (normative)

Spécifications pour les fibres multimodales de la sous-catégorie A1-OM1

B.1 Généralités

L'Annexe B contient les exigences particulières applicables aux fibres A1-OM1. Les exigences communes, rappelées pour faciliter la référence par rapport au corps du présent document, sont notées par une entrée dans la colonne «Référence». Les notes correspondantes du corps du présent document ne sont pas répétées, mais indiquées à l'aide d'un exposant "SS".

Une fibre de la sous-catégorie A1-OM1 est une fibre à gradient d'indice de $62,5/125 \mu\text{m}$.

B.2 Exigences dimensionnelles

Le Tableau B.1 contient les exigences dimensionnelles qui sont spécifiques aux fibres A1-OM1.

Tableau B.1 – Exigences dimensionnelles spécifiques aux fibres A1-OM1

Attributs	Unité	Limites	Référence
Diamètre de la gaine	μm	125 ± 2	
Non-circularité de la gaine	%	≤ 2	
Diamètre du noyau ^{SS}	μm	$62,5 \pm 3$	
Erreur de concentricité entre le cœur et la gaine	μm	≤ 3	
Non-circularité du cœur	%	≤ 6	5.2
Diamètre du revêtement primaire – incolore ^{SS}	μm	245 ± 10	5.2
Diamètre du revêtement primaire – coloré ^{SS}	μm	250 ± 15	5.2
Erreur de concentricité gaine-revêtement primaire	μm	$\leq 12,5$	5.2
Longueur ^{SS}	km	(voir 5.2)	5,2
^{SS} Voir les notes du corps du présent document.			

B.3 Exigences mécaniques

Le Tableau B.2 contient les exigences mécaniques qui sont spécifiques aux fibres A1-OM1.

Tableau B.2 – Exigences mécaniques spécifiques aux fibres A1-OM1

Attributs	Unité	Limites	Référence
Niveau de contrainte d'épreuve ^{SS}	GPa	$\geq 0,69$	5.3
Force de dénudage moyenne ^{SS}	N	$1,0 \leq F_{\text{avg}} \leq 5,0$	5.3
Force de dénudage de crête ^{SS}	N	$1,0 \leq F_{\text{peak}} \leq 8,9$	5.3
^{SS} Voir les notes du corps du présent document.			

B.4 Exigences de transmission

Le Tableau B.3 contient les exigences de transmission qui sont spécifiques aux fibres A1-OM1.

Tableau B.3 – Exigences de transmission spécifiques aux fibres A1-OM1

Attributs	Unité	Limites	Référence
Affaiblissement linéique maximal à 850 nm	dB/km	3,0	
Affaiblissement linéique maximal à 1 300 nm	dB/km	1,0	
Produit longueur-largeur de bande modale minimale à 850 nm	MHz·km	200	
Produit longueur-largeur de bande modale minimale à 1 300 nm	MHz·km	500	
Ouverture numérique ^{SS}	Sans dimension	$0,275 \pm 0,015$	
Pertes maximales par macrocourbures 100 tours sur un rayon de courbure de 37,5 mm à des longueurs d'onde de 850 nm et 1 300 nm ^a	dB	0,5	
Longueur d'onde de dispersion nulle, λ_0	nm	$1\,320 \leq \lambda_0 \leq 1\,365$ ^b	
Pente de dispersion nulle S_0 – de $1\,320 \text{ nm} \leq \lambda_0 \leq 1\,348 \text{ nm}$ – de $1\,348 \text{ nm} \leq \lambda_0 \leq 1\,365 \text{ nm}$	ps/(nm ² ·km)	$\leq 0,11$ ^b $\leq 0,001 (1\,458 - \lambda_0)$ ^b	
^a La condition d'injection pour la mesure des pertes par macrocourbures doit satisfaire à celle décrite dans l'IEC 61280-4-1. ^b Le coefficient de dispersion chromatique le plus défavorable à 850 nm ($S_0 = 0,11 \text{ ps/nm}^2\cdot\text{km}$ à $\lambda_0 = 1\,348 \text{ nm}$) est de -125 ps/(nm km) . ^{SS} Voir les notes du corps du présent document.			

B.5 Exigences environnementales

Les exigences de 5.5 doivent être satisfaites.

Annexe C (normative)

Spécifications pour les fibres multimodales de la sous-catégorie A1d

C.1 Généralités

L'Annexe C contient les exigences particulières applicables aux fibres A1d. Les exigences communes, rappelées pour faciliter la référence par rapport au corps du présent document, sont notées par une entrée dans la colonne "Référence". Les notes correspondantes du corps du présent document ne sont pas répétées, mais indiquées à l'aide d'un exposant "SS".

Une fibre de la sous-catégorie A1d est une fibre à gradient d'indice de 100/140 μm .

C.2 Exigences dimensionnelles

Le Tableau C.1 contient les exigences dimensionnelles qui sont spécifiques aux fibres A1d.

Tableau C.1 – Exigences dimensionnelles spécifiques aux fibres A1d

Attributs	Unité	Limites	Référence
Diamètre de la gaine	μm	140 ± 4	
Non-circularité de la gaine	%	≤ 4	
Diamètre du noyau ^{SS}	μm	100 ± 5	
Erreur de concentricité entre le cœur et la gaine	μm	≤ 6	
Non-circularité du cœur	%	≤ 6	5.2
Diamètre du revêtement primaire – incolore ^{SS}	μm	245 ± 10	5.2
Diamètre du revêtement primaire – coloré ^{SS}	μm	250 ± 15	5.2
Erreur de concentricité gaine-revêtement primaire	μm	$\leq 12,5$	5.2
Longueur ^{SS}	km	(voir 5.2)	5,2
^{SS} Voir les notes du corps du présent document.			

C.3 Exigences mécaniques

Le Tableau C.2 contient les exigences mécaniques qui sont spécifiques aux fibres A1d.

Tableau C.2 – Exigences mécaniques spécifiques aux fibres A1d

Attributs	Unité	Limites	Référence
Niveau de contrainte d'épreuve ^{SS}	GPa	$\geq 0,69$	5,3
Force de dénudage moyenne ^{SS}	N	$1,0 \leq F_{\text{avg}} \leq 5,0$	5,3
Force de dénudage de crête ^{SS}	N	$1,0 \leq F_{\text{peak}} \leq 8,9$	5,3
^{SS} Voir les notes du corps du présent document.			

C.4 Exigences de transmission

Le Tableau C.3 contient les exigences de transmission qui sont spécifiques aux fibres A1d.

Tableau C.3 – Exigences de transmission spécifiques aux fibres A1d

Attributs	Unité	Limites	Référence
Affaiblissement linéique maximal à 850 nm ^a	dB/km	3,5 à 7,0	
Affaiblissement linéique maximal à 1 300 nm ^a	dB/km	1,5 à 4,5	
Produit longueur-largeur de bande modale minimale à 850 nm ^a	MHz·km	10 à 200	
Produit longueur-largeur de bande modale minimale à 1 300 nm ^a	MHz·km	100 à 300	
Ouverture numérique ^{SS}	Sans dimension	$0,26 \pm 0,03$ ou $0,29 \pm 0,03$	
Pertes maximales par macrocourbures	dB	Fera l'objet d'une étude ultérieure	
Longueur d'onde de dispersion nulle, λ_0	nm	$1\,330 \leq \lambda_0 \leq 1\,385$ ^b	
Pente de dispersion nulle S_0 – de $1\,330 \text{ nm} \leq \lambda_0 \leq 1\,365 \text{ nm}$ – de $1\,365 \text{ nm} \leq \lambda_0 \leq 1\,385 \text{ nm}$	ps/(nm ² ·km)	$\leq 0\,105$ ^b $\leq 0,000\,5 (1\,575 - \lambda_0)$ ^b	
^a La colonne «Limites» forme une plage de valeurs qui peuvent être spécifiées.			
^b Le coefficient de dispersion chromatique le plus défavorable à 850 nm ($S_0 = 0\,105$ ps/(nm ² ·km) à $\lambda_0 = 1\,365$ nm) est de -126 ps/(nm km).			
^{SS} Voir les notes du corps du présent document.			

C.5 Exigences environnementales

Les exigences de 5.5 doivent être satisfaites.

Annexe D (normative)

Exigences concernant le retard de mode différentiel (DMD) de la fibre, la largeur de bande modale effective calculée (EMB_c) et la largeur de bande modale saturée calculée (OMB_c)

D.1 Exigences relatives au DMD pour les fibres A1-OM3

D.1.1 Généralités

Les fibres A1-OM3 choisies à l'aide de la méthode du masque de DMD doivent satisfaire aux exigences de D.1.2 et D.1.3. Les limites radiales, R_{INNER} et R_{OUTER} , ont été établies pour des émetteurs conformes aux exigences de l'Article E.4.

Voir l'Annexe E pour toute information concernant la largeur de bande modale effective (EMB).

D.1.2 Gabarits de DMD

Les fibres A1-OM3, lorsqu'elles sont mesurées selon l'IEC 60793-1-49, doivent satisfaire au moins à l'un des six gabarits du Tableau D.1, chacun incluant une exigence de masque intérieur et extérieur.

Tableau D.1 – Gabarits de DMD pour les fibres A1-OM3

Numéro du gabarit	Masque intérieur de DMD (ps/m) pour $R_{INNER} = 5 \mu\text{m}$ à $R_{OUTER} = 18 \mu\text{m}$	Masque extérieur de DMD (ps/m) pour $R_{INNER} = 0 \mu\text{m}$ à $R_{OUTER} = 23 \mu\text{m}$
1	$\leq 0,23$	$\leq 0,70$
2	$\leq 0,24$	$\leq 0,60$
3	$\leq 0,25$	$\leq 0,50$
4	$\leq 0,26$	$\leq 0,40$
5	$\leq 0,27$	$\leq 0,35$
6	$\leq 0,33$	$\leq 0,33$

Les exigences sur le DMD dans le Tableau D.1 sont représentées à la Figure D.1. Dans cette figure, le DMD autorisé (tel qu'il est mesuré selon l'IEC 60793-1-49) est tracé par rapport à la position de décalage radial de la sonde unimodale. Il y a un arbitrage entre la dureté du masque intérieur et du masque extérieur pour assurer qu'une quantité suffisante de l'énergie en bauds provenant d'un émetteur (conforme aux spécifications d'injection) arrive dans l'intervalle de temps exigé (défini par le débit en bauds du système de transmission).




Figure D.1 – Exigences relatives aux gabarits de DMD

La caractéristique "flottante" du masque intérieur est également représentée à la Figure D.1. Dans cette figure, le masque intérieur (5 μm à 18 μm) peut être positionné verticalement (temporairement) à un emplacement quelconque à l'intérieur du masque extérieur (0 μm à 23 μm). Le DMD est contraint de manière plus serrée dans le masque intérieur pour permettre des tolérances plus lâches sur le masque extérieur, ce qui améliore la fabrication des fibres conformes à la présente exigence. Dans le cas du masque de 0,33 ps/m, l'exigence est la même sur toute la plage de 0 μm à 23 μm , en créant un masque "plat".

L'IEC 60793-1-49 peut être utilisée pour garantir un produit longueur-largeur de bande modale effective minimale, lorsque des sources ayant des restrictions appropriées sont utilisées. Lorsque les exigences de condition d'injection concernant les émetteurs sont couplées aux exigences sur le DMD pour la fibre, un équilibre peut être obtenu entre les tolérances de la fibre et de l'émetteur. Une étude approfondie, utilisant des fibres fournies par des fabricants différents et des émetteurs lasers provenant de différents fabricants, avec des simulations extensives et détaillées, montre que les spécifications couplées ci-dessus sur les fibres et les sources donnent un produit longueur-largeur de bande modale effective minimale de 2 000 MHz·km [3] à [14].

L'utilisation d'un gabarit sur les valeurs de DMD permet un arbitrage efficace entre les propriétés de l'émetteur et celles de la fibre. La condition d'injection de l'émetteur est limitée par les exigences sur le flux inscrit en 4,5 μm et 19 μm exposées à l'Article E.4. La limitation concernant le flux inscrit de l'émetteur au rayon de 4,5 μm assure que très peu d'énergie est transportée par les modes d'ordres plus faibles de la fibre, ce qui permet une tolérance relâchée sur la structure modale excitée à des rayons de faible valeur. La limitation concernant le flux inscrit de l'émetteur au rayon de 19 μm assure que très peu d'énergie est transportée par les modes d'ordres plus élevés de la fibre, ce qui permet une tolérance relâchée sur la structure modale excitée à des rayons élevés.

D.1.3 Masques d'intervalle de DMD

Le DMD de la fibre A1-OM3 ne doit pas dépasser 0,25 ps/m pour n'importe quel intervalle de décalage radial donné dans le Tableau D.2.

Tableau D.2 – Masques d'intervalles de DMD pour les fibres A1-OM3

Numéro d'intervalle	R_{INNER} μm	R_{OUTER} μm
1	7	13
2	9	15
3	11	17
4	13	19

Ces masques d'intervalle éliminent les fibres possédant un DMD variant trop rapidement sur de courtes plages radiales. Les fibres réussissant cette sélection ont une interférence intersymbole plus faible que celles qui ne la réussissent pas.

D.2 Exigences relatives au EMB_c pour les fibres A1-OM3

D.2.1 Généralités

Les fibres A1-OM3 choisies à l'aide de la méthode de l' EMB_c doivent satisfaire aux exigences de D.2.2.

D.2.2 Largeur de bande effective calculée

Les formes d'impulsion optique de DMD peuvent être pondérées par un ensemble de distributions d'injection pour déterminer un ensemble correspondant de valeurs d' EMB_c . La valeur minimale de l' EMB_c (minEMB_c) dans cet ensemble doit satisfaire à l'exigence de l'Equation (D.1):

$$\text{minEMB}_c \geq 1\,770 \text{ MHz}\cdot\text{km} \quad (\text{D.1})$$

où

minEMB_c est déterminée à partir de la fonction de transfert complexe décrite dans l'IEC 60793-1-49, au moyen des pondérations définies au Tableau D.3.

NOTE 1 La valeur minimale de l' EMB_c est un paramètre de fibre, et il est possible que la valeur ne soit pas optimale pour être utilisée dans les modèles de système. Voir l'Annexe E pour toute information concernant le paramètre système correspondant appelé "largeur de bande modale effective" (EMB) et sa relation avec l' EMB_c .

NOTE 2 Voir l'Annexe F pour toute explication supplémentaire de la nomenclature des largeurs de bande.

Les pondérations données dans le Tableau D.3 sont fournies pour un DMD mesuré à des intervalles radiaux de 1 μm , en commençant par le centre du cœur ($r = 0$) pour dix lasers simulés avec des valeurs de flux inscrit (EF) correspondant à celles de dix lasers réels. Les pondérations de DMD du Tableau D.3 sont spécifiques aux sources satisfaisant aux spécifications de l'Article E.4.

Tableau D.3 – Pondérations de DMD

Position radiale	ID laser				
r (μm)	1	2	3	4	5
0	0	0	0	0	0
1	0,033 023	0,023 504	0	0	0
2	0,262 463	0,188 044	0	0	0
3	0,884 923	0,634 634	0	0	0
4	2,009 102	1,447 235	0,007 414	0,005 637	0,003 034
5	3,231 216	2,376 616	0,072 928	0,055 488	0,029 856
6	3,961 956	3,052 908	0,262 906	0,200 05	0,107 634
7	3,694 686	3,150 634	0,637 117	0,483 667	0,258 329
8	2,644 369	2,732 324	1,197 628	0,896 95	0,458 494
9	1,397 552	2,060 241	1,916 841	1,402 833	0,661 247
10	0,511 827	1,388 339	2,755 231	1,957 805	0,826 035
11	0,110 549	0,834 722	3,514 797	2,433 247	1,000 204
12	0,004 097	0,419 715	3,883 317	2,639 299	1,294 439
13	0,000 048	0,160 282	3,561 955	2,397 238	1,813 982
14	0,001 111	0,047 143	2,617 093	1,816 953	2,506 95
15	0,005 094	0,044 691	1,480 325	1,296 977	3,164 213
16	0,013 918	0,116 152	0,593 724	1,240 553	3,572 113
17	0,026 32	0,219 802	0,153 006	1,700 02	3,618 037
18	0,036 799	0,307 088	0,012 051	2,240 664	3,329 662
19	0,039 465	0,329 314	0	2,394 077	2,745 395
20	0,032 152	0,268 541	0	1,952 429	1,953 241
21	0,019 992	0,166 97	0	1,213 833	1,137 762
22	0,008 832	0,073 514	0	0,534 474	0,494 404
23	0,002 612	0,021 793	0	0,158 314	0,146 517
24	0,000 282	0,002 679	0	0,019 738	0,018 328
25	0	0	0	0	0

Position radiale	ID laser				
r (μm)	6	7	8	9	10
0	0	0	0	0	0
1	0,015 199	0,016 253	0,022 057	0,010 43	0,015 681
2	0,120 91	0,129 011	0,176 39	0,083 496	0,124 978
3	0,407 702	0,434 844	0,595 248	0,281 802	0,421 548
4	0,925 664	0,987 184	1,351 845	0,650 28	0,957 203
5	1,488 762	1,587 6	2,174 399	1,130 599	1,539 535
6	1,825 448	1,94 661 4	2,666 278	1,627 046	1,887 747
7	1,702 306	1,815 285	2,486 564	2,044 326	1,762 955
8	1,218 378	1,299 241	1,780 897	2,291 72	1,292 184
9	0,643 911	0,686 635	0,945 412	2,280 813	0,790 844
10	0,238 557	0,255 85	0,360 494	1,937 545	0,559 38
11	0,098 956	0,131 429	0,163 923	1,383 006	0,673 655
12	0,204 274	0,327 091	0,318 712	0,878 798	1,047 689
13	0,529 982	0,848 323	0,778 983	0,679 756	1,589 037
14	1,024 948	1,567 513	1,383 174	0,812 36	2,138 626
15	1,611 695	2,224 027	1,853 992	1,074 702	2,470 827
16	2,210 689	2,555 06	1,914 123	1,257 323	2,361 764
17	2,707 415	2,464 566	1,511 827	1,255 967	1,798 213
18	2,938 8	2,087 879	0,908 33	1,112 456	1,059 264
19	2,739 32	1,577 111	0,386 991	0,879 309	0,444 481
20	2,090 874	1,056 343	0,111 76	0,608 183	0,123 304
21	1,261 564	0,595 102	0,014 829	0,348 921	0,012 552
22	0,552 14	0,256 718	0,001 818	0,151 12	0
23	0,163 627	0,076 096	0,000 54	0,044 757	0
24	0,020 443	0,009 446	0	0,005 639	0
25	0	0	0	0	0

D.3 Exigences relative au DMD pour les fibres A1-OM4

D.3.1 Généralités

Les fibres A1-OM4 choisies à l'aide de la méthode du masque de DMD doivent satisfaire aux exigences de D.3.2 et D.3.3. Les informations liées sont données dans l'Article D.1. Les limites radiales, R_{INNER} et R_{OUTER} , ont été établies pour des émetteurs conformes aux exigences de l'Article E.4.

Voir l'Annexe E pour toute information concernant la largeur de bande modale effective (EMB).

D.3.2 Gabarits de DMD

Les fibres A1-OM4, lorsqu'elles sont mesurées selon l'IEC 60793-1-49, doivent satisfaire au moins à l'un des trois gabarits du Tableau D.4, chacun incluant une exigence de masque intérieur et extérieur.

Tableau D.4 – Gabarits de DMD pour les fibres A1-OM4

Numéro du gabarit	Masque intérieur de DMD (ps/m) pour $R_{\text{INNER}} = 5 \mu\text{m}$ à $R_{\text{OUTER}} = 18 \mu\text{m}$	Masque extérieur de DMD (ps/m) pour $R_{\text{INNER}} = 0 \mu\text{m}$ à $R_{\text{OUTER}} = 23 \mu\text{m}$
1	$\leq 0,10$	$\leq 0,30$
2	$\leq 0,11$	$\leq 0,17$
3	$\leq 0,14$	$\leq 0,14$

D.3.3 Masques d'intervalle de DMD

Le DMD de la fibre A1-OM4 ne doit pas dépasser 0,11 ps/m pour n'importe quel intervalle de décalage radial donné dans le Tableau D.5 lorsque la mesure est réalisée selon l'IEC 60793-1-49.

Tableau D.5 – Masques d'intervalles de DMD pour les fibres A1-OM4

Numéro d'intervalle	R_{INNER} μm	R_{OUTER} μm
1	7	13
2	9	15
3	11	17
4	13	19

D.4 Exigences relatives au EMB_c pour les fibres A1-OM4

D.4.1 Généralités

Les fibres A1-OM4 choisies à l'aide de la méthode de l' EMB_c doivent satisfaire aux exigences de D.4.2. Les informations liées sont données dans le texte d'introduction du Tableau D.3 en D.2.2.

D.4.2 Largeur de bande effective calculée

Les formes d'impulsion optique de DMD peuvent être pondérées par un ensemble de distributions d'injection pour déterminer un ensemble correspondant de valeurs d' EMB_c . La valeur minimale de l' EMB_c (minEMB_c) dans cet ensemble doit satisfaire à l'exigence de l'Equation (D.2):

$$\text{minEMB}_c \geq 4 \text{ 160 MHz} \cdot \text{km} \quad (\text{D.2})$$

où

minEMB_c est déterminée à partir de la fonction de transfert complexe décrite dans l'IEC 60793-1-49, au moyen des pondérations définies au Tableau D.3.

D.5 Exigences relatives à la largeur de bande modale des fibres A1-OM5

D.5.1 Généralités

Les fibres A1-OM5 doivent satisfaire aux exigences de D.5.2 et D.6. Les informations liées sont données dans le texte d'introduction du Tableau D.3 en D.2.2.

D.5.2 Largeur de bande modale effective calculée

Les formes d'impulsion optique de DMD doivent être pondérées par un ensemble de distributions d'injection pour déterminer un ensemble correspondant de valeurs d' EMB_c . La valeur minimale de l' EMB_c ($minEMB_c$) dans cet ensemble doit satisfaire à l'exigence des Equations (D.3) et (D.4):

$$minEMB_c \geq 4\ 160\ \text{MHz}\cdot\text{km à } 850\ \text{nm} \quad (\text{D.3})$$

$$minEMB_c \geq 2\ 190\ \text{MHz}\cdot\text{km à } 953\ \text{nm} \quad (\text{D.4})$$

où

$minEMB_c$ est déterminée à partir de la fonction de transfert complexe décrite dans l'IEC 60793-1-49, au moyen des pondérations définies au Tableau D.3.

D.6 Largeur de bande modale saturée calculée A1-OM2, A1-OM3, A1-OM4 et A1-OM5

Les formes d'impulsion optique de DMD pour les fibres A1-OM2, A1-OM3 et A1-OM4 doivent être pondérées par la distribution d'injection pour déterminer une valeur d' OMB_c correspondante à 850 nm. Pour les fibres A1-OM5, la distribution d'injection du Tableau D.6 doit être utilisée pour déterminer une valeur correspondante en 850 nm et 953 nm. Les pondérations du Tableau D.6 sont les mêmes que celles de l'IEC 60793-1-41 pour la méthode C.

Tableau D.6 – Pondération de DMD pour OMB_c

Position radiale, r μm	Pondération d'OFL
0	0
1	0,000 73
2	0,001 57
3	0,002 53
4	0,003 62
5	0,004 87
6	0,006 31
7	0,007 95
8	0,009 83
9	0,011 98
10	0,014 43
11	0,017 25
12	0,020 46
13	0,024 14
14	0,028 36
15	0,033 17
16	0,038 69
17	0,045 00
18	0,052 21
19	0,060 47
20	0,069 92
21	0,080 73
22	0,093 10
23	0,107 25
24	0,123 45
25	0,141 97

Annexe E (informative)

Considérations sur les systèmes, la largeur de bande modale et les émetteurs

E.1 Contexte

Lorsqu'une fibre multimodale est utilisée avec des émetteurs lasers, la largeur de bande de la combinaison peut varier fortement en fonction des détails de la structure des modes des lasers, des retards de mode de la fibre et du couplage entre le laser et les modes de la fibre. Plus précisément, la largeur de bande modale est la largeur de bande à -3 dB de la réponse impulsionnelle produite à partir des retards de mode d'une fibre particulière pondérée par la distribution de puissance de mode du laser injecté dans la fibre. Pour générer une estimation fiable de la largeur de bande lorsque la réponse impulsionnelle n'est pas gaussienne, la largeur de bande à 3 dB est remplacée par une extrapolation de la largeur de bande à 1,5 dB.

La connaissance de la structure des modes d'une fibre, telle qu'elle est déterminée par l'IEC 60793-1-49, permet de placer une limite plus faible sur la plage des largeurs de bandes rencontrée lors de l'utilisation d'une fibre donnée avec plusieurs émetteurs lasers. La technique de la valeur minimale de l'EMB_c (minEMB_c) présentée à l'Article E.3 sélectionne la fibre avec 10 lasers simulés qui explorent la distribution de puissance du mode observé; l'ensemble de 10 lasers simulés est considéré prudent par rapport aux lasers disponibles dans le commerce, mais plus restreint que l'ensemble de lasers théoriques du modèle TIA original représenté à la Figure E.2 [13]. Les lasers choisis présentent différentes caractéristiques de distribution de puissance du mode couplé: pour certains la puissance est davantage concentrée dans les modes d'ordres faibles, pour d'autres elle est davantage concentrée dans les modes d'ordres élevés, et pour d'autres encore elle est davantage concentrée dans les modes d'ordres faibles et élevés.

En utilisant des lasers qui assurent un couplage essentiellement dans les modes dont les retards sont bien délimités, la largeur de bande modale minimale peut être assurée. L'IEC 61280-1-4 peut être utilisée pour mesurer la condition d'injection des émetteurs lasers dans la fibre multimodale [15]. Des spécifications de condition d'injection choisies de manière adéquate peuvent restreindre les modes de la fibre utilisée par les émetteurs principalement à ceux dont les retards différentiels de propagation sont limités de manière appropriée.

Un produit longueur-largeur de bande modale minimale peut être assuré en combinant un émetteur satisfaisant aux spécifications de l'Article E.4 ci-dessous avec une fibre de 50 µm satisfaisant aux spécifications de l'Annexe D.

E.2 Considérations sur les systèmes

E.2.1 Fibres A1-OM3 et A1-OM4

Se reporter à l'Article E.3.

E.2.2 Fibre A1-OM5

Des spécifications de fibres pour des systèmes à haut débit de données ont été développées en utilisant des modèles de liaison [16]. Les modèles 10 Gb/s et 25 Gb/s sont construits sur le modèle de liaison à 1 Gb/s [16] qui inclut deux exigences: la marge ou pénalité de puissance est positive et l'interférence intersymbole (ISI) est inférieure à 3,6 dB.

Les spécifications de fibres A1-OM5 ont été développées à l'aide de modèles de liaison sous Excel pour le modèle de liaison IEEE 100GBASE-SR4 (le modèle "Example MMF Link Model.xls"[17]) et pour le modèle de liaison Fibre Channel 32GFC (le modèle "T11-12-376v0.xlsx" [18]). Les modèles de liaison étaient utilisés pour déterminer les exigences relatives à la largeur de bande sur la plage de longueurs d'onde de 840 nm à 953 nm. Les longueurs d'onde des modèles ont subi des variations à l'intérieur de cette plage. Dans les modèles de liaison, les paramètres de dispersion U_0 (longueur d'onde de dispersion nulle) et S_0 (pente de dispersion nulle) ont été ajustés aux nouvelles valeurs de 1 328 nm et 0,093 477 ps/nm²km basées sur des résultats interlaboratoires, et l'affaiblissement des fibres câblées est passé de 3,5 dB/km à 3,0 dB/km. Les modèles de liaison disposent d'une marge limitée au-delà de la plage de longueurs d'onde de 840 nm à 953 nm (contrairement au modèle IEEE P802.3ae 10GBASE-S [19] utilisé pour les fibres OM3, et qui est limité par une interférence intersymbole inférieure ou égale à 3,6 dB), et l'EMB dans le modèle de liaison a été ajusté pour atteindre une marge de 0,000 dB. Pour établir la spécification sur la largeur de bande modale effective, il a été convenu d'utiliser le modèle de liaison 32GFC avec une marge nulle parce que les exigences sur la largeur de bande modale effective sont supérieures à celles du modèle 100GBASE-SR4 (c'est-à-dire que les exigences sur la largeur de bande ont été choisies pour correspondre aux exigences des deux modèles de liaison des systèmes). Les spécifications normatives sur la largeur de bande modale effective sont 4 700 MHz·km à 850 nm et 2 470 MHz·km à 953 nm. Ces points sont représentés par des cercles dans la Figure E.1. Lorsque ces exigences sont satisfaites, la largeur de bande modale effective la plus défavorable attendue satisfait aux exigences du système, comme cela est expliqué à l'Article E.3.

E.3 Largeur de bande modale effective (EMB)

Au cours du développement de la sous-catégorie de fibre A1-OM3, une simulation de Monte-Carlo détaillée dans le domaine temporel a été utilisée pour évaluer la capacité de sélection des performances de différents projets de masque de DMD et de pondération DMD pour les émetteurs satisfaisant aux spécifications de l'Article E.4 [3] à [14]. Les propositions ont été jugées sur leur capacité à accepter des fibres ne faisant pas dépasser une valeur spécifique à l'interférence intersymbole (ISI) excédant une valeur spécifique, le plus souvent de 0,5 % de la vitesse [13]. La valeur ISI spécifique a été établie avec la feuille de calcul de budget de liaison IEEE 802.3ae [19] pour un canal qui prenait en compte les effets du temps de montée de l'émetteur, de la largeur de bande du récepteur et une fibre avec une largeur de bande modale de 2 000 MHz·km. Ainsi, par l'utilisation d'une simulation de Monte-Carlo, les fibres satisfaisant aux exigences de la sous-catégorie A1-OM3 donnent une EMB minimale de 2 000 MHz·km.

La valeur minimale de l'EMB est alignée sur les hypothèses de la feuille de calcul du budget de liaison de l'IEEE 802.3ae. Il est particulièrement important de noter que, dans la feuille de calcul, la dégradation de l'ISI est modélisée selon les hypothèses de forme d'onde gaussiennes appliquées aux valeurs de sortie de l'émetteur et de la fibre. D'après les résultats de la simulation de Monte-Carlo pour les fibres satisfaisant aux exigences, la relation de calcul entre l'ISI et la largeur de bande modale minimale de la fibre est pessimiste. Par conséquent, le calcul de l'EMB effectué à partir du DMD pondéré a intégré un facteur de 1,13 pour aligner les exigences de fibre développées avec la simulation de Monte-Carlo dans le domaine temporel sur le modèle de la feuille de calcul, comme représenté dans l'Equation (E.1).

$$EMB = 1,13 \times \min EMB_c \quad (E.1)$$

L'EMB obtenue par l'Equation (E.1) s'applique également aux modèles de liaison Fibre Channel. Si d'autres modèles sont utilisés, une EMB différente peut être appropriée.

Les fibres qui satisfont aux exigences des Articles D.3 et D.4 (à savoir les fibres A1-OM4) offrent une largeur de bande modale minimale à 850 nm qui est 2,35 fois plus élevée que la largeur de bande modale minimale des fibres qui satisfont aux exigences des Articles D.1 et D.2 (à savoir les fibres A1-OM3). Ainsi, leur EMB minimale est aussi 2,35 fois supérieure avec

les mêmes hypothèses de feuille de calcul de budget de liaison, comme indiqué par l'Equation (E.2).

$$\text{EMB} \geq 2,35 \times 2\,000 \text{ MHz}\cdot\text{km} \geq 4\,700 \text{ MHz}\cdot\text{km} \quad (\text{E.2})$$

Les études de performances des systèmes avec les fibres et sources lasers réelles confirment cette relation [20] à [22]. Des applications ont émergé et utilisent plusieurs longueurs d'onde au voisinage de 850 nm à 950 nm. Pour prendre en charge ces applications, une recommandation caractérisant l'EMB minimale pour A1-OM3, A1-OM4 et A1-OM5 est fournie sous la forme des Equations (E.3) à (E.9) et des Figures E.1 à E.3, il convient que ces équations ne soient pas extrapolées sans considération.

La population des fibres de sous-catégorie A1-OM3 offre généralement une EMB minimale estimée satisfaisant aux Equations (E.3) et (E.4) qui sont les équations de deux courbes de (a) 840 nm à 850 nm et (b) 850 nm à 953 nm comme représentées à la Figure E.1. L'unité de l'EMB dans les deux équations est MHz·km.

Pour $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:


$$\text{EMB} \geq 1\,826 + (2\,000 - 1\,826) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.3})$$

Pour $850 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 2\,000 \times (1,001\,0 - 0,980\,9x + 0,807\,3x^2 - 0,430\,4x^3 + 0,119\,4x^4) \quad (\text{E.4})$$

où

$$x = (\lambda_c - 850) / (953 - 850)$$



IEC

Figure E.1 – EMB large bande minimale estimée en fonction de la longueur d'onde pour A1-OM3

La population des fibres de sous-catégorie A1-OM4 offre généralement une EMB minimale estimée satisfaisant aux Equations (E.5) et (E.6) qui sont les équations de deux courbes de (a) 840 nm à 850 nm et (b) 850 nm à 953 nm dans la Figure E.2. L'unité de l'EMB dans les deux équations est MHz.km.

Pour $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:

$$\text{EMB} \geq 3\,840 + (4\,700 - 3\,840) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.5})$$

Pour $850 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 4\,700 \times (1,000\,2 - 2,154\,9x + 3,270\,0x^2 - 2,732\,8x^3 + 0,928\,0x^4) \quad (\text{E.6})$$

où

$$x = (\lambda_c - 850) / (953 - 850)$$




Figure E.2 – EMB large bande minimale estimée en fonction de la longueur d'onde pour A1-OM4

Les fibres qui satisfont aux exigences de l'Article D.5 (à savoir les fibres A1-OM5) offrent généralement une EMB estimée satisfaisant aux Equations (E.7), (E.8) et (E.9) qui sont les équations de trois segments de droite de (a) 840 nm à 850 nm, (b) 850 nm à 930 nm, et (c) 930 nm à 953 nm dans la Figure E.3. L'unité de l'EMB dans les trois équations est MHz.km.

Pour $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:

$$\text{EMB} \geq 3\,840 + (4\,700 - 3\,840) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.7})$$

Pour $850 \text{ nm} \leq \lambda_c \leq 930 \text{ nm}$:

$$\text{EMB} \geq 4\,700 + (2\,565 - 4\,700) \times (\lambda_c - 850) / (930 - 850) \quad (\text{E.8})$$

Pour $930 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 2\,565 + (2\,470 - 2\,565) \times (\lambda_c - 930) / (953 - 930) \quad (\text{E.9})$$

Les Equations (E.7), (E.8) et (E.9) sont les équations de trois segments de droite entre l'EMB minimale indiquée par le modèle de liaison 32GFC à 840 nm et les deux EMB minimales aux longueurs d'onde nominales de mesure 850 nm et 953 nm. Les Equations (E.7), (E.8) et (E.9) sont tracées dans la Figure E.3 avec des valeurs d'EMB de fermeture du modèle de liaison 32GFC. Les segments de droite de 840 nm à 953 nm ont été déterminés soigneusement pour fournir des recommandations d'EMB minimale sur la plage de longueurs d'onde sans introduire de manière intentionnelle de dépendance par rapport à une conception spéciale de fibres.




Figure E.3 – EMB large bande minimale estimée en fonction de la longueur d'onde pour A1-OM5

E.4 Exigences relatives au flux inscrit (EF) et à la longueur d'onde centrale pour l'émetteur

E.4.1 Flux inscrit

Les limites radiales de DMD des masques intérieurs, extérieurs et d'intervalles spécifiés aux Articles D.1 et D.3, et les pondérations de DMD spécifiées aux Articles D.2, D.4 et D.5, ont été établies en relation avec la plage limitée particulière des conditions d'injection laser spécifiées dans les Equations (E.10) et (E.11). La largeur de bande modale prévue pour les conditions d'injection à l'extérieur de cette plage n'a pas été déterminée, mais elle sera inférieure à celle prévue pour les conditions d'injection dans cette plage.

Il convient que la distribution de puissance de la condition d'injection de l'émetteur satisfasse aux exigences des Equations (E.10) et (E.11) lorsque les mesures sont réalisées conformément à l'IEC 61280-1-4 [15], l'émetteur étant couplé à une fibre de 50 µm satisfaisant aux spécifications du présent document.

$$\text{EF à rayon de } 4,5 \mu\text{m} \leq 30 \% \quad (\text{E.10})$$

$$\text{EF à rayon de } 19 \mu\text{m} \geq 86 \% \quad (\text{E.11})$$

Les positions approchées des pondérations de DMD spécifiées au Tableau D.3 sont représentées à la Figure E.4 ci-dessous, par rapport aux limites données dans les Equations (E.10) et (E.11) [2].




Figure E.4 – Position approchée de pondérations de DMD par rapport aux limites de flux inscrit des Equations (E.10) et (E.11)

Plusieurs normes d'application publiées satisfont aux exigences de E.4.1 et E.4.2 [23] à [26].

E.4.2 Longueur d'onde centrale pour les fibres A1-OM3 et A1-OM4

Dans la mesure où les retards de mode de la fibre varient avec la longueur d'onde, il convient que la longueur d'onde centrale de l'émetteur soit maintenue à une valeur proche de la longueur d'onde de mesure de DMD nominale de 850 nm pour obtenir la performance de largeur de bande modale la plus élevée sur la population des fibres concernées. Il peut être approprié de réduire la largeur de bande modale lorsque l'émetteur ne fonctionne pas à 850 nm [8]. Le document de la référence [27] donne une représentation de l'affaiblissement de largeur de bande pour les fibres de largeur de bande similaire au modèle de fibre A1-OM4.

Il convient que la longueur d'onde centrale de l'émetteur laser (λ_c) satisfasse aux exigences de l'Equation (E.12) lorsque les essais sont réalisés selon l'IEC 61280-1-3 [28].

$$840 \text{ nm} \leq \lambda_c \leq 860 \text{ nm} \quad (\text{E.12})$$

E.4.3 Longueur d'onde centrale pour une fibre A1-OM5

Dans la mesure où les retards de mode de la fibre varient avec la longueur d'onde, les meilleures performances de largeur de bande modale sont atteintes lorsque la longueur d'onde centrale de l'émetteur laser est entre les longueurs d'onde de mesure de DMD. Lorsque la longueur d'onde centrale de l'émetteur laser sort de cette plage, la largeur de bande modale peut se dégrader. Les Equations (E.7), (E.8) et (E.9) donnent des conseils sur les valeurs de largeur de bande entre les longueurs d'onde de mesure de DMD.

Il convient que la longueur d'onde centrale de l'émetteur laser (λ_c) satisfasse aux exigences de l'Equation (E.13) lorsque les essais sont réalisés selon l'IEC 61280-1-3 [28].

$$840 \text{ nm} \leq \lambda_c \leq 953 \text{ nm} \quad (\text{E.13})$$

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

Annexe F (informative)

Explication de la nomenclature des largeurs de bande

Le Tableau F.1 fournit des explications sur les paramètres de largeur de bande qui possèdent des noms et des abréviations similaires.

Tableau F.1 – Explication de la nomenclature des largeurs de bande

Nom du paramètre et abréviation	Description du paramètre
Largeur de bande modale effective calculée (EMB_c)	La largeur de bande modale calculée résultant d'une pondération particulière d'un DMD particulier.
Largeur de bande modale effective calculée minimale (EMB_c minimale ou $minEMB_c$)	La largeur de bande modale calculée minimale résultant d'un ensemble particulier de pondérations d'un DMD particulier.
Largeur de bande modale effective (EMB)	La largeur de bande modale qui résulte de la multiplication de la largeur de bande modale effective calculée minimale par 1,13 pour arriver à une valeur alignée avec les hypothèses du modèle de liaison IEEE 802.3ae utilisé pour les émetteurs conformes à l'Article E.2.
Largeur de bande modale saturée calculée (OMB_c)	La largeur de bande modale calculée résultant d'une pondération d'un DMD particulier pour simuler une condition d'injection saturée.

Annexe G (informative)

Indications préliminaires pour les éléments qui nécessitent une étude supplémentaire

G.1 Largeur de bande modale effective (EMB) à 1 300 nm

Les propriétés de dispersion chromatique permettent de transformer le DMD mesuré à une longueur d'onde en un DMD à une autre longueur d'onde. Ainsi, le DMD à 850 nm peut être utilisé pour prévoir le produit longueur-largeur de bande modale effective minimale à 1 300 nm. Une analyse préliminaire d'ingénierie indique que les fibres qui satisfont aux exigences de l'Annexe D pour une EMB de $\geq 2\,000$ MHz·km à 850 nm donnent également une EMB de ≥ 500 MHz·km à 1 300 nm.

Certains émetteurs à laser à 1 300 nm sont définis pour fonctionner à la fois avec des fibres multimodales et des fibres unimodales. Pour mieux assurer que les fibres multimodales, avec les performances de largeur de bande spécifiées uniquement sur la base des conditions d'injection saturée, délivrent au moins leur produit longueur-largeur de bande saturée minimale pour les émetteurs à 1 300 nm conçus pour injecter dans une fibre unimodale (par exemple 1000BASE-LX), l'IEEE Std 802.3TM spécifie l'utilisation des cordons de connexion de conditionnement de mode à injection à décalage lorsque de tels émetteurs sont connectés à ce type de fibre multimodale.

L'injection décalée est mise en œuvre en connectant une fibre unimodale à une fibre multimodale à l'intérieur d'un cordon de connexion en utilisant une plage spécifiée de décalage radial unimodal à multimodal. En injectant de manière très décalée du centre de la fibre unimodale dans la fibre multimodale, de nombreux modes sont excités ce qui produit une distribution de puissance de mode plus proche de celle d'une injection saturée que de celle de l'injection native qui, normalement, n'excite fortement que les modes d'ordres faibles.

Etant donné que les mesures de largeur de bande à injection saturée sont fortement dominées par le comportement des modes d'ordres élevés, elles ne sont pas sensibles au comportement des modes d'ordres faibles. C'est la raison pour laquelle, si l'on évite une forte excitation des modes d'ordres faibles, le cordon de connexion à injection décalée élimine la dépendance par rapport au comportement de ces modes à caractéristiques pauvres, et améliore la corrélation entre la largeur de bande minimale du système et la mesure du produit longueur-largeur de bande en injection saturée.

Cependant, la procédure d'essai du DMD mesurant le comportement de mode d'ordre faible, elle est capable de circonscrire la limite inférieure du produit largeur de bande-distance pour les injections natives de ces émetteurs à 1 300 nm. Les fibres satisfaisant aux spécifications A1-OM3 et A1-OM4 sont optimisées pour la largeur de bande de crête à 850 nm et possèdent un DMD de mode d'ordre faible limité de manière spécifique.

Le fait de fonctionner à des longueurs d'onde différentes de la longueur d'onde de crête introduit une augmentation systématique du DMD. L'augmentation la plus importante du DMD intervient pour les modes d'ordres les plus élevés. Ainsi, la largeur de bande saturée, qui est dominée par le DMD de mode d'ordre élevé, est un indicateur prudent de la largeur de bande modale effective la plus faible pour les injections à 1 300 nm natives qui concentrent la puissance dans les modes d'ordres faibles. C'est la raison pour laquelle il est prévu que les fibres A1-OM3 et A1-OM4 fournissent une EMB au moins aussi élevée que leur produit longueur-largeur de bande saturée minimale de 500 MHz·km à 1 300 nm, sans l'utilisation de cordons de connexion de conditionnement de mode.

G.2 Graduation de l'EMB avec le DMD

Des produits longueur-largeur de bande modale effective différents peuvent être déduits des gabarits et des masques d'intervalle définis aux Articles D.1 et D.3 simplement en graduant l'EMB de manière inversement proportionnelle à la largeur temporelle du DMD, si les trois conditions suivantes sont remplies:

- 1) la fibre est utilisée avec des émetteurs satisfaisant aux spécifications de E.4.1;
- 2) les limites de décalage radial des gabarits ne sont pas modifiées; et
- 3) les exigences du produit longueur-largeur de bande modale saturée sont graduées de manière directement proportionnelle à l'EMB.

La capacité de graduation est justifiée par les relations suivantes. Selon la théorie des guides d'ondes, la distribution de puissance de mode de l'émetteur est en correspondance directe avec les étendues radiales des masques de DMD intérieur et extérieur. La plage de longueurs d'onde de fonctionnement oblige le fonctionnement à forte proximité de la longueur d'onde de mesure nominale de DMD pour réduire les variations de largeur de bande modale dues à la longueur d'onde. La distribution de puissance de mode et l'étendue radiale des masques de DMD étant fixées, et la plage de longueurs d'onde de fonctionnement n'étant pas modifiée, la graduation est supportée par la proportionnalité inverse entre la largeur d'impulsion en valeur efficace et la largeur de bande [29] [30]. Dans ce cas, la largeur d'impulsion en valeur efficace est égale à la largeur temporelle du DMD. La graduation de la largeur de bande saturée directement proportionnelle à l'EMB souhaitée maintient la proportionnalité établie entre le DMD et la largeur de bande saturée.

Par exemple, un produit longueur-largeur de bande modale effective à 850 nm $\geq 1\,000$ MHz·km (moitié de 2 000 MHz·km) peut être utilisé avec des fibres satisfaisant à l'un des six gabarits de DMD de l'Article D.1, chaque modèle ayant le double de la largeur temporelle de DMD à la fois pour le masque intérieur et pour le masque extérieur, et un produit longueur-largeur de bande saturée de ≥ 750 MHz·km.

Annexe H (informative)

Applications et catégories de câbles supportées par les fibres A1

Le Tableau H.1 présente certaines applications normalisées au niveau international, ainsi que d'autres applications recommandées, qui sont supportées par les fibres A1. Il ne s'agit pas d'une liste exhaustive et beaucoup d'autres applications non spécifiquement énumérées peuvent être aussi supportées par ces mêmes fibres.

Tableau H.1 – Exemples d'applications normalisées prises en charge par les fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5 et dans certains cas par les fibres A1-OM1

Application	Source	Nom
1GFC	ISO/IEC 14165-115	1-Gigabit Fibre Channel
2GFC	ISO/IEC 14165-115	2-Gigabit Fibre Channel
4GFC	ANSI/INCITS 479	4-Gigabit Fibre Channel
8GFC	ANSI/INCITS 479	8-Gigabit Fibre Channel
10GFC	ISO/IEC 14165-116	10-Gigabit Fibre Channel
16GFC	ANSI/INCITS 479	16-Gigabit Fibre Channel
32GFC	ANSI/INCITS 512	32-Gigabit Fibre Channel
1000BASE-SX	ISO/IEC/IEEE 8802-3	Gigabit Ethernet
1000BASE-LX	ISO/IEC/IEEE 8802-3	Gigabit Ethernet
10GBASE-S	ISO/IEC/IEEE 8802-3	10-Gigabit Ethernet
25GBASE-SR	ISO/IEC/IEEE 8802-3	25-Gigabit Ethernet
40GBASE-SR4	ISO/IEC/IEEE 8802-3	40-Gigabit Ethernet
100GBASE-SR10	ISO/IEC/IEEE 8802-3	100-Gigabit Ethernet
100GBASE-SR4	ISO/IEC/IEEE 8802-3	100-Gigabit Ethernet

Annexe I (informative)

Applications Ethernet 1 gigabit, 10 gigabits, 25 gigabits, 40 gigabits et 100 gigabits

L'Annexe I est destinée à donner un résumé des exigences relatives aux fibres de catégories A1-OM2, A1-OM3, A1-OM4, A1-OM5 et A1-OM1, ainsi que des capacités de transmission correspondantes pour les normes d'application Ethernet 1 gigabit, 10 gigabits, 25 gigabits, 40 gigabits et 100 gigabits développées dans l'IEEE 802.3. Toutes les applications Ethernet à 1 Gb/s ou plus sont considérées comme des applications "d'injection laser".

Le Tableau I.1 donne un aperçu des exigences et des capacités de l'Ethernet 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s et 100 Gb/s. Les lignes du Tableau I.1 sont regroupées en sous-catégories et modèles de fibres par débit binaire croissant. Pour chaque poste, il existe une indication de la longueur de la liaison de l'application et des exigences concernant les caractéristiques d'injection de l'émetteur. Les exigences des caractéristiques d'injection de l'émetteur sont des trois types décrits ci-dessous.

- Cordon de connexion à conditionnement de mode à injection à décalage pour fonctionnement à 1 300 nm, comme défini dans l'IEEE 802.3.
- Rapport de puissance couplé (CPR) > 9 dB et soin d'éviter l'injection saturée radiale (ROFL) pour le fonctionnement à 1 Gb/s à 850 nm sur les fibres caractérisées seulement par la largeur de bande d'injection saturée (OFL). Le rapport de puissance couplé est défini dans l'IEC 61280-4-1:2009; l'injection saturée radiale est définie dans l'IEEE 802.3.
- Exigences de flux inscrit (EF) pour fonctionnement en 10 Gb/s, 25 Gb/s, 40 Gb/s et 100 Gb/s à 850 nm sur modèles de fibres A1-OM3, A1-OM4 et A1-OM5, avec largeur de bande modale effective assurée par la mesure de DMD. Les exigences sur le flux inscrit sont les suivantes: EF à un rayon de $4,5 \mu\text{m} \leq 30 \%$, et EF à un rayon de $19,0 \mu\text{m} \geq 86 \%$. Les mesures du flux inscrit sont présentées dans l'IEC 61280-1-4.

Tableau I.1 – Aperçu des exigences et des capacités de l'Ethernet 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s et 100 Gb/s

Sous-catégorie ou modèle de fibre	Débit binaire Gb/s	Longueur d'onde nominale							
		850 nm				1 300 nm			
		Largeur de bande modale minimale pour condition d'injection de mesure indiquée MHz·km	Largeur de bande modale minimale effective pour émetteurs satisfaisant l'exigence d'injection MHz·km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur	Longueur de liaison m	Largeur de bande modale minimale effective pour émetteurs satisfaisant l'exigence d'injection MHz·km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur
A1-OM1	1	160 pour OFL	n.s.	1000BASE-SX	CPR > 9 dB, éviter ROFL	220	n.s.	1000BASE-LX	Cordon de connexion à injection à décalage
A1-OM1	1	200 pour OFL	n.s.	1000BASE-SX	CPR > 9 dB, éviter ROFL	275	n.s.	1000BASE-LX	Cordon de connexion à injection à décalage
A1-OM1	10	160 pour OFL	n.s.	10GBASE-S	EF à un rayon de 4,5 µm ≤ 30 %, EF à un rayon de 19,0 µm ≥ 86 %	26	n.s.	10GBASE-LX4	Cordon de connexion à injection à décalage
A1-OM1	10	200 pour OFL	n.s.	10GBASE-S	EF à un rayon de 4,5 mm ≤ 30 %, EF à un rayon de 19,0 µm ≥ 86 %	33	n.s.	10GBASE-LX4	Cordon de connexion à injection à décalage

Longueur d'onde nominale											
Sous-catégorie ou modèle de fibre	Débit binaire Gb/s	850 nm						1 300 nm			
		Largeur de bande modale minimale pour condition d'injection de mesure indiquée MHz.km	Largeur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur	Longueur de liaison m	Largeur de bande modale minimale pour condition d'injection de mesure indiquée MHz.km	Largeur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur	Longueur de liaison m
A1-OM1	10	160 pour OFL	n.s.	n.s.	n.s.	n.s.	500 pour OFL	n.s.	10GBASE-LRM	Cordon de connexion à injection à décalage ou EF à un rayon de $5\text{ }\mu\text{m} \geq 30\%$, EF à un rayon de $11\text{ }\mu\text{m} \geq 81\%$	220
A1-OM1	10	200 pour OFL	n.s.	n.s.	n.s.	n.s.	500 pour OFL	n.s.	10GBASE-LRM	Cordon de connexion à injection à décalage ou EF à un rayon de $5\text{ }\mu\text{m} \geq 30\%$, EF à un rayon de $11\text{ }\mu\text{m} \geq 81\%$	220
A1-OM2	1	400 pour OFL	n.s.	1000BASE-SX	CPR > 9 dB, éviter ROFL	500	400 pour OFL	n.s.	1000BASE-LX	Cordon de connexion à injection à décalage	550
A1-OM2	1	500 pour OFL	n.s.	1000BASE-SX	CPR > 9 dB, éviter ROFL	550	500 pour OFL	n.s.	1000BASE-LX	Cordon de connexion à injection à décalage	550

Sous-catégorie ou modèle de fibre	Débit binaire Gb/s	Longueur d'onde nominale							
		850 nm				1 300 nm			
		Largueur de bande modale minimale pour condition d'injection de mesure indiquée MHz.km	Largueur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur	Longueur de liaison m	Largueur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur
A1-OM2	10	400 pour OFL	n.s.	10GBASE-S	EF à un rayon de 4,5 mm μ 30 %, EF à un rayon de 19,0 μ m $\leq$ 86 %	66	400 pour OFL	10GBASE-LX4	Cordon de connexion à injection à décalage
A1-OM2	10	500 pour OFL	n.s.	10GBASE-S	EF à un rayon de 4,5 μ m $\leq$ 30 %, EF à un rayon de 19,0 μ m $\leq$ 86 %	82	500 pour OFL	10GBASE-LX4	Cordon de connexion à injection à décalage
A1-OM2	10	400 pour OFL	n.s.	n.s.	n.s.	n.s.	500 pour OFL	10GBASE-LRM	Cordon de connexion à injection à décalage ou EF à un rayon de 5 μ m $\geq$ 30 %, EF à un rayon de 11 μ m $\geq$ 81 %

Sous-catégorie ou modèle de fibre	Débit binaire Gb/s	Longueur d'onde nominale									
		850 nm				1 300 nm					
		Largeur de bande modale minimale pour condition d'injection de mesure indiquée MHz.km	Largeur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur	Longueur de liaison m	Largeur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur	Longueur de liaison m	
A1-OM2	10	500 pour OFL	n.s.	n.s.	n.s.	n.s.	500 pour OFL	n.s.	10GBASE-LRM	Cordon de connexion à injection à décalage ou EF à un rayon de $5\text{ }\mu\text{m} \geq 30\%$, EF à un rayon de $11\text{ }\mu\text{m} \geq 81\%$	220
A1-OM3	10	1 500 pour OFL	2 000	10GBASE-S	EF à un rayon de $4,5\text{ }\mu\text{m} \leq 30\%$, EF à un rayon de $19,0\text{ }\mu\text{m} \geq 86\%$	300	500 pour OFL	n.s.	10GBASE-LX4	Cordon de connexion à injection à décalage	300
A1-OM3	10	1 500 pour OFL	2 000	n.s.	n.s.	n.s.	500 pour OFL	n.s.	10GBASE-LRM	EF à un rayon de $5\text{ }\mu\text{m} \geq 30\%$, EF à un rayon de $11\text{ }\mu\text{m} \geq 81\%$	220

Sous-catégorie ou modèle de fibre	Débit binaire Gb/s	Longueur d'onde nominale							
		850 nm				1 300 nm			
		Largeur de bande modale minimale pour condition d'injection de mesure indiquée MHz.km	Largeur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur	Longueur de liaison m	Largeur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur
A1-OM3	25	1 500 pour OFL	2 000	25GBASE-SR	EF à un rayon de $4,5 \mu\text{m} \leq 30 \%$, EF à un rayon de $19,0 \mu\text{m} \geq 86 \%$.	70	n.s.	n.s.	n.s.
A1-OM3	40	1 500 pour OFL	2 000	40GBASE-SR4	EF à un rayon de $4,5 \mu\text{m} \leq 30 \%$, EF à un rayon de $19,0 \mu\text{m} \geq 86 \%$.	100	n.s.	n.s.	n.s.
A1-OM3	100	1 500 pour OFL	2 000	100GBASE-SR10	EF à un rayon de $4,5 \mu\text{m} \leq 30 \%$, EF à un rayon de $19,0 \mu\text{m} \geq 86 \%$.	100	n.s.	n.s.	n.s.

Sous-catégorie ou modèle de fibre	Débit binaire Gb/s	Longueur d'onde nominale						
		850 nm			1 300 nm			
		Largeur de bande modale minimale pour condition d'injection de mesure indiquée MHz.km	Largeur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a	Exigence d'injection de l'émetteur	Longueur de liaison m	Largeur de bande modale minimale effective pour émetteurs satisfaisant à l'exigence d'injection MHz.km	IEEE 802.3 PMD ^a
A1-OM3	100	1 500 pour OFL	2 000	100GBASE-SR4	EF à un rayon de $4,5 \mu\text{m} \leq 30 \%$, EF à un rayon de $19,0 \mu\text{m} \geq 86 \%$.	70	n.s.	n.s.
A1-OM4 ou A1-OM5	10	3 500 pour OFL	4 700	10BASE-S	EF à un rayon de $4,5 \mu\text{m} \leq 30 \%$, EF à un rayon de $19,0 \mu\text{m} \geq 86 \%$.	400	n.s.	n.s.
A1-OM4 ou A1-OM5	25	3 500 pour OFL	4 700	25GBASE-SR	EF à un rayon de $4,5 \mu\text{m} \leq 30 \%$, EF à un rayon de $19,0 \mu\text{m} \geq 86 \%$.	100	n.s.	n.s.
A1-OM4 ou A1-OM5	40	3 500 pour OFL	4 700	40GBASE-SR4	EF à un rayon de $4,5 \mu\text{m} \leq 30 \%$, EF à un rayon de $19,0 \mu\text{m} \geq 86 \%$.	150 ^b	n.s.	n.s.

22.3 pour un dispositif, comme un émetteur-récepteur, qui relie au milieu de transmission.
e avec une connexion de 1,0 dB au maximum et un affaiblissement d'épaisseur.

Bibliographie

- [1] H. Murata, Handbook of Optical Fibers and Cables, 2nd Edition. New York: Marcel Dekker Inc., 1996, Figure 22
- [2] J. Abbott, S. Bickham, P. Dainese, M. Li, "Fibers for Short-Distance Applications", Chapter 7 in Optical Fiber Telecommunications VIA. New York: Elsevier, 2013, Figure 7.3
- [3] J. Ritger, J. Abbott, "New Delay Set for TIA Modelling", White paper, June 1, 2001. Adresse: <http://www.tiaonline.org/>
- [4] J. Ritger, J. Abbott, "Fiber Delays for 10 Gb Risk Assessment", Presentation to FO2.2.1, 25 juin 2001. Adresse: <http://www.tiaonline.org/>
- [5] P. Kolesar, "Source Characteristics Development", Presentation to FO2.2.1, juin 2001. Adresse: <http://www.tiaonline.org/>
- [6] S. Golowich, J. Ritger, P. Kolesar, "Simulation of 50 μ m 10 Gb Links", Presentation to FO2.2.1, 25 juin 2001. Adresse: <http://www.tiaonline.org/>
- [7] S. Golowich, P. Kolesar, J. Ritger, G. Giaretta, "Modelling, Simulation, and Experimental Study of a 50 μ m Multimode Fiber Serial 10 Gb Link", Presentation to IEEE 802.3ae, mai 2000 [consulté 2019-01-30]. Adresse: http://grouper.ieee.org/groups/802/3/ae/public/may00/golowich_1_0500.pdf
- [8] J. Ritger, "Risk Analysis: EF limits and Wavelength Dependence", Presentation to FO2.2.1, 25 juin 2001. Adresse: <http://www.tiaonline.org/>
- [9] S. Golowich, P. Kolesar, J. Ritger, P. Pepeljugoski, "Modelling and Simulations for 10 Gb Multimode Optical Fiber Link Component Specifications", OFC 2001, paper WDD57
- [10] P. Pepeljugoski, S. Golowich, "Measurements and simulations of intersymbol interference penalty in new high speed 50 μ m multimode fiber links operating at 10 Gb/s", OFC 2001, paper WDD40
- [11] J. Ritger, "Use of Differential Mode Delay in Qualifying Multi-Mode Optical Fiber for 10 Gbps Operation", OFMC 2001
- [12] M. Hackert, "ITA FO-2.2.1 March 12, 2001 Update", mars 2001 IEEE Plenary [consulté 2019-01-30]. Adresse: http://grouper.ieee.org/groups/802/3/ae/public/mar01/hackert_1_0301.pdf
- [13] P. Pepeljugoski, M. Hackert, J. Abbott, S. Swanson, S. Golowich, J. Ritger, P. Kolesar, C. Chen et P. Pleunis, "Development of System Specification for Laser Optimized 50 μ m Multimode Fiber for Multi-gigabit Short Wavelength LANs", J. Lightwave Tech., volume 21, No. 5, p. 1256-1275, mai 2003
- [14] P. Pepeljugoski, S. Golowich, J. Ritger, P. Kolesar, A. Risteski, "Modeling and Simulation of Next-Generation Multimode Fiber Links", J. Lightwave Tech. Vol. 21, No. 5, p. 1242-1255, mai 2003.
- [15] IEC 61280-1-4, *Procédures d'essai des sous-systèmes de télécommunication à fibres optiques – Partie 1-4: Sous-systèmes généraux de télécommunication – Méthode de mesure du flux inscrit de la source lumineuse*

- [16] D. Cunningham et W. Lane, Gigabit Ethernet Networking. New York: Macmillan Technical Publishing, 1999 (Chapter 9 – The Gigabit Ethernet Optical Link Model)
- [17] IEEE 100G-SR4 Example MMF Link Model.xls, Petrilla [consulté 2019-01-30]. Adresse: <http://www.ieee802.org/3/bm/public/may13/index.html>
- [18] 32G Fibre Channel Model T11-12-376v0, Cunningham 27/09/2012 [consulté 2019-02-25]. Adresse: https://standards.incits.org/apps/group_public/document.php?document_id=105920&w_g_abbrev=t11
- [19] IEEE P802.3ae 10Gb/s Ethernet Task Force Link Budget Spreadsheet (Version 3.1.16a) [consulté 2019-01-30]. Adresse: <http://grouper.ieee.org/groups/802/3/ae/public/index.html>
- [20] C. Caspar, R. Freund, F. Achten, A. Gholami, G. Kuyt, P. Matthijsse et D. Molin "Impact of Transceiver Characteristics on the Performance of 10 GbE Links Applying OM-4 Multimode Fibers", Proceedings of the 57th IWCS Conference, p. 295-303, Novembre 2008
- [21] A. Sengupta, "Simulation of 10GbE Multimode Optical Communications Systems", Proceedings of the 57th IWCS Conference, p. 320-326, Novembre 2008
- [22] G. Oulundsen III, Y. Sun, D. Vaidya, R. Lingle, Jr., T. Irujo, D. Mazzaresse, "Important Performance Characteristics of Enhanced OM3 Fiber for 10 Gb/s Operation", Proceedings of the 57th IWCS Conference, p. 327-334, Novembre 2008
- [23] IEEE Std 802.3™-2015, *IEEE Standard for Ethernet*, Clause 52 for 10GBASE-S, Clause 86 for 40GBASE-SR4 and 100GBASE-SR10, Clause 95 for 100GBASE-SR4, Clause 112 for 25GBASE-SR²
- [24] ISO/IEC 14165-116, Information technology – *Fibre channel – Part 116: 10 Gigabit (10GFC)* (disponible en anglais seulement)
- [25] ANSI/INCITS 479-2011, Information Technology – *Fibre Channel – Physical Interface – 5 (FC-PI-5)*, for 400-SN (4GFC), 800-SN and 800-SA (8GFC), 1600-SN (16GFC)³
- [26] ANSI/INCITS 512-2015, Information Technology – *Fibre Channel – Physical Interface – 6 (FC-PI-6)*, for 3200-SN (32GFC)
- [27] OM3, OM4, OM5 Modal Bandwidth Over Wavelengths for WDM, IEEE 802.3 NGMMF Study Group, 01-2018 [consulté 2019-01-30]. Adresse: http://grouper.ieee.org/groups/802/3/NGMMF/public/Jan18/kolesar_NGMMF_01_jan18.pdf
- [28] IEC 61280-1-3, *Procédures d'essai des sous-systèmes de télécommunication à fibres optiques – Partie 1-3: Sous-systèmes généraux de télécommunication – Mesure de la longueur d'onde centrale et de la largeur spectrale*

² Cette publication a été retirée et remplacée par l'IEEE Std 802.3-2018, mais pour les besoins du présent document, elle est citée comme référence.

³ Cette publication a été retirée, mais pour les besoins du présent document, elle est citée comme référence.

- [29] R. G. Smith et S. D. Personick, Receiver design for optical communication systems. In Topics in Applied Physics, Vol. 39, *Semiconductor Devices for Optical Communications*, H. Kressel (ed.). Berlin: Springer-Verlag, 1982
- [30] Gair D. Brown, Bandwidth and rise time calculations for digital multimode fiber-optic data links. *JLT* 10, n° 5, p. 675-678, 1992 mai

Références non numérotées

IEC 60793-2-10:2017, *Fibres optiques – Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1*

IEC 60794-1-1, *Câbles à fibres optiques – Partie 1-1: Spécification générique – Généralités*

IEC TR 62048:2014, *Optical fibres – Reliability – Power law theory* (disponible en anglais seulement)

ISO/IEC 11801:2002, *Information technology – Generic cabling for customer premises* (disponible en anglais seulement)⁴

ISO/IEC 11801-1:2017, *Information technology – Generic cabling for customer premises – Part 1: General requirements* (disponible en anglais seulement)

ISO/IEC 14165-115, *Information technology – Fibre channel – Part 115: Physical interfaces (FC-PI)* (disponible en anglais seulement)

ISO/IEC/IEEE 8802-3, *Information technology – Telecommunications and information exchange between systems – Local and metropolitan area networks – Specific requirements – Part 3: Standard for Ethernet* (disponible en anglais seulement)

⁴ Cette publication a été retirée et remplacée par l'ISO/IEC 11801-1:2017 et l'ISO/IEC 11801-2:2017, mais pour les besoins du présent document, elle est citée comme référence.

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

FINAL VERSION

VERSION FINALE



Optical fibres –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

Fibres optiques –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1

CONTENTS

FOREWORD	5
1 Scope	7
2 Normative references	8
3 Terms and definitions	9
4 Abbreviated terms	10
5 Specifications	10
5.1 General	10
5.2 Dimensional requirements	10
5.3 Mechanical requirements	12
5.4 Transmission requirements	12
5.5 Environmental requirements	14
5.5.1 General	14
5.5.2 Mechanical environmental requirements (common to all fibres in category A1)	15
5.5.3 Transmission environmental requirements	16
Annex A (normative) Specifications for sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 multimode fibres	17
A.1 General	17
A.2 Dimensional requirements	17
A.3 Mechanical requirements	18
A.4 Transmission requirements	18
A.5 Environmental requirements	20
Annex B (normative) Specifications for sub-category A1-OM1 multimode fibres	21
B.1 General	21
B.2 Dimensional requirements	21
B.3 Mechanical requirements	21
B.4 Transmission requirements	22
B.5 Environmental requirements	22
Annex C (normative) Specifications for sub-category A1d multimode fibres	23
C.1 General	23
C.2 Dimensional requirements	23
C.3 Mechanical requirements	23
C.4 Transmission requirements	24
C.5 Environmental requirements	24
Annex D (normative) Fibre differential mode delay (DMD), calculated effective modal bandwidth (EMB _c) and calculated overfilled modal bandwidth (OMB _c) requirements	25
D.1 A1-OM3 fibre DMD requirements	25
D.1.1 General	25
D.1.2 DMD templates	25
D.1.3 DMD interval masks	26
D.2 A1-OM3 fibre EMB _c requirements	27
D.2.1 General	27
D.2.2 Calculated effective bandwidth	27
D.3 A1-OM4 DMD requirements	29
D.3.1 General	29

D.3.2	DMD templates	29
D.3.3	DMD interval masks	30
D.4	A1-OM4 fibre EMB _C requirements	30
D.4.1	General	30
D.4.2	Calculated effective bandwidth	30
D.5	A1-OM5 fibre modal bandwidth requirements	30
D.5.1	General	30
D.5.2	Calculated effective modal bandwidth	31
D.6	A1-OM2, A1-OM3, A1-OM4 and A1-OM5 calculated overfilled modal bandwidth	31
Annex E (informative)	System, modal bandwidth, and transmitter considerations	33
E.1	Background	33
E.2	System considerations	33
E.2.1	A1-OM3 and A1-OM4 fibres	33
E.2.2	A1-OM5 fibre	33
E.3	Effective modal bandwidth (EMB)	34
E.4	Transmitter encircled flux (EF) and centre wavelength requirements	37
E.4.1	Encircled flux	37
E.4.2	Centre wavelength for A1-OM3 and A1-OM4 fibres	38
E.4.3	Centre wavelength for A1-OM5 fibre	38
Annex F (informative)	Bandwidth nomenclature explanation	40
Annex G (informative)	Preliminary indications for items needing further study	41
G.1	Effective modal bandwidth (EMB) at 1 300 nm	41
G.2	Scaling of EMB with DMD	41
Annex H (informative)	Applications and cabling categories supported by A1 fibres	43
Annex I (informative)	1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit and 100-Gigabit Ethernet applications	44
Bibliography		50
Figure 1	– Relation between bandwidths at 850 nm and 1 300 nm	14
Figure D.1	– DMD template requirements	26
Figure E.1	– Estimated minimum wide band EMB versus wavelength for A1-OM3	35
Figure E.2	– Estimated minimum wide band EMB versus wavelength for A1-OM4	36
Figure E.3	– Estimated minimum wide band EMB versus wavelength for A1-OM5	37
Figure E.4	– Approximate position of DMD weightings relative to the EF boundaries of Equations (E.10) and (E.11)	38
Table 1	– Cross reference IEC A1 multimode fibre designations to IEC 60793-2-10:2017	8
Table 2	– Dimensional attributes and measurement methods	11
Table 3	– Dimensional requirements common to category A1 fibres	11
Table 4	– Additional dimensional attributes required in sub-category specifications	11
Table 5	– Mechanical attributes and measurement methods	12
Table 6	– Mechanical requirements common to category A1 fibres	12
Table 7	– Transmission attributes and measurement methods	13
Table 8	– Additional transmission attributes required in sub-category specifications	13
Table 9	– Environmental exposure tests	15

Table 10 – Attributes measured for environmental tests	15
Table 11 – Strip force for environmental tests	15
Table 12 – Tensile strength for environmental tests	16
Table 13 – Stress corrosion susceptibility for environmental tests	16
Table 14 – Change in attenuation for environmental tests	16
Table A.1 – Dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres	18
Table A.2 – Mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres	18
Table A.3 – Transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres	19
Table B.1 – Dimensional requirements specific to A1-OM1 fibres	21
Table B.2 – Mechanical requirements specific to A1-OM1 fibres	21
Table B.3 – Transmission requirements specific to A1-OM1 fibres	22
Table C.1 – Dimensional requirements specific to A1d fibres	23
Table C.2 – Mechanical requirements specific to A1d fibres	23
Table C.3 – Transmission requirements specific to A1d fibres	24
Table D.1 – DMD templates for A1-OM3 fibres	25
Table D.2 – DMD interval masks for A1-OM3 fibres	27
Table D.3 – DMD weightings	28
Table D.4 – DMD templates for A1-OM4 fibres	30
Table D.5 – DMD interval masks for A1-OM4 fibres	30
Table D.6 – DMD weighting for OMB _C	32
Table F.1 – Bandwidth nomenclature explanation	40
Table H.1 – Some standardised applications supported by A1-OM2, A1-OM3, A1-OM4, A1-OM5 fibres and in some cases A1-OM1 fibres	43
Table I.1 – Summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities	45

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 60793-2-10 edition 7.1 contains the seventh edition (2019-05) [documents 86A/1932/FDIS and 86A/1939/RVD] and its amendment 1 (2022-01) [documents 86A/2121/CDV and 86A/2140/RVC].

This Final version does not show where the technical content is modified by amendment 1. A separate Redline version with all changes highlighted is available in this publication.

International Standard IEC 60793-2-10 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This seventh edition constitutes a technical revision.

This edition includes the following significant change with respect to the previous edition: revision of the naming convention for A1 multimode fibres, which better matches with those found in ISO/IEC standards. These changes are outlined in the scope of this document along with a cross reference table for the new names.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60793 series, published under the general title *Optical fibres*, can be found on the IEC website.

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under webstore.iec.ch in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

OPTICAL FIBRES –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

1 Scope

This part of IEC 60793 is applicable to optical fibre sub-categories A1-OM1, A1-OM2, A1-OM3, A1-OM4, A1-OM5, and A1d. These fibres are used or can be incorporated in information transmission equipment and optical fibre cables.

Sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 apply to 50/125 μm graded index fibre in four bandwidth grades. Each of these bandwidth grades is defined for two levels of macrobend loss performance that are distinguished by "a" or "b" suffix. Those sub-categories with suffix "a" are specified to meet traditional macrobend loss performance levels. Those sub-categories with suffix "b" are specified to meet enhanced macrobend loss (i.e. lower loss) performance levels.

Sub-category A1-OM5 is specified to support single wavelength or multi-wavelength transmission systems in the vicinity of 850 nm to 950 nm. Although not normatively specified, bandwidth information covering this wavelength range is also included for A1-OM3 and A1-OM4.

Sub-category A1-OM1 applies to 62,5/125 μm graded index fibre and sub-category A1d applies to 100/140 μm graded index fibre.

Other applications include, but are not restricted to, the following: short reach, high bit-rate systems in telephony, distribution and local networks carrying data, voice and/or video services; on-premises intra-building and inter-building fibre installations including data centres, local area networks (LANs), storage area networks (SANs), private branch exchanges (PBXs), video, various multiplexing uses, outside telephone cable plant use, and miscellaneous related uses.

Three types of requirements apply to these fibres:

- general requirements, as defined in IEC 60793-2;
- specific requirements common to the category A1 multimode fibres covered in this document and which are given in Clause 5;
- particular requirements applicable to individual fibre sub-categories and models, or specific applications, which are defined in the normative specification Annexes A to D.

Table 1 shows the cross reference between the IEC A1 multimode optical fibre designations used in this document compared to those used in IEC 60793-2-10:2017. The table also refers to the normative annexes A, B and C for the A1 sub-category multimode fibres in this document that contains the detailed specification.

Table 1 – Cross reference IEC A1 multimode fibre designations to IEC 60793-2-10:2017

Annex	Sub-category	Sub-category/Model	Core diameter (nominal)	ISO/IEC 11801-1:2017
	This document designations	IEC 60793-2-10:2017 designations		Usage of cabled OMx fibres
A	A1-OM2	A1a.1	50 µm ^a	OM2 ^b
	A1-OM3	A1a.2	50 µm	OM3
	A1-OM4	A1a.3	50 µm	OM4
	A1-OM5	A1a.4	50 µm	OM5
B	A1-OM1	A1b	62,5 µm ^c	OM1 ^d
C	A1d	A1d	100 µm	
^a Historically, ISO/IEC 11801:2002 also defined OM2 cables made with 62,5/125 µm fibres having a minimum overfilled launch bandwidth of 500 MHz·km at 850 nm and 500 MHz·km at 1 300 nm. This specific bandwidth combination of 62,5/125 µm fibre is not part of this document. ^b OM2 cables are not supported for new installations within ISO/IEC 11801-1:2017. ^c Historically, ISO/IEC 11801:2002 also defined OM1 cables made with 50/125 µm fibres having a minimum overfilled launch bandwidth of 200 MHz·km at 850 nm and 500 MHz·km at 1 300 nm. This specific bandwidth combination of 50/125 µm fibre is not part of this document. ^d OM1 cables are not supported for new installations within ISO/IEC 11801-1:2017.				

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-21, *Optical fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*

IEC 60793-1-30, *Optical fibres – Part 1-30: Measurement methods and test procedures – Fibre proof test*

IEC 60793-1-31, *Optical fibres – Part 1-31: Measurement methods and test procedures – Tensile strength*

IEC 60793-1-32, *Optical fibres – Part 1-32: Measurement methods and test procedures – Coating strippability*

IEC 60793-1-33, *Optical fibres – Part 1-33: Measurement methods and test procedures – Stress corrosion susceptibility*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-41, *Optical fibres – Part 1-41: Measurement methods and test procedures – Bandwidth*

IEC 60793-1-42, *Optical fibres – Part 1-42: Measurement methods and test procedures – Chromatic dispersion*

IEC 60793-1-43, *Optical fibres – Part 1-43: Measurement methods and test procedures – Numerical aperture measurement*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-1-47, *Optical fibres – Part 1-47: Measurement methods and test procedures – Macrobending loss*

IEC 60793-1-49, *Optical fibres – Part 1-49: Measurement methods and test procedures – Differential mode delay*

IEC 60793-1-50, *Optical fibres – Part 1-50: Measurement methods and test procedures – Damp heat (steady state) tests*

IEC 60793-1-51, *Optical fibres – Part 1-51: Measurement methods and test procedures – Dry heat (steady state) tests*

IEC 60793-1-52, *Optical fibres – Part 1-52: Measurement methods and test procedures – Change of temperature tests*

IEC 60793-1-53, *Optical fibres – Part 1-53: Measurement methods and test procedures – Water immersion tests*

IEC 60793-2, *Optical fibres – Part 2: Product specifications – General*

IEC 61280-4-1:2009, *Fibre-optic communication subsystem test procedures – Part 4-1: Installed cable plant – Multimode attenuation measurement*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Abbreviated terms

CPR	coupled power ratio
DMD	differential mode delay
EF	encircled flux
EMB	effective modal bandwidth
EMB _c	calculated effective modal bandwidth
LAN	local area network
MMF	multimode fibre
NA	numerical aperture
OFL	overfilled launch
OMB _c	overfilled launch modal bandwidth calculated from differential mode delay (also known as OFL _c)
PBX	private branch exchange
PMD	physical medium dependent
ROFL	radial overfilled launch
SAN	storage area network

5 Specifications

5.1 General

The fibre consists of a glass core with a graded index profile and a glass cladding in accordance with IEC 60793-2.

The term "glass" usually refers to material consisting of non-metallic oxides.

5.2 Dimensional requirements

Dimensional attributes and measurement methods are given in Table 2.

Requirements common to all fibres in category A1 are indicated in Table 3.

Table 4 lists additional attributes that shall be specified by each sub-category specification.

Table 2 – Dimensional attributes and measurement methods

Attributes	Measurement methods
Cladding diameter	IEC 60793-1-20
Core diameter ^{a, b}	IEC 60793-1-20
Cladding non-circularity	IEC 60793-1-20
Core non-circularity	IEC 60793-1-20
Core-cladding concentricity error	IEC 60793-1-20
Primary coating diameter	IEC 60793-1-21
Primary coating non-circularity	IEC 60793-1-21
Primary coating-cladding concentricity error	IEC 60793-1-21
Fibre length	IEC 60793-1-22
^a Core diameter is specified at $850 \text{ nm} \pm 10 \text{ nm}$ with a test specimen length of $2,0 \text{ m} \pm 0,2 \text{ m}$ and a threshold value, k_{CORE} , of 0,025 for A1 fibres except A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres. ^b Core diameter is specified at $850 \text{ nm} \pm 10 \text{ nm}$ with a test specimen length of $100 \text{ m} \pm 5 \%$ and a threshold value, k_{CORE} , of 0,025 for A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres.	

Table 3 – Dimensional requirements common to category A1 fibres

Attributes	Unit	Limits
Core non-circularity	%	≤ 6
Primary coating diameter – uncoloured ^a	μm	245 ± 10
Primary coating diameter – coloured ^a	μm	250 ± 15
Primary coating-cladding concentricity error	μm	$\leq 12,5$
Fibre length	km	^b
^a The limits on primary coating diameter are most commonly used in telecommunications cables. There are other applications, which use other primary coating diameters, several of which are listed below. Alternative nominal primary coating diameters and tolerance (μm): 400 ± 40 500 ± 50 700 ± 100 900 ± 100		
^b Length requirements vary and should be agreed between supplier and customer.		

Table 4 – Additional dimensional attributes required in sub-category specifications

Attributes
Cladding diameter
Cladding non-circularity
Core diameter
Core-cladding concentricity error

5.3 Mechanical requirements

Mechanical attributes and measurement methods are given in Table 5.

Requirements common to all fibres in category A1 are in Table 6.

Table 5 – Mechanical attributes and measurement methods

Attributes	Test methods
Proof test	IEC 60793-1-30
Tensile strength	IEC 60793-1-31
Primary coating strippability	IEC 60793-1-32
Stress corrosion susceptibility	IEC 60793-1-33

Table 6 – Mechanical requirements common to category A1 fibres

Attributes	Unit	Limits
Proof stress level	GPa	$\geq 0,69^a$
Average strip force ^b	N	$1,0 \leq F_{\text{avg}} \leq 5,0$
Peak strip force ^b	N	$1,0 \leq F_{\text{peak}} \leq 8,9$
Tensile strength (median) for 0,5 m specimen length	GPa	$\geq 3,8$
Stress corrosion susceptibility constant, n_d	-	≥ 18
^a The proof test value of 0,69 GPa equals about 1 % strain or about 8,8 N force, for A1-OM1 to A1-OM5 fibres. For the relation between these different units, see IEC TR 62048:2014, 8.4. ^b Either average strip force or peak strip force, which are defined in the test procedure, may be specified by agreement between supplier and customer.		

5.4 Transmission requirements

Transmission attributes and measurement methods are given in Table 7.

Table 8 lists additional attributes that shall be specified by each sub-category specification.

Table 7 – Transmission attributes and measurement methods

Attributes	Measurement methods
Attenuation coefficient	IEC 60793-1-40
Modal bandwidth ^{a,b}	IEC 60793-1-41
Numerical aperture ^{c,d}	IEC 60793-1-43
Chromatic dispersion	IEC 60793-1-42
Change of optical transmission	IEC 60793-1-46
Macrobending loss	IEC 60793-1-47
Differential mode delay ^e	IEC 60793-1-49
^a For modal bandwidth, either overfilled launch (OFL) or overfilled launch modal bandwidth calculated from differential mode delay (OMB_c) can be used. OMB_c is the reference test method for A1-OM2, A1-OM3 and A1-OM4 fibres at 850 nm and is the required method for A1-OM5 fibres at 850 nm and 953 nm. ^b 850 nm modal bandwidth is specified with a test specimen length of $1\,000\text{ m} \pm 5\%$ for A1-OM3 to A1-OM5 fibres. For A1-OM3 fibres, the 850 nm modal bandwidth is measured at $850\text{ nm} \pm 10\text{ nm}$. For A1-OM4 and A1-OM5 fibres, the 850 nm modal bandwidth is measured at $850\text{ nm} \pm 2\text{ nm}$. For A1-OM5 fibre, the modal bandwidth is also measured at $953\text{ nm} \pm 6\text{ nm}$. ^c Numerical aperture is specified at $850\text{ nm} \pm 10\text{ nm}$ with a test specimen length of $2\text{ m} \pm 0,2\text{ m}$ and a threshold value, k_{NA}, of 0,05 for A1 fibres except A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres. ^d Numerical aperture is specified at $850\text{ nm} \pm 10\text{ nm}$ with a test specimen length of $100\text{ m} \pm 5\%$ and a threshold value, k_{NA}, of 0,05 for A1-OM2b, A1-OM3b, A1-OM4b and A1-OM5b fibres. ^e Differential mode delay is specified with a test specimen length of $1\,000\text{ m} \pm 5\%$ for A1-OM3, A1-OM4 and A1-OM5 fibres. For A1-OM3 fibres, the DMD is measured at $850\text{ nm} \pm 10\text{ nm}$. For A1-OM4 and A1-OM5 fibres, the DMD is measured at $850\text{ nm} \pm 2\text{ nm}$. For A1-OM5 fibre, the DMD is also measured at $953\text{ nm} \pm 6\text{ nm}$.	

Specification compliance of chromatic dispersion can be assured by compliance to the numerical aperture (NA) specification for A1 fibre.

Table 8 – Additional transmission attributes required in sub-category specifications

Attributes
Attenuation coefficient
Modal bandwidth
Chromatic dispersion
Numerical aperture
Macrobending loss

For attenuation coefficient and modal bandwidth, the sub-category specifications may contain ranges of specifiable values instead of fixed limits. In this case, the actual values of the maximum attenuation coefficient and minimum modal bandwidth, at both 850 nm and 1 300 nm (or just at one of these wavelengths) shall be agreed between supplier and customer. For commercial purposes, the modal bandwidth is linearly normalized to 1 km.

For guidance purposes, Annex H shows a number of standardised applications supported by A1 fibres and Annex I shows transmission capabilities for these fibres.

The indicated maximum attenuation coefficients apply to uncabled optical fibres; for the maximum cabled attenuation coefficients, reference is made to IEC 60794-1-1, which can be used in conjunction with this document. Tighter specifications for the fibre may be requested to account for added attenuation in the cabling process.

Remarks on the specification of modal bandwidth:

Care should be taken in writing dual wavelength bandwidth specifications. It is understood that for category A1 fibres, the bandwidth at 850 nm may be related to the bandwidth at 1 300 nm in a way shown in Figure 1, depending on the refractive index parameter, g (see IEC 60793-2). See [1]¹, page 50, and [2], page 255, for similar figures. The shaded region under the curve of Figure 1 can be defined as the dual window area. In this area, regions X, Y, and Z are examples of where a fibre manufacturer may choose to optimise the process. That is, centre the production bandwidth peak at 850 nm, 1 300 nm, or between these two wavelengths.

Due to this optimisation of the manufacturing process, there will be combinations of bandwidth that are not possible (i.e., outside the shaded region).




Figure 1 – Relation between bandwidths at 850 nm and 1 300 nm

5.5 Environmental requirements

5.5.1 General

Environmental exposure tests and measurement methods are documented in two forms:

- relevant environmental attributes and test procedures are given in Table 9;
- measurements of a particular mechanical or transmission attribute that may change on the application of the environment are listed in Table 10.

¹ Numbers in square brackets refer to the Bibliography.

Table 9 – Environmental exposure tests

Environmental exposure	Test
Damp heat	IEC 60793-1-50
Dry heat	IEC 60793-1-51
Change of temperature	IEC 60793-1-52
Water immersion	IEC 60793-1-53

Table 10 – Attributes measured for environmental tests

Attribute	Measurement method
Change in optical transmission	IEC 60793-1-46
Attenuation	IEC 60793-1-40
Strip force	IEC 60793-1-32
Tensile strength	IEC 60793-1-31
Stress corrosion susceptibility	IEC 60793-1-33

These tests are normally conducted periodically as type-tests for a fibre and coating design. Unless otherwise indicated, the recovery period allowed between the completion of the environmental exposure and performing the attribute measurements shall be as stated in the particular environmental test method.

5.5.2 Mechanical environmental requirements (common to all fibres in category A1)

5.5.2.1 General

These tests are, in practice, the most severe requirements amongst the environments defined in Table 9.

Tables 11, 12, and 13 give the prescriptions for strip force, tensile strength and stress corrosion susceptibility respectively.

5.5.2.2 Strip force

The following attributes shall be verified following removal of the fibre from the particular environment.

Table 11 – Strip force for environmental tests

Environment	Average strip force N	Peak strip force N
Damp heat	$1,0 \leq F_{\text{avg}} \leq 5,0$	$1,0 \leq F_{\text{peak}} \leq 8,9$
Water immersion	$1,0 \leq F_{\text{avg}} \leq 5,0$	$1,0 \leq F_{\text{peak}} \leq 8,9$

5.5.2.3 Tensile strength

The following attribute shall be verified following removal of the fibre from the environment.

Table 12 – Tensile strength for environmental tests

Environment	Median tensile strength specimen length: 0,5 m GPa	15th percentile tensile strength specimen length: 0,5 m GPa
Damp heat	≥ 3,03	≥ 2,76
NOTE These requirements do not apply to hermetically coated fibre.		

5.5.2.4 Stress corrosion susceptibility

The following attribute shall be verified following removal of the fibre from the environment.

Table 13 – Stress corrosion susceptibility for environmental tests

Environment	Stress corrosion susceptibility constant, n_d
Damp heat	≥ 18
NOTE This requirement does not apply to hermetically coated fibre.	

5.5.3 Transmission environmental requirements

Change in attenuation from the initial value shall be less than the values in Table 14. Attenuation shall be measured periodically during the entire exposure to each environment and after removal.

Table 14 – Change in attenuation for environmental tests

Environment	Wavelength nm	Attenuation increase dB/km
Damp heat	850	≤ 0,20
	1 300	≤ 0,20
Dry heat	850	≤ 0,20
	1 300	≤ 0,20
Change of temperature	850	≤ 0,20
	1 300	≤ 0,20
Water immersion	850	≤ 0,20
	1 300	≤ 0,20

Annex A (normative)

Specifications for sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 multimode fibres

A.1 General

Annex A contains particular requirements applicable to sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres. Common requirements, repeated here for ease of reference from the main body of this document, are noted by a clause entry in the "Reference" column. The "Reference" column also refers to other annexes containing relevant information on the attribute. Relevant notes from the main body of this document are not repeated but indicated with a superscript "SS".

Sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 are 50/125 μm graded index multimode fibres in four bandwidth grades. All are specified using overfilled bandwidth metrics, while sub-categories A1-OM3, A1-OM4 and A1-OM5 also apply differential mode delay measurements to deliver laser-optimised performance near 850 nm. Sub-category A1-OM5 also specifies both overfilled and differential mode delay bandwidth metrics at 953 nm to deliver laser-optimized performance over a wavelength range in the vicinity of 850 nm to 950 nm. A1-OM3 complies with A1-OM2 specifications. A1-OM4 complies with A1-OM3 specifications. A1-OM5 complies with A1-OM4 specifications.

Sub-category A1-OM2, A1-OM3, A1-OM4 and A1-OM5 are also specified for two levels of macrobend loss performance that are distinguished by "a" or "b" suffix. Those with suffix "a" (i.e. models A1-OM2a, A1-OM3a, A1-OM4a and A1-OM5a) are specified to meet traditional macrobend loss performance levels. Those with suffix "b" (i.e. models A1-OM2b, A1-OM3b, A1-OM4b and A1-OM5b) are specified to meet enhanced macrobend loss (i.e. lower loss) performance levels, and thereby also comply with traditional macrobend loss performance.

The nomenclature for the A1-OM2, A1-OM3, A1-OM4 and A1-OM5 sub-categories establishes a coding hierarchy that permits designation of fibres with increasing specificity. For example, purchase orders for A1-OM3 may be filled by A1-OM3a or A1-OM3b. As a result, where specifications and descriptions apply to all models at lower hierarchical levels, only the common portion of the name is stated.

The dimensional, mechanical and environmental requirements are common to all and specified in Tables A.1 and A.2. The common and distinguishing transmission requirements are specified in Table A.3.

A.2 Dimensional requirements

Table A.1 contains dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres.

Table A.1 – Dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres

Attributes	Unit	Limits	Reference
Cladding diameter	μm	125 ± 1	
Cladding non-circularity	%	≤ 1	
Core diameter ^{SS}	μm	$50 \pm 2,5$	
Core-cladding concentricity error	μm	≤ 2	
Core non-circularity	%	≤ 6	5.2
Primary coating diameter – uncoloured ^{SS}	μm	245 ± 10	5.2
Primary coating diameter – coloured ^{SS}	μm	250 ± 15	5.2
Primary coating-cladding concentricity error	μm	$\leq 12,5$	5.2
Length	km	(see 5.2)	5.2
^{SS} See notes in the main body of this document.			

A.3 Mechanical requirements

Table A.2 contains the mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres.

Table A.2 – Mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres

Attributes	Unit	Limits	Reference
Proof stress level ^{SS}	GPa	$\geq 0,69$	5.3
Average strip force ^{SS}	N	$1,0 \leq F_{\text{avg}} \leq 5,0$	5.3
Peak strip force ^{SS}	N	$1,0 \leq F_{\text{peak}} \leq 8,9$	5.3
^{SS} See notes in the main body of this document..			

A.4 Transmission requirements

Table A.3 contains transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres.

Table A.3 – Transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres

Attributes		Unit	Limits				Reference
Fibre sub-category			A1-OM2	A1-OM3	A1-OM4	A1-OM5	
Targeted operational wavelength(s) ^a		nm	850				Annex E
Maximum attenuation coefficient at 850 nm		dB/km	2,5				
Maximum attenuation coefficient at 953 nm		dB/km	Not specified				1,8
Maximum attenuation coefficient at 1 300 nm		dB/km	0,8				
Minimum modal bandwidth-length product for overfilled launch at 850 nm ^{ss}		MHz·km	500	1 500	3 500	3 500	Clause D.6
Minimum modal bandwidth-length product for overfilled launch at 953 nm ^{ss}		MHz·km	Not specified				1 850
Minimum modal bandwidth-length product for overfilled launch at 1 300 nm		MHz·km	500				
Minimum effective modal bandwidth-length product at 850 nm ^{ss e}		MHz·km	Not specified	2 000 Meet Clause D.1 or Clause D.2	4 700 Meet Clause D.3 or Clause D.4	4 700 Meet Clause D.5	Annexes D, E, F, G
Minimum effective modal bandwidth-length product at 953 nm ^{SS e}		MHz·km	Not specified				2 470 Meet Clause D.5
Numerical aperture ^{ss}		Dimensionless	0,200 ± 0,015				
Fibre model			A1-OM2a	A1-OM3a	A1-OM4a	A1-OM5a	
Maximum macro-bending loss ^b	Bending radius	Number of turns	Max at 850 nm / 1 300 nm				
	37,5 mm	100	0,5 / 0,5				
	15 mm	2	1,0 / 1,0				
Fibre model			A1-OM2b	A1-OM3b	A1-OM4b	A1-OM5b	
Maximum macro-bending loss ^b	Bending radius	Number of turns	Max at 850 nm / 1 300 nm				
	37,5 mm	100	0,5 / 0,5				
	15 mm	2	0,1 / 0,3				
	7,5 mm	2	0,2 / 0,5				

Zero dispersion wavelength, λ_0	nm	$1\,295 \leq \lambda_0 \leq 1\,340$ ^c	$1\,297 \leq \lambda_0 \leq 1\,328$ ^d
Zero dispersion slope, S_0 ^e	ps/(nm ² ·km)	$S_0 \leq 0,105$ from $1\,295 \text{ nm} \leq \lambda_0 \leq 1\,310 \text{ nm}$, and $\leq 0,000\,375 (1\,590 - \lambda_0)$ from $1\,310 \text{ nm} \leq \lambda_0 \leq 1\,340 \text{ nm}$ ^c	$S_0 \leq 4 (-103) / (840 (1 - (\lambda_0/840)^4))$ ^d
^a Targeted operational wavelength(s) is informative. ^b The launch condition for the macrobending loss measurement shall fulfil that described in IEC 61280-4-1. ^c The worst case chromatic dispersion coefficient at 850 nm (e.g. $S_0 = 0,093\,75 \text{ ps}/(\text{nm}^2 \cdot \text{km})$ at $\lambda_0 = 1\,340 \text{ nm}$ or $S_0 = 0,101\,25 \text{ ps}/(\text{nm}^2 \cdot \text{km})$ at $\lambda_0 = 1\,320 \text{ nm}$) is – 104 ps/(nm·km). ^d The coordinate that generates the worst-case dispersion for operating wavelengths from 840 nm to 1 000 nm is $\lambda_0 = 1\,328 \text{ nm}$, $S_0 = 0,093\,477 \text{ ps}/(\text{nm}^2 \cdot \text{km})$. The worst case chromatic dispersion coefficient at 850 nm is –98,5 ps/(nm·km) ^e When assessing system link performance at wavelengths from 840 nm to 953 nm, refer to the appropriate estimated minimum EMB equations found in Annex E in addition to the dispersion specifications for A1-OM3, A1-OM4, and A1-OM5 fibres. SS See notes in the main body of this document.			

A.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex B (normative)

Specifications for sub-category A1-OM1 multimode fibres

B.1 General

Annex B contains particular requirements applicable to A1-OM1 fibres. Common requirements, repeated here for ease of reference from the main body of this document, are noted by a clause entry in the "Reference" column. Relevant notes from the main body of this document are not repeated but indicated with a superscript "SS".

Sub-category A1-OM1 fibre is a 62,5/125 µm graded index fibre.

B.2 Dimensional requirements

Table B.1 contains dimensional requirements specific to A1-OM1 fibres.

Table B.1 – Dimensional requirements specific to A1-OM1 fibres

Attributes	Unit	Limits	Reference
Cladding diameter	µm	125 ± 2	
Cladding non-circularity	%	≤ 2	
Core diameter ^{SS}	µm	$62,5 \pm 3$	
Core-cladding concentricity error	µm	≤ 3	
Core non-circularity	%	≤ 6	5.2
Primary coating diameter – uncoloured ^{SS}	µm	245 ± 10	5.2
Primary coating diameter – coloured ^{SS}	µm	250 ± 15	5.2
Primary coating-cladding concentricity error	µm	$\leq 12,5$	5.2
Length ^{SS}	km	(see 5.2)	5.2
^{SS} See notes in the main body of this document.			

B.3 Mechanical requirements

Table B.2 contains the mechanical requirements specific to A1-OM1 fibres.

Table B.2 – Mechanical requirements specific to A1-OM1 fibres

Attributes	Unit	Limits	Reference
Proof stress level ^{SS}	GPa	$\geq 0,69$	5.3
Average strip force ^{SS}	N	$1,0 \leq F_{avg} \leq 5,0$	5.3
Peak strip force ^{SS}	N	$1,0 \leq F_{peak} \leq 8,9$	5.3
^{SS} See notes in the main body of this document.			

B.4 Transmission requirements

Table B.3 contains transmission requirements specific to A1-OM1 fibres.

Table B.3 – Transmission requirements specific to A1-OM1 fibres

Attributes	Unit	Limits	Reference
Maximum attenuation coefficient at 850 nm	dB/km	3,0	
Maximum attenuation coefficient at 1 300 nm	dB/km	1,0	
Minimum modal bandwidth-length product at 850 nm	MHz·km	200	
Minimum modal bandwidth-length product at 1 300 nm	MHz·km	500	
Numerical aperture ^{SS}	Dimensionless	$0,275 \pm 0,015$	
Maximum macrobending loss 100 turns on bending radius of 37,5 mm at wavelengths 850 nm and 1 300 nm ^a	dB	0,5	
Zero dispersion wavelength, λ_0	nm	$1\,320 \leq \lambda_0 \leq 1\,365$ ^b	
Zero dispersion slope S_0 – from $1\,320 \text{ nm} \leq \lambda_0 \leq 1\,348 \text{ nm}$ – from $1\,348 \text{ nm} \leq \lambda_0 \leq 1\,365 \text{ nm}$	ps/(nm ² ·km)	$\leq 0,11$ ^b $\leq 0,001 (1\,458 - \lambda_0)$ ^b	
^a The launch condition for the macrobending loss measurement shall fulfil that described in IEC 61280-4-1. ^b The worst case chromatic dispersion coefficient at 850 nm ($S_0 = 0,11 \text{ ps}/(\text{nm}^2 \cdot \text{km})$ at $\lambda_0 = 1\,348 \text{ nm}$) is $-125 \text{ ps}/(\text{nm} \cdot \text{km})$. ^{SS} See notes in the main body of this document.			

B.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex C (normative)

Specifications for sub-category A1d multimode fibres

C.1 General

Annex C contains particular requirements for A1d fibres. Common requirements, repeated here for ease of reference from this document, are noted by an entry in the "Reference" column. Relevant notes from the main body of this document are not repeated but indicated with a superscript "SS".

Sub-category A1d fibre is a 100/140 µm graded index fibre.

C.2 Dimensional requirements

Table C.1 contains dimensional requirements specific to A1d fibres.

Table C.1 – Dimensional requirements specific to A1d fibres

Attributes	Unit	Limits	Reference
Cladding diameter	µm	140 ± 4	
Cladding non-circularity	%	≤ 4	
Core diameter ^{SS}	µm	100 ± 5	
Core-cladding concentricity error	µm	≤ 6	
Core non-circularity	%	≤ 6	5.2
Primary coating diameter – uncoloured ^{SS}	µm	245 ± 10	5.2
Primary coating diameter – coloured ^{SS}	µm	250 ± 15	5.2
Primary coating-cladding concentricity error	µm	$\leq 12,5$	5.2
Length ^{SS}	km	(see 5.2)	5.2
^{SS} See notes in the main body of this document.			

C.3 Mechanical requirements

Table C.2 contains the mechanical requirements specific to A1d fibres.

Table C.2 – Mechanical requirements specific to A1d fibres

Attributes	Unit	Limits	Reference
Proof stress level ^{SS}	GPa	$\geq 0,69$	5.3
Average strip force ^{SS}	N	$1,0 \leq F_{avg} \leq 5,0$	5.3
Peak strip force ^{SS}	N	$1,0 \leq F_{peak} \leq 8,9$	5.3
^{SS} See notes in the main body of this document.			

C.4 Transmission requirements

Table C.3 contains transmission requirements specific to A1d fibres.

Table C.3 – Transmission requirements specific to A1d fibres

Attributes	Unit	Limits	Reference
Maximum attenuation coefficient at 850 nm ^a	dB/km	3,5 to 7,0	
Maximum attenuation coefficient at 1 300 nm ^a	dB/km	1,5 to 4,5	
Minimum modal bandwidth-length product at 850 nm ^a	MHz·km	10 to 200	
Minimum modal bandwidth-length product at 1 300 nm ^a	MHz·km	100 to 300	
Numerical aperture ^{ss}	Dimensionless	$0,26 \pm 0,03$ or $0,29 \pm 0,03$	
Maximum macrobending loss	dB	For further study	
Zero dispersion wavelength, λ_0	nm	$1\,330 \leq \lambda_0 \leq 1\,385$ ^b	
Zero dispersion slope S_0 – from $1\,330\text{ nm} \leq \lambda_0 \leq 1\,365\text{ nm}$ – from $1\,365\text{ nm} \leq \lambda_0 \leq 1\,385\text{ nm}$	ps/(nm ² ·km)	$\leq 0,105$ ^b $\leq 0,000,5 (1\,575 - \lambda_0)$ ^b	
^a The limit column forms a range of values that may be specified.			
^b The worst case chromatic dispersion coefficient at 850 nm ($S_0 = 0,105$ ps/(nm ² ·km) at $\lambda_0 = 1\,365$ nm) is –126 ps/(nm·km).			
^{ss} See notes in the main body of this document.			

C.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex D (normative)

Fibre differential mode delay (DMD), calculated effective modal bandwidth (EMB_c) and calculated overfilled modal bandwidth (OMB_c) requirements

D.1 A1-OM3 fibre DMD requirements

D.1.1 General

A1-OM3 fibres selected using the DMD mask method shall meet the requirements of D.1.2 and D.1.3. The radial limits, R_{INNER} and R_{OUTER} , were established for transmitters meeting the requirements of Clause E.4.

Refer to Annex E for information regarding effective modal bandwidth (EMB).

D.1.2 DMD templates

A1-OM3 fibres shall meet at least one of the six templates in Table D.1, each of which includes an inner and outer mask requirement, when measured according to IEC 60793-1-49.

Table D.1 – DMD templates for A1-OM3 fibres

Template number	Inner mask DMD (ps/m) for $R_{\text{INNER}} = 5 \mu\text{m}$ to $R_{\text{OUTER}} = 18 \mu\text{m}$	Outer mask DMD (ps/m) for $R_{\text{INNER}} = 0 \mu\text{m}$ to $R_{\text{OUTER}} = 23 \mu\text{m}$
1	$\leq 0,23$	$\leq 0,70$
2	$\leq 0,24$	$\leq 0,60$
3	$\leq 0,25$	$\leq 0,50$
4	$\leq 0,26$	$\leq 0,40$
5	$\leq 0,27$	$\leq 0,35$
6	$\leq 0,33$	$\leq 0,33$

The DMD requirements in Table D.1 are illustrated in Figure D.1. In this figure, the allowable DMD (as measured according to IEC 60793-1-49) is plotted versus the radial offset position of the single mode probe. There is a trade-off between the tightness of the inner mask and the outer mask to ensure a sufficient amount of the baud energy from a transmitter (meeting the launch specifications) arrives within the required time period (defined by the baud rate of the transmission system).




Figure D.1 – DMD template requirements

The "floating" characteristic of the inner mask is also illustrated in Figure D.1. In this figure, the inner mask (5 μm to 18 μm) may be positioned vertically (temporally) anywhere within the outer mask (0 μm to 23 μm). The DMD is more tightly constrained in the inner mask to allow for looser tolerances on the outer mask providing for improved ability to manufacture fibre conforming to this requirement. In the case of the 0,33 ps/m mask, the requirement is the same over the whole range from 0 μm to 23 μm creating a "flat" mask.

IEC 60793-1-49 can be used to ensure a minimum effective modal bandwidth-length product, when using sources meeting appropriate restrictions. When the launch condition requirements on the transmitters are coupled to the DMD requirements on the fibre, a balance can be achieved between fibre tolerance and transmitter tolerance. A careful study, using fibres contributed by several different fibre manufacturers and laser transmitters from several different source manufacturers, and including extensive and detailed simulations, shows that the above coupled specifications on fibre and sources will yield a minimum effective modal bandwidth-length product of 2 000 MHz·km [3] to [14].

The use of a template on the values of DMD achieves an effective trade-off between transmitter and fibre properties. The transmitter launch condition is bounded by encircled flux requirements at 4,5 μm and 19 μm as discussed in Clause E.4. The limitation on the transmitter encircled flux at the 4,5 μm radius assures that very little energy is carried by the lowest order modes of the fibre, allowing the relaxed tolerance on modal structure excited at small radii. The limitation on the transmitter encircled flux at the 19 μm radius assures that very little energy is carried by the highest order modes of the fibre, allowing the relaxed tolerance on modal structure excited at high radii.

D.1.3 DMD interval masks

The A1-OM3 fibre DMD shall not exceed 0,25 ps/m for any of the radial offset intervals given in Table D.2.

Table D.2 – DMD interval masks for A1-OM3 fibres

Interval number	R_{INNER} μm	R_{OUTER} μm
1	7	13
2	9	15
3	11	17
4	13	19

These interval masks screen out fibres having DMD that change too rapidly over short radial ranges. Fibres passing this screen have lower inter-symbol interference than those that do not.

D.2 A1-OM3 fibre EMB_c requirements

D.2.1 General

A1-OM3 fibres selected using the EMB_c method shall meet the requirements of D.2.2.

D.2.2 Calculated effective bandwidth

The DMD optical pulse shapes can be weighted by a set of launch distributions to determine a corresponding set of EMB_c values. The minimum EMB_c (minEMB_c) within this set shall meet the requirement of Equation (D.1):

$$\text{minEMB}_c \geq 1.770 \text{ MHz}\cdot\text{km} \quad (\text{D.1})$$

where

minEMB_c is determined from the complex transfer function as described in IEC 60793-1-49 using the weights defined in Table D.3.

NOTE 1 Minimum EMB_c is a fibre parameter, and it is possible that its value is not optimal for use in system models. Refer to Annex E for information regarding the corresponding system parameter called the "effective modal bandwidth" (EMB) and its relationship to EMB_c .

NOTE 2 Refer to Annex F for additional explanation of bandwidth nomenclature.

Weightings within Table D.3 are provided for DMD measured at $1 \mu\text{m}$ radial intervals starting from the centre of the core ($r = 0$) for ten simulated lasers with encircled flux (EF) metrics that correspond to those of ten actual lasers. The DMD weightings in Table D.3 are specific to sources meeting the specifications of Clause E.4.

Table D.3 – DMD weightings

Radial position	Laser ID				
r (μm)	1	2	3	4	5
0	0	0	0	0	0
1	0,033 023	0,023 504	0	0	0
2	0,262 463	0,188 044	0	0	0
3	0,884 923	0,634 634	0	0	0
4	2,009 102	1,447 235	0,007 414	0,005 637	0,003 034
5	3,231 216	2,376 616	0,072 928	0,055 488	0,029 856
6	3,961 956	3,052 908	0,262 906	0,200 05	0,107 634
7	3,694 686	3,150 634	0,637 117	0,483 667	0,258 329
8	2,644 369	2,732 324	1,197 628	0,896 95	0,458 494
9	1,397 552	2,060 241	1,916 841	1,402 833	0,661 247
10	0,511 827	1,388 339	2,755 231	1,957 805	0,826 035
11	0,110 549	0,834 722	3,514 797	2,433 247	1,000 204
12	0,004 097	0,419 715	3,883 317	2,639 299	1,294 439
13	0,000 048	0,160 282	3,561 955	2,397 238	1,813 982
14	0,001 111	0,047 143	2,617 093	1,816 953	2,506 95
15	0,005 094	0,044 691	1,480 325	1,296 977	3,164 213
16	0,013 918	0,116 152	0,593 724	1,240 553	3,572 113
17	0,026 32	0,219 802	0,153 006	1,700 02	3,618 037
18	0,036 799	0,307 088	0,012 051	2,240 664	3,329 662
19	0,039 465	0,329 314	0	2,394 077	2,745 395
20	0,032 152	0,268 541	0	1,952 429	1,953 241
21	0,019 992	0,166 97	0	1,213 833	1,137 762
22	0,008 832	0,073 514	0	0,534 474	0,494 404
23	0,002 612	0,021 793	0	0,158 314	0,146 517
24	0,000 282	0,002 679	0	0,019 738	0,018 328
25	0	0	0	0	0

Radial position	Laser ID				
r (μm)	6	7	8	9	10
0	0	0	0	0	0
1	0,015 199	0,016 253	0,022 057	0,010 43	0,015 681
2	0,120 91	0,129 011	0,176 39	0,083 496	0,124 978
3	0,407 702	0,434 844	0,595 248	0,281 802	0,421 548
4	0,925 664	0,987 184	1,351 845	0,650 28	0,957 203
5	1,488 762	1,587 6	2,174 399	1,130 599	1,539 535
6	1,825 448	1,94 661 4	2,666 278	1,627 046	1,887 747
7	1,702 306	1,815 285	2,486 564	2,044 326	1,762 955
8	1,218 378	1,299 241	1,780 897	2,291 72	1,292 184
9	0,643 911	0,686 635	0,945 412	2,280 813	0,790 844
10	0,238 557	0,255 85	0,360 494	1,937 545	0,559 38
11	0,098 956	0,131 429	0,163 923	1,383 006	0,673 655
12	0,204 274	0,327 091	0,318 712	0,878 798	1,047 689
13	0,529 982	0,848 323	0,778 983	0,679 756	1,589 037
14	1,024 948	1,567 513	1,383 174	0,812 36	2,138 626
15	1,611 695	2,224 027	1,853 992	1,074 702	2,470 827
16	2,210 689	2,555 06	1,914 123	1,257 323	2,361 764
17	2,707 415	2,464 566	1,511 827	1,255 967	1,798 213
18	2,938 8	2,087 879	0,908 33	1,112 456	1,059 264
19	2,739 32	1,577 111	0,386 991	0,879 309	0,444 481
20	2,090 874	1,056 343	0,111 76	0,608 183	0,123 304
21	1,261 564	0,595 102	0,014 829	0,348 921	0,012 552
22	0,552 14	0,256 718	0,001 818	0,151 12	0
23	0,163 627	0,076 096	0,000 54	0,044 757	0
24	0,020 443	0,009 446	0	0,005 639	0
25	0	0	0	0	0

D.3 A1-OM4 DMD requirements

D.3.1 General

A1-OM4 fibres selected using the DMD mask method shall meet the requirements of D.3.2 and D.3.3. See Clause D.1 for supporting information. The radial limits, R_{INNER} and R_{OUTER} , were established for transmitters meeting the requirements of Clause E.4.

Refer to Annex E for information regarding effective modal bandwidth (EMB).

D.3.2 DMD templates

A1-OM4 fibres shall meet at least one of the three templates in Table D.4, each of which includes an inner and outer mask requirement, when measured according to IEC 60793-1-49.

Table D.4 – DMD templates for A1-OM4 fibres

Template number	Inner mask DMD (ps/m) for $R_{\text{INNER}} = 5 \mu\text{m}$ to $R_{\text{OUTER}} = 18 \mu\text{m}$	Outer mask DMD (ps/m) for $R_{\text{INNER}} = 0 \mu\text{m}$ to $R_{\text{OUTER}} = 23 \mu\text{m}$
1	$\leq 0,10$	$\leq 0,30$
2	$\leq 0,11$	$\leq 0,17$
3	$\leq 0,14$	$\leq 0,14$

D.3.3 DMD interval masks

The A1-OM4 fibre DMD shall not exceed 0,11 ps/m for any of the radial offset intervals given in Table D.5 when measured according to IEC 60793-1-49.

Table D.5 – DMD interval masks for A1-OM4 fibres

Interval number	R_{INNER} μm	R_{OUTER} μm
1	7	13
2	9	15
3	11	17
4	13	19

D.4 A1-OM4 fibre EMB_c requirements

D.4.1 General

A1-OM4 fibres selected using the EMB_c method shall meet the requirements of D.4.2. See the introductory text for Table D.3 in D.2.2 for supporting information.

D.4.2 Calculated effective bandwidth

The DMD optical pulse shapes can be weighted by a set of launch distributions to determine a corresponding set of EMB_c values. The minimum EMB_c (minEMB_c) within this set shall meet the requirement of Equation (D.2):

$$\text{minEMB}_c \geq 4 \, 160 \, \text{MHz} \cdot \text{km} \quad (\text{D.2})$$

where

minEMB_c is determined from the complex transfer function as described in IEC 60793-1-49 using the weights defined in Table D.3.

D.5 A1-OM5 fibre modal bandwidth requirements

D.5.1 General

A1-OM5 fibres shall meet the requirements of D.5.2 and D.6. See the introductory text for Table D.3 in D.2.2 for supporting information.

D.5.2 Calculated effective modal bandwidth

The DMD optical pulse shapes shall be weighted by a set of launch distributions to determine a corresponding set of EMB_c values. The minimum EMB_c ($minEMB_c$) within this set shall meet the requirement of Equations (D.3) and (D.4):

$$minEMB_c \geq 4\ 160\ \text{MHz}\cdot\text{km at 850 nm} \quad (\text{D.3})$$

$$minEMB_c \geq 2\ 190\ \text{MHz}\cdot\text{km at 953 nm} \quad (\text{D.4})$$

where

$minEMB_c$ is determined from the complex transfer function as described in IEC 60793-1-49 using the weights defined in Table D.3.

D.6 A1-OM2, A1-OM3, A1-OM4 and A1-OM5 calculated overfilled modal bandwidth

The DMD optical pulse shapes shall be weighted for A1-OM2, A1-OM3 and A1-OM4 fibres by the launch distribution of Table D.6 to determine a corresponding OMB_c value at 850 nm. For A1-OM5 fibres, the launch distribution of Table D.6 shall be used to determine a corresponding value at 850 nm and 953 nm. The weights of Table D.6 are the same as those in IEC 60793-1-41 for method C.

Table D.6 – DMD weighting for OMB_c

Radial position, r μm	OFL weighting
0	0
1	0,000 73
2	0,001 57
3	0,002 53
4	0,003 62
5	0,004 87
6	0,006 31
7	0,007 95
8	0,009 83
9	0,011 98
10	0,014 43
11	0,017 25
12	0,020 46
13	0,024 14
14	0,028 36
15	0,033 17
16	0,038 69
17	0,045 00
18	0,052 21
19	0,060 47
20	0,069 92
21	0,080 73
22	0,093 10
23	0,107 25
24	0,123 45
25	0,141 97

Annex E (informative)

System, modal bandwidth, and transmitter considerations

E.1 Background

When a multimode fibre is used with laser transmitters, the bandwidth of the combination may vary widely, depending on the details of the modal structure of the lasers, the modal delay structure of the fibre, and the coupling between the laser and the fibre modes. More precisely, modal bandwidth is the –3 dB bandwidth of the impulse response produced from the modal delays of a particular fibre weighted by the mode power distribution excited by a particular laser. To generate a robust bandwidth estimate when the impulse response is non-Gaussian, the 3 dB bandwidth is replaced by an extrapolation of the 1,5 dB bandwidth.

Knowledge of the modal structure of a fibre, as determined by IEC 60793-1-49, allows a lower limit to be placed on the range of bandwidths which will be experienced when using a given fibre with various laser transmitters. The minEMB_c technique reviewed in Clause E.3 screens the fibre with 10 simulated lasers that explore the observed mode power distribution; the set of 10 simulated lasers is believed to be conservative compared to commercially available lasers but narrower than the set of theoretical lasers in the original TIA model shown in Figure E.2 [13]. The chosen lasers exhibit a variety of coupled mode power distribution characteristics: some with power more concentrated in lower order modes, some with power more concentrated in higher order modes, and some with both low order and high order mode power concentrations.

By using lasers which couple primarily into modes with well bounded delays, minimum modal bandwidth can be ensured. IEC 61280-1-4 can be used to measure the launch condition of laser transmitters into multimode fibre [15]. Appropriately selected launch condition specifications can restrict the modes of the fibre used by the transmitters primarily to those with appropriately limited differential mode delays.

A minimum modal bandwidth-length product can be ensured by combining a transmitter meeting the specifications in Clause E.4 below with a 50 µm fibre meeting the specifications in Annex D.

E.2 System considerations

E.2.1 A1-OM3 and A1-OM4 fibres

Refer to Clause E.3.

E.2.2 A1-OM5 fibre

Fibre specifications for high data systems have been developed using link models [16]. The 10 Gb/s and 25 Gb/s models build on the 1 Gb/s link model [16] which includes both a requirement that the power penalty or margin be positive and that the inter-symbol interference (ISI) be less than 3,6 dB.

The A1-OM5 fibre specifications were developed using the Excel link models for IEEE 100GBASE-SR4 (Example MMF Link Model.xls [17]) and Fibre Channel 32GFC (T11-12-376v0.xlsx [18]). The link models were used to determine the bandwidth requirements over the wavelength range from 840 nm to 953 nm. The wavelengths were varied within this range in the models. In the link models, the dispersion parameters U_0 (zero dispersion wavelength) and S_0 (zero dispersion slope) were adjusted to new values of 1 328 nm and 0,093 477 ps/(nm²·km) based on round-robin results, and the cabled fibre attenuation was decreased from 3,5 dB/km to 3,0 dB/km. Both link models are margin-limited over the 840 nm to 953 nm wavelength range (unlike the IEEE P802.3ae 10GBASE-S model [19] used for OM3,

which is inter-symbol interference limited to less than or equal to 3,6 dB), and the EMB in the link model was adjusted to achieve a margin of 0,000 dB. For setting the EMB specification, it was agreed to use the 32GFC link model with zero margin because the EMB requirements are higher than for the 100GBASE-SR4 model (that is, bandwidth requirements were chosen that met requirements of both system link models). The normative EMB specifications are 4 700 MHz·km at 850 nm and 2 470 MHz·km at 953 nm. These are marked with circles in Figure E.1. With these requirements fulfilled, the expected worst-case EMB lies on or above the system requirements, as explained in Clause E.3.

E.3 Effective modal bandwidth (EMB)

During the development of fibre sub-category A1-OM3, a detailed time-domain Monte-Carlo simulation was used to assess the performance-screening ability of various DMD mask and DMD weighting proposals for transmitters meeting the specifications of Clause E.4 [3] to [14]. The proposals were judged based on their ability to pass fibres that did not cause inter-symbol interference (ISI) to exceed a specific value more often than a 0,5 % rate [13]. The specific ISI value was established via the IEEE 802.3ae link budget spreadsheet [19] for a channel that included the effects of transmitter rise time, receiver bandwidth, and a fibre with 2 000 MHz·km modal bandwidth. Thus, through the use of the Monte-Carlo simulation, fibres meeting the requirements of sub-category A1-OM3 provide a minimum EMB of 2 000 MHz·km.

The minimum EMB value is aligned with the assumptions of the IEEE 802.3ae link budget spreadsheet. Of particular relevance is the fact that, in the spreadsheet, the ISI impairment is modelled under Gaussian waveform assumptions for the transmitter and fibre outputs. According to the results of the Monte-Carlo simulation for fibres passing the requirements, the spreadsheet relationship between ISI and minimum fibre modal bandwidth is pessimistic. Therefore, the calculation of EMB from weighted DMD included a factor of 1,13 to align the fibre requirements developed with the time-domain Monte-Carlo simulation with the spreadsheet model as shown in Equation (E.1).

$$EMB = 1,13 \times \min EMB_c \quad (E.1)$$

The EMB derived by Equation (E.1) also applies to the Fibre Channel link models. If other models are used, then a different EMB may be appropriate.

Fibres passing the requirements of Clauses D.3 and D.4 (i.e. A1-OM4 fibres) provide a minimum modal bandwidth at 850 nm that is 2,35 times higher than the minimum modal bandwidth of those passing the requirements of Clauses D.1 and D.2 (i.e. A1-OM3 fibres). As such, their minimum EMB is also 2,35 times higher under the same link budget spreadsheet assumptions as stated by Equation (E.2).

$$EMB \geq 2,35 \times 2\,000 \text{ MHz}\cdot\text{km} \geq 4\,700 \text{ MHz}\cdot\text{km} \quad (E.2)$$

System performance studies with actual fibres and laser sources support this relationship [20] to [22]. Applications have emerged which will utilize multiple wavelengths in the vicinity of 850 nm to 950 nm. To support these applications, guidance which characterizes the minimum EMB for A1-OM3, A1-OM4, and A1-OM5 is provided in the form of Equations (E.3) through (E.9) and Figures E.1 through E.3. These equations should not be extrapolated without due consideration.

The population of A1-OM3 subcategory fibres generally exhibit estimated minimum EMB meeting Equations (E.3) and (E.4) which are depicted as two curves from (a) 840 nm to 850 nm and (b) 850 nm to 953 nm as depicted in Figure E.1. The unit of EMB in the two equations is MHz·km.

For $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:


$$\text{EMB} \geq 1\,826 + (2\,000 - 1\,826) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.3})$$

For $850 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 2\,000 \times (1,001\,0 - 0,980\,9x + 0,807\,3x^2 - 0,430\,4x^3 + 0,119\,4x^4) \quad (\text{E.4})$$

where

$$x = (\lambda_c - 850) / (953 - 850)$$



IEC

Figure E.1 – Estimated minimum wide band EMB versus wavelength for A1-OM3

The population of A1-OM4 subcategory fibres generally exhibit estimated minimum EMB meeting Equations (E.5) and (E.6) which are depicted as two curves from (a) 840 nm to 850 nm and (b) 850 nm to 953 nm in Figure E.2. The unit of EMB in the two equations is MHz.km.

For $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:

$$\text{EMB} \geq 3\,840 + (4\,700 - 3\,840) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.5})$$

For $850 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 4\,700 \times (1,000\,2 - 2,154\,9x + 3,270\,0x^2 - 2,732\,8x^3 + 0,928\,0x^4) \quad (\text{E.6})$$

where

$$x = (\lambda_c - 850) / (953 - 850)$$




Figure E.2 – Estimated minimum wide band EMB versus wavelength for A1-OM4

Fibres passing the requirements of Clause D.5 (i.e. A1-OM5 fibres) generally exhibit estimated EMB meeting Equations (E.7), (E.8) and (E.9), which are depicted as three straight-line segments from (a) 840 nm to 850 nm, (b) 850 nm to 930 nm, and (c) 930 nm to 953 nm in Figure E.3. The unit of EMB in all three equations is MHz.km.

For $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:

$$\text{EMB} \geq 3\,840 + (4\,700 - 3\,840) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.7})$$

For $850 \text{ nm} \leq \lambda_c \leq 930 \text{ nm}$:


$$\text{EMB} \geq 4\,700 + (2\,565 - 4\,700) \times (\lambda_c - 850) / (930 - 850) \quad (\text{E.8})$$

For $930 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 2\,565 + (2\,470 - 2\,565) \times (\lambda_c - 930) / (953 - 930) \quad (\text{E.9})$$

Equations (E.7), (E.8), and (E.9) describe three straight line segments between the minimum EMB indicated by the 32GFC link model at 840 nm and the two minimum EMBs at the nominal measurement wavelengths of 850 nm and 953 nm. Equations (E.7), (E.8) and (E.9) are plotted in Figure E.3 along with values of EMB that close the 32GFC link model. The straight line segments from 840 nm to 953 nm were carefully established as providing a minimum EMB

guidance over the wavelength range while not intentionally introducing special fibre design dependence.



IEC

Figure E.3 – Estimated minimum wide band EMB versus wavelength for A1-OM5

E.4 Transmitter encircled flux (EF) and centre wavelength requirements

E.4.1 Encircled flux


The DMD radial limits of the inner, outer and interval masks specified in Clauses D.1 and D.3, and the DMD weightings specified in Clauses D.2, D.4 and D.5, were established in conjunction with the particular bounded range of laser launch conditions specified in Equations (E.10) and (E.11). The minimum modal bandwidth for launch conditions outside of this range has not been determined, but will be lower than for launch conditions within this range.

The transmitter launch condition power distribution should meet the requirements of Equations (E.10) and (E.11) when measured according to IEC 61280-1-4 [15] with the transmitter coupled into a 50- μm fibre meeting the specifications of this document.

$$\text{EF at radius } 4,5 \mu\text{m} \leq 30 \% \quad (\text{E.10})$$

$$\text{EF at radius } 19 \mu\text{m} \geq 86 \% \quad (\text{E.11})$$

The approximate positions of the DMD weightings specified in Table D.3 are depicted in the Figure E.4 below, relative to the boundaries given in Equations (E.10) and (E.11) [2].



IEC

Figure E.4 – Approximate position of DMD weightings relative to the EF boundaries of Equations (E.10) and (E.11)

Several published application standards meet the requirements of E.4.1 and E.4.2 [23] to [26].

E.4.2 Centre wavelength for A1-OM3 and A1-OM4 fibres

Because the fibre's modal delays change with wavelength, the transmitter centre wavelength should be kept close to the nominal DMD measurement wavelength of 850 nm to achieve the highest modal bandwidth performance over the population of passing fibres. It may be appropriate to de-rate the modal bandwidth when the transmitter is not operating at 850 nm [8]. See [27] for an illustration of bandwidth roll-off for fibres with bandwidth similar to fibre model A1-OM4.

The laser transmitter centre wavelength (λ_c) should meet the requirements of Equation (E.12) when tested according to IEC 61280-1-3 [28].

$$840 \text{ nm} \leq \lambda_c \leq 860 \text{ nm} \quad (\text{E.12})$$

E.4.3 Centre wavelength for A1-OM5 fibre

Because the fibre's modal delays change with wavelength, the highest modal bandwidth performance is attained when the laser transmitter centre wavelength is between the DMD measurement wavelengths. When the laser transmitter's centre wavelength is outside this range, the modal bandwidth may degrade. See Equation (E.7), (E.8) and (E.9) for advice on bandwidth values between the DMD measurement wavelengths.

The laser transmitter centre wavelength (λ_c) should meet the requirements of Equation (E.13) when tested according to IEC 61280-1-3 [28].

$$840 \text{ nm} \leq \lambda_c \leq 953 \text{ nm} \quad (\text{E.13})$$

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

Annex F (informative)

Bandwidth nomenclature explanation

Table F.1 provides explanations of bandwidth parameters that have similar names and abbreviations.

Table F.1 – Bandwidth nomenclature explanation

Parameter name and abbreviation	Parameter description
Calculated effective modal bandwidth (EMB_c)	The calculated modal bandwidth resulting from a particular weighting of a particular DMD.
Minimum calculated effective modal bandwidth (minimum EMB_c or $minEMB_c$)	The minimum calculated modal bandwidth resulting from a particular set of weightings of a particular DMD.
Effective modal bandwidth (EMB)	The modal bandwidth that results from multiplying the minimum calculated effective modal bandwidth by 1,13 to arrive at a value aligned with the assumptions of the IEEE 802.3ae link model for transmitters compliant to Clause E.2.
Calculated overfilled modal bandwidth (OMB_c)	The calculated modal bandwidth resulting from weighting a particular DMD to simulate an overfilled launch condition.

Annex G (informative)

Preliminary indications for items needing further study

G.1 Effective modal bandwidth (EMB) at 1 300 nm

Chromatic dispersion properties allow DMD measured at one wavelength to be transformed to DMD at another wavelength. Thus, 850 nm DMD may be used to predict minimum effective modal bandwidth-length product at 1 300 nm. Preliminary engineering analysis indicates that fibres meeting the requirements of Annex D for $\geq 2\,000$ MHz·km EMB at 850 nm will also provide ≥ 500 MHz·km EMB at 1 300 nm.

Some 1 300 nm laser-based transmitters are defined to operate into both multimode fibre and single mode fibre. In order to provide better assurance that multimode fibres, with bandwidth performance specified only on the basis of overfilled launch conditions, deliver at least their minimum overfilled bandwidth-length product for 1 300 nm transmitters designed to launch into single mode fibre (e.g. 1000BASE-LX), IEEE Std 802.3™ specifies the use of offset-launch mode-conditioning patch cords when connecting such transmitters to this type of multimode fibre.

The offset-launch is implemented by joining a single mode fibre to a multimode fibre within the patch cord using a specified range of single mode-to-multimode radial offset. By launching significantly off-centre from the single mode fibre into the multimode fibre, many modes are excited that produce a mode power distribution closer to that of an overfilled launch than that of the native launch, which typically strongly excites only low-order modes.

Because overfilled-launch bandwidth measurements are heavily dominated by high-order mode behaviour, they are insensitive to the behaviour of low-order modes. Therefore, by avoiding strong excitation of the low-order modes, the offset-launch patch cord eliminates dependence on the behaviour of these poorly-characterized modes, and improves the correlation between minimum system bandwidth and the overfilled launch bandwidth-length measurement.

However, because the DMD test procedure does measure low-order mode behaviour, it is capable of bounding the lower limit of bandwidth-distance product for the native launches of these 1 300 nm transmitters. Fibres meeting A1-OM3 and A1-OM4 specifications are optimised for peak bandwidth at 850 nm, and have specifically limited low-order mode DMD.

Operating at wavelengths different from the peak wavelength introduces a systematic increase in DMD. The largest increase in DMD occurs for the highest order modes. Thus the overfilled bandwidth, which is dominated by high-order mode DMD, is a conservative indicator of lowest effective modal bandwidth for native 1 300 nm launches that concentrate power in the low order modes. Therefore, A1-OM3 and A1-OM4 fibres are expected to provide EMB at least as high as their 500 MHz·km minimum overfilled bandwidth-length product at 1 300 nm without the use of mode conditioning patch cords.

G.2 Scaling of EMB with DMD

Different effective modal bandwidth-length products can be derived from the templates and interval masks defined in Clauses D.1 and D.3 simply by scaling EMB in inverse proportion to DMD temporal width, provided the following three conditions are met:

- 1) the fibre is used with transmitters meeting the specifications in E.4.1;
- 2) the radial offset limits of the templates are not changed; and
- 3) the overfilled modal bandwidth-length product requirements are scaled in direct proportion to the EMB.

This scaling ability is substantiated by the following relationships. From the waveguide theory, the mode power distribution of the transmitter relates directly to the radial extents of the inner and outer DMD masks. The operating wavelength range constrains operation in close proximity to the nominal DMD measurement wavelength to minimise modal bandwidth changes due to wavelength. With the mode power distribution and the radial extent of the DMD masks fixed, and the operating wavelength range unchanged, scaling is supported by the inverse proportionality between RMS pulse width and bandwidth [29] [30]. In this case, the RMS pulse width equates to the DMD temporal width. Scaling the overfilled bandwidth in direct proportion to the desired EMB maintains the established proportionality between the DMD and overfilled bandwidth.

For example, an effective modal bandwidth-length product at 850 nm of $\geq 1\,000$ MHz·km (one-half of 2 000 MHz·km) can be provided with fibre meeting any of the six DMD templates given in Clause D.1, with each template having double the DMD temporal width in both the inner and outer masks, and an overfilled bandwidth-length product of ≥ 750 MHz·km.

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

Annex H (informative)

Applications and cabling categories supported by A1 fibres

Table H.1 shows various internationally standardised applications, as well as other recommended applications, which are supported by A1 fibres. It is not an exhaustive list, and many other applications not specifically listed may also be supported.

**Table H.1 – Some standardised applications supported by
A1-OM2, A1-OM3, A1-OM4, A1-OM5 fibres and in some cases A1-OM1 fibres**

Application	Source	Name
1GFC	ISO/IEC 14165-115	1-Gigabit Fibre Channel
2GFC	ISO/IEC 14165-115	2-Gigabit Fibre Channel
4GFC	ANSI/INCITS 479	4-Gigabit Fibre Channel
8GFC	ANSI/INCITS 479	8-Gigabit Fibre Channel
10GFC	ISO/IEC 14165-116	10-Gigabit Fibre Channel
16GFC	ANSI/INCITS 479	16-Gigabit Fibre Channel
32GFC	ANSI/INCITS 512	32-Gigabit Fibre Channel
1000BASE-SX	ISO/IEC/IEEE 8802-3	Gigabit Ethernet
1000BASE-LX	ISO/IEC/IEEE 8802-3	Gigabit Ethernet
10GBASE-S	ISO/IEC/IEEE 8802-3	10-Gigabit Ethernet
25GBASE-SR	ISO/IEC/IEEE 8802-3	25-Gigabit Ethernet
40GBASE-SR4	ISO/IEC/IEEE 8802-3	40-Gigabit Ethernet
100GBASE-SR10	ISO/IEC/IEEE 8802-3	100-Gigabit Ethernet
100GBASE-SR4	ISO/IEC/IEEE 8802-3	100-Gigabit Ethernet

Annex I (informative)

1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit and 100-Gigabit Ethernet applications

Annex I is intended to outline a summary of category A1-OM2, A1-OM3, A1-OM4, A1-OM5 and A1-OM1 fibre requirements and related transmission capabilities for the 1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit, and 100-Gigabit Ethernet application standards developed within IEEE 802.3. All the Ethernet applications at 1 Gb/s or higher are considered as "laser launch" applications.

Table I.1 shows a summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities. The rows of Table I.1 are grouped by fibre sub-category and model and listed by increasing data rate. For each line item, there is an indication of the application link length and the requirements on transmitter launch characteristics. The requirements of the transmitter launch characteristics are of three types

- Offset-launch mode-conditioning patch cord for 1 300 nm operations, defined in IEEE 802.3.
- Coupled power ratio (CPR) > 9 dB and avoidance of radial overfilled launch (ROFL) for 1 Gb/s 850 nm operations on fibres characterised solely by overfilled launch (OFL) bandwidth. CPR is defined in IEC 61280-4-1:2009; ROFL is defined in IEEE 802.3.
- Encircled Flux (EF) requirements for 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s 850 nm operation on fibre models A1-OM3, A1-OM4 and A1-OM5 with effective modal bandwidth ensured by DMD measurement. The EF requirements are: EF at 4,5 μm radius $\leq 30\%$ and EF at 19,0 μm radius $\geq 86\%$. For EF measurements, see IEC 61280-1-4.

Table I.1 – Summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength									
		850 nm					1 300 nm				
		Minimum modal bandwidth for indicated measurement launch condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Minimum modal bandwidth for indicated measurement launch condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m
A1-OM1	1	160 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	220	500 for OFL	n.s.	1000BASE-LX	Offset-launch patch cord	550
A1-OM1	1	200 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	275	500 for OFL	n.s.	1000BASE-LX	Offset-launch patch cord	550
A1-OM1	10	160 for OFL	n.s.	10GBASE-S	EF at 4,5 μm radius ≤ 30 %, EF at 19,0 μm radius ≥ 86 %	26	500 for OFL	n.s.	10GBASE-LX4	Offset-launch patch cord	300
A1-OM1	10	200 for OFL	n.s.	10GBASE-S	EF at 4,5 μm radius ≤ 30 %, EF at 19,0 μm radius ≥ 86 %	33	500 for OFL	n.s.	10GBASE-LX4	Offset-launch patch cord	300
A1-OM1	10	160 for OFL	n.s.	n.s.	n.s.	n.s.	500 for OFL	n.s.	10GBASE-LRM	Offset-launch patch cord or EF at 5 μm radius ≥ 30 %, EF at 11 μm radius ≥ 81 %	220

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength							
		850 nm				1 300 nm			
		Minimum modal bandwidth for indicated measurement condition MHz-km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz-km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Minimum modal bandwidth for indicated measurement condition MHz-km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz-km	IEEE 802.3 PMD ^a
A1-OM1	10	200 for OFL	n.s.	n.s.	n.s.	n.s.	500 for OFL	n.s.	10GBASE-LRM
A1-OM2	1	400 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	500	400 for OFL	n.s.	1000BASE-LX
A1-OM2	1	500 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	550	500 for OFL	n.s.	1000BASE-LX
A1-OM2	10	400 for OFL	n.s.	10GBASE-S	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	66	400 for OFL	n.s.	10GBASE-LX4
A1-OM2	10	500 for OFL	n.s.	10GBASE-S	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	82	500 for OFL	n.s.	10GBASE-LX4
A1-OM2	10	500 for OFL	n.s.	10GBASE-S	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	82	500 for OFL	n.s.	10GBASE-LX4

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength					
		850 nm			1 300 nm		
		Minimum modal bandwidth for indicated measurement launch condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Link length m
A1-OM2	10	400 for OFL	n.s.	n.s.	n.s.	500 for OFL	100
A1-OM2	10	500 for OFL	n.s.	n.s.	n.s.	500 for OFL	220
A1-OM3	10	1 500 for OFL	2 000	10GBASE-SR EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	300	500 for OFL	300
A1-OM3	10	1 500 for OFL	2 000	n.s.	n.s.	500 for OFL	220

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength							
		850 nm				1 300 nm			
		Minimum modal bandwidth for indicated measurement condition MHz-km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz-km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Minimum modal bandwidth for indicated measurement condition MHz-km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz-km	IEEE 802.3 PMD ^a
A1-OM3	25	1 500 for OFL	2 000	25GBASE-SR	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	70	500 for OFL	n.s.	n.s.
A1-OM3	40	1 500 for OFL	2 000	40GBASE-SR4	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	100	500 for OFL	n.s.	n.s.
A1-OM3	100	1 500 for OFL	2 000	100GBASE-SR10	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	100	500 for OFL	n.s.	n.s.
A1-OM3	100	1 500 for OFL	2 000	100GBASE-SR4	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	70	500 for OFL	n.s.	n.s.
A1-OM4 or A1-OM5	10	3 500 for OFL	4 700	10BASE-S	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	400	500 for OFL	n.s.	n.s.

[illegible]

Bibliography

- [1] H. Murata, Handbook of Optical Fibers and Cables, 2nd Edition. New York: Marcel Dekker Inc., 1996, Figure 22
- [2] J. Abbott, S. Bickham, P. Dainese, M. Li, "Fibers for Short-Distance Applications", Chapter 7 in Optical Fiber Telecommunications VIA. New York: Elsevier, 2013, Figure 7.3
- [3] J. Ritger, J. Abbott, "New Delay Set for TIA Modelling", White paper, June 1, 2001. Available at: <http://www.tiaonline.org/>
- [4] J. Ritger, J. Abbott, "Fiber Delays for 10 Gb Risk Assessment", Presentation to FO2.2.1, June 25, 2001. Available at: <http://www.tiaonline.org/>
- [5] P. Kolesar, "Source Characteristics Development", Presentation to FO2.2.1, June 2001. Available at: <http://www.tiaonline.org/>
- [6] S. Golowich, J. Ritger, P. Kolesar, "Simulation of 50 μ m 10 Gb Links", Presentation to FO2.2.1, June 25, 2001. Available at: <http://www.tiaonline.org/>
- [7] S. Golowich, P. Kolesar, J. Ritger, G. Giaretta, "Modelling, Simulation, and Experimental Study of a 50 μ m Multimode Fiber Serial 10 Gb Link", Presentation to IEEE 802.3ae, May, 2000 [viewed 2019-01-30]. Available at: http://grouper.ieee.org/groups/802/3/ae/public/may00/golowich_1_0500.pdf
- [8] J. Ritger, "Risk Analysis: EF limits and Wavelength Dependence", Presentation to FO2.2.1, June 25, 2001. Available at: <http://www.tiaonline.org/>
- [9] S. Golowich, P. Kolesar, J. Ritger, P. Pepeljugoski, "Modelling and Simulations for 10 Gb Multimode Optical Fiber Link Component Specifications", OFC 2001, paper WDD57
- [10] P. Pepeljugoski, S. Golowich, "Measurements and simulations of intersymbol interference penalty in new high speed 50 μ m multimode fiber links operating at 10 Gb/s", OFC 2001, paper WDD40
- [11] J. Ritger, "Use of Differential Mode Delay in Qualifying Multi-Mode Optical Fiber for 10 Gbps Operation", OFMC 2001
- [12] M. Hackert, "ITA FO-2.2.1 March 12, 2001 Update", March 2001 IEEE Plenary [viewed 2019-01-30]. Available at: http://grouper.ieee.org/groups/802/3/ae/public/mar01/hackert_1_0301.pdf
- [13] P. Pepeljugoski, M. Hackert, J. Abbott, S. Swanson, S. Golowich, J. Ritger, P. Kolesar, C. Chen and P. Pleunis, "Development of System Specification for Laser Optimized 50 μ m Multimode Fiber for Multi-gigabit Short Wavelength LANs", J. Lightwave Tech., volume 21, No. 5, p. 1256-1275, May 2003
- [14] P. Pepeljugoski, S. Golowich, J. Ritger, P. Kolesar, A. Risteski, " Modeling and Simulation of Next-Generation Multimode Fiber Links", J. Lightwave Tech. Vol. 21, No. 5, p. 1242-1255, May 2003.
- [15] IEC 61280-1-4, *Fibre optic communication subsystem test procedures – Part 1-4: General communication subsystems – Light source encircled flux measurement method*

- [16] D. Cunningham and W. Lane, Gigabit Ethernet Networking. New York: Macmillan Technical Publishing, 1999 (Chapter 9 – The Gigabit Ethernet Optical Link Model)
- [17] IEEE 100G-SR4 Example MMF Link Model.xls, Petrilla [viewed 2019-01-30]. Available at: <http://www.ieee802.org/3/bm/public/may13/index.html>
- [18] 32G Fibre Channel Model T11-12-376v0, Cunningham 9/27/2012 [viewed 2019-02-25]. Available at: https://standards.incits.org/apps/group_public/document.php?document_id=105920&wg_abbrev=t11
- [19] IEEE P802.3ae 10Gb/s Ethernet Task Force Link Budget Spreadsheet (Version 3.1.16a) [viewed 2019-01-30]. Available at: <http://grouper.ieee.org/groups/802/3/ae/public/index.html>
- [20] C. Caspar, R. Freund, F. Achten, A. Gholami, G. Kuyt, P. Matthijsse and D. Molin "Impact of Transceiver Characteristics on the Performance of 10 GbE Links Applying OM-4 Multimode Fibers", Proceedings of the 57th IWCS Conference, p. 295-303, November 2008
- [21] A. Sengupta, "Simulation of 10GbE Multimode Optical Communications Systems", Proceedings of the 57th IWCS Conference, p. 320-326, November 2008
- [22] G. Oulundsen III, Y. Sun, D. Vaidya, R. Lingle, Jr., T. Irujo, D. Mazzaresse, "Important Performance Characteristics of Enhanced OM3 Fiber for 10 Gb/s Operation", Proceedings of the 57th IWCS Conference, p. 327-334, November 2008
- [23] IEEE Std 802.3TM-2015, *IEEE Standard for Ethernet*, Clause 52 for 10GBASE-S, Clause 86 for 40GBASE-SR4 and 100GBASE-SR10, Clause 95 for 100GBASE-SR4, Clause 112 for 25GBASE-SR2
- [24] ISO/IEC 14165-116, Information technology – *Fibre channel – Part 116: 10 Gigabit (10GFC)*
- [25] ANSI/INCITS 479-2011, Information Technology – *Fibre Channel – Physical Interface – 5 (FC-P1-5)*, for 400-SN (4GFC), 800-SN and 800-SA (8GFC), 1600-SN (16GFC)³
- [26] ANSI/INCITS 512-2015, Information Technology – *Fibre Channel – Physical Interface – 6 (FC-P1-6)*, for 3200-SN (32GFC)
- [27] OM3, OM4, OM5 Modal Bandwidth Over Wavelengths for WDM, IEEE 802.3 NGMMF Study Group, 01-2018 [viewed 2019-01-30]. Available at: http://grouper.ieee.org/groups/802/3/NGMMF/public/Jan18/kolesar_NGMMF_01_jan18.pdf
- [28] IEC 61280-1-3, *Fibre optic communication subsystem test procedures – Part 1-3: General communication subsystems – Central wavelength and spectral width measurement*

² This publication has been withdrawn and replaced by IEEE Std 802.3-2018, but for the purposes of this document, it is given as a reference.

³ This publication has been withdrawn, but for the purposes of this document, it is given as a reference.

- [29] R. G. Smith and S. D. Personick, Receiver design for optical communication systems. In Topics in Applied Physics, Vol. 39, *Semiconductor Devices for Optical Communications*, H. Kressel (ed.). Berlin: Springer-Verlag, 1982
- [30] Gair D. Brown, Bandwidth and rise time calculations for digital multimode fiber-optic data links. *JLT* 10, no. 5, p. 675-678, 1992 May

Non-numbered references

IEC 60793-2-10:2017, *Optical fibres – Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres*

IEC 60794-1-1, *Optical fibre cables – Part 1-1: Generic specification – General*

IEC TR 62048:2014, *Optical fibres – Reliability – Power law theory*

ISO/IEC 11801:2002, *Information technology – Generic cabling for customer premises*⁴

ISO/IEC 11801-1:2017, *Information technology – Generic cabling for customer premises – Part 1: General requirements*

ISO/IEC 14165-115, *Information technology – Fibre channel – Part 115: Physical interfaces (FC-PI)*

ISO/IEC/IEEE 8802-3, *Information technology – Telecommunications and information exchange between systems – Local and metropolitan area networks – Specific requirements – Part 3: Standard for Ethernet*

⁴ This publication has been withdrawn and replaced by ISO/IEC 11801-1:2017 and ISO/IEC 11801-2:2017, but for the purposes of this document, it is given as a reference.

IECNORM.COM : Click to view the full PDF of IEC 60793-2-10:2019+AMD1:2022 CSV

SOMMAIRE

AVANT-PROPOS	57
1 Domaine d'application	59
2 Références normatives	60
3 Termes et définitions	61
4 Termes abrégés	62
5 Spécifications	62
5.1 Généralités	62
5.2 Exigences dimensionnelles	62
5.3 Exigences mécaniques	64
5.4 Exigences de transmission	64
5.5 Exigences environnementales	66
5.5.1 Généralités	66
5.5.2 Exigences liées à l'environnement mécanique (communes à toutes les fibres de catégorie A1)	67
5.5.3 Exigences d'environnement pour la transmission	68
Annexe A (normative) Spécifications pour les fibres multimodales de la sous-catégorie A1-OM2, A1-OM3, A1-OM4 et A1-OM5	69
A.1 Généralités	69
A.2 Exigences dimensionnelles	69
A.3 Exigences mécaniques	70
A.4 Exigences de transmission	70
A.5 Exigences environnementales	72
Annexe B (normative) Spécifications pour les fibres multimodales de la sous-catégorie A1-OM1	73
B.1 Généralités	73
B.2 Exigences dimensionnelles	73
B.3 Exigences mécaniques	73
B.4 Exigences de transmission	74
B.5 Exigences environnementales	74
Annexe C (normative) Spécifications pour les fibres multimodales de la sous-catégorie A1d	75
C.1 Généralités	75
C.2 Exigences dimensionnelles	75
C.3 Exigences mécaniques	75
C.4 Exigences de transmission	76
C.5 Exigences environnementales	76
Annexe D (normative) Exigences concernant le retard de mode différentiel (DMD) de la fibre, la largeur de bande modale effective calculée (EMB_C) et la largeur de bande modale saturée calculée (OMB_C)	77
D.1 Exigences relatives au DMD pour les fibres A1-OM3	77
D.1.1 Généralités	77
D.1.2 Gabarits de DMD	77
D.1.3 Masques d'intervalle de DMD	79
D.2 Exigences relatives au EMB_C pour les fibres A1-OM3	79
D.2.1 Généralités	79
D.2.2 Largeur de bande effective calculée	79

D.3	Exigences relative au DMD pour les fibres A1-OM4	81
D.3.1	Généralités	81
D.3.2	Gabarits de DMD	81
D.3.3	Masques d'intervalle de DMD	82
D.4	Exigences relatives au EMB _C pour les fibres A1-OM4	82
D.4.1	Généralités	82
D.4.2	Largeur de bande effective calculée	82
D.5	Exigences relatives à la largeur de bande modale des fibres A1-OM5.....	82
D.5.1	Généralités	82
D.5.2	Largeur de bande modale effective calculée	83
D.6	Largeur de bande modale saturée calculée A1-OM2, A1-OM3, A1-OM4 et A1-OM5	83
Annexe E (informative) Considérations sur les systèmes, la largeur de bande modale et les émetteurs		85
E.1	Contexte	85
E.2	Considérations sur les systèmes	85
E.2.1	Fibres A1-OM3 et A1-OM4.....	85
E.2.2	Fibre A1-OM5	85
E.3	Largeur de bande modale effective (EMB)	86
E.4	Exigences relatives au flux inscrit (EF) et à la longueur d'onde centrale pour l'émetteur.....	90
E.4.1	Flux inscrit.....	90
E.4.2	Longueur d'onde centrale pour les fibres A1-OM3 et A1-OM4.....	91
E.4.3	Longueur d'onde centrale pour une fibre A1-OM5	91
Annexe F (informative) Explication de la nomenclature des largeurs de bande		93
Annexe G (informative) Indications préliminaires pour les éléments qui nécessitent une étude supplémentaire		94
G.1	Largeur de bande modale effective (EMB) à 1 300 nm	94
G.2	Graduation de l'EMB avec le DMD	95
Annexe H (informative) Applications et catégories de câbles supportées par les fibres A1.....		96
Annexe I (informative) Applications Ethernet 1 gigabit, 10 gigabits, 25 gigabits, 40 gigabits et 100 gigabits		97
Bibliographie.....		105
Figure 1 – Relation entre les largeurs de bande à 850 nm et à 1 300 nm		66
Figure D.1 – Exigences relatives aux gabarits de DMD		78
Figure E.1 – EMB large bande minimale estimée en fonction de la longueur d'onde pour A1-OM3		88
Figure E.2 – EMB large bande minimale estimée en fonction de la longueur d'onde pour A1-OM4		89
Figure E.3 – EMB large bande minimale estimée en fonction de la longueur d'onde pour A1-OM5		90
Figure E.4 – Position approchée de pondérations de DMD par rapport aux limites de flux inscrit des Equations (E.10) et (E.11)		91
Tableau 1 – Correspondance entre les désignations de fibres optiques multimodales IEC A1 et l'IEC 60793-2-10:2017		60
Tableau 2 – Attributs dimensionnels et méthodes de mesure		63

Tableau 3 – Exigences dimensionnelles communes aux fibres de catégorie A1	63
Tableau 4 – Attributs dimensionnels supplémentaires exigés dans les spécifications de sous-catégories	63
Tableau 5 – Attributs mécaniques et méthodes de mesure.....	64
Tableau 6 – Exigences mécaniques communes aux fibres de catégorie A1	64
Tableau 7 – Attributs de transmission et méthodes de mesure	65
Tableau 8 – Attributs de transmission supplémentaires exigés dans les spécifications de sous-catégories	65
Tableau 9 – Essais d'exposition à l'environnement	67
Tableau 10 – Attributs mesurés pour les essais d'environnement.....	67
Tableau 11 – Force de dénudage pour les essais d'environnement.....	67
Tableau 12 – Résistance à la traction pour les essais d'environnement	68
Tableau 13 – Résistance à la corrosion sous contrainte pour les essais d'environnement	68
Tableau 14 – Variation de l'affaiblissement pour les essais d'environnement	68
Tableau A.1 – Exigences dimensionnelles spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5	70
Tableau A.2 – Exigences mécaniques spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5.....	70
Tableau A.3 – Exigences de transmission spécifiques aux fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5	71
Tableau B.1 – Exigences dimensionnelles spécifiques aux fibres A1-OM1	73
Tableau B.2 – Exigences mécaniques spécifiques aux fibres A1-OM1	74
Tableau B.3 – Exigences de transmission spécifiques aux fibres A1-OM1	74
Tableau C.1 – Exigences dimensionnelles spécifiques aux fibres A1d	75
Tableau C.2 – Exigences mécaniques spécifiques aux fibres A1d.....	76
Tableau C.3 – Exigences de transmission spécifiques aux fibres A1d.....	76
Tableau D.1 – Gabarits de DMD pour les fibres A1-OM3.....	77
Tableau D.2 – Masques d'intervalles de DMD pour les fibres A1-OM3	79
Tableau D.3 – Pondérations de DMD	80
Tableau D.4 – Gabarits de DMD pour les fibres A1-OM4.....	82
Tableau D.5 – Masques d'intervalles de DMD pour les fibres A1-OM4	82
Tableau D.6 – Pondération de DMD pour OMB _C	84
Tableau E.1 – Explication de la nomenclature des largeurs de bande	93
Tableau H.1 – Exemples d'applications normalisées prises en charge par les fibres A1-OM2, A1-OM3, A1-OM4 et A1-OM5 et dans certains cas par les fibres A1-OM1	96
Tableau I.1 – Aperçu des exigences et des capacités de l'Ethernet 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s et 100 Gb/s.....	98

COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

FIBRES OPTIQUES –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1

AVANT-PROPOS

- 1) La Commission Electrotechnique Internationale (IEC) est une organisation mondiale de normalisation composée de l'ensemble des comités électrotechniques nationaux (Comités nationaux de l'IEC). L'IEC a pour objet de favoriser la coopération internationale pour toutes les questions de normalisation dans les domaines de l'électricité et de l'électronique. A cet effet, l'IEC – entre autres activités – publie des Normes internationales, des Spécifications techniques, des Rapports techniques, des Spécifications accessibles au public (PAS) et des Guides (ci-après dénommés "Publication(s) de l'IEC"). Leur élaboration est confiée à des comités d'études, aux travaux desquels tout Comité national intéressé par le sujet traité peut participer. Les organisations internationales, gouvernementales et non gouvernementales, en liaison avec l'IEC, participent également aux travaux. L'IEC collabore étroitement avec l'Organisation Internationale de Normalisation (ISO), selon des conditions fixées par accord entre les deux organisations.
- 2) Les décisions ou accords officiels de l'IEC concernant les questions techniques représentent, dans la mesure du possible, un accord international sur les sujets étudiés, étant donné que les Comités nationaux de l'IEC intéressés sont représentés dans chaque comité d'études.
- 3) Les Publications de l'IEC se présentent sous la forme de recommandations internationales et sont agréées comme telles par les Comités nationaux de l'IEC. Tous les efforts raisonnables sont entrepris afin que l'IEC s'assure de l'exactitude du contenu technique de ses publications; l'IEC ne peut pas être tenue responsable de l'éventuelle mauvaise utilisation ou interprétation qui en est faite par un quelconque utilisateur final.
- 4) Dans le but d'encourager l'uniformité internationale, les Comités nationaux de l'IEC s'engagent, dans toute la mesure possible, à appliquer de façon transparente les Publications de l'IEC dans leurs publications nationales et régionales. Toutes divergences entre toutes Publications de l'IEC et toutes publications nationales ou régionales correspondantes doivent être indiquées en termes clairs dans ces dernières.
- 5) L'IEC elle-même ne fournit aucune attestation de conformité. Des organismes de certification indépendants fournissent des services d'évaluation de conformité et, dans certains secteurs, accèdent aux marques de conformité de l'IEC. L'IEC n'est responsable d'aucun des services effectués par les organismes de certification indépendants.
- 6) Tous les utilisateurs doivent s'assurer qu'ils sont en possession de la dernière édition de cette publication.
- 7) Aucune responsabilité ne doit être imputée à l'IEC, à ses administrateurs, employés, auxiliaires ou mandataires, y compris ses experts particuliers et les membres de ses comités d'études et des Comités nationaux de l'IEC, pour tout préjudice causé en cas de dommages corporels et matériels, ou de tout autre dommage de quelque nature que ce soit, directe ou indirecte, ou pour supporter les coûts (y compris les frais de justice) et les dépenses découlant de la publication ou de l'utilisation de cette Publication de l'IEC ou de toute autre Publication de l'IEC, ou au crédit qui lui est accordé.
- 8) L'attention est attirée sur les références normatives citées dans cette publication. L'utilisation de publications référencées est obligatoire pour une application correcte de la présente publication.
- 9) L'attention est attirée sur le fait que certains des éléments de la présente Publication de l'IEC peuvent faire l'objet de droits de brevet. L'IEC ne saurait être tenue pour responsable de ne pas avoir identifié de tels droits de brevets et de ne pas avoir signalé leur existence.

Cette version consolidée de la Norme IEC officielle et de son amendement a été préparée pour la commodité de l'utilisateur.

L'IEC 60793-2-10 édition 7.1 contient la septième édition (2019-05) [documents 86A/1932/FDIS et 86A/1939/RVD] et son amendement 1 (2022-01) [documents 86A/2121/CDV et 86A/2140/RVC].

Cette version Finale ne montre pas les modifications apportées au contenu technique par l'amendement 1. Une version Redline montrant toutes les modifications est disponible dans cette publication.

La Norme internationale IEC 60793-2-10 a été établie par le sous-comité 86A: Fibres et câbles, du comité d'études 86 de l'IEC: Fibres optiques.

Cette septième édition constitue une révision technique.

La présente édition inclut les modifications majeures suivantes par rapport à l'édition précédente: révision de la convention de dénomination pour les fibres multimodales A1, correspondant mieux aux noms compris dans les normes ISO/IEC. Ces modifications sont indiquées dans le domaine d'application du présent document avec une table de correspondance pour les nouveaux noms.

Ce document a été rédigé selon les Directives ISO/IEC, Partie 2.

Une liste de toutes les parties de la série IEC 60793, publiées sous le titre général *Fibres optiques*, peut être consultée sur le site web de l'IEC.

Le comité a décidé que le contenu de la publication de base et de son amendement ne sera pas modifié avant la date de stabilité indiquée sur le site web de l'IEC sous webstore.iec.ch dans les données relatives à la publication recherchée. A cette date, la publication sera

- reconduite,
- supprimée,
- remplacée par une édition révisée, ou
- amendée.

IMPORTANT – Le logo "colour inside" qui se trouve sur la page de couverture de cette publication indique qu'elle contient des couleurs qui sont considérées comme utiles à une bonne compréhension de son contenu. Les utilisateurs devraient, par conséquent, imprimer cette publication en utilisant une imprimante couleur.

FIBRES OPTIQUES –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1

1 Domaine d'application

La présente partie de l'IEC 60793 est applicable aux fibres optiques des sous-catégories A1-OM1, A1-OM2, A1-OM3, A1-OM4, A1-OM5 et A1d. Ces fibres sont utilisées ou peuvent être intégrées dans des équipements destinés à la transmission de l'information et dans des câbles à fibres optiques.

Les sous-catégories A1-OM2, A1-OM3, A1-OM4 et A1-OM5 s'appliquent à la fibre à gradient d'indice de 50/125 μm dans quatre classes de largeur de bande. Chaque classe de largeur de bande est définie pour deux niveaux de performances en matière de pertes par macrocourbures, qui se distinguent par le suffixe "a" ou "b". Les sous-catégories qui comportent le suffixe "a" sont spécifiées de façon à satisfaire aux niveaux de performances classiques en matière de pertes par macrocourbures. Les sous-catégories qui comportent le suffixe "b" sont spécifiées de façon à satisfaire aux niveaux de performances avancées en matière de pertes par macrocourbures (c'est-à-dire des niveaux de pertes plus faibles).

La sous-catégorie A1-OM5 est spécifiée pour prendre en charge des systèmes de transmission à une seule ou plusieurs longueurs d'onde au voisinage de 850 nm à 950 nm. Bien qu'elles ne soient pas spécifiées sur le plan normatif, les informations de largeur de bande couvrant cette plage de longueurs d'onde sont également incluses pour A1-OM3 et A1-OM4.

La sous-catégorie A1-OM1 s'applique aux fibres à gradient d'indice de 62,5/125 μm et la sous-catégorie A1d à celles de gradient d'indice de 100/140 μm .

D'autres applications comprennent, mais sans s'y limiter, ce qui suit: les systèmes téléphoniques de courtes distances à haut débit, les réseaux de distribution et les réseaux locaux qui transportent des données, la voix et/ou des services vidéo; et les connexions par fibres intra ou inter bâtiment dans les locaux utilisateurs, englobant les centres de traitement de données, les réseaux locaux (LAN), les réseaux dédiés sauvegarde (SAN), les centraux téléphoniques privés (PABX), la vidéo, les différentes utilisations de multiplexage, l'utilisation d'une installation de câble du réseau téléphonique externe et les différentes utilisations associées.

Trois types d'exigences s'appliquent à ces fibres:

- les exigences générales, qui sont définies dans l'IEC 60793-2;
- des exigences spécifiques communes aux fibres multimodales de catégorie A1, couvertes par le présent document et qui sont données à l'Article 5;
- des exigences particulières applicables à des sous-catégories et des modèles particuliers de fibres ou à des applications spécifiques, qui sont définies dans les Annexes de spécifications normatives A à D.

Le Tableau 1 montre la correspondance entre les désignations de fibres optiques multimodales IEC A1 utilisées dans le présent document et celles utilisées dans l'IEC 60793-2-10:2017. Le tableau se réfère également aux Annexes normatives A, B et C pour les fibres multimodales de la sous-catégorie A1 dans le présent document contenant la spécification particulière.

Tableau 1 – Correspondance entre les désignations de fibres optiques multimodales IEC A1 et l'IEC 60793-2-10:2017

Annexe	Sous-catégorie	Sous-catégorie/ Modèle	Diamètre du noyau (nominal)	ISO/IEC 11801-1:2017
	Désignations du présent document	Désignations de l'IEC 60793-2-10:2017		Utilisation de fibres OMx câblées
A	A1-OM2	A1a.1	50 µm ^a	OM2 ^b
	A1-OM3	A1a.2	50 µm	OM3
	A1-OM4	A1a.3	50 µm	OM4
	A1-OM5	A1a.4	50 µm	OM5
B	A1-OM1	A1b	62,5 µm ^c	OM1 ^d
C	A1d	A1d	100 µm	
^a Historiquement, l'ISO/IEC 11801:2002 définissait également des câbles OM2 faits de fibres de 62,5/125 µm ayant une largeur de bande à injection saturée minimale de 500 MHz·km à 850 nm et 500 MHz·km à 1 300 nm. Cette combinaison de largeur de bande spécifique de fibres de 62,5/125 µm ne fait pas partie du présent document. ^b Les câbles OM2 ne sont pas pris en charge dans les nouvelles installations dans l'ISO/IEC 11801-1:2017. ^c Historiquement, l'ISO/IEC 11801:2002 définissait également des câbles OM1 faits de fibres de 50/125 µm ayant une largeur de bande à injection saturée minimale de 200 MHz·km à 850 nm et 500 MHz·km à 1 300 nm. Cette combinaison de largeur de bande spécifique de fibres de 50/125 µm ne fait pas partie du présent document. ^d Les câbles OM1 ne sont pas pris en charge dans les nouvelles installations dans l'ISO/IEC 11801-1:2017.				

2 Références normatives

Les documents suivants sont cités dans le texte de sorte qu'ils constituent, pour tout ou partie de leur contenu, des exigences du présent document. Pour les références datées, seule l'édition citée s'applique. Pour les références non datées, la dernière édition du document de référence s'applique (y compris les éventuels amendements).

IEC 60793-1-20, *Fibres optiques – Partie 1-20: Méthodes de mesure et procédures d'essai – Géométrie de la fibre*

IEC 60793-1-21, *Fibres optiques – Partie 1-21: Méthodes de mesure et procédures d'essai – Géométrie du revêtement*

IEC 60793-1-22, *Fibres optiques – Partie 1-22: Méthodes de mesure et procédures d'essai – Mesure de la longueur*

IEC 60793-1-30, *Fibres optiques – Partie 1-30: Méthodes de mesure et procédures d'essai – Essais de sélection*

IEC 60793-1-31, *Fibres optiques – Partie 1-31: Méthodes de mesure et procédures d'essai – Résistance à la traction*

IEC 60793-1-32, *Fibres optiques – Partie 1-32: Mesures de mesure et procédures d'essai – Dénudabilité du revêtement*

IEC 60793-1-33, *Fibres optiques – Partie 1-33: Méthodes de mesure et procédures d'essai – Résistance à la corrosion sous contrainte*

IEC 60793-1-40, *Fibres optiques – Partie 1-40: Méthodes de mesure et procédures d'essai – Affaiblissement*

IEC 60793-1-41, *Fibres optiques – Partie 1-41: Méthodes de mesure et procédures d'essai – Largeur de bande*

IEC 60793-1-42, *Fibres optiques – Partie 1-42: Méthodes de mesure et procédures d'essai – Dispersion chromatique*

IEC 60793-1-43, *Optical fibres – Part 1-43: Measurement methods and test procedures – Numerical aperture measurement* (disponible en anglais seulement)

IEC 60793-1-46, *Fibres optiques – Partie 1-46: Méthodes de mesure et procédures d'essai – Contrôle des variations du facteur de transmission optique*

IEC 60793-1-47, *Fibres optiques – Partie 1-47: Méthodes de mesure et procédures d'essai – Pertes par macrocourbures*

IEC 60793-1-49, *Fibres optiques – Partie 1-49: Méthodes de mesure et procédures d'essai – Retard différentiel de mode*

IEC 60793-1-50, *Fibres optiques – Partie 1-50: Méthodes de mesure et procédures d'essai – Essais de chaleur humide (état continu)*

IEC 60793-1-51, *Fibres optiques – Partie 1-51: Méthodes de mesure et procédures d'essai – Essais de chaleur sèche (état continu)*

IEC 60793-1-52, *Fibres optiques – Partie 1-52: Méthodes de mesure et procédures d'essai – Essais de variations de température*

IEC 60793-1-53, *Fibres optiques – Partie 1-53: Méthodes de mesure et procédures d'essai – Essais d'immersion dans l'eau*

IEC 60793-2, *Fibres optiques – Partie 2: Spécifications de produits – Généralités*

IEC 61280-4-1:2009, *Procédures d'essai des sous-systèmes de télécommunication à fibres optiques – Partie 4-1: Installation câblée – Mesure de l'affaiblissement en multimodal*

3 Termes et définitions

Aucun terme n'est défini dans le présent document.

L'ISO et l'IEC tiennent à jour des bases de données terminologiques destinées à être utilisées en normalisation, consultables aux adresses suivantes:

- IEC Electropedia: disponible à l'adresse <http://www.electropedia.org/>
- ISO Online browsing platform: disponible à l'adresse <http://www.iso.org/obp>

4 Termes abrégés

CPR	coupled power ratio (rapport de puissance couplé)
DMD	differential mode delay (retard de mode différentiel)
EF	encircled flux (flux inscrit)
EMB	effective modal bandwidth (largeur de bande modale effective)
EMB _c	calculated effective modal bandwidth (largeur de bande modale effective calculée)
LAN	local area network (réseau local)
MMF	multimode fibre (fibre multimodale)
NA	numerical aperture (ouverture numérique)
OFL	overfilled launch (injection saturée)
OMB _c	overfilled launch modal bandwidth calculated from differential mode delay (largeur de bande modale à injection saturée, calculée à partir du retard de mode différentiel) – également appelée OFL _c)
PBX	private branch exchange (central téléphonique privé)
PMD	physical medium dependent (dépendant du support physique)
ROFL	radial overfilled launch (injection saturée radiale)
SAN	storage area network (réseau dédié sauvegarde)

5 Spécifications

5.1 Généralités

La fibre est constituée d'un cœur de verre avec un profil à gradient d'indice et d'une gaine de verre conformément à l'IEC 60793-2.

Le terme "verre" se réfère habituellement à des matériaux constitués d'oxydes non métalliques.

5.2 Exigences dimensionnelles

Les attributs dimensionnels et les méthodes de mesure applicables sont donnés dans le Tableau 2.

Les exigences communes à toutes les fibres de catégorie A1 sont données dans le Tableau 3.

Le Tableau 4 énumère les attributs supplémentaires qui doivent être indiqués par chaque spécification de sous-catégorie.

Tableau 2 – Attributs dimensionnels et méthodes de mesure

Attributs	Méthodes de mesure
Diamètre de la gaine	IEC 60793-1-20
Diamètre du cœur ^{a, b}	IEC 60793-1-20
Non-circularité de la gaine	IEC 60793-1-20
Non-circularité du cœur	IEC 60793-1-20
Erreur de concentricité entre le cœur et la gaine	IEC 60793-1-20
Diamètre du revêtement primaire	IEC 60793-1-21
Non-circularité du revêtement primaire	IEC 60793-1-21
Erreur de concentricité gaine-revêtement primaire	IEC 60793-1-21
Longueur de fibre	IEC 60793-1-22
^a Le diamètre du cœur est spécifié à 850 nm ± 10 nm avec une longueur de spécimen d'essai de 2,0 m ± 0,2 m et une valeur de seuil, k_{CORE} , de 0,025 pour les fibres A1, à l'exception des fibres A1-OM2b, A1-OM3b, A1-OM4b et A1-OM5b. ^b Le diamètre du cœur est spécifié à 850 nm ± 10 nm avec une longueur de spécimen d'essai de 100 m ± 5 % et une valeur de seuil, k_{CORE} , de 0,025 pour les fibres A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b.	

Tableau 3 – Exigences dimensionnelles communes aux fibres de catégorie A1

Attributs	Unité	Limites
Non-circularité du cœur	%	≤ 6
Diamètre du revêtement primaire – incolore ^a	μm	245 ± 10
Diamètre du revêtement primaire – coloré ^a	μm	250 ± 15
Erreur de concentricité gaine-revêtement primaire	μm	≤ 12,5
Longueur de fibre	km	^b
^a Les limites sur le diamètre du revêtement primaire sont plus communément utilisées dans les câbles de télécommunications. Il existe d'autres applications qui utilisent d'autres diamètres de revêtement primaire; plusieurs d'entre eux sont donnés ci-dessous. Autres diamètres nominaux et tolérances pour le revêtement primaire (μm): 400 ± 40 500 ± 50 700 ± 100 900 ± 100 ^b Les exigences de longueurs varient et il convient qu'elles fassent l'objet d'un accord entre fournisseur et client.		

Tableau 4 – Attributs dimensionnels supplémentaires exigés dans les spécifications de sous-catégories

Attributs
Diamètre de la gaine
Non-circularité de la gaine
Diamètre du cœur
Erreur de concentricité entre le cœur et la gaine

5.3 Exigences mécaniques

Les attributs mécaniques et les méthodes de mesure applicables sont donnés dans le Tableau 5.

Les exigences communes à toutes les fibres de catégorie A1 sont données dans le Tableau 6.

Tableau 5 – Attributs mécaniques et méthodes de mesure

Attributs	Méthodes d'essais
Essai d'épreuve	IEC 60793-1-30
Résistance à la traction	IEC 60793-1-31
Dénudabilité du revêtement primaire	IEC 60793-1-32
Résistance à la corrosion sous contrainte	IEC 60793-1-33

Tableau 6 – Exigences mécaniques communes aux fibres de catégorie A1

Attributs	Unité	Limites
Niveau de contrainte d'épreuve	GPa	$\geq 0,69^a$
Force de dénudage moyenne ^b	N	$1,0 \leq F_{avg} \leq 5,0$
Force de dénudage de crête ^b	N	$1,0 \leq F_{peak} \leq 8,9$
Résistance à la traction (moyenne) pour une longueur de spécimen de 0,5 m	GPa	$\geq 3,8$
Constante de résistance à la corrosion sous contrainte, n_d	-	≥ 18
^a La valeur d'essai d'épreuve de 0,69 GPa est égale à une déformation d'environ 1 % ou une force d'environ 8,8 N, pour les fibres A1-OM1 à A1-OM5. Pour la relation entre ces différentes unités, voir l'IEC TR 62048:2014, 8.4. ^b Soit la force de dénudage moyenne, soit la force de dénudage de crête, qui sont toutes les deux définies dans la procédure d'essai, peut être spécifiée par accord entre fournisseur et client.		

5.4 Exigences de transmission

Les attributs de transmission et les méthodes de mesure applicables sont donnés dans le Tableau 7.

Le Tableau 8 énumère les attributs supplémentaires qui doivent être indiqués par chaque spécification de sous-catégorie.

Tableau 7 – Attributs de transmission et méthodes de mesure

Attributs	Méthodes de mesure
Affaiblissement linéique	IEC 60793-1-40
Largeur de bande modale ^{a,b}	IEC 60793-1-41
Ouverture numérique ^{c,d}	IEC 60793-1-43
Dispersion chromatique	IEC 60793-1-42
Variations du facteur de transmission optique	IEC 60793-1-46
Pertes par macrocourbures	IEC 60793-1-47
Retard de mode différentiel ^e	IEC 60793-1-49
^a Pour la largeur de bande modale, soit l'injection saturée (OFL), soit la largeur de bande modale à injection saturée calculée à partir du retard de mode différentiel (OMB_c) peut être utilisée. L'OMB_c est la méthode d'essai de référence pour les fibres A1-OM2, A1-OM3 et A1-OM4 à 850 nm et la méthode exigée pour les fibres A1-OM5 à 850 nm et 953 nm. ^b La largeur de bande modale 850 nm est spécifiée avec une longueur de spécimen d'essai de 1 000 m ± 5 % pour les fibres A1-OM3 à A1-OM5. Pour les fibres A1-OM3, la largeur de bande modale 850 nm est mesurée à 850 nm ± 10 nm. Pour les fibres A1-OM4 et A1-OM5, la largeur de bande modale 850 nm est mesurée à 850 nm ± 2 nm. Pour les fibres A1-OM5, la largeur de bande modale est également mesurée à 953 nm ± 6 nm. ^c L'ouverture numérique est spécifiée à 850 nm ± 10 nm avec une longueur de spécimen d'essai de 2 m ± 0,2 m et une valeur de seuil, k_{NA}, de 0,05 pour les fibres A1, à l'exception des fibres A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b. ^d L'ouverture numérique est spécifiée à 850 nm ± 10 nm avec une longueur de spécimen d'essai de 100 m ± 5 % et une valeur de seuil, k_{NA}, de 0,05 pour les fibres A1-OM2b, A1-OM3b, A1-OM4b et A1-OM5b. ^e Le retard de mode différentiel est spécifié avec une longueur de spécimen d'essai de 1 000 m ± 5 % pour les fibres A1-OM3, A1-OM4 et A1-OM5. Pour les fibres A1-OM3, le retard de mode différentiel est mesuré à 850 nm ± 10 nm. Pour les fibres A1-OM4 et A1-OM5, le retard de mode différentiel est mesuré à 850 nm ± 2 nm. Pour les fibres A1-OM5, le retard de mode différentiel est également mesuré à 953 nm ± 6 nm.	

La conformité à la spécification relative à la dispersion chromatique peut être assurée par la conformité à la spécification relative à l'ouverture numérique pour les fibres A1.

Tableau 8 – Attributs de transmission supplémentaires exigés dans les spécifications de sous-catégories

Attributs
Affaiblissement linéique
Largeur de bande modale
Dispersion chromatique
Ouverture numérique
Pertes par macrocourbures

Pour l'affaiblissement linéique et la largeur de bande modale, les spécifications de sous-catégories peuvent contenir des plages de valeurs qui peuvent être choisies par spécification au lieu des limites fixées. Dans ce cas, les valeurs réelles de l'affaiblissement linéique maximal et de la largeur de bande modale minimale, à 850 nm et à 1 300 nm (ou à une seule de ces longueurs d'onde) doivent faire l'objet d'un accord entre fournisseur et client. Dans un but commercial, la largeur de bande modale est normalisée linéairement à 1 km.

À des fins de recommandations, l'Annexe H montre plusieurs applications normalisées prises en charge par les fibres A1, et l'Annexe I des capacités de transmissions pour ces mêmes fibres.