

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Electric and optical fibre cables – Test methods for non-metallic materials –
Part 402: Miscellaneous tests – Water absorption tests**

**Câbles électriques et à fibres optiques – Méthodes d'essai pour les matériaux
non-métalliques –
Partie 402: Essais divers – Essais d'absorption d'eau**

IECNORM.COM : Click to view the full PDF of IEC 60811-402:2012



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2012 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Useful links:

IEC publications search - www.iec.ch/searchpub

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Liens utiles:

Recherche de publications CEI - www.iec.ch/searchpub

La recherche avancée vous permet de trouver des publications CEI en utilisant différents critères (numéro de référence, texte, comité d'études,...).

Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Just Published CEI - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications de la CEI. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (VEI) en ligne.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Electric and optical fibre cables – Test methods for non-metallic materials –
Part 402: Miscellaneous tests – Water absorption tests**

**Câbles électriques et à fibres optiques – Méthodes d'essai pour les matériaux
non-métalliques –
Partie 402: Essais divers – Essais d'absorption d'eau**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

K

ICS 29.035.01; 29.060.20

ISBN 978-2-88912-962-1

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Test method	6
4.1 General.....	6
4.2 Pre-conditioning	6
4.3 Electrical water absorption test.....	6
4.3.1 Apparatus.....	6
4.3.2 Preparation of test pieces	7
4.3.3 Test procedure	7
4.3.4 Evaluation of results	7
4.4 Gravimetric water absorption test	7
4.4.1 Preparation of test piece.....	7
4.4.2 Testing procedure.....	8
4.4.3 Expression of results	9
5 Test report.....	9
Bibliography.....	10
Table 1 – d.c. test voltages	7

IECNORM.COM : Click to view the full PDF of IEC 60811-402:2012

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**ELECTRIC AND OPTICAL FIBRE CABLES –
TEST METHODS FOR NON-METALLIC MATERIALS –****Part 402: Miscellaneous tests –
Water absorption tests**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60811-402 has been prepared by IEC technical committee 20: Electric cables.

This Part 402 of IEC 60811 cancels and replaces Clause 9 of IEC 60811-1-3:1993, which is withdrawn. Full details of the replacements are shown in Annex A of IEC 60811-100:2012.

There are no specific technical changes with respect to the previous edition, but see the Foreword to IEC 60811-100:2012.

The text of this standard is based on the following documents:

FDIS	Report on voting
20/1286/FDIS	20/1335/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

This part of IEC 60811 shall be used in conjunction with IEC 60811-100.

A list of all the parts in the IEC 60811 series, published under the general title *Electric and optical fibre cables – Test methods for non-metallic materials*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IECNORM.COM : Click to view the full PDF of IEC 60811-402:2012

INTRODUCTION

The IEC 60811 series specifies the test methods to be used for testing non-metallic materials of all types of cables. These test methods are intended to be referenced in standards for cable construction and for cable materials.

NOTE 1 Non-metallic materials are typically used for insulating, sheathing, bedding, filling or taping within cables.

NOTE 2 These test methods are accepted as basic and fundamental and have been developed and used over many years principally for the materials in all energy cables. They have also been widely accepted and used for other cables, in particular optical fibre cables, communication and control cables and cables for ships and offshore applications.

IECNORM.COM : Click to view the full PDF of IEC 60811-402:2012

ELECTRIC AND OPTICAL FIBRE CABLES – TEST METHODS FOR NON-METALLIC MATERIALS –

Part 402: Miscellaneous tests – Water absorption tests

1 Scope

This Part 402 of IEC 60811 describes water absorption tests which typically apply to cross-linked and thermoplastic compounds used for insulating and sheathing materials.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60811-100:2012, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 100: General*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60811-100 apply.

4 Test method

4.1 General

This part of IEC 60811 shall be used in conjunction with IEC 60811-100.

Unless otherwise specified, tests shall be carried out at room temperature.

4.2 Pre-conditioning

All the tests shall be carried out not less than 16 h after the extrusion or cross-linking, if any, of the insulating or sheathing compounds.

If the test is carried out at room temperature, the test pieces shall be kept for at least 3 h at a temperature of $(23 \pm 5) ^\circ\text{C}$.

4.3 Electrical water absorption test

4.3.1 Apparatus

The following apparatus shall be used:

- a) a.c and d.c voltage sources;
- b) voltmeter;
- c) water bath with heating equipment.

4.3.2 Preparation of test pieces

The cores to be tested shall be removed from a sample of finished cable approximately 3 m long. Care shall be taken to avoid damage to the insulation during removal of the cores.

4.3.3 Test procedure

a) Pre-test

The cores shall be immersed in a water bath in which the water has been heated to the temperature specified in the standard for the type of cable.

The ends of the cores shall protrude sufficiently above the water level to prevent damage due to leakage current along the surface of the cores when the required voltage is applied between the conductors and the water.

After the cores have been immersed in the water for 1 h, an a.c. voltage of 4 kV shall be applied between the conductors and the water for 5 min. If any sample of core breaks down, it shall be removed from the water bath and not used in the main test specified in item b) below. However, the test shall be repeated not more than twice, by taking another sample of the same core, which shall be subjected to the same pre-test.

The object of the pre-test is to ensure that only undamaged cores are used for the main test.

b) Main test

Cores which are satisfactory on the pre-test shall remain in the water bath with the water still maintained at the temperature specified in the relevant standard.

A d.c. voltage in accordance with Table 1 below shall be applied between the conductors and the water for the time specified in the standard for the type of cable, the negative pole being connected to the conductor of each test piece.

Table 1 – DC test voltages

Thickness, t , of insulation specified Mean value mm	DC voltage V
0,8 and 0,9	800
1,0 and 1,2	1 000
1,2 < t ≤ 1,6	1 400
1,6 < t ≤ 2,0	2 000
2,0 < t	2 500

4.3.4 Evaluation of results

No breakdown shall occur.

4.4 Gravimetric water absorption test

4.4.1 Preparation of test piece

- a) For cables with conductors of nominal cross-sectional area equal to or less than 25 mm² and rated voltage up to and including 0,6/1 kV:

Each test piece shall be a piece of core approximately 300 mm in length.

- b) For all other cables:

Slices of 0,6 mm to 0,9 mm thickness shall be ground or cut with surfaces approximately parallel and free from roughness.

Test pieces 80 mm to 100 mm long and 4 mm to 5 mm wide shall be punched out of the slices.

- c) Two test pieces shall be prepared from each core to be tested.

4.4.2 Testing procedure

- a) For test pieces as in item a) of 4.4.1:

Clean the surface of the test piece by rubbing with a filter paper moistened with water.

Allow the test piece to dry at $(70 \pm 2) ^\circ\text{C}$ to constant weight. It may also be allowed to dry by placing it for 24 h in a low-pressure oven at not more than 6,6 mbar and $(70 \pm 2) ^\circ\text{C}$. Cool the sample in a desiccator.

Weigh the test piece to within 0,1 mg. Let M1 be the mass in milligrams.

Wind the test piece around a mandrel, whose diameter is between six and eight times that of the test piece, so as to bend it to a U shape and force the ends through apertures bored in the cover of a suitable glass vessel. Only the two test pieces of the same core should be in the glass vessel.

Adjust the position of the test piece such that 250 mm of its length is immersed when the vessel is filled with water up to the edge of the fitted cover.

Use preboiled distilled or deionized water.

Allow the test piece to remain at the temperature and for the time specified in the product standard. If the time is not specified, it shall be 14 days for specified thicknesses up to 1,0 mm, 21 days for thicknesses between 1,1 mm and 1,5 mm, and 28 days for thicknesses above 1,5 mm. If the temperature is not specified, it shall be 5 K below the maximum conductor temperature, but not exceeding $90 ^\circ\text{C}$. The water level shall be maintained up to the inside surface of the cover.

The water is then allowed to cool to ambient temperature. Remove the test piece and shake off any drops of water adhering to it, wipe lightly with a filter paper and weigh to the nearest milligram within 2 min to 3 min of its being removed from the water. Let M2 be the new mass in milligrams.

Finally, dry out the test piece under the same conditions as were used before immersion, i.e. using whichever of the two alternative methods described above had been used before the first weighing. Let M3 be the final mass in milligrams.

- b) For test pieces as in item b) of 4.4.1:

The test pieces, with thoroughly cleaned surfaces, shall be heated at $(70 \pm 2) ^\circ\text{C}$ under vacuum (residual pressure close to 1 mbar) for 72 h. Materials of substantially different compositions shall not be treated in the same cell or oven at the same time.

After this treatment, the test pieces shall be cooled for 1 h in a desiccator and weighed to the nearest 0,1 mg (mass M1).

The test pieces shall then be immersed in deionized (or distilled) water at the temperature and for the time specified in the standard for the type of cable. If the temperature is not specified, it shall be 5 K below the maximum conductor temperature, but not greater than $90 ^\circ\text{C}$. Each test piece shall be completely immersed in a separate glass to be equipped with a condenser, or in a beaker covered with a glass lid.

If a condenser is used, its upper part shall be covered with aluminium foil to prevent any contamination.

After the time specified in the standard for the type of cable, or after 14 days if the time is not specified in the cable standard, the test pieces shall be transferred into deionized (or distilled) water at room temperature and kept there to cool. Each test piece shall then be removed from the water, shaken to detach any adherent drops, dried with special filter

paper leaving no fibres, and weighed to the nearest 0,1 mg (mass M2). Finally the test piece shall be treated under the same conditions as were used before immersion. Let M3 be the final mass in milligrams.

4.4.3 Expression of results

The mass variation in milligrams shall be calculated from one of the following formulae:

- a) if the final mass M3 is less than M1:

$$(M2 - M3)/A$$

- b) if the final mass M3 is greater than M1:

$$(M2 - M1)/A$$

where A is, for test pieces as in item a) of 4.4.1, the surface area in square centimetres of the 250 mm long immersed portion of sample, and, for test pieces as in item b) of 4.4.1, the total surface area of the immersed test piece in square centimetres.

The mean value of the mass variation of the two test pieces shall be recorded as the value for the core.

5 Test report

The test report shall be in accordance with that given in IEC 60811-100.

Bibliography

IEC 60811-1-3:1993, *Insulating and sheathing materials of electric cables – Common test methods – Part 1: General application – Section 3: Methods for determining the density - Water absorption tests - Shrinkage test*
(withdrawn)

IECNORM.COM : Click to view the full PDF of IEC 60811-402:2012

IECNORM.COM : Click to view the full PDF of IEC 60811-402:2012

SOMMAIRE

AVANT-PROPOS	13
INTRODUCTION.....	15
1 Domaine d'application	16
2 Références normatives	16
3 Termes et définitions	16
4 Méthode d'essai	16
4.1 Généralités.....	16
4.2 Préconditionnement.....	16
4.3 Essai électrique d'absorption d'eau	16
4.3.1 Appareillage	16
4.3.2 Préparation des éprouvettes	17
4.3.3 Mode opératoire	17
4.3.4 Evaluation des résultats	18
4.4 Méthode pondérale pour l'absorption d'eau	18
4.4.1 Préparation des éprouvettes	18
4.4.2 Mode opératoire	18
4.4.3 Expression des résultats.....	19
5 Rapport d'essai	19
Bibliographie.....	20
Tableau 1 – Tensions continues d'essai.....	17

IECNORM.COM : Click to view the full PDF of IEC 60811-402:2012

COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

**CÂBLES ÉLECTRIQUES ET À FIBRES OPTIQUES –
MÉTHODES D'ESSAI POUR LES MATÉRIAUX NON-MÉTALLIQUES –****Partie 402: Essais divers –
Essais d'absorption d'eau**

AVANT-PROPOS

- 1) La Commission Electrotechnique Internationale (CEI) est une organisation mondiale de normalisation composée de l'ensemble des comités électrotechniques nationaux (Comités nationaux de la CEI). La CEI a pour objet de favoriser la coopération internationale pour toutes les questions de normalisation dans les domaines de l'électricité et de l'électronique. A cet effet, la CEI – entre autres activités – publie des Normes internationales, des Spécifications techniques, des Rapports techniques, des Spécifications accessibles au public (PAS) et des Guides (ci-après dénommés "Publication(s) de la CEI"). Leur élaboration est confiée à des comités d'études, aux travaux desquels tout Comité national intéressé par le sujet traité peut participer. Les organisations internationales, gouvernementales et non gouvernementales, en liaison avec la CEI, participent également aux travaux. La CEI collabore étroitement avec l'Organisation Internationale de Normalisation (ISO), selon des conditions fixées par accord entre les deux organisations.
- 2) Les décisions ou accords officiels de la CEI concernant les questions techniques représentent, dans la mesure du possible, un accord international sur les sujets étudiés, étant donné que les Comités nationaux de la CEI intéressés sont représentés dans chaque comité d'études.
- 3) Les Publications de la CEI se présentent sous la forme de recommandations internationales et sont agréées comme telles par les Comités nationaux de la CEI. Tous les efforts raisonnables sont entrepris afin que la CEI s'assure de l'exactitude du contenu technique de ses publications; la CEI ne peut pas être tenue responsable de l'éventuelle mauvaise utilisation ou interprétation qui en est faite par un quelconque utilisateur final.
- 4) Dans le but d'encourager l'uniformité internationale, les Comités nationaux de la CEI s'engagent, dans toute la mesure possible, à appliquer de façon transparente les Publications de la CEI dans leurs publications nationales et régionales. Toutes divergences entre toutes Publications de la CEI et toutes publications nationales ou régionales correspondantes doivent être indiquées en termes clairs dans ces dernières.
- 5) La CEI elle-même ne fournit aucune attestation de conformité. Des organismes de certification indépendants fournissent des services d'évaluation de conformité et, dans certains secteurs, accèdent aux marques de conformité de la CEI. La CEI n'est responsable d'aucun des services effectués par les organismes de certification indépendants.
- 6) Tous les utilisateurs doivent s'assurer qu'ils sont en possession de la dernière édition de cette publication.
- 7) Aucune responsabilité ne doit être imputée à la CEI, à ses administrateurs, employés, auxiliaires ou mandataires, y compris ses experts particuliers et les membres de ses comités d'études et des Comités nationaux de la CEI, pour tout préjudice causé en cas de dommages corporels et matériels, ou de tout autre dommage de quelque nature que ce soit, directe ou indirecte, ou pour supporter les coûts (y compris les frais de justice) et les dépenses découlant de la publication ou de l'utilisation de cette Publication de la CEI ou de toute autre Publication de la CEI, ou au crédit qui lui est accordé.
- 8) L'attention est attirée sur les références normatives citées dans cette publication. L'utilisation de publications référencées est obligatoire pour une application correcte de la présente publication.
- 9) L'attention est attirée sur le fait que certains des éléments de la présente Publication de la CEI peuvent faire l'objet de droits de brevet. La CEI ne saurait être tenue pour responsable de ne pas avoir identifié de tels droits de brevets et de ne pas avoir signalé leur existence.

La Norme internationale CEI 60811-402 a été établie par le comité d'études 20 de la CEI: Câbles électriques.

La présente Partie 402 de la CEI 60811 annule et remplace l'Article 9 de la CEI 60811-1-3:1993, qui est supprimée. L'ensemble des informations relatives aux remplacements figure dans l'Annexe A de la CEI 60811-100:2012.

Aucune modification technique n'a été effectuée par rapport à l'édition précédente; voir cependant l'avant-propos de la CEI 60811-100:2012.

Le texte de cette norme est issu des documents suivants:

FDIS	Rapport de vote
20/1286/FDIS	20/1335/RVD

Le rapport de vote indiqué dans le tableau ci-dessus donne toute information sur le vote ayant abouti à l'approbation de cette norme.

Cette publication a été rédigée selon les Directives ISO/CEI, Partie 2.

La présente partie de la CEI 60811 doit être utilisée conjointement avec la CEI 60811-100.

Une liste de toutes les parties de la série CEI 60811, publiées sous le titre général *Câbles électriques et à fibres optiques – Méthodes d'essai pour les matériaux non-métalliques*, peut être consultée sur le site web de la CEI.

Le comité a décidé que le contenu de cette publication ne sera pas modifié avant la date de stabilité indiquée sur le site web de la CEI sous "<http://webstore.iec.ch>" dans les données relatives à la publication recherchée. A cette date, la publication sera

- reconduite,
- supprimée,
- remplacée par une édition révisée, ou
- amendée.

IECNORM.COM : Click to view the full PDF of IEC 60811-402:2012

INTRODUCTION

La série CEI 60811 précise les méthodes à employer pour les essais des matériaux non-métalliques sur tous les types de câbles. Ces méthodes d'essai seront citées en référence dans les normes relatives à la construction des câbles et aux matériaux des câbles.

NOTE 1 Les matériaux non-métalliques sont généralement utilisés pour l'isolation, le gainage, le matelassage, le remplissage ou le rubanage des câbles.

NOTE 2 Ces méthodes d'essai sont reconnues comme fondamentales; elles ont été développées et utilisées durant de nombreuses années, principalement pour les matériaux dans tous les câbles de distribution d'énergie. Elles ont aussi été largement reconnues et utilisées pour d'autres types de câbles, en particulier les câbles à fibres optiques, les câbles de communication et de commande, ainsi que les câbles utilisés à bord des navires et dans les applications offshore.

IECNORM.COM : Click to view the full PDF of IEC 60811-402:2012

CÂBLES ÉLECTRIQUES ET À FIBRES OPTIQUES – MÉTHODES D'ESSAI POUR LES MATÉRIAUX NON-MÉTALLIQUES –

Partie 402: Essais divers – Essais d'absorption d'eau

1 Domaine d'application

La présente Partie 402 de la CEI 60811 décrit les essais d'absorption d'eau, généralement applicables aux mélanges réticulés et thermoplastiques utilisés dans les matériaux d'isolation et de gainage.

2 Références normatives

Les documents suivants sont cités en référence de manière normative, en intégralité ou en partie, dans le présent document et sont indispensables pour son application. Pour les références datées, seule l'édition citée s'applique. Pour les références non datées, la dernière édition du document de référence s'applique (y compris les éventuels amendements).

CEI 60811-100:2012, *Câbles électriques et à fibres optiques – Méthodes d'essai pour les matériaux non-métalliques – Partie 100: Généralités*

3 Termes et définitions

Pour les besoins du présent document, les termes et définitions donnés dans la CEI 60811-100 s'appliquent.

4 Méthode d'essai

4.1 Généralités

La présente partie de la CEI 60811 doit être utilisée conjointement avec la CEI 60811-100.

Les essais doivent être effectués à la température ambiante, sauf spécification contraire.

4.2 Preconditionnement

Tous les essais doivent être réalisés au moins 16 h après l'extrusion ou la réticulation, s'il y a lieu, des mélanges d'isolation ou de gainage.

Si l'essai est effectué à la température ambiante, les éprouvettes doivent être conservées pendant au moins 3 h à une température de $(23 \pm 5) ^\circ\text{C}$.

4.3 Essai électrique d'absorption d'eau

4.3.1 Appareillage

Les appareils suivants doivent être utilisés:

- a) des sources de tension alternative et continue;
- b) un voltmètre;

c) un bain avec un dispositif de chauffage.

4.3.2 Préparation des éprouvettes

Les conducteurs à soumettre aux essais doivent être prélevés à partir d'un échantillon de câble fini d'environ 3 m de long. On doit prendre toutes les précautions nécessaires pour ne pas endommager l'isolant au cours du retrait des conducteurs.

4.3.3 Mode opératoire

a) Essai préliminaire

Les conducteurs doivent être immergés dans un bain, dont l'eau a été chauffée à la température spécifiée dans la norme applicable au type de câble considéré.

Les extrémités de chaque conducteur doivent émerger suffisamment au-dessus du niveau de l'eau pour éviter tout dommage dû au courant de fuite le long du conducteur, lorsqu'on applique la tension prescrite entre l'âme et l'eau.

Après immersion des conducteurs dans l'eau pendant 1 h, on doit appliquer, pendant 5 min, une tension alternative de 4 kV entre les âmes et l'eau. Si un échantillon de conducteur claque, il doit être enlevé du bain et ne doit pas être utilisé pour l'essai principal spécifié au point b) ci-dessous. Néanmoins, on ne doit pas répéter l'essai plus de deux fois, en prenant un autre échantillon prélevé sur le même conducteur, qui doit être soumis au même essai préliminaire.

L'objet de cet essai préliminaire est de s'assurer qu'aucun conducteur endommagé n'est utilisé pour l'essai principal.

b) Essai principal

Les conducteurs qui ont satisfait à l'essai préliminaire doivent rester dans le bain, l'eau étant toujours maintenue à la température spécifiée dans la norme applicable.

On doit appliquer une tension continue dont la valeur est spécifiée dans le Tableau 1 ci-dessous, entre les âmes et l'eau pendant la durée spécifiée dans la norme particulière au type de câble considéré, le pôle négatif étant relié à l'âme de chaque éprouvette.

Tableau 1 – Tensions continues d'essai

Épaisseur, t , de l'isolant spécifiée Valeur moyenne mm	Tension continue V
0,8 et 0,9	800
1,0 et 1,2	1 000
1,2 $< t \leq 1,6$	1 400
1,6 $< t \leq 2,0$	2 000
2,0 $< t$	2 500