

INTERNATIONAL STANDARD



**Multicore and symmetrical pair/quad cables for digital communications –
Part 11: Symmetrical single pair cables with transmission characteristics
up to ~~600 MHz~~ 1,25 GHz – Horizontal floor wiring – Sectional specification**

IECNORM.COM : Click to view the full PDF of IEC 61156-11:2023 RLV



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2023 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IECNORM.COM : Click to view the full PDF of IEC 61558-11:2023 PLV

INTERNATIONAL STANDARD



**Multicore and symmetrical pair/quad cables for digital communications –
Part 11: Symmetrical single pair cables with transmission characteristics
up to ~~600 MHz~~ 1,25 GHz – Horizontal floor wiring – Sectional specification**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 33.120.20

ISBN 978-2-8322-6984-8

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	5
1 Scope	7
2 Normative references	7
3 Terms and definitions	8
4 Installation considerations	8
4.1 General remarks	8
4.2 Bending radius of installed cable	8
4.3 Climatic conditions	8
5 Materials and cable construction	9
5.1 General remarks	9
5.2 Cable construction	9
5.3 Conductor	9
5.4 Insulation	9
5.5 Cable element	9
5.6 Screening of the cable element	9
5.7 Cable make-up	9
5.8 Screening of the cable core	9
5.9 Sheath	10
5.10 Identification	10
5.11 Finished cable	10
6 Characteristics and requirements	10
6.1 General remarks	10
6.2 Electrical characteristics and tests	11
6.2.1 Conductor resistance	11
6.2.2 Resistance unbalance	11
6.2.3 Dielectric strength	11
6.2.4 Insulation resistance	11
6.2.5 Mutual capacitance	11
6.2.6 Capacitance unbalance	11
6.2.7 Transfer impedance	11
6.2.8 Coupling attenuation and low frequency coupling attenuation	12
6.2.9 Current-carrying capacity	13
6.3 Transmission characteristics	13
6.3.1 Velocity of propagation (phase velocity)	13
6.3.2 Phase delay and differential delay (delay skew)	13
6.3.3 Attenuation (α)	13
6.3.4 Unbalance attenuation (TCL and EL TCTL)	14
6.3.5 Alien (exogenous) near-end crosstalk (PS ANEXT)	16
6.3.6 Alien (exogenous) far-end crosstalk (PS AACR-F)	16
6.3.7 Alien (exogenous) crosstalk of bundled cables	17
6.3.8 Impedance	17
6.3.9 Return loss (RL)	17
6.4 Mechanical and dimensional characteristics and requirements	17
6.4.1 Dimensional requirements	17
6.4.2 Elongation at break of the conductor	18
6.4.3 Tensile strength of the insulation	18

6.4.4	Elongation at break of the insulation	18
6.4.5	Adhesion of the insulation to the conductor.....	18
6.4.6	Elongation at break of the sheath	18
6.4.7	Tensile strength of the sheath.....	18
6.4.8	Crush test of the cable.....	18
6.4.9	Impact test of the cable	18
6.4.10	Bending under tension	18
6.4.11	Repeated bending of the cable	18
6.4.12	Tensile performance of the cable.....	18
6.4.13	Shock-test requirements of the cable	18
6.4.14	Bump-test requirements of the cable	18
6.4.15	Vibration-test requirements of a cable	19
6.5	Environmental characteristics	19
6.5.1	Shrinkage of the insulation	19
6.5.2	Wrapping test of the insulation after thermal ageing	19
6.5.3	Bending test of insulation at low temperature.....	19
6.5.4	Elongation at break of the sheath after ageing	19
6.5.5	Tensile strength of the sheath after ageing	19
6.5.6	Sheath pressure test at high temperature	19
6.5.7	Cold bend test of the cable	19
6.5.8	Heat shock test.....	19
6.5.9	Damp heat steady state	19
6.5.10	Solar radiation	19
6.5.11	Solvents and contaminating fluids.....	19
6.5.12	Salt mist and sulphur dioxide.....	20
6.5.13	Water immersion	20
6.5.14	Hygroscopicity	20
6.5.15	Wicking.....	20
6.5.16	Flame propagation characteristics of a single cable	20
6.5.17	Flame propagation characteristics of bunched cables	20
6.5.18	Halogen gas evolution	20
6.5.19	Smoke generation.....	20
6.5.20	Toxic gas emission	20
6.5.21	Integrated fire test method for cables in environmental air handling spaces.....	21
7	Bundled cable requirements	21
7.1	General.....	21
7.2	Single pairs sharing one sheath	21
7.2.1	General	21
7.2.2	Near-end crosstalk (NEXT)	21
7.2.3	Attenuation to crosstalk ratio far-end (PS ACR-F).....	22
Annex A (informative)	Blank detail specification	23
Annex B (informative)	Background information for coupling attenuation and low frequency coupling attenuation requirements	28
Bibliography		29
Table 1 – Transfer impedance		12
Table 2 – Coupling attenuation		12

Table 3 – Low frequency coupling attenuation	13
Table 4 – Attenuation equation constants	14
Table 5 – TCL requirements.....	15
Table 6 – EL TCTL requirements	15
Table 7 – PS ANEXT requirements	16
Table 8 – PS AACR-F requirements.....	16
Table 9 – RL requirements.....	17
Table 10 – NEXT and PS NEXT requirements.....	21
Table 11 – ACR-F and PS ACR-F requirements	22

IECNORM.COM : Click to view the full PDF of IEC 61156-11:2023 RLV

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**MULTICORE AND SYMMETRICAL PAIR/QUAD CABLES
FOR DIGITAL COMMUNICATIONS –****Part 11: Symmetrical single pair cables with transmission characteristics
up to ~~600 MHz~~ 1,25 GHz – Horizontal floor wiring – Sectional specification**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition IEC 61156-11:2019. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

IEC 61156-11 has been prepared by subcommittee 46C: Wires and symmetric cables, of IEC technical committee 46: Cables, wires, waveguides, RF connectors, RF and microwave passive components and accessories. It is an International Standard.

This second edition cancels and replaces the first edition published in 2019. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) additional cable type in support of T1-C generic single pair cabling up to 1,25 GHz;
- b) introduction of low frequency coupling attenuation as an integral parameter describing screening efficiency at frequencies below 30 MHz.

The text of this International Standard is based on the following documents:

Draft	Report on voting
46C/1254/FDIS	46C/1258/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 61156 series, published under the general title *Multicore and symmetrical pair/quad cables for digital communications*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

MULTICORE AND SYMMETRICAL PAIR/QUAD CABLES FOR DIGITAL COMMUNICATIONS –

Part 11: Symmetrical single pair cables with transmission characteristics up to ~~600 MHz~~ 1,25 GHz – Horizontal floor wiring – Sectional specification

1 Scope

~~This part of IEC 61156 describes cables intended to be used for transmission of 1 Gbps over a single twisted pair for office, home and industrial application. An example of existing application is 1000BASE-T1, see ISO/IEC TR 11801-9906¹. The transmission characteristics of these cables are specified up to a frequency of 600 MHz and at a temperature of 20 °C. The cable type recognised is intended to be used for shielded channels with a nominal length of 40 m. Possible designs are U/FTP, X/UTP and X/FTP, where X stands for F, S or SF. This part of IEC 61156 describes cables intended to be used for single balanced pair (office, home, industrial) applications according to ISO/IEC 11801-1. An example of existing application is 1000BASE-T1, see ISO/IEC TR 11801-9906. The transmission characteristics of these cables are specified up to a frequency of 1,25 GHz and at a temperature of 20 °C. The T1-C type cable is specified up to 600 MHz, the T1-D type cable up to 1,25 GHz. Depending on the MICE environment and the installation conditions either unscreened or screened cables can be used. A blank detail specification can be found in Annex A.~~

These cables can comprise more than one pair in the event that several systems are operated in parallel. In this case, refer to Clause 7.

The cables covered by this document are intended to operate with voltages and currents normally encountered in communication systems. While these cables are not intended to be used in conjunction with low impedance sources, for example the electric power supplies of public utility mains, they are intended to be used to support the delivery of low-voltage remote powering applications.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60708:2005, *Low-frequency cables with polyolefin insulation and moisture barrier polyolefin sheath*

IEC 61156-1:2007, *Multicore and symmetrical pair/quad cables for digital communications – Part 1: Generic specification*

~~IEC 61156-1:2007/AMD1:2009²~~

¹ ~~Under consideration.~~

² ~~A consolidated version of this publication exists, comprising IEC 61156-1:2007 and IEC 61156-1:2007/AMD1:2009.~~

IEC 61156-5:~~2009~~, *Multicore and symmetrical pair/quad cables for digital communications – Part 5: Symmetrical pair/quad cables with transmission characteristics up to 1 000 MHz – Horizontal floor wiring – Sectional specification*

IEC 62153-4-3:~~2013~~, *Metallic communication cable test methods – Part 4-3: Electromagnetic compatibility (EMC) – Surface transfer impedance – Triaxial method*

IEC 62153-4-5:~~2006~~, *Metallic communication cables test methods – Part 4-5: Electromagnetic compatibility (EMC) – ~~Coupling Screening~~ or ~~screening~~ coupling attenuation – Absorbing clamp method*

IEC 62153-4-9:2018, *Metallic communication cable test methods – Part 4-9: Electromagnetic compatibility (EMC) – Coupling attenuation of screened balanced cables, triaxial method*
IEC 62153-4-9:2018/AMD1:2020

ISO/IEC TS 29125:~~2017~~, *Information technology – Telecommunications cabling requirements for remote powering of terminal equipment*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 61156-1:~~2007~~ and in ~~IEC 61156-1:2007/AMD1:2009~~ apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 Installation considerations

4.1 General remarks

Installation area considerations are defined in IEC 61156-1:~~2007~~. Other areas may be considered.

4.2 Bending radius of installed cable

The minimum bending radius of the cable shall be equal to or less than four times the outside diameter of the cable unless otherwise specified.

4.3 Climatic conditions

Under static conditions, the cable shall operate at least in the temperature range of the environment from –20 °C to +60 °C.

The attenuation increase due to the elevated operating temperature (temperature of the environment) is described in 6.3.3.2.

In the case of application of remote powering, the maximum temperature of the conductor shall not exceed the maximum operation temperature under static conditions (60 °C) in order to maintain the integrity of the dielectric material performance which is aligned to the environmental temperature range.

Extended temperature ranges are permitted and ~~may~~ shall be specified in the relevant detail specification.

5 Materials and cable construction

5.1 General remarks

For the purposes of this document, the requirements of IEC 61156-5:~~2009~~ apply.

The choice of materials and cable construction shall be suitable for the intended application and installation of the cable and in line with the requirements of IEC 61156-1. ~~Particular care shall be taken to meet~~ Ensure that any requirements for EMC and fire performance (such as burning properties, smoke generation, evolution of halogen gas) are met. Regional regulations can apply as well.

5.2 Cable construction

The cable construction shall be in accordance with the details and dimensions given in the relevant detail specification.

5.3 Conductor

The conductor shall be a solid annealed copper conductor in accordance with the requirements of IEC 61156-1:~~2007~~ and should have a nominal diameter between 0,4 mm and 0,65 mm. A conductor diameter of up to ~~1,0~~ 1,05 mm may be used.

NOTE The conductor dimensions seen in practice are wider than those dimensions that correspond to the resistance requirements according to 6.2.1 and are therefore relevant for the design of the contact terminals of connecting hardware.

5.4 Insulation

The conductor shall be insulated with a suitable material. Examples of suitable materials are:

- polyolefin;
- fluoropolymer;
- low-smoke ~~zero~~-halogen-free thermoplastic material.

The colour code shall be in accordance with IEC 60708 if not specified differently in the relevant detail specification.

5.5 Cable element

The cable element shall be a ~~pair and shall be~~ balanced twisted pair. The entire cable may comprise more than one cable element, see 6.3.5 and Clause 7.

5.6 Screening of the cable element

The screen of the cable element (if exists) shall be in accordance with the requirements of IEC 61156-1:~~2007~~.

5.7 Cable make-up

Fillers or spacers may be used in the cable elements and to separate cable elements. The cable elements and their screens, if they are screened, may be covered by an intermediate jacket. This jacket shall be in accordance with 5.9. The core of the cable may be wrapped with a protective layer of non-hygroscopic and non-wicking material.

5.8 Screening of the cable core

For screened cables, a screen for the cable core shall be provided. The screen shall be in accordance with the requirements of IEC 61156-1:~~2007~~.

5.9 Sheath

The sheath material shall consist of a suitable material. Examples of suitable materials are:

- polyolefin;
- PVC;
- fluoropolymer;
- low-smoke ~~zero~~-halogen-free thermoplastic material.

The sheath shall be continuous, having a thickness as uniform as possible. A non-metallic ripcord may be provided. When provided, the ripcord shall be non-hygroscopic and non-wicking.

The colour of the sheath is not specified but it should be specified in the relevant detail specification.

5.10 Identification

Each length of cable shall be identified as to the supplier and, when required, a traceability code, using one or a combination of the following methods:

- appropriately coloured threads or tapes;
- with a printed tape;
- printing on the cable core wrapping;
- marking on the sheath.

Additional markings, such as length marking, are permitted. If used, such markings shall refer to this document.

5.11 Finished cable

The finished cable shall be adequately protected for storage and shipment.

6 Characteristics and requirements

6.1 General remarks

Clause 6 lists the characteristics and minimum requirements of a cable complying with this document. Test methods shall be in accordance with the requirements of IEC 61156-1:2007 and IEC 61156-1:2007/AMD1:2009, except for the length of the cable under test which shall be as specified in Clause 6.

The computed requirements in dB, rounded to one decimal place, shall be used to determine compliance.

The tests for electrical characteristics in accordance with 6.2 shall be carried out on a cable length of not less than 100 m, unless otherwise specified.

The tests for transmission characteristics in accordance with 6.3 shall be carried out on a cable length of 100 m, unless otherwise specified. For T1-D type cables a length of 50 m may be used to improve accuracy at high frequencies.

For measurements over a wide frequency range as required for T1-D type cable, a balun-less measurement technique is recommended, see IEC TR 61156-1-2³.

6.2 Electrical characteristics and tests

6.2.1 Conductor resistance

The maximum conductor resistance at or corrected to 20 °C shall not exceed ~~145~~ 72,5 Ω/km.

6.2.2 Resistance unbalance

6.2.2.1 Resistance unbalance within a pair

The resistance unbalance shall not exceed 2,0 %.

6.2.2.2 Resistance unbalance between pairs

If applicable, for example in the case of bundled cables (see Clause 7), the pair-to-pair resistance unbalance shall not exceed 5,0 %.

6.2.3 Dielectric strength

There shall be no failures when a test is performed on a conductor/conductor and, where screens are present, on a conductor/screen with 1,0 kV DC for 1 min or, alternatively, with 2,5 kV DC for 2 s. An AC voltage may be used. The AC voltage levels in these cases shall be 0,7 kV AC for 1 min or alternatively 1,7 kV AC for 2 s.

6.2.4 Insulation resistance

The test shall be performed on:

- conductor/conductor;
- conductor/screen (if exists).

The minimum insulation resistance at or corrected to 20 °C shall be not less than ~~5 GΩ·km~~ 5 000 MΩ·km when tested immediately after the dielectric strength test.

6.2.5 Mutual capacitance

The mutual capacitance is not specified but may be indicated in the relevant detail specification.

6.2.6 Capacitance unbalance

The maximum capacitance unbalance pair to ground shall not exceed 1 200 pF/km at a frequency of 800 Hz or 1 000 Hz.

6.2.7 Transfer impedance

For screened cables, ~~Two~~ three grades of performance are recognised for transfer impedance. The transfer impedance measured in accordance with IEC 62153-4-3 shall not exceed the values of at least one grade shown in Table 1. Requirements at frequencies below 1 MHz are for further studies (ffs).

³ Currently under revision to become a TS.

Table 1 – Transfer impedance

Frequency range MHz	Maximum surface transfer impedance mΩ/m	
	Grade 1	Grade 2
1 to 10	$Z_t \leq 15f^{-0,176}$	$Z_t \leq 50f^{0,301}$
10 to 30	$Z_t \leq 10 \frac{f}{10}$	$Z_t \leq 23,392f^{0,631}$
Where f is the frequency in MHz.		

Frequency range f in MHz	Maximum surface transfer impedance in mΩ/m		
	Grade 1	Grade 1b	Grade 2
0,1 to 1	15	30	50
1 to 10	$Z_t \leq 15(f)^{-0,176}$	$Z_t \leq 30(f)^{-0,176}$	$Z_t \leq 50(f)^{-0,301}$
10 to 20	$Z_t \leq 10 \frac{f}{10}$	$Z_t \leq 20 \frac{f}{10}$	$Z_t \leq 23,392(f)^{0,631}$

6.2.8 Coupling attenuation and low frequency coupling attenuation

~~Four~~ Three performance types for coupling attenuation are recognised. Coupling attenuation shall be measured using either the absorbing clamp method (IEC 62153-4-5) or the triaxial method for screened cables (IEC 62153-4-9). When measured using one of these methods, the coupling attenuation in the frequency range from $f = 30$ MHz to ~~1 000 MHz~~ 1 GHz for T1-C type cables or 1,25 GHz for T1-D type cables shall meet the requirements of Type I, Type Ib or Type II indicated in Table 2.

Table 2 – Coupling attenuation

Coupling attenuation type	Frequency range MHz	Coupling attenuation dB
Type I	30 to 100	≥ 85
	100 to 1 000 for T1-C type cables 100 to 1 000 1 250 for T1-D type cables	$\geq 85 - 20 \log_{10}(f/100)$; f in MHz
Type Ib	30 to 100	≥ 70
	100 to 1 000 for T1-C type cables 100 to 1 250 for T1-D type cables	$\geq 70 - 20 \log_{10}(f/100)$; f in MHz
Type II	30 to 100	≥ 55
	100 to 1 000 for T1-C type cables 100 to 1 250 for T1-D type cables	$\geq 55 - 20 \log_{10}(f/100)$; f in MHz

For frequencies below 30 MHz three performance types for low frequency coupling attenuation are recognised (see Table 3). Low frequency coupling attenuation shall be measured using the triaxial method according to IEC 62153-4-9 in a tube of 3 m length.

Table 3 – Low frequency coupling attenuation

Low frequency coupling attenuation type	Frequency range MHz	Low frequency coupling attenuation dB
Type I	0,1 to 30	$\geq 85 - 10 \log_{10} (f/30)$, 100 dB max. (ffs); f in MHz
Type Ib	0,1 to 30	$\geq 70 - 10 \log_{10} (f/30)$, 85 dB max. (ffs); f in MHz
Type II	0,1 to 30	$\geq 55 - 10 \log_{10} (f/30)$, 70 dB max. (ffs); f in MHz

Further details about the background of coupling attenuation versus low frequency coupling attenuation requirements are given in Annex B.

NOTE Coupling attenuation and low frequency coupling attenuation requirements according to Type II are not applicable for MICE E3.

6.2.9 Current-carrying capacity

The maximum current-carrying capacity is installation dependent and therefore not specified but may be indicated in the relevant detail specification. Further guidance with respect to current-carrying capacity is provided by ISO/IEC TS 29125:2017.

NOTE Local regulations can apply when supplying remote power.

6.3 Transmission characteristics

6.3.1 Velocity of propagation (phase velocity)

The requirements are not specified but may be indicated in the relevant detail specification.

6.3.2 Phase delay and differential delay (delay skew)

6.3.2.1 Phase delay

The phase delay, τ , shall not exceed the value obtained from Formula (1) in the frequency range from 0,1 MHz to 600 MHz for T1-C type cables or 1,25 GHz for T1-D type cables. The requirements from 0,1 MHz to 1 MHz are ffs.

$$\tau = 534 + \frac{36}{\sqrt{f}} \quad (1)$$

where

τ is the phase delay in ns/100 m;

f is the frequency in MHz.

6.3.2.2 Differential delay (delay skew)

If applicable, for example in the case of bundled cables (see Clause 7), the maximum delay skew between any two pairs, when measured at $(20 \pm 3) ^\circ\text{C}$, shall not exceed 25 ns/100 m in the frequency range from 0,1 MHz to 600 MHz for T1-C type cables or 1,25 GHz for T1-D type cables. The requirements from 0,1 MHz to 1 MHz are ffs.

6.3.3 Attenuation (α)

6.3.3.1 Attenuation at 20 °C operating temperature

The maximum attenuation, α , of any pair in the frequency range indicated in Table 4 shall not exceed the value obtained from Formula (2). The requirements from 0,1 MHz to 1 MHz are ffs.

$$\alpha = a\sqrt{f} + bf + c/\sqrt{f} \quad (2)$$

where

α is the attenuation expressed in dB/100 m;

a, b, c are constants indicated in Table 4;

f is the frequency expressed in MHz.

Table 4 – Attenuation equation constants

Frequency range MHz	Constants		
	a	b	c
0,1 to 600 for T1-C type cables 0,1 to 1 250 for T1-D type cables	1,8	0,005	0,25

6.3.3.2 Attenuation at elevated operating temperature

The increase of the maximum attenuation from Formula (2) due to elevated environmental temperature above 20 °C is obtained by calculation as follows:

- for unscreened cables: 0,4 %/°C, for the temperature range from 20 °C to 40 °C and 0,6 %/ °C for the temperature range from 40 °C to 60 °C;
- for screened cables: 0,2 %/ °C in the temperature range from 20 °C to 60 °C.

In the event of application of remote powering, the actual conductor temperature should be considered in order to calculate the attenuation increase. If an extended environmental temperature range is specified (see 4.3) the temperature coefficients given in 6.3.3.2 might not be applicable. The method provided in IEC 61156-1 should be used to determine temperature coefficients in this case.

6.3.4 Unbalance attenuation (TCL and EL TCTL)

The minimum near-end unbalance attenuation (transverse conversion loss (TCL)) shall not be less than the value obtained from Table 5 in the frequency range from 0,1 MHz to 600 MHz for T1-C type cables or 1,25 GHz for T1-D type cables. The requirements from 0,1 MHz to 1 MHz are ffs.

Table 5 – TCL requirements

Frequency range MHz	TCL dB
1 to 600	$50 - 15 \log_{10}(f)$; f in MHz; 40 dB maximum

	Screened cables dB	Unscreened cables dB
Level 1	$40 - 15 \log_{10}(f)$; f in MHz; 40 dB maximum 7 dB minimum	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum
Level 2	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum
Level 3	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum	$76 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum
Level 4	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum	$84 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum

The minimum equal-level far-end unbalance attenuation (equal-level transverse conversion transfer loss (EL TCTL)) shall not be less than the value obtained from Table 6 in the frequency range from 0,1 MHz to 600 MHz for T1-C type cables or 1,25 GHz for T1-D type cables. The requirements from 0,1 MHz to 1 MHz are ffs.

Table 6 – EL TCTL requirements

Frequency range MHz	EL-TCTL dB
1 to 600	$40 - 20 \log_{10}(f)$; f in MHz; 5 dB minimum

	Screened cables dB	Unscreened cables dB
Level 1	$40 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum	$40 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum
Level 2	$50 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum	$50 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum
Level 3	$60 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum	$60 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum

For calculation of EL TCTL, the TCTL and the attenuation measurement of the test specimen with the same length as defined in 6.1 shall be used.

6.3.5 Alien (exogenous) near-end crosstalk (PS ANEXT)

The PS ANEXT (power-sum alien near-end crosstalk) of the cable when tested in accordance with IEC 61156-1:2007 shall be not less than the values obtained from Table 7. The requirements from 0,1 MHz to 1 MHz are ffs.

Table 7 – PS ANEXT requirements

Frequency range MHz	PS ANEXT dB
1 to 100	67
100 to 600	67

Cable type	Frequency range MHz	PS ANEXT dB
T1-C type cables	0,1 to 100	70
	100 to 600	$70 - 10 \log_{10}(f/100)$; f in MHz
T1-D type cables	0,1 to 100	75
	100 to 1 250	$75 - 10 \log_{10}(f/100)$; f in MHz

For screened cables meeting the requirements of 6.2.7 and 6.2.8 (minimum Type ~~IE~~) ANEXT is proven by design (ffs).

6.3.6 Alien (exogenous) far-end crosstalk (PS AACR-F)

The PS AACR-F (power-sum alien attenuation to crosstalk ratio far-end) of the cable when tested in accordance with IEC 61156-1:2007 shall not be less than the values obtained from Table 8. The requirements from 0,1 MHz to 1 MHz are ffs.

For calculation of AACR-F, the AFEXT and the attenuation measurement of the test specimen with a length as specified in 6.1 shall be used.

Table 8 – PS AACR-F requirements

Frequency range MHz	PS AACR-F dB
1 to 600	$103 - 20 \log_{10}(f)$; f in MHz

Cable type	Frequency range MHz	PS AACR-F dB
T1-C type cables	0,1 to 600	$98 - 20 \log_{10}(f)$; f in MHz
T1-D type cables	0,1 to 1 250	$103 - 20 \log_{10}(f)$; f in MHz

~~If AFEXT up to 600 MHz is greater than 90 dB, the AACR-F may not be calculated.~~

If AFEXT up to 600 MHz is greater than 90 dB for T1-C type cables or greater than 90 dB up to 1 GHz and greater than 80 dB from 1 GHz to 1,25 GHz for T1-D type cables, it might not be

possible to calculate the AACR-F and it can be assumed the criteria according to Table 8 are met.

For those frequencies where the calculated limit value of PS AACR-F is greater than 75 dB for T1-C type cables, the requirement shall be 75 dB.

For those frequencies where the calculated limit value of PS AACR-F is greater than 80 dB for T1-D type cables, the requirement shall be 80 dB.

For screened cables meeting the requirements in accordance with 6.2.7 and 6.2.8 (minimum Type Ib), AFEXT is proven by design.

6.3.7 Alien (exogenous) crosstalk of bundled cables

The relevant requirements of this document – especially those of 6.3.5 and 6.3.6 – apply; see also Clause 7.

6.3.8 Impedance

The fitted or mean characteristic impedance measured in accordance with IEC 61156-1:2007/AMD1:2009 shall be $100\ \Omega \pm 5\ \Omega$ at 100 MHz. A measurement of the input impedance is not sufficient to ensure return loss limits.

Recommendations ~~contained~~ given in IEC TR 61156-1-2 and IEC TR 61156-1-5 for improvement of measurement uncertainty ~~may~~ can be considered.

6.3.9 Return loss (RL)

The minimum return loss of any pair in the frequency range indicated in Table 9 shall not be less than the values in Table 9.

Table 9 – RL requirements

Frequency range MHz	RL dB
0,1 to 1	$20 + 10 \log_{10}(f)$; f in MHz (ffs)
1 to 10	$20 + 5 \log_{10}(f)$; f in MHz
10 to 20	25
20 to 600	$25 - 7 \log_{10}(f/20)$; f in MHz 17,3 dB minimum
600 to 1 250 T1-D type cables only	$17,3 - 10 \log_{10}(f/600)$; f in MHz

When using a balun-less measurement technique, the corresponding descriptions of IEC TR 61156-1-2 ~~may~~ can be considered. Recommendations contained in IEC TR 61156-1-5 for improvement of measurement uncertainty by a correction technique ~~may~~ can be considered.

6.4 Mechanical and dimensional characteristics and requirements

6.4.1 Dimensional requirements

The overall diameter of insulation, the nominal thickness of the sheath and the maximum overall diameter of the sheath are not specified, but shall be indicated in the relevant detail specification.

6.4.2 Elongation at break of the conductor

The minimum elongation at break of the conductor shall be not less than 8 %.

6.4.3 Tensile strength of the insulation

The tensile strength of the insulation is not specified, but may be indicated in the relevant detail specification.

6.4.4 Elongation at break of the insulation

The minimum value of the elongation at break of the insulation shall be not less than 100 %.

6.4.5 Adhesion of the insulation to the conductor

The adhesion of the insulation to the conductor is not specified, but may be indicated in the relevant detail specification.

6.4.6 Elongation at break of the sheath

The minimum value of the elongation at break of any sheath shall be not less than 100 %.

6.4.7 Tensile strength of the sheath

The minimum tensile strength of any sheath shall be not less than 9 MPa.

6.4.8 Crush test of the cable

The crush resistance of the cable is not specified but may be indicated in the relevant detail specification.

6.4.9 Impact test of the cable

The impact resistance of the cable is not specified but may be indicated in the relevant detail specification.

6.4.10 Bending under tension

The bending performance of the cable is not specified but may be indicated in the relevant detail specification.

6.4.11 Repeated bending of the cable

Not applicable.

6.4.12 Tensile performance of the cable

The tensile strength of the cable is not specified but may be indicated in the relevant detail specification.

6.4.13 Shock-test requirements of the cable

Not applicable.

6.4.14 Bump-test requirements of the cable

Not applicable.

6.4.15 Vibration-test requirements of a cable

Not applicable.

6.5 Environmental characteristics

6.5.1 Shrinkage of the insulation

When tested at $(100 \pm 2) ^\circ\text{C}$ for 1 h, the shrinkage of the insulation shall not exceed 5 %. The length of the sample shall be 150 mm, and the shrink-back shall be measured as the sum from both ends.

6.5.2 Wrapping test of the insulation after thermal ageing

Not applicable.

6.5.3 Bending test of insulation at low temperature

The bending test of the insulated conductor shall be carried out at $(-20 \pm 2) ^\circ\text{C}$. The mandrel diameter shall be 6 mm. There shall be no cracks in the insulation.

6.5.4 Elongation at break of the sheath after ageing

The ageing regime shall be seven days at $(100 \pm 2) ^\circ\text{C}$. The elongation at break after ageing shall not be less than 50 % of the unaged value.

6.5.5 Tensile strength of the sheath after ageing

The ageing regime shall be seven days at $(100 \pm 2) ^\circ\text{C}$. The tensile strength after ageing shall be not less than 70 % of the unaged value.

6.5.6 Sheath pressure test at high temperature

Not applicable.

6.5.7 Cold bend test of the cable

The bending test shall be carried out at $(-20 \pm 2) ^\circ\text{C}$. The mandrel diameter shall be eight times the overall diameter of the cable. There shall be no cracks in the sheath.

6.5.8 Heat shock test

Not applicable.

6.5.9 Damp heat steady state

Not applicable.

6.5.10 Solar radiation

The resistance to solar radiation is not specified but may be specified in the relevant detail specification.

6.5.11 Solvents and contaminating fluids

The resistance to solvents and contaminating fluids is not specified but may be specified in the relevant detail specification.

6.5.12 Salt mist and sulphur dioxide

Not applicable.

6.5.13 Water immersion

Not applicable.

6.5.14 Hygroscopicity

The amount of moisture gained after 3 h shall not exceed 1 % in weight.

6.5.15 Wicking

The test solution shall not wet the filter paper at the end of 6 h.

6.5.16 Flame propagation characteristics of a single cable

~~If required by local regulations and/or indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1 unless regional or local regulations (e.g. the Construction Products Regulation (CPR) in Europe) apply.~~

If indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1.

6.5.17 Flame propagation characteristics of bunched cables

~~If required by local regulations and/or indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1 unless regional or local regulations (e.g. CPR in Europe) apply.~~

If indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1.

6.5.18 Halogen gas evolution

~~If required by local regulations and/or indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1 unless regional or local regulations (e.g. CPR in Europe) apply.~~

If indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1.

6.5.19 Smoke generation

~~If required by local regulations and/or indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1 unless regional or local regulations (e.g. CPR in Europe) apply.~~

If indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1.

6.5.20 Toxic gas emission

~~If required by local regulations and/or indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1 unless regional or local regulations (e.g. CPR in Europe) apply.~~

If indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1.

6.5.21 Integrated fire test method for cables in environmental air handling spaces

~~If required by local regulations and/or indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1 unless regional or local regulations (e.g. CPR in Europe) apply.~~

If indicated in the relevant detail specification, the test shall be performed in accordance with IEC 61156-1.

7 Bundled cable requirements

7.1 General

In bundled cables, break-out cables or cable harnesses, several one-pair cables as described in this document may be bundled. Such arrangements shall be specified in a detail specification agreed on by the manufacturer and the customer. Relevant safety regulations in addition to this document shall be taken into account. The limits for alien crosstalk shall apply for the crosstalk between the one-pair cables as described in this document.

7.2 Single pairs sharing one sheath

7.2.1 General

In the event that several pairs are operating in parallel in a multi-pair cable, the crosstalk between the pairs shall be considered. The most obvious case of four-pair cables is assumed in 7.2 for the requirements of near-end and far-end crosstalk. In the case of a different pair-count, the applicable power-sum requirements in this document for the relevant pair-count shall be met in order to achieve similar noise levels.

7.2.2 Near-end crosstalk (NEXT)

The requirements of Table 10 apply to four-pair cables only. If applicable, the worst near-end crosstalk shall not be less than the values indicated in Table 10.

Table 10 – NEXT and PS NEXT requirements

Frequency range MHz	NEXT requirement dB	PS NEXT requirement dB
1 to 600	$111,7 - 15 \log_{10}(f)$; f in MHz	$108,7 - 15 \log_{10}(f)$; f in MHz

Frequency range MHz	NEXT requirement dB	PS NEXT requirement dB
1 to 600 for T1-C type cables 1 to 1 250 for T1-D type cables	$114 - 15 \log_{10}(f)$; f in MHz	$111 - 15 \log_{10}(f)$; f in MHz

For those frequencies where the calculated value of NEXT is greater than 78 dB, the requirement shall be 78 dB. For those frequencies where the calculated value of PS NEXT is greater than 75 dB, the requirement shall be 75 dB.

7.2.3 Attenuation to crosstalk ratio far-end (PS ACR-F)

The requirements of Table 11 apply to four-pair cables only. If applicable, the pair-to-pair ACR-F in dB for any combination shall be greater than or equal to the value obtained from Table 11.

Table 11 – ACR-F and PS ACR-F requirements

Frequency range MHz	ACR-F requirement dB	PS ACR-F requirement dB
1 to 600	$99 - 20 \log_{10}(f);$ f in MHz	$96 - 20 \log_{10}(f);$ f in MHz

Frequency range MHz	ACR-F requirement dB	PS ACR-F requirement dB
1 to 600 for T1-C type cables 1 to 1 250 for T1-D type cables	$133 - 20 \log_{10}(f);$ f in MHz	$130 - 20 \log_{10}(f);$ f in MHz

For calculation of ACR-F, the FEXT and the attenuation measurement of the test specimen with length as defined in 6.1 shall be used.

If FEXT up to 600 MHz is greater than 90 dB for T1-C type cables or greater than 90 dB up to 1 GHz and greater than 80 dB from 1 GHz to 1,25 GHz for T1-D type cables, the ACR-F may not be calculated.

For those frequencies where the calculated limit value of ACR-F is greater than 78 dB, the requirement shall be 78 dB. For those frequencies where the calculated value of PS ACR-F is greater than 75 dB, the requirement shall be 75 dB.

Annex A (informative)

Blank detail specification

The blank detail specification determines the layout and style for detail specifications describing symmetrical single pair cables with transmission characteristics up to ~~600 MHz~~ 1,25 GHz. Detail specifications, based on the blank detail specification, may be prepared by a national organization, a manufacturer, or a user. The detail specification ~~shall~~ should be written in accordance with the layout of the blank detail specification described here.

This blank detail specification includes additional recommended environmental characteristics and severities, which are derived from the environmental classifications that are specified for cabling for various environments.

NOTE Environmental classifications are presented in ISO/IEC 11801-1 with three levels of severity in four areas: mechanical, ingress, climatic, and electromagnetic; thus, in tabular form, they are referred to as the "MICE table".

The numbers shown in brackets on this and the following pages correspond to the following items of required information, which shall be entered in the spaces provided.

- [1] Name and address of the organization that has prepared the document.
- [2] IEC document number, issue number and date of issue.
- [3] Address of the organization from which the document is available.
- [4] Related documents.
- [5] Any other reference to the cable: national reference, trade name, etc.
- [6] A complete description of the cable, which ~~shall~~ should include:
 - a) type and number of elements;
 - b) nominal impedance;
 - c) screening;
 - d) application;
 - e) other distinguishing performance characteristics.
- [7] Details of the cable material and construction.
- [8] Special requirements for bending radius or operating temperatures.
- [9] List of cable characteristics, separated into electrical, transmission, mechanical and environmental characteristics.
- [10] Appropriate subclause references to this document.
- [11] Requirements applicable to the relevant cable. The values entered ~~shall~~ should meet as a minimum the requirements of this document.
- [12] Comments – Relevant remarks.

[1] Prepared by:		[2] Document: Issue: Date:	
[3] Available from:		[4] Generic specification: IEC 61156-1 Sectional specification: IEC 61156-11 Blank detail specification: IEC 61156-11:20192023, Annex A	
[5] Additional references:			
[6] Cable description: a) Type and number of elements: b) Nominal impedance: c) Screening: d) Application: e) Other distinguishing performance characteristics:			
[7] Cable construction:	Subclause		[12] Comments
	5.2	Cable construction:	
	5.3	Conductor description:	
	5.4	Insulation description: Maximum diameter: Colour code of elements:	
	5.5	Cable element:	
	5.6	Screening of the cable element: Tape material Minimum overlap Drain wire Braid wire Braid material	
	5.7	Cable make-up:	
	5.8	Screening of the cable core: Tape material Minimum overlap Drain wire Braid wire Braid material	
	5.9	Sheath: Material Nominal thickness Colour Maximum overall diameter Marking Ripcord	
	5.10	Identification	
5.11	Packaging of finished cable		
[8] Minimum bending radius for static bending: Minimum bending radius for dynamic bending: Temperature range for installation: Operating temperature range under static conditions: C1: -10 °C to +60 °C C2: -25 °C to +70 °C C3: -40 °C to +70 °C			

[9] Characteristics	[10] Subclause	[11]	[12] Comments
Electrical characteristics	6.2		
Conductor resistance	6.2.1	$\leq \dots \Omega/\text{km}$	
Resistance unbalance	6.2.2		
Resistance unbalance within a pair	6.2.2.1	$\leq \dots \%$	
Resistance unbalance between pairs	6.2.2.2	$\leq \dots \%$	
Dielectric strength			
Conductor/conductor	6.2.3	$\dots \text{ kV (time of application)}$	
Conductor/screen		$\dots \text{ kV (time of application)}$	
Insulation resistance			
Conductor/conductor	6.2.4	$\geq \dots \text{ M}\Omega \cdot \text{km}$	
Conductor/screen		$\geq \dots \text{ M}\Omega \cdot \text{km}$	
Mutual capacitance	6.2.5	$\leq \dots \text{ pF/mnF/km}$	
Capacitance unbalance pair to ground	6.2.6	$\leq \dots \text{ pF/mkm}$	
Transfer impedance	6.2.7		Cable should be according to Grade 1 or Grade 2, if screened.
Coupling attenuation	6.2.8	$\dots \text{ dB}$	Cable type should be Type I, Ib or II.
Low frequency coupling attenuation	6.2.8	$\dots \text{ dB}$	
Current-carrying capacity	6.2.9	$\dots \text{ mA}$	The current-carrying capacity is dependent on the installation conditions in accordance with ISO/IEC TS 29125.
Transmission characteristics	6.3		
Velocity of propagation	6.3.1		
Phase delay	6.3.2.1	$\leq \dots \text{ ns/100 m}$	
Differential delay (delay skew)	6.3.2.2	$\leq \dots \text{ ns/100 m}$	
Attenuation			
General figures	6.3.3.1	$\leq \dots \text{ dB/100 m}$	
Environmental temperature effects	6.3.3.2	$\leq \dots \text{ }^\circ\text{C}$	
Unbalance attenuation near-end (TCL)	6.3.4	$\geq \dots \text{ dB}$	Cable grade shall be identified.
Unbalance attenuation far-end (EL TCL)	6.3.4	$\geq \dots \text{ dB}$	
Near-end crosstalk	7.2.2, if applicable	$\geq \dots \text{ dB}$	
Attenuation to crosstalk ratio far-end	7.2.3, if applicable	$\geq \dots \text{ dB}$	
Power sum alien (exogenous) near-end crosstalk	6.3.5	$\geq \dots \text{ dB}$	
Power sum alien (exogenous) attenuation to crosstalk ratio far-end crosstalk	6.3.6	$\geq \dots \text{ dB}$	
Alien crosstalk of bundled cables	6.3.7	$\geq \dots \text{ dB}$	In case additional requirements are specified.
Fitted or mean impedance	6.3.8		
Return loss	6.3.9	$\geq \dots \text{ dB}$	

Mechanical and dimensional characteristics	6.4		
Dimensional requirements Insulation diameter Sheath thickness Cable diameter	6.4.1	... mm	
Elongation at break of the conductors	6.4.2	≥ ... %	
Tensile strength of the insulation	6.4.3	≥ ... MPa	
Elongation at break of the insulation	6.4.4	≥ ... %	
Adhesion of the insulation to the conductor	6.4.5		
Elongation at break of the sheath	6.4.6	≥ ... %	
Tensile strength of the sheath	6.4.7	≥ ... MPa	
Crush test of the cable	6.4.8	M1: ≥ 45 N over 25 mm (linear) min. M2: ≥ 1 100 N over 150 mm (linear) min. M3: ≥ 2 200 N over 150 mm (linear) min.	
Impact test of the cable	6.4.9	M1: ≥ 1 J M2: ≥ 10 J M3: ≥ 30 J	
Bending under tension	6.4.10		
Repeated bending of the cable	6.4.11		Not applicable
Tensile performance of the cable	6.4.12		
Shock test	6.4.13	Not applicable	
Bump test	6.4.14	Not applicable	
Vibration test	6.4.15	Not applicable	

Environmental characteristics	6.5		
Shrinkage of insulation	6.5.1	≤ ... %	
Wrapping test of insulation after thermal ageing	6.5.2	Not applicable	
Bending test of insulation at low temperature	6.5.3		
Elongation at break of the sheath after ageing	6.5.4	≥ ... %	
Tensile strength of the sheath after ageing	6.5.5	≥ ... MPa	
Sheath pressure test at high temperature	6.5.6	Not applicable	
Cold bend test of cable	6.5.7		
Heat shock test	6.5.8	Not applicable	
Damp heat steady state	6.5.9	Not applicable	
Solar radiation	6.5.10	C1: Not applicable C2, C3: Under consideration	
Solvents and contaminating fluids	6.5.11		
Salt mist and sulphur dioxide tests	6.5.12	Not applicable	
Water immersion test	6.5.13	Not applicable	
Hygroscopicity	6.5.14		
Wicking	6.5.15		
Flame propagation characteristics of a single cable	6.5.16		
Flame propagation characteristics of bunched cables	6.5.17		
Halogen gas evolution	6.5.18		
Smoke generation	6.5.19		The requirement and the test method shall be specified in the detail specification.
Toxic gas emission	6.5.20		
Integrated fire test	6.5.21		
Bundled cable requirements	7		
Near-end crosstalk requirements	7.2.2		
Far end crosstalk requirements	7.2.3		
When a characteristic applies but a specific value is not considered necessary, then NS for "not specified" should be entered in the appropriate place. When NS is used, the appropriate requirements in the specification should apply. When a characteristic is marked as not applicable, it is not required by Clause 4 to Clause 7, but may can be required in the detail specification. Ingress requirements using particles are not applicable to a cable. Electromagnetic requirements coming from the MICE table, i.e. Table 2 of ISO/IEC 11801-1:2017 have been dealt with by using the requirements that are given for transfer impedance, screening attenuation and coupling attenuation. ESD requirements are considered not applicable. The proposed severities are taken from the MICE table, i.e. Table 2 of ISO/IEC 11801-1:2017. Depending on the actual need of end users, other severities may be agreed between the customer and suppliers.			

Annex B (informative)

Background information for coupling attenuation and low frequency coupling attenuation requirements

The parameter coupling attenuation has been specified in the first edition of IEC 62153-4-5 in 2006. Coupling attenuation is an integral measure of screening efficiency of balanced cables. It combines the effects of reduction of interference by balance and by screening attenuation in case the cable is screened. The background of the theory of coupling attenuation measurement is described in IEC 62153-4-5 and IEC TS 62153-4-1. An important detail of the theory is that an electrically long coupling length is needed where the inner system and the outer system can interact.

For the measurement based on absorbing clamps as described in IEC 62153-4-5 the following framework is typical:

- The inner system (the cable under test) is fed via a balun.
- The detection of the leakage signal in the outer system is achieved by absorbing clamps.
- Absorbing clamps with a frequency range of 30 MHz to 1 GHz are used. Either a pair of absorbing clamps are used or an absorbing clamp and a ferrite absorber block with similar absorbing characteristics to an absorbing clamp.
- The coupling length (the distance between the absorbing clamps) is 6 m, which is assumed to be electrically long for frequencies of 30 MHz and higher.
- The measurement result is evaluated using an envelope trace having a plateau from 30 MHz to 100 MHz followed by a slope with $20 \log(f)$ increase, where f is the frequency in MHz.

Coupling attenuation measurement is also possible using the triaxial method according to IEC 62153-4-9. An important advantage of this approach is that the frequency range is no longer limited by the absorbing clamps. In case the triaxial method is used to extend the frequency range towards lower frequencies, ensure that for the typical coupling length the measurement set-up is not electrically long any more. For example if a coupling length of 6 m is assumed to be electrically long at 30 MHz, this would lead to a necessary coupling length of 60 m for 3 MHz and 600 m for 300 kHz.

The coupling length needed for an extension of a coupling attenuation measurement to 100 kHz is not practicable for almost every laboratory and furthermore longer than the maximum cable length specified by the respective application. Therefore a new parameter has been introduced in IEC 62153-4-9:2018/AMD1:2020, Annex D, i.e. low frequency coupling attenuation. In contrast to the usual absorbing clamp method it is based on the following typical framework:

- The inner system (the cable under test) is fed without a balun but using a modal decomposition technique. Nevertheless, a balun can still be used.
- The detection of the leakage signal in the outer system is achieved by the triaxial set-up.
- The frequency range is limited towards high frequencies by the requirement that the set-up has to be electrically short. Towards low frequencies only the capabilities of the used network analyser are limiting.
- A 3 m long triaxial set-up is assumed to be electrically short up to 30 MHz.
- An envelope trace is defined as having a plateau from 100 kHz up to 0,95 MHz followed by a slope with $10 \log(f)$ increase up to 30 MHz, where f is the frequency in MHz.

Both parameters, coupling attenuation and low frequency coupling attenuation, are usually described by the value of the plateau only.

Bibliography

IEC TR 61156-1-2, *Multicore and symmetrical pair/quad cables for digital communications – Part 1-2: Electrical transmission characteristics and test methods of symmetrical pair/quad cables*

IEC TR 61156-1-5, *Multicore and symmetrical pair/quad cables for digital communications – Part 1-5: Correction procedures for the measurement results of return loss and input impedance*

IEC TS 62153-4-1, *Metallic communication cable test methods – Part 4-1: Electromagnetic compatibility (EMC) – Introduction to electromagnetic screening measurements*

ISO/IEC 11801-1:2017, *Information technology – Generic cabling for customer premises – Part 1: General requirements*

ISO/IEC 11801-1:2017/AMD1:–⁴

ISO/IEC TR 11801-9906, *Information technology – ~~Guidance for balanced cabling in support of 1 Gbit/s over 1 pair, for Industrial applications~~⁵ Generic cabling for customer premises –Part 9906: Balanced 1-pair cabling channels up to 600 MHz for single pair Ethernet (SPE)*

Hähner, Mund, Schmid, *History and recent trends of triaxial test procedure; Proceedings of the IWCS 2018*

⁴ Under development. Stage at the time of publication: ISO/IEC CDV 11801-1:2017/AMD1:2023.

⁵ ~~Under consideration.~~

IECNORM.COM : Click to view the full PDF of IEC 61156-11:2023 RLV

INTERNATIONAL STANDARD

**Multicore and symmetrical pair/quad cables for digital communications –
Part 11: Symmetrical single pair cables with transmission characteristics up to
1,25 GHz – Horizontal floor wiring – Sectional specification**

IECNORM.COM : Click to view the full PDF of IEC 61156-11:2023 RLV

CONTENTS

FOREWORD	5
1 Scope	7
2 Normative references	7
3 Terms and definitions	8
4 Installation considerations	8
4.1 General remarks	8
4.2 Bending radius of installed cable	8
4.3 Climatic conditions	8
5 Materials and cable construction	8
5.1 General remarks	8
5.2 Cable construction	8
5.3 Conductor	9
5.4 Insulation	9
5.5 Cable element	9
5.6 Screening of the cable element	9
5.7 Cable make-up	9
5.8 Screening of the cable core	9
5.9 Sheath	9
5.10 Identification	10
5.11 Finished cable	10
6 Characteristics and requirements	10
6.1 General remarks	10
6.2 Electrical characteristics and tests	10
6.2.1 Conductor resistance	10
6.2.2 Resistance unbalance	10
6.2.3 Dielectric strength	11
6.2.4 Insulation resistance	11
6.2.5 Mutual capacitance	11
6.2.6 Capacitance unbalance	11
6.2.7 Transfer impedance	11
6.2.8 Coupling attenuation and low frequency coupling attenuation	11
6.2.9 Current-carrying capacity	12
6.3 Transmission characteristics	12
6.3.1 Velocity of propagation (phase velocity)	12
6.3.2 Phase delay and differential delay (delay skew)	12
6.3.3 Attenuation (α)	13
6.3.4 Unbalance attenuation (TCL and EL TCTL)	14
6.3.5 Alien (exogenous) near-end crosstalk (PS ANEXT)	14
6.3.6 Alien (exogenous) far-end crosstalk (PS AACR-F)	15
6.3.7 Alien (exogenous) crosstalk of bundled cables	15
6.3.8 Impedance	15
6.3.9 Return loss (RL)	16
6.4 Mechanical and dimensional characteristics and requirements	16
6.4.1 Dimensional requirements	16
6.4.2 Elongation at break of the conductor	16
6.4.3 Tensile strength of the insulation	16

6.4.4	Elongation at break of the insulation	16
6.4.5	Adhesion of the insulation to the conductor.....	16
6.4.6	Elongation at break of the sheath	16
6.4.7	Tensile strength of the sheath.....	16
6.4.8	Crush test of the cable.....	17
6.4.9	Impact test of the cable	17
6.4.10	Bending under tension	17
6.4.11	Repeated bending of the cable	17
6.4.12	Tensile performance of the cable.....	17
6.4.13	Shock-test requirements of the cable	17
6.4.14	Bump-test requirements of the cable	17
6.4.15	Vibration-test requirements of a cable	17
6.5	Environmental characteristics	17
6.5.1	Shrinkage of the insulation	17
6.5.2	Wrapping test of the insulation after thermal ageing	17
6.5.3	Bending test of insulation at low temperature.....	17
6.5.4	Elongation at break of the sheath after ageing	17
6.5.5	Tensile strength of the sheath after ageing	18
6.5.6	Sheath pressure test at high temperature	18
6.5.7	Cold bend test of the cable	18
6.5.8	Heat shock test.....	18
6.5.9	Damp heat steady state	18
6.5.10	Solar radiation	18
6.5.11	Solvents and contaminating fluids.....	18
6.5.12	Salt mist and sulphur dioxide.....	18
6.5.13	Water immersion	18
6.5.14	Hygroscopicity	18
6.5.15	Wicking.....	18
6.5.16	Flame propagation characteristics of a single cable	18
6.5.17	Flame propagation characteristics of bunched cables	18
6.5.18	Halogen gas evolution	19
6.5.19	Smoke generation.....	19
6.5.20	Toxic gas emission	19
6.5.21	Integrated fire test method for cables in environmental air handling spaces.....	19
7	Bundled cable requirements	19
7.1	General.....	19
7.2	Single pairs sharing one sheath	19
7.2.1	General	19
7.2.2	Near-end crosstalk (NEXT)	19
7.2.3	Attenuation to crosstalk ratio far-end (PS ACR-F).....	20
Annex A (informative)	Blank detail specification	21
Annex B (informative)	Background information for coupling attenuation and low frequency coupling attenuation requirements	26
Bibliography		27
Table 1 – Transfer impedance		11
Table 2 – Coupling attenuation		12

Table 3 – Low frequency coupling attenuation	12
Table 4 – Attenuation equation constants	13
Table 5 – TCL requirements.....	14
Table 6 – EL TCTL requirements	14
Table 7 – PS ANEXT requirements	15
Table 8 – PS AACR-F requirements.....	15
Table 9 – RL requirements.....	16
Table 10 – NEXT and PS NEXT requirements.....	19
Table 11 – ACR-F and PS ACR-F requirements	20

IECNORM.COM : Click to view the full PDF of IEC 61156-11:2023 RLV

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**MULTICORE AND SYMMETRICAL PAIR/QUAD CABLES
FOR DIGITAL COMMUNICATIONS –****Part 11: Symmetrical single pair cables with transmission characteristics
up to 1,25 GHz – Horizontal floor wiring – Sectional specification**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 61156-11 has been prepared by subcommittee 46C: Wires and symmetric cables, of IEC technical committee 46: Cables, wires, waveguides, RF connectors, RF and microwave passive components and accessories. It is an International Standard.

This second edition cancels and replaces the first edition published in 2019. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) additional cable type in support of T1-C generic single pair cabling up to 1,25 GHz;
- b) introduction of low frequency coupling attenuation as an integral parameter describing screening efficiency at frequencies below 30 MHz.

The text of this International Standard is based on the following documents:

Draft	Report on voting
46C/1254/FDIS	46C/1258/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 61156 series, published under the general title *Multicore and symmetrical pair/quad cables for digital communications*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IECNORM.COM : Click to view the full PDF of IEC 61156-11:2023 PDF

MULTICORE AND SYMMETRICAL PAIR/QUAD CABLES FOR DIGITAL COMMUNICATIONS –

Part 11: Symmetrical single pair cables with transmission characteristics up to 1,25 GHz – Horizontal floor wiring – Sectional specification

1 Scope

This part of IEC 61156 describes cables intended to be used for single balanced pair (office, home, industrial) applications according to ISO/IEC 11801-1. An example of existing application is 1000BASE-T1, see ISO/IEC TR 11801-9906. The transmission characteristics of these cables are specified up to a frequency of 1,25 GHz and at a temperature of 20 °C. The T1-C type cable is specified up to 600 MHz, the T1-D type cable up to 1,25 GHz. Depending on the MICE environment and the installation conditions either unscreened or screened cables can be used. A blank detail specification can be found in Annex A.

These cables can comprise more than one pair in the event that several systems are operated in parallel. In this case, refer to Clause 7.

The cables covered by this document are intended to operate with voltages and currents normally encountered in communication systems. While these cables are not intended to be used in conjunction with low impedance sources, for example the electric power supplies of public utility mains, they are intended to be used to support the delivery of low-voltage remote powering applications.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60708, *Low-frequency cables with polyolefin insulation and moisture barrier polyolefin sheath*

IEC 61156-1, *Multicore and symmetrical pair/quad cables for digital communications – Part 1: Generic specification*

IEC 61156-5, *Multicore and symmetrical pair/quad cables for digital communications – Part 5: Symmetrical pair/quad cables with transmission characteristics up to 1 000 MHz – Horizontal floor wiring – Sectional specification*

IEC 62153-4-3, *Metallic communication cable test methods – Part 4-3: Electromagnetic compatibility (EMC) – Surface transfer impedance – Triaxial method*

IEC 62153-4-5, *Metallic communication cables test methods – Part 4-5: Electromagnetic compatibility (EMC) – Screening or coupling attenuation – Absorbing clamp method*

IEC 62153-4-9:2018, *Metallic communication cable test methods – Part 4-9: Electromagnetic compatibility (EMC) – Coupling attenuation of screened balanced cables, triaxial method*
IEC 62153-4-9:2018/AMD1:2020

ISO/IEC TS 29125, *Information technology – Telecommunications cabling requirements for remote powering of terminal equipment*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 61156-1 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 Installation considerations

4.1 General remarks

Installation area considerations are defined in IEC 61156-1. Other areas may be considered.

4.2 Bending radius of installed cable

The minimum bending radius of the cable shall be equal to or less than four times the outside diameter of the cable unless otherwise specified.

4.3 Climatic conditions

Under static conditions, the cable shall operate at least in the temperature range of the environment from $-20\text{ }^{\circ}\text{C}$ to $+60\text{ }^{\circ}\text{C}$.

The attenuation increase due to the elevated operating temperature (temperature of the environment) is described in 6.3.3.2.

In the case of application of remote powering, the maximum temperature of the conductor shall not exceed the maximum operation temperature under static conditions ($60\text{ }^{\circ}\text{C}$) in order to maintain the integrity of the dielectric material performance which is aligned to the environmental temperature range.

Extended temperature ranges are permitted and shall be specified in the relevant detail specification.

5 Materials and cable construction

5.1 General remarks

For the purposes of this document, the requirements of IEC 61156-5 apply.

The choice of materials and cable construction shall be suitable for the intended application and installation of the cable and in line with the requirements of IEC 61156-1. Ensure that any requirements for EMC and fire performance (such as burning properties, smoke generation, evolution of halogen gas) are met. Regional regulations can apply as well.

5.2 Cable construction

The cable construction shall be in accordance with the details and dimensions given in the relevant detail specification.

5.3 Conductor

The conductor shall be a solid annealed copper conductor in accordance with the requirements of IEC 61156-1 and should have a nominal diameter between 0,4 mm and 0,65 mm. A conductor diameter of up to 1,05 mm may be used.

NOTE The conductor dimensions seen in practice are wider than those dimensions that correspond to the resistance requirements according to 6.2.1 and are therefore relevant for the design of the contact terminals of connecting hardware.

5.4 Insulation

The conductor shall be insulated with a suitable material. Examples of suitable materials are:

- polyolefin;
- fluoropolymer;
- low-smoke halogen-free thermoplastic material.

The colour code shall be in accordance with IEC 60708 if not specified differently in the relevant detail specification.

5.5 Cable element

The cable element shall be a balanced twisted pair. The entire cable may comprise more than one cable element, see 6.3.5 and Clause 7.

5.6 Screening of the cable element

The screen of the cable element (if exists) shall be in accordance with the requirements of IEC 61156-1.

5.7 Cable make-up

Fillers or spacers may be used in the cable elements and to separate cable elements. The cable elements and their screens, if they are screened, may be covered by an intermediate jacket. This jacket shall be in accordance with 5.9. The core of the cable may be wrapped with a protective layer of non-hygroscopic and non-wicking material.

5.8 Screening of the cable core

For screened cables, a screen for the cable core shall be provided. The screen shall be in accordance with the requirements of IEC 61156-1.

5.9 Sheath

The sheath material shall consist of a suitable material. Examples of suitable materials are:

- polyolefin;
- PVC;
- fluoropolymer;
- low-smoke halogen-free thermoplastic material.

The sheath shall be continuous, having a thickness as uniform as possible. A non-metallic ripcord may be provided. When provided, the ripcord shall be non-hygroscopic and non-wicking.

The colour of the sheath is not specified but it should be specified in the relevant detail specification.

5.10 Identification

Each length of cable shall be identified as to the supplier and, when required, a traceability code, using one or a combination of the following methods:

- appropriately coloured threads or tapes;
- with a printed tape;
- printing on the cable core wrapping;
- marking on the sheath.

Additional markings, such as length marking, are permitted. If used, such markings shall refer to this document.

5.11 Finished cable

The finished cable shall be adequately protected for storage and shipment.

6 Characteristics and requirements

6.1 General remarks

Clause 6 lists the characteristics and minimum requirements of a cable complying with this document. Test methods shall be in accordance with the requirements of IEC 61156-1, except for the length of the cable under test which shall be as specified in Clause 6.

The computed requirements in dB, rounded to one decimal place, shall be used to determine compliance.

The tests for electrical characteristics in accordance with 6.2 shall be carried out on a cable length of not less than 100 m, unless otherwise specified.

The tests for transmission characteristics in accordance with 6.3 shall be carried out on a cable length of 100 m, unless otherwise specified. For T1-D type cables a length of 50 m may be used to improve accuracy at high frequencies.

For measurements over a wide frequency range as required for T1-D type cable, a balun-less measurement technique is recommended, see IEC TR 61156-1-2¹.

6.2 Electrical characteristics and tests

6.2.1 Conductor resistance

The maximum conductor resistance at or corrected to 20 °C shall not exceed 72,5 Ω/km.

6.2.2 Resistance unbalance

6.2.2.1 Resistance unbalance within a pair

The resistance unbalance shall not exceed 2,0 %.

6.2.2.2 Resistance unbalance between pairs

If applicable, for example in the case of bundled cables (see Clause 7), the pair-to-pair resistance unbalance shall not exceed 5,0 %.

¹ Currently under revision to become a TS.

6.2.3 Dielectric strength

There shall be no failures when a test is performed on a conductor/conductor and, where screens are present, on a conductor/screen with 1,0 kV DC for 1 min or, alternatively, with 2,5 kV DC for 2 s. An AC voltage may be used. The AC voltage levels in these cases shall be 0,7 kV AC for 1 min or alternatively 1,7 kV AC for 2 s.

6.2.4 Insulation resistance

The test shall be performed on:

- conductor/conductor;
- conductor/screen (if exists).

The minimum insulation resistance at or corrected to 20 °C shall be not less than 5 000 MΩ·km when tested immediately after the dielectric strength test.

6.2.5 Mutual capacitance

The mutual capacitance is not specified but may be indicated in the relevant detail specification.

6.2.6 Capacitance unbalance

The maximum capacitance unbalance pair to ground shall not exceed 1 200 pF/km at a frequency of 800 Hz or 1 000 Hz.

6.2.7 Transfer impedance

For screened cables, three grades of performance are recognised for transfer impedance. The transfer impedance measured in accordance with IEC 62153-4-3 shall not exceed the values of at least one grade shown in Table 1. Requirements at frequencies below 1 MHz are for further studies (ffs).

Table 1 – Transfer impedance

Frequency range f in MHz	Maximum surface transfer impedance in mΩ/m		
	Grade 1	Grade 1b	Grade 2
0,1 to 1	15	30	50
1 to 10	$Z_t \leq 15(f)^{-0,176}$	$Z_t \leq 30(f)^{-0,176}$	$Z_t \leq 50(f)^{-0,301}$
10 to 20	$Z_t \leq 10 \frac{f}{10}$	$Z_t \leq 20 \frac{f}{10}$	$Z_t \leq 23,392(f)^{0,631}$

6.2.8 Coupling attenuation and low frequency coupling attenuation

Three performance types for coupling attenuation are recognised. Coupling attenuation shall be measured using either the absorbing clamp method (IEC 62153-4-5) or the triaxial method for screened cables (IEC 62153-4-9). When measured using one of these methods, the coupling attenuation in the frequency range from $f = 30$ MHz to 1 GHz for T1-C type cables or 1,25 GHz for T1-D type cables shall meet the requirements of Type I, Type Ib or Type II indicated in Table 2.

Table 2 – Coupling attenuation

Coupling attenuation type	Frequency range MHz	Coupling attenuation dB
Type I	30 to 100	≥ 85
	100 to 1 000 for T1-C type cables 100 to 1 250 for T1-D type cables	$\geq 85 - 20 \log_{10}(f/100)$; f in MHz
Type Ib	30 to 100	≥ 70
	100 to 1 000 for T1-C type cables 100 to 1 250 for T1-D type cables	$\geq 70 - 20 \log_{10}(f/100)$; f in MHz
Type II	30 to 100	≥ 55
	100 to 1 000 for T1-C type cables 100 to 1 250 for T1-D type cables	$\geq 55 - 20 \log_{10}(f/100)$; f in MHz

For frequencies below 30 MHz three performance types for low frequency coupling attenuation are recognised (see Table 3). Low frequency coupling attenuation shall be measured using the triaxial method according to IEC 62153-4-9 in a tube of 3 m length.

Table 3 – Low frequency coupling attenuation

Low frequency coupling attenuation type	Frequency range MHz	Low frequency coupling attenuation dB
Type I	0,1 to 30	$\geq 85 - 10 \log_{10}(f/30)$, 100 dB max. (ffs); f in MHz
Type Ib	0,1 to 30	$\geq 70 - 10 \log_{10}(f/30)$, 85 dB max. (ffs); f in MHz
Type II	0,1 to 30	$\geq 55 - 10 \log_{10}(f/30)$, 70 dB max. (ffs); f in MHz

Further details about the background of coupling attenuation versus low frequency coupling attenuation requirements are given in Annex B.

NOTE Coupling attenuation and low frequency coupling attenuation requirements according to Type II are not applicable for MICE E3.

6.2.9 Current-carrying capacity

The maximum current-carrying capacity is installation dependent and therefore not specified but may be indicated in the relevant detail specification. Further guidance with respect to current-carrying capacity is provided by ISO/IEC TS 29125.

NOTE Local regulations can apply when supplying remote power.

6.3 Transmission characteristics

6.3.1 Velocity of propagation (phase velocity)

The requirements are not specified but may be indicated in the relevant detail specification.

6.3.2 Phase delay and differential delay (delay skew)

6.3.2.1 Phase delay

The phase delay, τ , shall not exceed the value obtained from Formula (1) in the frequency range from 0,1 MHz to 600 MHz for T1-C type cables or 1,25 GHz for T1-D type cables. The requirements from 0,1 MHz to 1 MHz are ffs.

$$\tau = 534 + \frac{36}{\sqrt{f}} \quad (1)$$

where

τ is the phase delay in ns/100 m;

f is the frequency in MHz.

6.3.2.2 Differential delay (delay skew)

If applicable, for example in the case of bundled cables (see Clause 7), the maximum delay skew between any two pairs, when measured at $(20 \pm 3)^\circ\text{C}$, shall not exceed 25 ns/100 m in the frequency range from 0,1 MHz to 600 MHz for T1-C type cables or 1,25 GHz for T1-D type cables. The requirements from 0,1 MHz to 1 MHz are ffs.

6.3.3 Attenuation (α)

6.3.3.1 Attenuation at 20 °C operating temperature

The maximum attenuation, α , of any pair in the frequency range indicated in Table 4 shall not exceed the value obtained from Formula (2). The requirements from 0,1 MHz to 1 MHz are ffs.

$$\alpha = a\sqrt{f} + bf + c/\sqrt{f} \quad (2)$$

where

α is the attenuation expressed in dB/100 m;

a, b, c are constants indicated in Table 4;

f is the frequency expressed in MHz.

Table 4 – Attenuation equation constants

Frequency range MHz	Constants		
	a	b	c
0,1 to 600 for T1-C type cables 0,1 to 1 250 for T1-D type cables	1,8	0,005	0,25

6.3.3.2 Attenuation at elevated operating temperature

The increase of the maximum attenuation from Formula (2) due to elevated environmental temperature above 20 °C is obtained by calculation as follows:

- for unscreened cables: 0,4 %/°C, for the temperature range from 20 °C to 40 °C and 0,6 %/°C for the temperature range from 40 °C to 60 °C;
- for screened cables: 0,2 %/°C in the temperature range from 20 °C to 60 °C.

In the event of application of remote powering, the actual conductor temperature should be considered in order to calculate the attenuation increase. If an extended environmental temperature range is specified (see 4.3), the temperature coefficients given in 6.3.3.2 might not be applicable. The method provided in IEC 61156-1 should be used to determine temperature coefficients in this case.

6.3.4 Unbalance attenuation (TCL and EL TCTL)

The minimum near-end unbalance attenuation (transverse conversion loss (TCL)) shall not be less than the value obtained from Table 5 in the frequency range from 0,1 MHz to 600 MHz for T1-C type cables or 1,25 GHz for T1-D type cables. The requirements from 0,1 MHz to 1 MHz are ffs.

Table 5 – TCL requirements

	Screened cables dB	Unscreened cables dB
Level 1	$40 - 15 \log_{10}(f)$; f in MHz; 40 dB maximum 7 dB minimum	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum
Level 2	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum
Level 3	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum	$76 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum
Level 4	$68 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum	$84 - 15 \log_{10}(f)$; f in MHz; 53 dB maximum 7 dB minimum

The minimum equal-level far-end unbalance attenuation (equal-level transverse conversion transfer loss (EL TCTL)) shall not be less than the value obtained from Table 6 in the frequency range from 0,1 MHz to 600 MHz for T1-C type cables or 1,25 GHz for T1-D type cables. The requirements from 0,1 MHz to 1 MHz are ffs.

Table 6 – EL TCTL requirements

	Screened cables dB	Unscreened cables dB
Level 1	$40 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum	$40 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum
Level 2	$50 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum	$50 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum
Level 3	$60 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum	$60 - 20 \log_{10}(f)$; f in MHz; 53 dB maximum 6 dB minimum

For calculation of EL TCTL, the TCTL and the attenuation measurement of the test specimen with the same length as defined in 6.1 shall be used.

6.3.5 Alien (exogenous) near-end crosstalk (PS ANEXT)

The PS ANEXT (power-sum alien near-end crosstalk) of the cable when tested in accordance with IEC 61156-1 shall be not less than the values obtained from Table 7. The requirements from 0,1 MHz to 1 MHz are ffs.

Table 7 – PS ANEXT requirements

Cable type	Frequency range MHz	PS ANEXT dB
T1-C type cables	0,1 to 100	70
	100 to 600	$70 - 10 \log_{10}(f/100)$; f in MHz
T1-D type cables	0,1 to 100	75
	100 to 1 250	$75 - 10 \log_{10}(f/100)$; f in MHz

For screened cables meeting the requirements of 6.2.7 and 6.2.8 (minimum Type I) ANEXT is proven by design (ffs).

6.3.6 Alien (exogenous) far-end crosstalk (PS AACR-F)

The PS AACR-F (power-sum alien attenuation to crosstalk ratio far-end) of the cable when tested in accordance with IEC 61156-1 shall not be less than the values obtained from Table 8. The requirements from 0,1 MHz to 1 MHz are ffs.

For calculation of AACR-F, the AFEXT and the attenuation measurement of the test specimen with a length as specified in 6.1 shall be used.

Table 8 – PS AACR-F requirements

Cable type	Frequency range MHz	PS AACR-F dB
T1-C type cables	0,1 to 600	$98 - 20 \log_{10}(f)$; f in MHz
T1-D type cables	0,1 to 1 250	$103 - 20 \log_{10}(f)$; f in MHz

If AFEXT up to 600 MHz is greater than 90 dB for T1-C type cables or greater than 90 dB up to 1 GHz and greater than 80 dB from 1 GHz to 1,25 GHz for T1-D type cables, it might not be possible to calculate the AACR-F and it can be assumed the criteria according to Table 8 are met.

For those frequencies where the calculated limit value of PS AACR-F is greater than 75 dB for T1-C type cables, the requirement shall be 75 dB.

For those frequencies where the calculated limit value of PS AACR-F is greater than 80 dB for T1-D type cables, the requirement shall be 80 dB.

For screened cables meeting the requirements in accordance with 6.2.7 and 6.2.8 (minimum Type Ib), AFEXT is proven by design.

6.3.7 Alien (exogenous) crosstalk of bundled cables

The relevant requirements of this document – especially those of 6.3.5 and 6.3.6 – apply; see also Clause 7.

6.3.8 Impedance

The fitted or mean characteristic impedance measured in accordance with IEC 61156-1 shall be $100 \Omega \pm 5 \Omega$ at 100 MHz. A measurement of the input impedance is not sufficient to ensure return loss limits.

Recommendations given in IEC TR 61156-1-2 and IEC TR 61156-1-5 for improvement of measurement uncertainty can be considered.

6.3.9 Return loss (RL)

The minimum return loss of any pair in the frequency range indicated in Table 9 shall not be less than the values in Table 9.

Table 9 – RL requirements

Frequency range MHz	RL dB
0,1 to 1	$20 + 10 \log_{10} (f)$; f in MHz (ffs)
1 to 10	$20 + 5 \log_{10} (f)$; f in MHz
10 to 20	25
20 to 600	$25 - 7 \log_{10} (f/20)$; f in MHz 17,3 dB minimum
600 to 1 250 T1-D type cables only	$17,3 - 10 \log_{10} (f/600)$; f in MHz

When using a balun-less measurement technique, the corresponding descriptions of IEC TR 61156-1-2 can be considered. Recommendations contained in IEC TR 61156-1-5 for improvement of measurement uncertainty by a correction technique can be considered.

6.4 Mechanical and dimensional characteristics and requirements

6.4.1 Dimensional requirements

The overall diameter of insulation, the nominal thickness of the sheath and the maximum overall diameter of the sheath are not specified, but shall be indicated in the relevant detail specification.

6.4.2 Elongation at break of the conductor

The minimum elongation at break of the conductor shall be not less than 8 %.

6.4.3 Tensile strength of the insulation

The tensile strength of the insulation is not specified, but may be indicated in the relevant detail specification.

6.4.4 Elongation at break of the insulation

The minimum value of the elongation at break of the insulation shall be not less than 100 %.

6.4.5 Adhesion of the insulation to the conductor

The adhesion of the insulation to the conductor is not specified, but may be indicated in the relevant detail specification.

6.4.6 Elongation at break of the sheath

The minimum value of the elongation at break of any sheath shall be not less than 100 %.

6.4.7 Tensile strength of the sheath

The minimum tensile strength of any sheath shall be not less than 9 MPa.

6.4.8 Crush test of the cable

The crush resistance of the cable is not specified but may be indicated in the relevant detail specification.

6.4.9 Impact test of the cable

The impact resistance of the cable is not specified but may be indicated in the relevant detail specification.

6.4.10 Bending under tension

The bending performance of the cable is not specified but may be indicated in the relevant detail specification.

6.4.11 Repeated bending of the cable

Not applicable.

6.4.12 Tensile performance of the cable

The tensile strength of the cable is not specified but may be indicated in the relevant detail specification.

6.4.13 Shock-test requirements of the cable

Not applicable.

6.4.14 Bump-test requirements of the cable

Not applicable.

6.4.15 Vibration-test requirements of a cable

Not applicable.

6.5 Environmental characteristics

6.5.1 Shrinkage of the insulation

When tested at $(100 \pm 2) ^\circ\text{C}$ for 1 h, the shrinkage of the insulation shall not exceed 5 %. The length of the sample shall be 150 mm, and the shrink-back shall be measured as the sum from both ends.

6.5.2 Wrapping test of the insulation after thermal ageing

Not applicable.

6.5.3 Bending test of insulation at low temperature

The bending test of the insulated conductor shall be carried out at $(-20 \pm 2) ^\circ\text{C}$. The mandrel diameter shall be 6 mm. There shall be no cracks in the insulation.

6.5.4 Elongation at break of the sheath after ageing

The ageing regime shall be seven days at $(100 \pm 2) ^\circ\text{C}$. The elongation at break after ageing shall not be less than 50 % of the unaged value.