

INTERNATIONAL STANDARD

**Ferrite cores – Dimensions –
Part 12: Ring cores**

Withdrawing
IECNORM.COM: Click to view the full PDF of IEC 62317-12:2016



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2016 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

IECNORM.COM: Click to view the full document
PDF GENERATED BY IECNORM.COM
2016-12-20 17:12:20

INTERNATIONAL STANDARD

**Ferrite cores – Dimensions –
Part 12: Ring cores**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.100.10

ISBN 978-2-8322-3642-0

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Abbreviated terms	5
5 Primary standards	5
5.1 General	5
5.2 Dimensions of ring-cores.....	5
5.2.1 Designation of dimensions	5
5.2.2 Identification of standard sizes.....	6
5.2.3 Effective parameter values.....	6
5.2.4 Dimensional limits for standard sizes	6
5.3 Coating.....	14
Bibliography	15
Table 1 – Ring core dimension designations	6
Table 2 – Standard ring cores	7
Table 3 – Effective parameters of ring cores	9
Table 4 – Uncoated ring cores recommended dimensional limits	12

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FERRITE CORES – DIMENSIONS –**Part 12: Ring cores****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62317-12 has been prepared IEC technical committee 51: Magnetic components, ferrite and magnetic powder materials.

This first edition cancels and replaces the first edition of IEC TR 61604 published in 1997. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to IEC TR 61604:

- a) amendment of Clause 5 concerning the relationship between standard of European, Japanese and U.S.A. sizes;
- b) addition of Subclause 5.3 concerning coating.

The text of this standard is based on the following documents:

CDV	Report on voting
51/1128/CDV	51/1143/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 62317 series, under the general title *Ferrite cores – Dimensions*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

FERRITE CORES – DIMENSIONS –

Part 12: Ring cores

1 Scope

This part of IEC 62317 specifies the dimensions that are of importance for mechanical interchangeability for a preferred range of ring-cores, also called toroid cores, and the effective parameter values to be used in calculations involving them.

The selection of core sizes for this document is based on the philosophy of including those sizes which are industrial standards, meaning that they are in broad-based use within industry. See IEC 62317-1 for more detail concerning the philosophy of selecting core sizes to be included.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60205, *Calculation of the effective parameters of magnetic piece parts*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Abbreviated terms

ID inside diameter
OD outside diameter

5 Primary standards

5.1 General

Compliance with the following requirements ensures mechanical interchangeability of complete assemblies and wound coils.

5.2 Dimensions of ring-cores

5.2.1 Designation of dimensions

Table 1 describes the alphabetic character assignments for the dimensions of ferrite ring cores.

Table 1 – Ring core dimension designations

Letter	Dimension description
<i>A</i>	Outside diameter
<i>B</i>	Inside diameter
<i>C</i>	Height

5.2.2 Identification of standard sizes

Table 2 shows the nominal dimensions for the range of standard ring cores. Table 2 also shows, where applicable, the origin and regional name of each standard size, whether from historical European sizes, historical Japanese sizes, or historical USA sizes. The previous IEC Technical Report, 61604, detailed the different ring sizes that were tooled and commonly used in the three distinct geographic regions. IEC TR 61604 laid the groundwork for the present standard, which reflects the more global nature of the industry, compared with the time when ferrite standards were evolving in different parts of the world. Manufacturers tend to have more globally complete offerings of ring sizes than before, leading to a profusion of different sizes.

The number of different ring sizes used in total is quite large, far in excess of the 82 commonly known standard sizes shown here, for a couple of reasons: ring cores are relatively inexpensive to build tooling for, nor does a new ring core require an expensive new coil former to be tooled up, meaning that custom ring cores are often commercially practical. Ferrite rings, lacking a residual air gap, such as E-cores and other shapes have at their mating surfaces, exhibit directly the full magnetic performance possible in the ferrite material, meaning that tooling up precisely optimal new dimensions can give a significant advantage to a designer who is optimizing for best possible performance.

5.2.3 Effective parameter values

The effective parameter values for the standard ring cores are given in Table 3. For global practicality and simplicity, the effective parameters in this document are calculated from the nominal dimensions assuming cores of rectangular cross section, and are useful for reference and comparison of cores. For cores having a cross section with an appreciable average rounding radius, more precise values can be calculated from the method given in IEC 60205, if required.

5.2.4 Dimensional limits for standard sizes

The standard tolerance limits for uncoated ring cores are given in Table 4. Manufacturers may choose to offer looser standard limits for ferrite materials that exhibit greater process variability, or tighter limits for applications that justify higher processing and yield costs to achieve narrower dimensional range.

The limits take account of shrinkage variation and warping during firing. The specification for out-of-round condition of the inner or outer circumference is that the inside diameter (ID) and outside diameter (OD) must stay within the indicated limits, measured at any point. Similarly, the specification for non-flat condition of the sides of a ring is that the height minimum and maximum must be achieved at all points.

Table 2 – Standard ring cores (1 of 3)

Nominal uncoated dimensions			Size reference
<i>A</i> mm	<i>B</i> mm	<i>C</i> mm	
2,5	1,3	1,3	
2,5	1,5	0,8	
2,5	1,5	1,0	Europe R2,5
3,1	1,3	1,3	
3,1	1,8	2,0	
3,5	1,8	1,3	
3,9	1,8	1,8	
3,9	2,2	1,3	USA T3,9
4,0	2,0	2,0	
4,0	2,2	1,6	Europe R4
4,83	2,29	1,27	USA T4,8
5,84	3,05	1,52	USA T5,8
6,0	3,0	2,0	
6,0	4,0	2,0	
6,3	3,8	2,5	Europe R6,3
7,62	3,18	4,78	USA T7,6
8,0	4,0	2,0	
8,2	3,7	4,0	
9,0	6,0	3,0	
9,53	4,75	3,18	USA T9,5
10,0	5,0	4,0	
10,0	5,0	5,0	Japan FOR 10
10,0	6,0	4,0	Europe R10
12,0	6,0	4,0	Japan FOR12
12,7	7,1	5,1	
12,7	7,92	6,35	USA T12,7
13,2	7,4	4,0	
13,6	7,0	3,5	
14,0	8,0	7,0	
14,0	9,0	5,0	
15,88	8,89	4,7	USA T15,9
16,0	9,0	5,0	
16,0	9,6	6,3	Europe R16
16,0	12,0	8,0	
18,0	10,0	10,0	Japan FOR 18
18,5	9,8	10,3	Japan FOR 19
20,0	10,0	7,0	Europe R20

Table 2 (2 of 3)

Nominal uncoated dimensions				Size reference
A mm	B mm	C mm		
20,0	12,0	10,0		Japan FOR 20
22,0	14,0	10,0		Japan FOR 22
22,1	13,72	6,35		USA T22,1
25,0	15,0	10,0		Europe R25
25,0	15,0	12,0		Japan FOR 25
25,4	15,49	9,53		USA T25,4
26,9	14,2	12,2		
28,0	16,0	13,0		Japan FOR 28
29,0	19,0	7,49		USA T29,0
30,8	19,1	12,7		
31,0	19,0	13,0		Japan FOR 31
32,0	19,0	13,0		
36,0	23,0	10,0		USA T36,0
36,0	23,0	15,0		Europe R36
38,0	19,0	13,0		Japan FOR 38
38,0	22,0	13,0		
38,1	19,0	6,35		USA T38,1
40,0	24,0	16,0		Europe R40
40,0	24,0	20,0		
41,8	26,2	18,0		
44,5	30,0	13,0		Japan FOR 45
47,0	27,0	15,0		Japan FOR 47
49,1	31,8	15,9		
49,1	33,8	15,9		
50,0	30,0	20,0		Europe R50
51,0	32,0	19,0		
55,0	32,0	19,0		
58,0	41,0	18,0		
61,0	35,6	12,7		
63,0	38,0	25,0		Europe R63
68,0	48,0	13,0		
72,0	48,0	20,0		
73,7	38,9	12,7		USA T73,7
80,0	40,0	15,0		
80,0	50,0	20,0		
85,7	55,5	12,7		
96,0	70,0	20,0		

Table 2 (3 of 3)

Nominal uncoated dimensions			Size reference
A mm	B mm	C mm	
102,0	65,0	15,0	
104,0	80,0	20,0	
107,0	65,0	18,0	
127,0	89,0	20,0	
140,0	106,0	25,0	
152,0	104,0	19,0	
202,0	153,0	25,0	
305,0	207,0	30,0	

Table 3 – Effective parameters of ring cores (1 of 3)

A mm	B mm	C mm	C ₁ mm ⁻¹	C ₂ mm ⁻³	A _e mm ²	l _e mm	V _e mm ³
2,5	1,3	1,3	7,3911	9,8183	0,753	5,56	4,19
2,5	1,5	0,8	15,375	39,281	0,391	6,02	2,36
2,5	1,5	1,0	12,300	25,140	0,489	6,02	2,94
3,1	1,3	1,3	5,5616	5,0603	1,10	6,11	6,72
3,1	1,8	2,0	5,7791	4,5560	1,27	7,33	9,30
3,5	1,8	1,3	7,2683	6,8236	1,07	7,74	8,25
3,9	1,8	1,8	4,5146	2,5101	1,80	8,12	14,6
3,9	2,2	1,3	8,7610	8,3338	1,05	9,21	9,68
4,0	2,0	2,0	4,5324	2,3584	1,92	8,71	16,7
4,0	2,2	1,6	6,5687	4,6991	1,40	9,18	12,8
4,83	2,29	1,27	6,6293	4,3045	1,54	10,2	15,7
5,84	3,05	1,52	6,3635	3,1081	2,05	13,0	26,7
6,0	3,0	2,0	4,5324	1,5723	2,88	13,1	37,7
6,0	4,0	2,0	7,7481	3,9274	1,97	15,3	30,2
6,3	3,8	2,5	4,9714	1,6250	3,06	15,2	46,5
7,62	3,18	4,78	1,5042	0,15100	9,96	15,0	149
8,0	4,0	2,0	4,5324	1,1792	3,84	17,4	67,0
8,2	3,7	4,0	1,9739	0,23114	8,54	16,9	144
9,0	6,0	3,0	5,1654	1,1637	4,44	22,9	102
9,53	4,75	3,18	2,8376	0,38869	7,30	20,7	151
10,0	5,0	4,0	2,2662	0,23584	9,61	21,8	209
10,0	5,0	5,0	1,8129	0,15094	12,0	21,8	262
10,0	6,0	4,0	3,0750	0,39281	7,83	24,1	188

Table 3 (2 of 3)

A mm	B mm	C mm	C_1 mm ⁻¹	C_2 mm ⁻³	A_e mm ²	l_e mm	V_e mm ³
12,0	6,0	4,0	2,266 2	0,196 53	11,5	26,1	301
12,7	7,1	5,1	2,118 6	0,152 59	13,9	29,4	408
12,7	7,92	6,35	2,095 4	0,140 65	14,9	31,2	465
13,2	7,4	4,0	2,714 2	0,240 59	11,3	30,6	345
13,6	7,0	3,5	2,703 0	0,242 75	11,1	30,1	335
14,0	8,0	7,0	1,604 0	0,078 393	20,5	32,8	671
14,0	9,0	5,0	2,844 1	0,231 26	12,3	35,0	430
15,88	8,89	4,7	2,304 4	0,144 26	16,0	36,8	588
16,0	9,0	5,0	2,184 1	0,128 29	17,0	37,2	633
16,0	9,6	6,3	1,952 4	0,098 969	19,7	38,5	760
16,0	12,0	8,0	2,730 1	0,171 81	15,9	43,4	689
18,0	10,0	10,0	1,069 0	0,027 502	38,9	41,5	1 610
18,5	9,8	10,3	0,960 07	0,022 158	43,3	41,6	1 800
20,0	10,0	7,0	1,295 0	0,038 504	33,6	43,6	1 460
20,0	12,0	10	1,230 0	0,031 425	39,1	48,1	1 880
22,0	14,0	10,0	1,390 1	0,035 349	39,3	54,7	2 150
22,1	13,72	6,35	2,075 6	0,079 499	26,1	54,2	1 410
25,0	15,0	10,0	1,230 0	0,025 140	48,9	60,2	2 940
25,0	15,0	12,0	1,025 0	0,017 458	58,7	60,2	3 530
25,4	15,49	9,53	1,333 1	0,028 812	46,3	61,7	2 850
26,9	14,2	12,2	0,806 12	0,010 764	74,9	60,4	4 520
28,0	16,0	13,0	0,863 67	0,011 365	76,0	65,6	4 990
29,0	19,0	7,49	1,983 8	0,053 767	36,9	73,2	2 700
30,8	19,1	12,7	1,035 4	0,014 203	72,9	75,5	5 500
31,0	19,0	13,0	0,987 28	0,012 912	76,5	75,5	5 770
32,0	19,0	13,0	0,927 15	0,011 223	82,6	76,6	6 330
36,0	23,0	10,0	1,402 4	0,021 939	63,9	89,6	5 730
36,0	23,0	15,0	0,934 95	0,009 750 7	95,9	89,6	8 600
38,0	19,0	13,0	0,697 29	0,005 875 7	119	82,7	9 820
38,0	22,0	13,0	0,884 32	0,008 716 9	101	89,7	9 100
38,1	19,0	6,35	1,422 1	0,024 412	58,3	8,8	4 830
40,0	24,0	16,0	0,768 75	0,006 137 6	125	96,3	12 100
40,0	24,0	20,0	0,615 00	0,003 928 1	157	96,3	15 100
41,8	26,2	18,0	0,747 25	0,005 419 8	138	103	14 200
44,5	30,0	13,0	1,225 8	0,013 175	93,0	114	10 600
47,0	27,0	15,0	0,755 68	0,005 168 2	146	110	16 200
49,1	31,8	15,9	0,909 70	0,006 719 0	135	123	16 700

Table 3 (3 of 3)

A mm	B mm	C mm	C_1 mm ⁻¹	C_2 mm ⁻³	A_e mm ²	l_e mm	V_e mm ³
49,1	33,8	15,9	1,058 3	0,008 802 2	120	127	15 300
50,0	30,0	20,0	0,615 00	0,003 142 5	196	120	23 600
51,0	32,0	19,0	0,709 51	0,004 002 5	177	126	22 300
55,0	32,0	19,0	0,610 59	0,002 863 4	213	130	27 800
58,0	41,0	18,0	1,006 3	0,006 643 5	151	152	23 100
61,0	35,6	12,7	0,918 69	0,005 834 9	157	145	22 800
63,0	38,0	25,0	0,497 14	0,001 625 0	306	152	46 500
68,0	48,0	13,0	1,387 6	0,010 782	129	179	23 000
72,0	48,0	20,0	0,774 81	0,003 272 9	237	183	43 400
73,7	38,9	12,7	0,774 23	0,003 624 5	214	165	35 300
80,0	40,0	15,0	0,604 31	0,002 096 3	288	174	50 200
80,0	50,0	20,0	0,668 42	0,002 269 4	295	197	58 000
85,7	55,5	12,7	1,138 7	0,006 031 9	189	215	40 600
96,0	70,0	20,0	0,994 64	0,003 857 4	258	256	66 100
102,0	65,0	15,0	0,929 63	0,003 407 1	273	254	69 200
104,0	80,0	20,0	1,197 4	0,005 017 9	239	286	68 200
107,0	65,0	18,0	0,700 31	0,001 891 4	370	259	96 000
127,0	89,0	20,0	0,883 58	0,002 349 8	376	332	125 000
140,0	106,0	25,0	0,903 39	0,002 139 4	422	381	161 000
152,0	104,0	19,0	0,871 42	0,001 934 0	451	393	177 000
202,0	153,0	25,0	0,904 61	0,001 486 4	609	551	335 000
305,0	207,0	30,0	0,540 36	0,000 372 22	1450	784	1 140 000

Table 4 – Uncoated ring cores recommended dimensional limits (1 of 3)

<i>A</i> mm	Min. mm	Max. mm	<i>B</i> mm	Min. mm	Max. mm	<i>C</i> mm	Min. mm	Max. mm
2,5	2,35	2,65	1,3	1,15	1,45	1,3	1,15	1,45
2,5	2,35	2,65	1,5	1,35	1,65	0,8	0,65	0,95
2,5	2,35	2,65	1,5	1,35	1,65	1,0	0,85	1,15
3,1	2,95	3,25	1,3	1,15	1,45	1,3	1,15	1,45
3,1	2,95	3,25	1,8	1,65	1,95	2,0	1,85	2,15
3,5	3,35	3,65	1,8	1,65	1,95	1,3	1,15	1,45
3,9	3,75	4,05	1,8	1,65	1,95	1,8	1,65	1,95
3,9	3,79	4,09	2,2	2,09	2,39	1,3	1,12	1,42
4,0	3,80	4,20	2,0	1,85	2,15	2,0	1,85	2,15
4,0	3,80	4,20	2,2	2,05	2,35	1,6	1,45	1,75
4,83	4,63	5,03	2,29	2,14	2,44	1,27	1,12	1,42
5,84	5,64	6,04	3,05	2,90	3,20	1,52	1,37	1,67
6,0	5,80	6,20	3,0	2,85	3,15	2,0	1,85	2,15
6,0	5,80	6,20	4,0	3,85	4,15	2,0	1,85	2,15
6,3	6,10	6,50	3,8	3,65	3,95	2,5	2,35	2,65
7,62	7,42	7,82	3,18	3,03	3,33	4,78	4,48	5,08
8,0	7,80	8,20	4,0	3,85	4,15	2,0	1,85	2,15
8,2	8,00	8,40	3,7	3,55	3,85	4,0	3,75	4,25
9,0	8,70	9,30	6,0	5,80	6,20	3,0	2,80	3,20
9,53	9,23	9,83	4,75	4,55	4,95	3,18	3,03	3,33
10,0	9,70	10,30	5,0	4,80	5,20	4,0	3,85	4,15
10,0	9,70	10,30	5,0	4,80	5,20	5,0	4,85	5,15
10,0	9,70	10,30	6,0	5,80	6,20	4,0	3,85	4,15
12,0	11,60	12,40	6,0	5,75	6,25	4,0	3,85	4,15
12,7	12,30	13,10	7,1	6,85	7,35	5,1	4,90	5,30
12,7	12,30	13,10	7,92	7,67	8,17	6,35	6,15	6,55
13,2	12,80	13,60	7,4	7,15	7,65	4,0	3,85	4,15
13,6	13,20	14,00	7,0	6,75	7,25	3,5	3,35	3,65
14,0	13,50	14,50	8,0	7,70	8,30	7,0	6,80	7,20
14,0	13,50	14,50	9,0	8,70	9,30	5,0	4,80	5,20
15,88	15,38	16,38	8,89	8,59	9,19	4,7	4,50	4,90
16,0	15,50	16,50	9,0	8,70	9,30	5,0	4,80	5,20
16,0	15,50	16,50	9,6	9,30	9,90	6,3	6,10	6,50
16,0	15,50	16,50	12,0	11,70	12,30	8,0	7,70	8,30

Table 4 (2 of 3)

<i>A</i> mm	Min. mm	Max. mm	<i>B</i> mm	Min. mm	Max. mm	<i>C</i> mm	Min. mm	Max. mm
18,0	17,40	18,60	10,0	9,70	10,30	10,0	9,70	10,30
18,5	17,90	19,10	9,8	9,50	10,10	10,3	10,00	10,60
20,0	19,40	20,60	10,0	9,70	10,30	7,0	6,80	7,20
20,0	19,40	20,60	12,0	11,70	12,30	10,0	9,70	10,30
22,0	21,40	22,60	14,0	13,60	14,40	10,0	9,70	10,30
22,1	21,50	22,70	13,72	13,32	14,12	6,35	6,15	6,55
25,0	24,25	25,75	15,0	14,50	15,50	10,0	9,70	10,30
25,0	24,25	25,75	15,0	14,50	15,50	12,0	11,60	12,40
25,4	24,65	26,15	15,49	14,99	15,99	9,53	9,23	9,83
26,9	26,15	27,65	14,2	13,70	14,70	12,2	11,80	12,60
28,0	27,25	28,75	16,0	15,50	16,50	13,0	12,50	13,50
29,0	28,00	30,00	19,0	18,40	19,60	7,49	7,09	7,89
30,8	29,80	31,80	19,1	18,50	19,70	12,7	12,30	13,10
31,0	30,00	32,00	19,0	18,40	19,60	13,0	12,60	13,40
32,0	31,00	33,00	19,0	18,40	19,60	13,0	12,60	13,40
36,0	34,90	37,10	23,0	22,30	23,70	10,0	9,70	10,30
36,0	34,90	37,10	23,0	22,30	23,70	15,0	14,50	15,50
38,0	36,80	39,20	19,0	18,30	19,70	13,0	12,50	13,50
38,0	36,80	39,20	22,0	21,30	22,70	13,0	12,50	13,50
38,1	36,90	39,30	19,0	18,30	19,70	6,35	6,05	6,65
40,0	38,80	41,20	24,0	23,30	24,70	16,0	15,50	16,50
40,0	38,80	41,20	24,0	23,30	24,70	20,0	19,30	20,70
41,8	40,60	43,00	26,2	25,50	26,90	18,0	17,40	18,60
44,5	43,15	45,85	30,0	29,20	30,80	13,0	12,60	13,40
47,0	45,65	48,35	27,0	26,20	27,80	15,0	14,50	15,50
49,1	47,60	50,60	31,8	30,90	32,70	15,9	15,40	16,40
49,1	47,60	50,60	33,8	32,90	34,70	15,9	15,30	16,50
50,0	48,50	51,50	30,0	29,10	30,90	20,0	19,40	20,60
51,0	49,50	52,50	32,0	31,10	32,90	19,0	18,40	19,60
55,0	53,30	56,70	32,0	31,10	32,90	19,0	18,40	19,60
58,0	56,30	59,70	41,0	40,10	41,90	18,0	17,40	18,60
61,0	59,10	62,90	35,6	34,50	36,70	12,7	12,20	13,20
63,0	61,10	64,90	38,0	36,90	39,10	25,0	24,20	25,80
68,0	66,10	69,90	48,0	46,80	49,20	13,0	12,50	13,50
72,0	70,00	74,00	48,0	46,80	49,20	20,0	19,40	20,60
73,7	71,70	75,70	38,9	37,70	40,10	12,7	12,20	13,20
80,0	77,60	82,40	40,0	38,80	41,20	15,0	14,40	15,60

Table 4 (3 of 3)

<i>A</i> mm	Min. mm	Max. mm	<i>B</i> mm	Min. mm	Max. mm	<i>C</i> mm	Min. mm	Max. mm
80,0	77,60	82,40	50,0	48,80	51,20	20,0	19,20	20,80
85,7	83,30	88,10	55,5	54,10	56,90	12,7	12,10	13,30
96,0	93,20	98,80	70,0	68,00	72,00	20,0	19,20	20,80
102,0	99,00	105,00	65,0	63,00	67,00	15,0	14,40	15,60
104,0	101,00	107,00	80,0	77,50	82,50	20,0	19,20	20,80
107,0	104,00	110,00	65,0	63,00	67,00	18,0	17,20	18,80
127,0	123,00	131,00	89,0	86,50	91,50	20,0	19,20	20,80
140,0	136,00	144,00	106,0	103,00	109,00	25,0	24,20	25,80
152,0	147,50	156,50	104,0	101,00	107,00	19,0	18,20	19,80
202,0	196,00	208,00	153,0	149,00	157,00	25,0	24,00	26,00
305,0	296,00	314,00	207,0	202,00	212,00	36,0	29,00	31,00

5.3 Coating

A variety of materials are used to provide dielectric protection by coating the surfaces of the ring cores to form a barrier. These include epoxies, polyurethanes, nylons, and paraxylolones.

Manufacturers generally specify limits for maximum OD with coating, minimum ID with coating, and maximum height with coating. The limits take into account bare core variation and coating variation.

Minimum OD, maximum ID, and minimum height are either not specified, or are considered of secondary importance, since coating cannot have a negative thickness. The thickness of the coating is not directly specified or measured. Coating is controlled for adequate thickness by means of voltage breakdown testing and visual inspection.