

# INTERNATIONAL STANDARD



**Printed electronics –  
Part 203: Materials – Semiconductor ink**

IECNORM.COM : Click to view the full PDF of IEC 62899-203:2018



## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2018 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

#### IEC Catalogue - [webstore.iec.ch/catalogue](http://webstore.iec.ch/catalogue)

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

#### IEC publications search - [webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

#### IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

#### Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing 21 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

#### IEC Glossary - [std.iec.ch/glossary](http://std.iec.ch/glossary)

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

#### IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [sales@iec.ch](mailto:sales@iec.ch).

IECNORM.COM : Click to view the full text of IEC 60389-23:2018

# INTERNATIONAL STANDARD



**Printed electronics –  
Part 203: Materials – Semiconductor ink**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

ICS 29.045; 87.080

ISBN 978-2-8322-6073-9

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

|                                                                                                             |    |
|-------------------------------------------------------------------------------------------------------------|----|
| FOREWORD.....                                                                                               | 4  |
| INTRODUCTION.....                                                                                           | 6  |
| 1 Scope.....                                                                                                | 7  |
| 2 Normative references .....                                                                                | 7  |
| 3 Terms and definitions .....                                                                               | 8  |
| 4 Atmospheric conditions for evaluation and conditioning .....                                              | 10 |
| 5 Evaluation of properties of semiconductor ink.....                                                        | 10 |
| 5.1 Specimen.....                                                                                           | 10 |
| 5.2 Contents .....                                                                                          | 10 |
| 5.2.1 Solid contents.....                                                                                   | 10 |
| 5.2.2 Non-volatile content.....                                                                             | 10 |
| 5.3 Physical properties .....                                                                               | 11 |
| 5.3.1 Density .....                                                                                         | 11 |
| 5.3.2 Rheology .....                                                                                        | 11 |
| 5.3.3 Surface tension .....                                                                                 | 12 |
| 5.3.4 Flash point.....                                                                                      | 12 |
| 5.3.5 Evaporation rate .....                                                                                | 12 |
| 6 Properties of semiconductive layer .....                                                                  | 13 |
| 6.1 Semiconductor type .....                                                                                | 13 |
| 6.2 Test piece .....                                                                                        | 13 |
| 6.2.1 General .....                                                                                         | 13 |
| 6.2.2 Substrate.....                                                                                        | 13 |
| 6.2.3 Semiconductor ink .....                                                                               | 13 |
| 6.2.4 Dimensions of test piece.....                                                                         | 13 |
| 6.2.5 Preparation of test piece.....                                                                        | 14 |
| 6.3 Electrical properties .....                                                                             | 14 |
| 6.3.1 Charge mobility .....                                                                                 | 14 |
| 6.3.2 Dielectric properties.....                                                                            | 14 |
| 6.3.3 Ionisation potential .....                                                                            | 15 |
| 6.4 Optical properties .....                                                                                | 15 |
| 6.4.1 Overview .....                                                                                        | 15 |
| 6.4.2 Luminous transmittance.....                                                                           | 15 |
| 6.4.3 Chromaticity .....                                                                                    | 16 |
| 6.4.4 Uniformity of colour .....                                                                            | 16 |
| 6.4.5 Haze.....                                                                                             | 18 |
| 6.4.6 Refractive index.....                                                                                 | 18 |
| 6.4.7 Luminous transmittance.....                                                                           | 18 |
| 7 Storage .....                                                                                             | 19 |
| 7.1 Storage conditions .....                                                                                | 19 |
| 7.2 Method for measuring deterioration caused by ageing .....                                               | 19 |
| Annex A (informative) Example of measurements for measuring the deterioration of ink caused by ageing ..... | 20 |
| Annex B (informative) Example of chromacity uniformity measurement test points .....                        | 21 |
| Bibliography.....                                                                                           | 22 |

|                                                                                                                    |    |
|--------------------------------------------------------------------------------------------------------------------|----|
| Figure A.1 – Example of a series of TFT mobility measurements for an ink to evaluate deterioration over time ..... | 20 |
| Figure B.1 – Chromacity uniformity test point locations .....                                                      | 21 |

IECNORM.COM : Click to view the full PDF of IEC 62899-203:2018

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## PRINTED ELECTRONICS –

## Part 203: Materials – Semiconductor ink

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62899-203 has been prepared by IEC technical committee 119: Printed Electronics.

The text of this International Standard is based on the following documents:

| FDIS         | Report on voting |
|--------------|------------------|
| 119/226/FDIS | 119/234/RVD      |

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 62899 series, published under the general title *Printed electronics*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

**IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.**

IECNORM.COM : Click to view the full PDF of IEC 62899-203:2018

## INTRODUCTION

The IEC 62899 series deals mainly with evaluation methods for materials of printed electronics. The series also includes storage methods, packaging and marking, and transportation conditions.

The IEC 62899 series is divided into several parts according to each material. Each part is prepared as a generic specification containing fundamental information for the area of printing electronics.

The IEC 62899 series consists of the following parts:

Part 1: Terminology

Part 201: Materials – Substrates

Part 202: Materials – Conductive ink

Part 203: Materials – Semiconductor ink

Part 250: Material technologies required in printed electronics for wearable smart devices

Part 301-X: Equipment – Contact printing – Rigid master

Part 302-X: Equipment – Inkjet

Part 303-X: Equipment – Roll-to-roll printing

Part 401: Printability – Overview

Part 402-X: Printability – Measurement of qualities

Part 403-X: Printability – Requirements for reproducibility

Part 502-X: Quality assessment – Organic light emitting diode (OLED) elements

Furthermore, sectional specifications, blank detail specifications, and detail specifications for each material will be based on these parts.

This part of IEC 62899 is prepared for semiconducting materials used in printed electronics and contains the test conditions, the evaluation methods and the storage conditions.

## PRINTED ELECTRONICS –

### Part 203: Materials – Semiconductor ink

#### 1 Scope

This part of IEC 62899 defines terms and specifies standard methods for characterisation and evaluation.

This document is applicable to semiconductor inks and semiconductive layers that are made from semiconductor inks.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 62860, *Test methods for the characterization of organic transistors and materials*

ISO 5-2, *Photography and graphic technology – Density measurements – Part 2: Geometric conditions for transmittance density*

ISO 5-3, *Photography and graphic technology – Density measurements – Part 3: Spectral conditions*

ISO 124, *Latex, rubber – Determination of total solids content*

ISO 291, *Plastics – Standard atmospheres for conditioning and testing*

ISO 304, *Surface active agents – Determination of surface tension by drawing up liquid films*

ISO 489:1999, *Plastics – Determination of refractive index*

ISO 758, *Liquid chemical products for industrial use – Determination of density at 20°C*

ISO 1183-1, *Plastics – Methods for determining the density of non-cellular plastics – Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 2555, *Plastics – Resins in the liquid state or as emulsions or dispersions – Determination of apparent viscosity by the Brookfield Test method*

ISO 2592, *Petroleum and related products – Determination of flash and fire points – Cleveland closed cup method*

ISO 2719, *Determination of flash point – Pensky-Martens closed cup method*

ISO 2811-1, *Paints and varnishes – Determination of density – Part 1: Pycnometer method*

ISO 2811-2, *Paints and varnishes – Determination of density – Part 2: Immersed body (plummet) method*

ISO 2884-1, *Paints and varnishes – Determination of viscosity using rotary viscometers – Part 1: Cone-and-plate viscometer operated at a high rate of shear*

ISO 3219, *Plastics – Polymers/resins in the liquid state or as emulsions or dispersions – Determination of viscosity using a rotational viscometer with defined shear rate*

ISO 3251, *Paints, varnishes and plastics – Determination of non-volatile-matter content*

ISO 3664, *Graphic technology and photography – Viewing conditions*

ISO 3679, *Determination of flash no-flash and flash point – Rapid equilibrium closed cup method*

ISO 13468-1:1996, *Plastics – Determination of the total luminous transmittance of transparent materials – Part 1: Single-beam instrument*

ISO 13468-2:1999, *Plastics – Determination of the total luminous transmittance of transparent materials – Part 2: Double-beam instrument*

ISO 13655, *Graphic technology – Spectral measurement and colorimetric computation for graphic arts images*

ISO 14488, *Particulate materials – Sampling and sample splitting for the determination of particulate properties*

ISO 14782, *Plastics – Determination of haze for transparent materials*

ISO 15212-1, *Oscillation-type density meters – Part 1: Laboratory instruments*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 62860 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

NOTE The terms in italic font are those defined in Clause 3.

#### 3.1

##### **semiconductive material**

ingredient of a printing or coating material, which itself is electrically semiconductive

#### 3.2

##### **semiconductor ink**

liquid in which one or more particles, small molecules or polymers are dissolved or dispersed, and which becomes an electrically *semiconductive layer* through solvent removal or post treatment such as UV, photonic, or thermal processing

### 3.3

#### **semiconductive layer**

film-like semiconductive body of material made of *semiconductor ink* (3.2), which is printed or coated on a substrate, followed, as necessary, by using a post treatment such as UV, photonic, or thermal processing

### 3.4

#### **semiconductor film**

substrate (sheet or roll) with *semiconductive layer* (3.3)

### 3.5

#### **solid content**

mass fraction of an ingredient which effectively functions as a *semiconductive material* dissolved or dispersed in a solvent to form a *semiconductor ink* (3.2)

Note 1 to entry: In some instances the ink may include insulating materials, sometimes referred to as binders, or other additives included to improve the film formation during coating or printing.

### 3.6

#### **non-volatile content**

mass fraction of residue obtained by evaporation of the volatile solvent under specific conditions, in *semiconductor ink* (3.2)

### 3.7

#### **dispersion**

heterogeneous system in which fine separated materials are distributed uniformly in other materials

### 3.8

#### **flash point**

lowest liquid temperature at which, under certain standardized conditions, a liquid gives off vapours in quantity such as to be capable of forming an ignitable vapour/air mixture

[SOURCE: IEC 60050-212:2010, 212-18-05]

### 3.9

#### **field effect mobility**

majority carrier mobility of *semiconductive material* derived through the transfer curve measurement of a fabricated *TFT* device

Note 1 to entry: The field effect mobility is usually derived from either saturation or linear approximations.

Note 2 to entry: Field effect mobility is given in units of  $\text{cm}^2/\text{V}\cdot\text{s}$ .

### 3.10

#### **thin-film transistor**

##### **TFT**

switching device made from three electrodes (source, drain and gate) and semiconducting and insulating layers wherein potentials applied to a gate electrode modulate charge carriers on the opposite side of the insulating layer situated between the gate and *semiconductive layer*

Note 1 to entry: The change in charge density in the *semiconductive layer* changes its conductivity, and this in turn allows a modulation in current flow between the source and drain electrodes for a given source-drain potential difference.

Note 2 to entry: *TFTs* are found in a wide variety of electronic devices such as integrated circuits and display backplanes.

## 4 Atmospheric conditions for evaluation and conditioning

The standard atmosphere for evaluation (test and measurement) and storage of the specimen shall be a temperature of  $(23 \pm 2) ^\circ\text{C}$  and relative humidity of  $(50 \pm 10) \%$ , conforming to standard atmosphere class 2 specified in ISO 291. If a polymer substrate is used for a test piece coated with a semiconductive layer, the standard atmosphere for evaluation shall be a temperature of  $(23 \pm 1) ^\circ\text{C}$  and relative humidity of  $(50 \pm 5) \%$ , conforming to standard atmosphere class 1 specified in ISO 291.

If conditioning is necessary, the same standard atmosphere as specified above shall apply.

## 5 Evaluation of properties of semiconductor ink

### 5.1 Specimen

The specimen for evaluation shall be prepared according to ISO 14488 or an equivalent method. If necessary, dilution by a compatible solvent may be allowed. For semiconductor inks, in many cases the properties to be evaluated could be influenced by the choice of solvent and method of deposition. Consideration of the likely effects of solvent choice and ink deposition should be made in light of the semiconductor chemistry and/or the ink composition.

### 5.2 Contents

#### 5.2.1 Solid contents

##### 5.2.1.1 Determination of solid content

Solid content of semiconductive materials and non-semiconductive materials shall be determined by the theoretical mass fraction (expressed as a percentage) of functional ingredients to the total ink mass. Functional ingredients include semiconductive materials, their precursors or binders, or any additives.

##### 5.2.1.2 Report of the results

The report shall include the following items:

- a) unique specimen identification;
- b) date of test;
- c) atmospheric conditions of test;
- d) solid content.

#### 5.2.2 Non-volatile content

##### 5.2.2.1 Principle

Non-volatile content is determined by measuring the mass of residue after evaporation of the volatile ingredients and calculating the mass fraction (expressed as a percentage) to the total ink mass.

##### 5.2.2.2 Test method

The test method shall be as specified in ISO 3251 with the following exceptions:

- a) Air pressure: 86 kPa to 106 kPa.
- b) If specified by the manufacturer, the test may be performed under reduced pressure. The conditions and procedures for reducing the pressure shall be as specified in ISO 124 or by the manufacturer.
- c) The materials which do not react with the ink during an examination shall be used.

d) Repeat the test until the weight becomes constant within 5 %.

#### **5.2.2.3 Report of the results**

The report shall include the following items:

- a) specimen identification;
- b) test conditions (air pressure if reduced, drying temperature and time);
- c) specimen mass;
- d) results.

### **5.3 Physical properties**

#### **5.3.1 Density**

##### **5.3.1.1 Measuring method**

The measuring method shall either be the pycnometer method as specified in ISO 758, ISO 1183-1 and ISO 2811-1, the method using oscillation-type density meters as specified in ISO 15212-1, or the immersed body (plummet) method as specified in ISO 2811-2. The detailed product specifications shall specify the measuring method to be used.

##### **5.3.1.2 Equipment**

Equipment shall be as specified in the measurement method (see 5.3.1.1) or shall be equipment considered equivalent or superior.

##### **5.3.1.3 Report of the results**

The report shall include the following items:

- a) specimen identification;
- b) measurement method;
- c) measurement atmosphere (temperature and relative humidity);
- d) results.

#### **5.3.2 Rheology**

##### **5.3.2.1 Measuring method**

Viscosity shall be measured using a Brookfield type rotational viscometer as specified in ISO 2555, cone-and-plate viscometer as specified in ISO 2884-1, or rotational viscometer as specified in ISO 3219.

The detailed product specifications shall specify the measuring method and measuring temperature to be used.

##### **5.3.2.2 Report of the results**

The report shall include the following items:

- a) standard number of the measurement method;
- b) specimen identification;
- c) measuring temperature;
- d) viscometer model;
- e) viscosity expressed in millipascal second (mPa·s) at (a) shear rate(s) appropriate to the printing method(s) for which the ink is proposed to be used by the supplier.

### **5.3.3 Surface tension**

#### **5.3.3.1 Measuring method**

Surface tension shall be measured using the drawing up liquid film (Wilhelmy) method as specified in ISO 304 with the following exceptions:

- a) equipment considered equivalent to that in ISO 304 may be used;
- b) the test jig shall be made of platinum;
- c) the equipment shall be calibrated using pure water and a hanging weight.

#### **5.3.3.2 Report of the results**

The report shall include the following items:

- a) specimen identification;
- b) measuring temperature;
- c) surface tension expressed in millinewton per metre (mN/m).

### **5.3.4 Flash point**

#### **5.3.4.1 Measuring method**

Flash point shall be measured according to ISO 2592 in the case of an open system. The method of "open system" is preferable for safety, however, "closed systems" are also widely used. The measurement method based on ISO 2719 (closed system) and ISO 3679 (closed system) may be applied if a closed system is required.

#### **5.3.4.2 Report of the results**

The report shall include the following items:

- a) specimen identification;
- b) test conditions (temperature, humidity and atmospheric pressure);
- c) sampling conditions (type of ink used, dispersive media and concentration);
- d) results;
- e) others (special items).

### **5.3.5 Evaporation rate**

#### **5.3.5.1 General**

The evaporation rate is a property which is necessary for the printed electronics ink, but the details of the evaluation condition and the measuring method are significantly different for the ink. In this document, a common framework for the method is specified as a guideline. The detailed conditions and measurements may be determined between trading partners depending on the properties of the ink.

#### **5.3.5.2 Measuring method**

The evaporation rate of solvent from an ink formulation can be determined by measuring the time taken for 90% of the mass of the solvent content of the ink formulation to evaporate.

A flat absorbent material (such as a filter paper) is positioned on a sensitive mass balance located inside a dry air (< 5% relative humidity) or nitrogen cabinet at atmospheric pressure. A known volume of ink (such as 1 ml) is dispensed in a straight line on the absorbent material to produce a repeatable area of wetted film on the filter paper. Dried air or nitrogen is passed through the cabinet at a controlled temperature and flow rate. The temperature and flow rate may be determined between trading partners depending on the properties of the ink, but these

conditions shall be included in the report. The location of the entry and exit ports for the dry air or nitrogen should be chosen so as not to disturb the mass balance readings throughout the test.

The evaporation rate can be calculated by measuring the difference in mass over a period of time. It is recommended that sufficient measurements be made to allow five or more points to be plotted on a graph of mass loss versus time for values of between 10 % and 90 % loss of solvent from the ink. The test should be repeated a total of three times and the evaporation rates averaged for that ink. In order to make a comparison, the procedure should be conducted with a known solvent such as n-butyl acetate and the evaporation rate normalised to this solvent.

In the case of an ink comprising a solvent mixture, an increased number of measurements shall be made in order to clearly show how the evaporation rate changes over time. It is recommended that a balance with automated data logging be used in order to facilitate the capture of sufficient data to describe the detailed behaviour. The results may be presented in graphical form for the case where the solvent evaporation rate is varying with time in a complex manner. These results can also be compared with those for n-butyl acetate by plotting both data on the same graph.

#### **5.3.5.3 Report of the results**

The report shall include the following items:

- a) specimen identification;
- b) test conditions (mass of ink, flow rate of air/nitrogen, solvent used for comparison);
- c) results (normalised to the solvent used for comparison).

### **6 Properties of semiconductive layer**

#### **6.1 Semiconductor type**

Methods described in IEC 62860 are applicable to the evaluations of printable semiconductors. However, for the purposes of this document the test methods for organic or inorganic printable semiconductors will be the same. No distinction between the two classes of material is necessary.

#### **6.2 Test piece**

##### **6.2.1 General**

Test pieces are used for evaluating the semiconductive layer.

##### **6.2.2 Substrate**

The substrate for the test piece shall be clean and of smooth-surface non-alkali glass which will not affect the ink. Other substrate materials may be used if agreed between the trading partners (supplier and purchaser).

##### **6.2.3 Semiconductor ink**

According to 5.1, except no dilution is allowed.

##### **6.2.4 Dimensions of test piece**

The dimensions of the test piece shall be as specified in each test method. If evaluation is possible, a test piece with smaller and/or thinner dimensions than specified may be used.

### 6.2.5 Preparation of test piece

The test piece shall be prepared according to the following procedure:

- a) Prior to ink printing or coating, the substrate surface shall be cleaned by appropriate means using an organic solvent such as acetone.
- b) Print or coat the ink onto the substrate surface using an appropriate method to form a uniform layer of ink.
- c) Solidify the ink by appropriate means to produce an electrically semiconductive layer.

## 6.3 Electrical properties

### 6.3.1 Charge mobility

#### 6.3.1.1 General

The method of direct charge mobility measurement should be described for measurement of the semiconductive layer. Direct measurement of the charge mobility may not be possible for all material types. This may be due to the absence of sufficient charges in the semiconductor for Hall effect measurements to be made.

#### 6.3.1.2 TFTs

TFT field effect mobility measurements can be used to give an indication of the performance of the ink in a particular application. In this case measurements should be made according to IEC 62860. Charge mobility should be calculated in the linear and/or saturated regime and presented graphically as a variable for a range of gate voltages in the accumulation mode. This will enable the gate voltage dependence of the mobility to be seen for a given material. TFTs should be constructed with channel lengths covering a factor of 5 from smallest to largest in order to illustrate any variation in performance arising from short channel effects. Ideally the smallest channel length tested should be less than  $< 10 \mu\text{m}$  since these dimensions are where the channel length shortening effects have the greatest effect upon device performance.

#### 6.3.1.3 Diodes

Charge mobility measurement through time of flight (TOF) or space charge limited current (SCLC) measurements may also be used to evaluate the performance of the semiconductive layer in a diode configuration. The test method should be described, detailing the preparation method for the device contacts and the voltage measurement regimes used to conduct the study.

### 6.3.2 Dielectric properties

The dielectric properties of the semiconductor film can be measured by forming a capacitor structure using the semiconductor as a dielectric. Measurement of the capacitance of a known thickness of the semiconductor (at a frequency of 1 kHz) will enable the permittivity  $\epsilon_r$  to be calculated using the formula:

$$\epsilon_r = \frac{\epsilon_0 A}{d \cdot C}$$

where

$d$  semiconductor thickness,

$\epsilon_0$  permittivity of free space,

$A$  area of capacitor,

$C$  measured capacitance.

For applications where the semiconductor is operating at higher frequencies, the capacitance can be measured at different frequencies to establish the variation of the permittivity with frequency. For the capacitance measurement either a capacitance meter, LCR meter or frequency analyser may be used. Care should be taken to account for any parasitic capacitance in the measurement leads or test fixture. The dimensions of the electrodes and thickness of the film should be reported, and these should be chosen so as to avoid any edge effects that would alter the accuracy of the measurement. It is recommended that the diameter of the capacitor plates (or length for the case of a square device) be at least 1 000 times larger than the thickness of the semiconductor film.

### **6.3.3 Ionisation potential**

Ionisation potential for p-type materials can be measured using photoelectron spectroscopy in air. The test method and the film preparation conditions should be described, including the atmospheric conditions in the laboratory.

## **6.4 Optical properties**

### **6.4.1 Overview**

The tests specified in 6.4.2 through 6.4.7 shall be used for transparent or equivalent materials.

### **6.4.2 Luminous transmittance**

#### **6.4.2.1 General**

Luminous transmittance is presented as total luminous transmittance.

#### **6.4.2.2 Measuring method**

Luminous transmittance shall be measured using the single-beam method as specified in ISO 13468-1, or the double-beam method as specified in ISO 13468-2, with the following details. If agreed between the trading partners (supplier and purchaser), another method which is considered equivalent may be used.

The detailed product specifications shall specify the applicable measuring method.

#### **6.4.2.3 Measuring equipment**

Measuring equipment shall be as specified in ISO 13468-1:1996, Clause 4 or ISO 13468-2:1999, Clause 4 as appropriate. Measuring equipment according to ISO 13655 or ISO 5-2 may be used.

#### **6.4.2.4 Wavelength or wavelength range used in the test**

Luminous transmittance shall be measured either at a particular wavelength or a wavelength range, as agreed between the trading partners (supplier and purchaser) considering factors such as material characteristics or application.

#### **6.4.2.5 Report of the results**

The report shall include the following items:

- a) measuring method and equipment;
- b) measuring wavelength or wavelength range;
- c) specimen thickness;
- d) luminous transmittance.

### **6.4.3 Chromaticity**

#### **6.4.3.1 General**

According to ISO 11664-4, chromaticity is presented as CIE (1976)  $L^*a^*b^*$  colour space.

#### **6.4.3.2 Measuring method**

The measuring method shall be the reflected light method or the transmitted light method, depending on the application and the purpose.

If the reflected light method is used, a reflecting diffuser shall be placed on both the surface to be measured and the other surface, with the specimen in between.

The reflecting diffuser shall be a perfect reflecting diffuser or a reference diffuser used for calibrating measuring equipment.

#### **6.4.3.3 Measuring equipment and auxiliaries**

The measuring equipment and light source shall be in accordance with at least one of the following: ISO 5-2, ISO 5-3, ISO 3664 or ISO 13655, and shall be specified in the detailed product specifications.

#### **6.4.3.4 Expression of the results**

The results shall be presented as the numerical values of each of the  $L^*a^*b^*$  coordinate axes, or shall be plotted in the  $L^*a^*b^*$  colour space. If agreed between the trading partners (supplier and purchaser), the results may be presented instead by the numerical value of a specific coordinate axis or the numerical values of two specific coordinate axes of the  $L^*a^*b^*$  colour space. In this case, the coordinate axis or axes concerned shall be clearly stated.

#### **6.4.3.5 Report of the results**

The report shall include the following items:

- a) measuring instrument and light source;
- b) measurement method (reflected light or transmitted light);
- c) chromaticity (numerical values of each of the  $L^*a^*b^*$  coordinate axes, plotted in the  $L^*a^*b^*$  colour space, or the numerical value of a specific coordinate axis or numerical values of two specific coordinate axes of the  $L^*a^*b^*$  colour space).

### **6.4.4 Uniformity of colour**

#### **6.4.4.1 Principle**

Colour differences are obtained at 10 points on the specimen and their average is evaluated by the difference from the standard chromaticity and standard deviation.

#### **6.4.4.2 Measuring equipment**

According to 6.4.3.3.

#### **6.4.4.3 Illuminant (light source)**

According to 6.4.3.3.

#### 6.4.4.4 Measuring method

According to 6.4.3, chromaticity shall be measured at 10 points on a single specimen using the same instrument and under the same conditions. Five or more pairs of points are selected so that all 10 points are chosen, as shown in Annex B. From the colour difference between each pair of points, the mean colour difference, the difference between the reference chromaticity and the mean, and the standard deviation are calculated.

#### 6.4.4.5 Calculation of colour difference

Colour difference is calculated by using the colour difference formula based on the numerical values of each of the  $L^*a^*b^*$  coordinate axes, or using the colour difference formula based on lightness, chroma, and hue.

The colour difference based on the  $L^*a^*b^*$  colour system is calculated by using the following formula:

$$\Delta E^*_{ab} = \left[ (\Delta L^*)^2 + (\Delta a^*)^2 + (\Delta b^*)^2 \right]^{\frac{1}{2}}$$

where:

$\Delta E^*_{ab}$  is the colour difference based on the  $L^*a^*b^*$  colour system;

$\Delta L^*, \Delta a^*, \Delta b^*$  is the difference in  $L^*$  and difference in colour coordinates  $a^*$  and  $b^*$  of the chromaticity between the pair of points obtained in 6.4.3.

The colour difference based on the luminosity, chroma, and hue is calculated by using the following formula:

$$\Delta E^*_{ab} = \left[ (\Delta L^*)^2 + (\Delta aC^*_{ab})^2 + (\Delta Hb^*_{ab})^2 \right]^{\frac{1}{2}}$$

where:

$\Delta E^*_{ab}$  is the colour difference based on the  $L^*a^*b^*$  colour system;

$\Delta L^*$  is the difference in luminosity  $L^*$  of the chromaticity between the pair of points obtained in 6.4.3;

$\Delta C^*_{ab}$  is the difference in  $ab$  chroma of the chromaticity between the pair of points obtained in 6.4.3;

$\Delta H^*_{ab}$  is the difference in  $ab$  hue of the chromaticity between the pair of points obtained in 6.4.3.

The colour difference formula in CIE DE 2000 (see CIE Publication No.142) may also be used for calculating colour difference.

#### 6.4.4.6 Report of the results

The report shall include the following items:

- measuring instruments;
- measurement method (reflected light or transmitted light);
- standard chromaticity;
- difference between the standard chromaticity and the mean, and standard deviation.

## **6.4.5 Haze**

### **6.4.5.1 Measuring method**

Haze shall be measured using the method specified in ISO 14782. A similar method may be used as agreed between the trading partners (supplier and purchaser).

### **6.4.5.2 Report of the results**

The report shall include the following items:

- a) thickness of the specimen;
- b) type of light source;
- c) haze.

## **6.4.6 Refractive index**

### **6.4.6.1 Measuring method**

The refractive index shall be measured using method A (for measuring the refractive index of films using a refractometer) specified in ISO 489 or a similar method.

### **6.4.6.2 Contacting liquid**

A contacting liquid with a refractive index higher than that of the measured object and with a substrate which does not swell or dissolve as listed in ISO 489:1999, Table 1, shall be used. When using a plastic film for the substrate, choose the contact liquid in consideration of the refractive index, swelling and melting of the substrate.

### **6.4.6.3 Conditioning**

Conditioning shall be performed at a temperature of  $(23 \pm 2) ^\circ\text{C}$  and a relative humidity of  $(50 \pm 10) \%$  for 88 h or longer. Other conditioning shall be determined by the trading partners (supplier and purchaser), if necessary.

### **6.4.6.4 Report of the results**

The report shall include the following items:

- a) refractometer used, and the type of the light source and wavelength;
- b) refractive index;
- c) dispersion (if applicable).

## **6.4.7 Luminous transmittance**

### **6.4.7.1 General**

Luminous transmittance is presented as total luminous transmittance.

### **6.4.7.2 Measuring equipment**

Luminous transmittance shall be measured using the single-beam method as specified in ISO 13468-1, or the double-beam method as specified in ISO 13468-2, with the following details. If agreed between the trading partners (supplier and purchaser), another method which is considered equivalent may be used.

The detailed product specifications shall specify the applicable measuring method.