

TECHNICAL REPORT



**HV polymeric insulators for indoor and outdoor use tracking and erosion testing
by wheel test and 5 000 h test**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2024 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IECNORM.COM : Click to view the full PDF of IEC 62139-12+AMD1:2024 CSV

TECHNICAL REPORT



**HV polymeric insulators for indoor and outdoor use tracking and erosion testing
by wheel test and 5 000 h test**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.080.10

ISBN 978-2-8322-9239-6

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope and object.....	6
2 Normative references	6
3 Terms and definitions	6
4 Background to the tracking and erosion tests	8
4.1 Difference between the tracking and erosion and accelerated ageing tests on polymeric insulators	8
4.2 The wheel test.....	8
4.3 The 5 000h multiple stress test.....	9
5 Classification of tests	10
6 General requirements for insulator test specimens	10
7 The tests	10
7.1 Wheel test.....	10
7.1.1 Test specimens	10
7.1.2 Procedure.....	10
7.1.3 Test conditions	12
7.1.4 Acceptance criteria	12
7.2 5 000 hour test (test at multiple stresses).....	12
7.2.1 Test specimen	12
7.2.2 Procedure.....	12
7.2.3 Test conditions	13
7.2.4 Voltage.....	16
7.2.5 Solar simulation.....	16
7.2.6 Artificial rain	16
7.2.7 Dry heat	17
7.2.8 Humidity	17
7.2.9 Pollution.....	17
7.2.10 Salt fog calibration.....	17
7.2.11 Acceptance criteria	19
Bibliography.....	20
Figure 1 – Test arrangement of the tracking wheel test.....	11
Figure 2 – Typical layout of the test specimens in the chamber and main dimensions of the chamber.....	13
Figure 3 – Multiple stress cycle.....	14
Figure 4 – Typical layout of the rain and salt fog spray systems and the xenon lamp	15
Figure 5 – Spectrum of xenon arc lamp and solar spectrum	16
Figure 6 – Reference porcelain insulator.....	

INTERNATIONAL ELECTROTECHNICAL COMMISSION

HV POLYMERIC INSULATORS FOR INDOOR AND OUTDOOR USE TRACKING AND EROSION TESTING BY WHEEL TEST AND 5 000H TEST

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch> or www.iso.org/patents. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 62730 edition 1.1 contains the first edition (2012-03) [documents 36/305/DTR and 36/316A/RVC] and its amendment 1 (2024-06) [documents 36/596/DTR and 36/601/RVDTR].

In this Redline version, a vertical line in the margin shows where the technical content is modified by amendment 1. Additions are in green text, deletions are in strikethrough red text. A separate Final version with all changes accepted is available in this publication.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 62730, which is a technical report, has been prepared by IEC technical committee 36: Insulators.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this document and its amendment will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The '*colour inside*' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

IEC 62217 [1]¹ included three different tracking and erosion tests. One, the 1 000 hour salt-fog test, was included in the main text as a default test and two others, the 5 000 hour test and the tracking wheel test, were given in annexes as alternative tests.

Following a decision by TC 36 it was decided that it was desirable to have a single standardised test in IEC 62217; hence a study of the usage and effectiveness of all three tests was undertaken by Working Group 12 of TC 36. The results of this study indicated that, while the 5 000h and the tracking wheel tests each had their advantages, only the 1 000 hour salt fog test was adapted to all insulator types and was more economical to perform.

It was decided by TC 36 to adopt the 1 000 hour salt-fog test as the only standardised test. It was also decided to draft this Technical Report to reproduce the 5 000 hour and the tracking wheel test procedures in order to keep the information on the test methods and parameters available for those wishing to use those tests for research or other purposes.

The tracking and erosion tests given in this technical report are considered as screening tests intended to reject materials or designs which are inadequate. These tests are not intended to predict long-term performance for insulator designs under cumulative service stresses.

Composite insulators are used in both a.c. and d.c. applications. In spite of this fact a specific tracking and erosion test procedure for d.c. applications as a design test has not yet been defined and accepted.

IEC Guide 111 has been followed during preparation of this technical report wherever possible.

¹ Numbers in square brackets refer to the Bibliography.

HV POLYMERIC INSULATORS FOR INDOOR AND OUTDOOR USE TRACKING AND EROSION TESTING BY WHEEL TEST AND 5 000H TEST

1 Scope and object

This technical report is applicable to polymeric insulators whose insulating body consists of one or various organic materials. Polymeric insulators covered by this technical report include both solid core and hollow insulators. They are intended for use on overhead lines and in indoor and outdoor equipment with a rated voltage greater than 1 000 V.

The object of this technical report is:

- to define the common terms used;
- to give the background behind the development and use of the 5 000 h multiple stress test and the tracking wheel test;
- to describe the test methods for the 5 000 h multiple stress test and the tracking wheel tests on polymeric insulators;
- to describe possible acceptance or failure criteria, if applicable;

These tests, criteria and recommendations are intended to give a common basis for the 5 000h multiple stress test and the tracking wheel test when they are used for research or required as a supplementary design test. These tests are not mandatory and their use is subject to prior agreement between the interested parties.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-47:2007, *International Electrotechnical Vocabulary – Part 471: Insulators*

IEC 60060-1, *High-voltage test techniques – Part 1: General definitions and test requirements*.

IEC 60507, *Artificial pollution tests on high-voltage insulators to be used on a.c. systems*

IEC 60815-2, *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions – Part 2: Ceramic and glass insulators for a.c. systems*

3 Terms and definitions

For the purposes of this document the terms and definitions given in IEC 60050 (471) and the following apply:

3.1

polymeric insulator

insulator whose insulating body consists of at least one organic based material. Coupling devices may be attached to the ends of the insulating body

Note 1 to entry: Polymeric insulators are also known as non-ceramic insulators.

[SOURCE: IEC 60050-471:2007, 471-01-13, modified]

3.2 core

central insulating part of an insulator which provides the mechanical characteristics

Note 1 to entry: The housing and sheds are not part of the core.

[SOURCE: IEC 60050-471:2007, 471-01-03]

3.3 insulator trunk

central insulating part of an insulator from which the sheds project.

Note 1 to entry: Also known as shank on smaller insulators.

[SOURCE: IEC 60050-471:2007, 471-01-11]

3.4 housing

external insulating part of a composite insulator providing the necessary creepage distance and protects the core from the environment

Note 1 to entry: An intermediate sheath made of insulating material may be part of the housing.

[SOURCE: IEC 60050-471:2007, 471-01-09]

3.5 shed

insulating part, projecting from the insulator trunk, intended to increase the creepage distance.

Note 1 to entry: The shed can be with or without ribs.

[SOURCE: IEC 60050-471:2007, 471-01-15]

3.6 creepage distance

shortest distance or the sum of the shortest distances along the surface on an insulator between two conductive parts which normally have the operating voltage between them

Note 1 to entry: The surface of cement or of any other non-insulating jointing material is not considered as forming part of the creepage distance.

Note 2 to entry: If a high resistance coating is applied to parts of the insulating part of an insulator, such parts are considered to be effective insulating surfaces and the distance over them is included in the creepage distance.

[SOURCE: IEC 60050-471:2007, 471-01-04]

3.7 interfaces

surface between the different materials. Various interfaces occur in most composite insulators, e.g.:

- between housing and fixing devices;
- between various parts of the housing; e.g. between sheds, or between sheath and sheds;
- between core and housing;

3.8 tracking

process which forms irreversible degradation by formation of conductive paths (tracks) starting and developing on the surface of an insulating material. These paths are conductive even under dry conditions

3.9

erosion

irreversible and non-conducting degradation of the surface of the insulator that occurs by loss of material. This can be uniform, localized or tree-shaped.

Note 1 to entry: Light surface traces, commonly tree-shaped, can occur on composite insulators as on ceramic insulators, after partial flashover. These traces are not considered to be objectionable as long as they are non-conductive. When they are conductive they are classified as tracking.

3.10

crack

any internal fracture or surface fissure of depth greater than 0,1 mm

3.11

puncture

permanent loss of dielectric strength due to a disruptive discharge passing through the solid insulating material of an insulator

[SOURCE: IEC 60050-471:2007, 471-01-14, modified]

4 Background to the tracking and erosion tests

4.1 Difference between the tracking and erosion and accelerated ageing tests on polymeric insulators

Although this Technical Report describes tracking and erosion tests which often may be referred to in the literature as “ageing tests”, it is important to note that they are not accelerated ageing tests in the sense that these tests do not simulate exactly real life degradation conditions nor do they accelerate them to give a life-equivalent test in a short time. Rather they use continuous, cyclic or combined stresses to try to detect potential weaknesses which could compromise the insulators performance in service.

The tests are better described as screening tests, which can be used to reject materials, designs, or combinations thereof which are inadequate.

The ageing mechanisms on a polymeric insulator generally do not cause a progressive reduction of easily measurable ageing-induced properties with time. The transition from “good condition” to “end of life” is frequently rapid with no forewarning and might be observed by, for instance, erosion to depths comparable to those obtained in the 1 000 hour salt fog test defined in IEC 62217 or deep UV-initiated cracks in the surfaces. The time and speed of this transition depends on multiple parameters, both of the insulator material and design and of the operating environment. Hence the use of such ageing tests for true “end of life” prediction is only possible when relevant data on damage and degradation is available for the same or similar insulators in the same or similar environments.

Therefore these tests are used to give a general indication of the quality of the design and materials with respect to the stresses arising in relatively harsh but not extreme environments.

For further information, see [2].

4.2 The wheel test

The tracking wheel test was originally developed in Canada and introduced in the Canadian Electrical Association Light Weight Insulator Working Group CEA LWIWG-01 – Dead-end suspension composite insulator standard in 1991. It was named Tracking Wheel # 2.

The # 1 version was a spray system rather than a dip system.

The original concept was to energize, at 35 V/mm of creepage, the insulator sample which had been dipped in a NaCl solution of 1,40 g/l of water and allowed to drip. It was continuous for the duration of the 30 000 cycles. The original acceptance criteria were: no tracking, no erosion to the core and no shed or housing puncture. Every unit was then tested with a steep front impulse and a power frequency voltage test.

The wheel test was not deemed to be an ageing test by the CEA. Although there were discussions 20 years ago to correlate the aspects of the tested insulators with insulators in the field and to estimate an aging factor, such correlation was never implied in the standard. There was also consideration to modify the test parameters to reflect different pollution severities. This was never introduced.

In the LWIWG-01-1996 version, the description of the test was modified to describe the de-ionized water and introduce a rest period of 24 hours where the dip tank is empty. It was observed during the first part of the 1990s that silicone-based housings did not perform well when the test was uninterrupted. This corresponds to the concept of hydrophobicity recovery which had gained popularity by that time.

In 2010, the test in the standard was re-affirmed in CSA C411.5 with basically the same parameters.

In this IEC version, there are no provisions for a rest period, nor impulse and flashover tests following the 30 000 cycles. There is allocation for test interruptions and a requirement to change the dip tank solution weekly. The IEC version gives precise guidelines as to the acceptable erosion depth.

This test is mandatory in the CSA insulator standards. For more than 20 years, this test has been considered able to detect insulator designs that are not suitable for use on overhead transmission lines. It is not meant as an ageing test with an estimated acceleration factor.

4.3 The 5 000h multiple stress test

The 5 000h multiple stress test was initially developed by CIGRE WG 22.10 which was set up in 1978 to establish a technical basis for minimum requirements for composite insulators. Their work was published in 1983 [3] and included a proposal for a multi-stress 5 000 hour test combining cycles of humidity, heating, rain, salt fog and solar radiation on energised insulators. The intention of the test was to reproduce any synergy between the multiple stresses seen by insulators in service that might not be present in a single stress test. Later work by EDF in France using the same “CIGRE” cycles reported varying acceleration factors with respect to different test station environments [4] and classed the test as an accelerated ageing test.

A similar, but not identical, test cycle was used in Italy as an accelerated ageing test and it was deemed necessary to “fix” the test parameters by including it in IEC 61109:1992 [5]. At this point it was given as an alternative to the 1 000h salt-fog test for insulators intended for extreme conditions. IEC 61109:1992 did not mention any acceleration factors.

When it was decided to group common tests for composite insulators into IEC 62217:2005, the test was included as an alternative tracking and erosion test, not an accelerated ageing test. The version of the test in 62217:2005 had been revised by IEC TC 36 WG12 on the basis of work between Sweden and France to improve the reproducibility of the test which had been shown to be problematic [6]. The main improvement involved calibration of the salt-fog cycle by using standard dummy insulators at each test position to set up fog distribution and flow rate.

The procedure included in this Technical Report includes some minor alterations to further improve reproducibility.

5 Classification of tests

Previously, these tests were alternative or supplementary design tests.

6 General requirements for insulator test specimens

Insulator test specimens for tests of polymeric insulators shall be checked prior to tests:

- for correct assembly, for example by applying the mechanical routine test specified in the relevant product standard,
- by visual examination according to the relevant product standard;
- for conformance of dimensions with the actual drawing.

For dimensions d without tolerances the following tolerances are acceptable:

- $\pm (0,04 \times d + 1,5)$ mm when $d \leq 300$ mm;
- $\pm (0,025 \times d + 6)$ mm when $d > 300$ mm with a maximum tolerance of 50 mm.

The measurement of creepage distances shall be related to the design dimensions and tolerances as determined from the insulator drawing, even if this dimension is greater than the value originally specified. When a minimum creepage is specified, the negative tolerance is also limited by this value.

The housing colour of the test specimens shall be approximately as specified in the drawing.

The number of test specimens, their selection and dimensions are specified in the relevant product standard or agreed upon by the interested parties.

7 The tests

7.1 Wheel test

7.1.1 Test specimens

Two test insulators of identical design with a creepage distance between 500 mm and 800 mm shall be taken from the production line. If such insulators cannot be taken from the production line, special test specimens shall be made from other insulators so that the creepage distance falls between the given values. These special test specimens shall be fitted with standard production end fittings.

Up to two pairs of test specimens can be tested simultaneously on one wheel. It is recommended not to mix widely differing materials on the same wheel.

The test samples shall be properly marked so that the pairs can be easily identified at the end of the test.

7.1.2 Procedure

The test specimens shall be cleaned with de-ionized water before starting the test. The test specimens are mounted on the wheel as shown in Figure 1. They go through four positions in one cycle. Each test specimen remains stationary for about 40 s in each of the four positions. The 90° rotation from one position to the next takes about 8 s. In the first part of the cycle the insulator is dipped into a saline solution. The second part of the test cycle permits the excess saline solution to drip off the specimen, ensuring that the light wetting of the surface gives rise to sparking across dry bands that will form during the third part of the cycle. In that part the specimen is submitted to a power frequency voltage. In the last part of the cycle the surface of the specimen that had been heated by the dry band sparking is allowed to cool.

The test voltage is supplied by a test transformer. When loaded with a resistive current of 250 mA on the high voltage side the test circuit shall exhibit a maximum drop of 5 % in its output voltage.

The salt solution shall be replaced weekly. Weekly interruptions of the test for inspection purposes, each of these not exceeding 1 h are permissible. Interruption periods will not be counted in the test duration. One longer interruption up to 60 h is allowed. An additional testing time of three times the duration of the interruption period shall be added. The final test report shall include details of all interruptions.




Figure 1 – Test arrangement of the tracking wheel test

7.1.3 Test conditions

Electrical stress:	The power frequency test voltage in kV is determined by dividing the actual creepage distance in mm by 28,6.
NaCl content of de-ionised water:	$1,40 \text{ kg/m}^3 \pm 0,06 \text{ kg/m}^3$
Ambient temperature:	$20 \text{ °C} \pm 5 \text{ K}$
Test duration:	30 000 cycles

7.1.4 Acceptance criteria

The test specimens of identical design shall be assessed together. Pairs of test specimens of different design shall be assessed separately. The numbers of flashovers and trip-outs shall be recorded and noted in the test report. Photographs shall be made to record the test results. The samples may be washed and lightly brushed in order to remove any loose matter.

The test is regarded as passed, if on both test specimens:

- no tracking occurs, (a Meg Ohm-meter shall be applied along any suspect path, using 1 kV DC or higher. The probes shall be between 5 mm to 10 mm apart. A resistance of less than $2 \text{ M}\Omega$ shall constitute failure);
- For composite insulators: erosion shall not reach the core and in any case the erosion depth shall be less than 3 mm;
- for resin insulators: erosion depth is less than 3 mm;
- no shed, housing or interface is punctured.

7.2 5 000 hour test (test at multiple stresses)

7.2.1 Test specimen

Two test insulators of identical design with a creepage distance between 500 mm and 800 mm shall be taken from the production line. If such insulators cannot be taken from the production line, special test specimens shall be made from other insulators so that the creepage distance falls between the given values. These special test specimens shall be fitted with standard production end fittings.

7.2.2 Procedure

The test shall be carried out in a moisture sealed corrosion-proof chamber, the volume of which shall not exceed 20 m^3 .

An example of a chamber is presented in Figure 2.

An insulated porthole equipped with a wiper and a mobile filter stopping ultraviolet radiation permits observation of the equipment on test.

NOTE 1 Outside the chamber there are: tanks of salt water and de-ionised water, together with the pumps, heaters, pipes for water and air, fans, the medium voltage step-up transformer, and its protections, the power supply to the ultraviolet radiation generator, all the electrical circuits and the devices for control, automatic control, measurement and regulation.




Figure 2 – Typical layout of the test specimens in the chamber and main dimensions of the chamber

NOTE 2 Chambers with a size larger than 20 m³ can be used in order to allow testing of full-size objects if the criteria for calibration and environment (e.g. time to reach temperature during dry heat period) are fulfilled.

7.2.3 Test conditions

The cycle of stresses applied to the insulators and repeated for a period of 5 000 h is shown in Figure 3. The cycle is designed so that the test specimens are also subjected to the effects of temperature variation and condensation.

The test specimens are arranged vertically in the chamber as shown in Figure 4. There shall be a clearance of at least 400 mm between adjacent edges of the sheds of test specimens and between the test specimens and the roof, the walls and the floor.

The test specimens shall be cleaned with de-ionised water before starting the test.

Up to three pairs of test specimens with comparable creepage distance can be tested simultaneously.

Weekly interruptions of the test for inspection purposes, each of these not exceeding 1 h are permissible. Interruption periods shall not be counted in the test duration. Five longer interruptions up to 60 h each are allowed. An additional testing time of three times the duration of the interruption period shall be added. The final test report shall include all details of interruptions.






Figure 3 – Multiple stress cycle

IEC 480/12



Key

- | | |
|--|-----------------------|
| 1 rain nozzle | 4 test specimen |
| 2 salt fog spray nozzle (IEC 60507 type) | 5 isolating insulator |
| 3 xenon UV lamp | 6 HV power supply |

Figure 4 – Typical layout of the rain and salt fog spray systems and the xenon lamp

7.2.4 Voltage


The power frequency test voltage in kilovolts is adjusted to the actual creepage distance of the test specimens. It is determined by dividing the creepage distance in millimetres by 34,6 (equal to a specific creepage distance of 20 mm/kV, calculated as phase-to-phase value).

The supply circuit, when loaded with a continuous resistive current of 250 mA (r.m.s.) during 1 s on the high voltage side shall experience a maximum voltage drop of 5 %. The protection level shall be set at 1 A (r.m.s.).

7.2.5 Solar simulation

The simulated solar irradiation is provided by a xenon arc lamp with a nominal output of 6 500 W and equipped with 2 boron silicate glass filters (see example in Figure 5). The distance between the xenon lamp and test specimens is approximately 480 mm.

A new lamp and filters shall be used at the beginning of each test. The filters and, if necessary, the lamp shall be replaced during the test according to the lamp manufacturer's recommendations.



IEC 482/12

Key

- Spectrum of the xenon arc lamp equipped with two boron silicate filters.
- Solar spectrum at midday in June, latitude 42°.

Figure 5 – Spectrum of xenon arc lamp and solar spectrum

7.2.6 Artificial rain

The artificial rain shall be provided by nozzles mounted above the test specimens and outside their perimeter (see Figure 4). The average precipitation rate shall be in accordance with IEC 60060-1. Water of a minimum resistivity of 85 Ωm shall be used. Each of the test specimens is sprayed individually.

7.2.7 Dry heat

The chamber is heated up to $50\text{ °C} \pm 2\text{ °C}$; the time for the temperature to rise is 15 min as a maximum.

NOTE It is recommended to heat and insulate the walls of the chamber.

7.2.8 Humidity

Nominal relative humidity: $RH = 95\% \pm 3\%$ at 50 °C .

7.2.9 Pollution

The pollution is simulated by a salt fog (salinity: $7\text{ kg/m}^3 \pm 5\%$) sprayed by nozzles of the IEC 60507 type.

~~Each of the test specimens is sprayed individually.~~

~~Each spray nozzle is mounted below the corresponding test specimen and points upwards towards the centre of it, within an angle of $40^\circ \pm 10^\circ$ to the horizontal plane.~~

~~In case of unused test positions, insulators with comparable dimensions shall be placed at the unused positions and the corresponding spray nozzles shall be in service.~~

The spray nozzles are mounted close to the bottom of the chamber and spray upwards towards the roof of the chamber. The fog should fill up the chamber and not be directly sprayed on to the test specimen. Salt water prepared from NaCl dissolved in tap water should be supplied to the spray nozzles. The fog intensity and uniformity should be maintained in the specimen's exposure zone.


7.2.10 Salt fog calibration

~~To ensure the test reproducibility and the severity level of the salt fog, the salt fog shall be adjusted by using the method of calibration described below.~~

~~For this purpose a reference insulator is used. Its characteristics are:~~

- ~~• porcelain long rod insulator (hydrophilic material),~~
- ~~• normal shed profile (according to IEC 60815-2),~~
- ~~• Creepage factor = $2,2 \pm 10\%$ (according to IEC 60815-2),~~
- ~~• Shed diameter = $140\text{ mm} \pm 5\%$.~~

~~An example of a reference insulator is shown in Figure 6.~~



~~Key~~

~~Characteristics:~~

~~IEC ref: H4-125~~

~~Nominal creepage distance: 500 mm~~

~~Dry arcing distance: 225 mm~~

~~Length H: 210 mm~~

~~Shed diameter D: 140 mm~~

~~Figure 6 — Reference porcelain insulator~~

~~The reference insulator shall be carefully cleaned so that traces of dirt and grease are removed.~~

~~Water, preferably heated to about 50 °C, with the addition of trisodium phosphate or another detergent, shall be used to wash the surface of the insulator. Subsequently, the insulator is to be thoroughly rinsed with tap water. The surface of the insulator is deemed to be sufficiently clean and free from any grease if the surface is completely hydrophilic.~~

~~After cleaning, the insulating parts of the insulator should not be touched by hand.~~

~~Before every calibration period, the insulator shall be again thoroughly washed with tap water only, in order to remove all traces of pollution.~~

~~The reference insulator shall be installed at each of the different test positions. Insulators with comparable dimensions shall be placed on the other test positions.~~

~~The power frequency test voltage in kilovolts is adjusted to the actual creepage distance of the reference insulator. It is determined by dividing the creepage distance in millimetres by 34,6 (equal to a specific creepage distance of 20 mm/kV, calculated as phase to phase value) within a tolerance of ±5 %.~~

~~All the salt fog nozzles shall be in service.~~

~~The fog (position of nozzles and flow rate) is adjusted to obtain an average level of the maximum peak currents (the maximum value recorded every 1 min.) in the range 100 to 200 mA, measured during 4 h. An establishment time of the leakage current of 30 min maximum is permitted and not included in the calibration.~~

~~This is applied to all test locations.~~

~~Each test position can be calibrated separately. Alternatively, it is allowed to locate a reference insulator at each test position and to perform the calibration of all test positions simultaneously and independently. If the positions are calibrated individually, the calibration shall be repeated to ensure that the initial fog corrections have not influenced the neighbouring test positions.~~

The calibration will be carried out before the start of the test.

At least two clean collecting receptacles with a collecting area of $8\,000\text{ mm}^2 \pm 2\,000\text{ mm}^2$ and a maximum height of 100 mm each are placed as close as practical to the position of the ends of the test object. The receptacles are positioned in such a way that they are not shielded by the test specimens and to avoid dripping from the construction elements of the chamber or another source.

They should collect between 1,5 ml and 2,0 ml of precipitation per hour (corrected to $8\,000\text{ mm}^2$ collecting area) averaged over a minimum period of 16 h.

NOTE The flow rate necessary to obtain such precipitation (typically of the order of $0,3\text{ l/m}^3\text{h}$ based on a chamber not larger than 15 m^3) should be noted. (The water flow rate is defined in litres per hour and per cubic meter of the test chamber volume.) Subsequently during the test, the flow rate should be checked at least every 100 h and should remain within $\pm 25\%$ of the initial value.

It is not permitted to re-circulate the water.

7.2.11 Acceptance criteria

The test specimens of identical design shall be assessed together. The numbers of flashovers and trip-outs shall be recorded and noted in the test report. Photographs shall be made to record the test results. The samples may be washed and lightly brushed in order to remove any loose matter.

The test is regarded as passed if on both test specimens:

- no tracking occurs (a Meg Ohm-meter shall be applied along a suspect path, using 1 kV DC or higher. The probes shall be between 5 mm to 10 mm apart. A resistance of less than $2\text{ M}\Omega$ shall constitute failure);
- for composite insulators: erosion depth is less than 3 mm and does not reach the core, if applicable;
- for resin insulators: erosion depth is less than 3 mm;
- no shed, housing or interface is punctured.

Bibliography

- [1] IEC 62217, *Polymeric insulators for indoor and outdoor use with a nominal voltage > 1000 V – General definitions, test methods and acceptance criteria*
- [2] CIGRE technical Brochure No. 142: “Natural and artificial ageing and pollution testing of polymeric insulators”, June 1999
- [3] “Technical basis for minimal requirements for composite insulators” CIGRE WG22-10, ELECTRA N°88, May 1983, pp 89-114
- [4] Accelerated ageing test for non-ceramic insulators EDF’s experience”, G. Riquel – SEE Workshop: Non-ceramic outdoor insulation, Paris 15-16 April 1993
- [5] IEC 61109, *Insulators for overhead lines – Composite suspension and tension insulators for a.c. systems with a nominal voltage greater than 1 000 V – Definitions, test methods and acceptance criteria*
- [6] “IEC ageing test: A critical review and further test development” – Gutman, Hartings, Riquel – IEEE Stockholm Power Tech 1995
- [7] IEC 61952, *Insulators for overhead lines – Composite line post insulators for A.C. systems with a nominal voltage greater than 1 000 V – Definitions, test methods and acceptance criteria*

IECNORM.COM : Click to view the full PDF of IEC TR 62730:2012+AMD1:2024 CSV

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope and object.....	6
2 Normative references	6
3 Terms and definitions	6
4 Background to the tracking and erosion tests	8
4.1 Difference between the tracking and erosion and accelerated ageing tests on polymeric insulators	8
4.2 The wheel test.....	8
4.3 The 5 000h multiple stress test.....	9
5 Classification of tests	10
6 General requirements for insulator test specimens	10
7 The tests	10
7.1 Wheel test.....	10
7.1.1 Test specimens	10
7.1.2 Procedure.....	10
7.1.3 Test conditions	12
7.1.4 Acceptance criteria	12
7.2 5 000 hour test (test at multiple stresses).....	12
7.2.1 Test specimen	12
7.2.2 Procedure.....	12
7.2.3 Test conditions	13
7.2.4 Voltage.....	15
7.2.5 Solar simulation.....	15
7.2.6 Artificial rain	16
7.2.7 Dry heat	16
7.2.8 Humidity	16
7.2.9 Pollution.....	16
7.2.10 Salt fog calibration.....	17
7.2.11 Acceptance criteria	17
Bibliography.....	18
Figure 1 – Test arrangement of the tracking wheel test.....	11
Figure 2 – Typical layout of the test specimens in the chamber and main dimensions of the chamber.....	13
Figure 3 – Multiple stress cycle.....	14
Figure 4 – Typical layout of the rain and salt fog spray systems and the xenon lamp	15
Figure 5 – Spectrum of xenon arc lamp and solar spectrum	16

INTERNATIONAL ELECTROTECHNICAL COMMISSION

HV POLYMERIC INSULATORS FOR INDOOR AND OUTDOOR USE TRACKING AND EROSION TESTING BY WHEEL TEST AND 5 000H TEST

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch> or www.iso.org/patents. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 62730 edition 1.1 contains the first edition (2012-03) [documents 36/305/DTR and 36/316A/RVC] and its amendment 1 (2024-06) [documents 36/596/DTR and 36/601/RVDTR].

This Final version does not show where the technical content is modified by amendment 1. A separate Redline version with all changes highlighted is available in this publication.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 62730, which is a technical report, has been prepared by IEC technical committee 36: Insulators.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this document and its amendment will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The '*colour inside*' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

IEC 62217 [1]¹ included three different tracking and erosion tests. One, the 1 000 hour salt-fog test, was included in the main text as a default test and two others, the 5 000 hour test and the tracking wheel test, were given in annexes as alternative tests.

Following a decision by TC 36 it was decided that it was desirable to have a single standardised test in IEC 62217; hence a study of the usage and effectiveness of all three tests was undertaken by Working Group 12 of TC 36. The results of this study indicated that, while the 5 000h and the tracking wheel tests each had their advantages, only the 1 000 hour salt fog test was adapted to all insulator types and was more economical to perform.

It was decided by TC 36 to adopt the 1 000 hour salt-fog test as the only standardised test. It was also decided to draft this Technical Report to reproduce the 5 000 hour and the tracking wheel test procedures in order to keep the information on the test methods and parameters available for those wishing to use those tests for research or other purposes.

The tracking and erosion tests given in this technical report are considered as screening tests intended to reject materials or designs which are inadequate. These tests are not intended to predict long-term performance for insulator designs under cumulative service stresses.

Composite insulators are used in both a.c. and d.c. applications. In spite of this fact a specific tracking and erosion test procedure for d.c. applications as a design test has not yet been defined and accepted.

IEC Guide 111 has been followed during preparation of this technical report wherever possible.

¹ Numbers in square brackets refer to the Bibliography.

HV POLYMERIC INSULATORS FOR INDOOR AND OUTDOOR USE TRACKING AND EROSION TESTING BY WHEEL TEST AND 5 000H TEST

1 Scope and object

This technical report is applicable to polymeric insulators whose insulating body consists of one or various organic materials. Polymeric insulators covered by this technical report include both solid core and hollow insulators. They are intended for use on overhead lines and in indoor and outdoor equipment with a rated voltage greater than 1 000 V.

The object of this technical report is:

- to define the common terms used;
- to give the background behind the development and use of the 5 000 h multiple stress test and the tracking wheel test;
- to describe the test methods for the 5 000 h multiple stress test and the tracking wheel tests on polymeric insulators;
- to describe possible acceptance or failure criteria, if applicable;

These tests, criteria and recommendations are intended to give a common basis for the 5 000h multiple stress test and the tracking wheel test when they are used for research or required as a supplementary design test. These tests are not mandatory and their use is subject to prior agreement between the interested parties.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-47:2007, *International Electrotechnical Vocabulary – Part 471: Insulators*

IEC 60060-1, *High-voltage test techniques – Part 1: General definitions and test requirements*.

IEC 60507, *Artificial pollution tests on high-voltage insulators to be used on a.c. systems*

IEC 60815-2, *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions – Part 2: Ceramic and glass insulators for a.c. systems*

3 Terms and definitions

For the purposes of this document the terms and definitions given in IEC 60050 (471) and the following apply:

3.1

polymeric insulator

insulator whose insulating body consists of at least one organic based material. Coupling devices may be attached to the ends of the insulating body

Note 1 to entry: Polymeric insulators are also known as non-ceramic insulators.

[SOURCE: IEC 60050-471:2007, 471-01-13, modified]

3.2 core

central insulating part of an insulator which provides the mechanical characteristics

Note 1 to entry: The housing and sheds are not part of the core.

[SOURCE: IEC 60050-471:2007, 471-01-03]

3.3 insulator trunk

central insulating part of an insulator from which the sheds project.

Note 1 to entry: Also known as shank on smaller insulators.

[SOURCE: IEC 60050-471:2007, 471-01-11]

3.4 housing

external insulating part of a composite insulator providing the necessary creepage distance and protects the core from the environment

Note 1 to entry: An intermediate sheath made of insulating material may be part of the housing.

[SOURCE: IEC 60050-471:2007, 471-01-09]

3.5 shed

insulating part, projecting from the insulator trunk, intended to increase the creepage distance.

Note 1 to entry: The shed can be with or without ribs.

[SOURCE: IEC 60050-471:2007, 471-01-15]

3.6 creepage distance

shortest distance or the sum of the shortest distances along the surface on an insulator between two conductive parts which normally have the operating voltage between them

Note 1 to entry: The surface of cement or of any other non-insulating jointing material is not considered as forming part of the creepage distance.

Note 2 to entry: If a high resistance coating is applied to parts of the insulating part of an insulator, such parts are considered to be effective insulating surfaces and the distance over them is included in the creepage distance.

[SOURCE: IEC 60050-471:2007, 471-01-04]

3.7 interfaces

surface between the different materials. Various interfaces occur in most composite insulators, e.g.:

- between housing and fixing devices;
- between various parts of the housing; e.g. between sheds, or between sheath and sheds;
- between core and housing;

3.8 tracking

process which forms irreversible degradation by formation of conductive paths (tracks) starting and developing on the surface of an insulating material. These paths are conductive even under dry conditions

3.9

erosion

irreversible and non-conducting degradation of the surface of the insulator that occurs by loss of material. This can be uniform, localized or tree-shaped.

Note 1 to entry: Light surface traces, commonly tree-shaped, can occur on composite insulators as on ceramic insulators, after partial flashover. These traces are not considered to be objectionable as long as they are non-conductive. When they are conductive they are classified as tracking.

3.10

crack

any internal fracture or surface fissure of depth greater than 0,1 mm

3.11

puncture

permanent loss of dielectric strength due to a disruptive discharge passing through the solid insulating material of an insulator

[SOURCE: IEC 60050-471:2007, 471-01-14, modified]

4 Background to the tracking and erosion tests

4.1 Difference between the tracking and erosion and accelerated ageing tests on polymeric insulators

Although this Technical Report describes tracking and erosion tests which often may be referred to in the literature as “ageing tests”, it is important to note that they are not accelerated ageing tests in the sense that these tests do not simulate exactly real life degradation conditions nor do they accelerate them to give a life-equivalent test in a short time. Rather they use continuous, cyclic or combined stresses to try to detect potential weaknesses which could compromise the insulators performance in service.

The tests are better described as screening tests, which can be used to reject materials, designs, or combinations thereof which are inadequate.

The ageing mechanisms on a polymeric insulator generally do not cause a progressive reduction of easily measurable ageing-induced properties with time. The transition from “good condition” to “end of life” is frequently rapid with no forewarning and might be observed by, for instance, erosion to depths comparable to those obtained in the 1 000 hour salt fog test defined in IEC 62217 or deep UV-initiated cracks in the surfaces. The time and speed of this transition depends on multiple parameters, both of the insulator material and design and of the operating environment. Hence the use of such ageing tests for true “end of life” prediction is only possible when relevant data on damage and degradation is available for the same or similar insulators in the same or similar environments.

Therefore these tests are used to give a general indication of the quality of the design and materials with respect to the stresses arising in relatively harsh but not extreme environments.

For further information, see [2].

4.2 The wheel test

The tracking wheel test was originally developed in Canada and introduced in the Canadian Electrical Association Light Weight Insulator Working Group CEA LWIWG-01 – Dead-end suspension composite insulator standard in 1991. It was named Tracking Wheel # 2.

The # 1 version was a spray system rather than a dip system.

The original concept was to energize, at 35 V/mm of creepage, the insulator sample which had been dipped in a NaCl solution of 1,40 g/l of water and allowed to drip. It was continuous for the duration of the 30 000 cycles. The original acceptance criteria were: no tracking, no erosion to the core and no shed or housing puncture. Every unit was then tested with a steep front impulse and a power frequency voltage test.

The wheel test was not deemed to be an ageing test by the CEA. Although there were discussions 20 years ago to correlate the aspects of the tested insulators with insulators in the field and to estimate an aging factor, such correlation was never implied in the standard. There was also consideration to modify the test parameters to reflect different pollution severities. This was never introduced.

In the LWIWG-01-1996 version, the description of the test was modified to describe the de-ionized water and introduce a rest period of 24 hours where the dip tank is empty. It was observed during the first part of the 1990s that silicone-based housings did not perform well when the test was uninterrupted. This corresponds to the concept of hydrophobicity recovery which had gained popularity by that time.

In 2010, the test in the standard was re-affirmed in CSA C411.5 with basically the same parameters.

In this IEC version, there are no provisions for a rest period, nor impulse and flashover tests following the 30 000 cycles. There is allocation for test interruptions and a requirement to change the dip tank solution weekly. The IEC version gives precise guidelines as to the acceptable erosion depth.

This test is mandatory in the CSA insulator standards. For more than 20 years, this test has been considered able to detect insulator designs that are not suitable for use on overhead transmission lines. It is not meant as an ageing test with an estimated acceleration factor.

4.3 The 5 000h multiple stress test

The 5 000h multiple stress test was initially developed by CIGRE WG 22.10 which was set up in 1978 to establish a technical basis for minimum requirements for composite insulators. Their work was published in 1983 [3] and included a proposal for a multi-stress 5 000 hour test combining cycles of humidity, heating, rain, salt fog and solar radiation on energised insulators. The intention of the test was to reproduce any synergy between the multiple stresses seen by insulators in service that might not be present in a single stress test. Later work by EDF in France using the same “CIGRE” cycles reported varying acceleration factors with respect to different test station environments [4] and classed the test as an accelerated ageing test.

A similar, but not identical, test cycle was used in Italy as an accelerated ageing test and it was deemed necessary to “fix” the test parameters by including it in IEC 61109:1992 [5]. At this point it was given as an alternative to the 1 000h salt-fog test for insulators intended for extreme conditions. IEC 61109:1992 did not mention any acceleration factors.

When it was decided to group common tests for composite insulators into IEC 62217:2005, the test was included as an alternative tracking and erosion test, not an accelerated ageing test. The version of the test in 62217:2005 had been revised by IEC TC 36 WG12 on the basis of work between Sweden and France to improve the reproducibility of the test which had been shown to be problematic [6]. The main improvement involved calibration of the salt-fog cycle by using standard dummy insulators at each test position to set up fog distribution and flow rate.

The procedure included in this Technical Report includes some minor alterations to further improve reproducibility.

5 Classification of tests

Previously, these tests were alternative or supplementary design tests.

6 General requirements for insulator test specimens

Insulator test specimens for tests of polymeric insulators shall be checked prior to tests:

- for correct assembly, for example by applying the mechanical routine test specified in the relevant product standard,
- by visual examination according to the relevant product standard;
- for conformance of dimensions with the actual drawing.

For dimensions d without tolerances the following tolerances are acceptable:

- $\pm (0,04 \times d + 1,5)$ mm when $d \leq 300$ mm;
- $\pm (0,025 \times d + 6)$ mm when $d > 300$ mm with a maximum tolerance of 50 mm.

The measurement of creepage distances shall be related to the design dimensions and tolerances as determined from the insulator drawing, even if this dimension is greater than the value originally specified. When a minimum creepage is specified, the negative tolerance is also limited by this value.

The housing colour of the test specimens shall be approximately as specified in the drawing.

The number of test specimens, their selection and dimensions are specified in the relevant product standard or agreed upon by the interested parties.

7 The tests

7.1 Wheel test

7.1.1 Test specimens

Two test insulators of identical design with a creepage distance between 500 mm and 800 mm shall be taken from the production line. If such insulators cannot be taken from the production line, special test specimens shall be made from other insulators so that the creepage distance falls between the given values. These special test specimens shall be fitted with standard production end fittings.

Up to two pairs of test specimens can be tested simultaneously on one wheel. It is recommended not to mix widely differing materials on the same wheel.

The test samples shall be properly marked so that the pairs can be easily identified at the end of the test.

7.1.2 Procedure

The test specimens shall be cleaned with de-ionized water before starting the test. The test specimens are mounted on the wheel as shown in Figure 1. They go through four positions in one cycle. Each test specimen remains stationary for about 40 s in each of the four positions. The 90° rotation from one position to the next takes about 8 s. In the first part of the cycle the insulator is dipped into a saline solution. The second part of the test cycle permits the excess saline solution to drip off the specimen, ensuring that the light wetting of the surface gives rise to sparking across dry bands that will form during the third part of the cycle. In that part the specimen is submitted to a power frequency voltage. In the last part of the cycle the surface of the specimen that had been heated by the dry band sparking is allowed to cool.

The test voltage is supplied by a test transformer. When loaded with a resistive current of 250 mA on the high voltage side the test circuit shall exhibit a maximum drop of 5 % in its output voltage.

The salt solution shall be replaced weekly. Weekly interruptions of the test for inspection purposes, each of these not exceeding 1 h are permissible. Interruption periods will not be counted in the test duration. One longer interruption up to 60 h is allowed. An additional testing time of three times the duration of the interruption period shall be added. The final test report shall include details of all interruptions.




Figure 1 – Test arrangement of the tracking wheel test