

TECHNICAL SPECIFICATION

IEC TS 62073

First edition
2003-06

Guidance on the measurement of wettability of insulator surfaces

*Mesure de l'hydrophobicité
de la surface des isolateurs*



Reference number
IEC/TS 62073:2003(E)

Publication numbering

As from 1 January 1997 all IEC publications are issued with a designation in the 60000 series. For example, IEC 34-1 is now referred to as IEC 60034-1.

Consolidated editions

The IEC is now publishing consolidated versions of its publications. For example, edition numbers 1.0, 1.1 and 1.2 refer, respectively, to the base publication, the base publication incorporating amendment 1 and the base publication incorporating amendments 1 and 2.

Further information on IEC publications

The technical content of IEC publications is kept under constant review by the IEC, thus ensuring that the content reflects current technology. Information relating to this publication, including its validity, is available in the IEC Catalogue of publications (see below) in addition to new editions, amendments and corrigenda. Information on the subjects under consideration and work in progress undertaken by the technical committee which has prepared this publication, as well as the list of publications issued, is also available from the following:

- **IEC Web Site** (www.iec.ch)

- **Catalogue of IEC publications**

The on-line catalogue on the IEC web site (http://www.iec.ch/searchpub/cur_fut.htm) enables you to search by a variety of criteria including text searches, technical committees and date of publication. On-line information is also available on recently issued publications, withdrawn and replaced publications, as well as corrigenda.

- **IEC Just Published**

This summary of recently issued publications (http://www.iec.ch/online_news/justpub/jp_entry.htm) is also available by email. Please contact the Customer Service Centre (see below) for further information.

- **Customer Service Centre**

If you have any questions regarding this publication or need further assistance, please contact the Customer Service Centre:

Email: custserv@iec.ch
Tel: +41 22 919 02 11
Fax: +41 22 919 03 00

TECHNICAL SPECIFICATION

IEC TS 62073

First edition
2003-06

Guidance on the measurement of wettability of insulator surfaces

*Mesure de l'hydrophobicité
de la surface des isolateurs*

© IEC 2003 — Copyright - all rights reserved

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Electrotechnical Commission, 3, rue de Varembé, PO Box 131, CH-1211 Geneva 20, Switzerland
Telephone: +41 22 919 02 11 Telefax: +41 22 919 03 00 E-mail: inmail@iec.ch Web: www.iec.ch



Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

PRICE CODE

S

For price, see current catalogue

CONTENTS

FOREWORD	4
INTRODUCTION	6
1 Scope and object	7
2 Terms and definitions	7
3 Methods for measurement of wetting properties	9
4 Method A – Contact angle method	10
4.1 General	10
4.2 Equipment	10
4.3 Measurement procedure	10
4.4 Evaluation	11
5 Method B – Surface tension method	11
5.1 General	11
5.2 Safety precautions	12
5.3 Equipment and reagents	12
5.4 Measurement procedure	12
5.5 Evaluation	13
6 Method C – The spray method	13
6.1 General	13
6.2 Equipment	13
6.3 Measurement procedure	13
6.4 Evaluation	14
7 Documentation	15
Annex A (normative) Guidelines regarding the applicability and comments on the limitations of the different methods described in this technical specification	16
Annex B (normative) Method A – Contact angle method	18
Annex C (normative) Method B – Surface tension method	19
Annex D (normative) Method C – Spray method	21
Figure 1 – Definition of the static contact angle	8
Figure 2 – Definition of the advancing angle (θ_a) and the receding angle (θ_r) inside a liquid drop resting on an inclined solid surface	9
Figure 3 – Measurements of the advancing angle (θ_a) and the receding angle (θ_r) by adding or withdrawing water from a droplet	11
Figure B.1 – Measurement of the advancing angle (θ_a) and the receding angle (θ_r) by using the captive bubble technique	18

Table 1 – Criteria for the determination of wettability class (WC).....	14
Table C.1 – Concentrations of ethylene-glycol-monoethyl-ether (cellosolve), formamide mixtures used in measuring surface tension of insulator surfaces in the range 30 mN/m to 56 mN/m ($T = 20\text{ }^{\circ}\text{C}$).....	19
Table C.2 – Concentrations of distilled water and formamide mixture used in measuring surface tension of insulator surfaces in the range 58 mN/m to 73 mN/m ($T = 20\text{ }^{\circ}\text{C}$).....	20
Table C.3 – Concentrations of distilled water and sodium chloride in mixtures used in measuring surface tension of insulator surfaces in the range 73 mN/m to 82 mN/m ($T = 20\text{ }^{\circ}\text{C}$)	20

IECNORM.COM: Click to view the full PDF of IEC TS 62073:2003

Withd 2003

INTERNATIONAL ELECTROTECHNICAL COMMISSION

GUIDANCE ON THE MEASUREMENT OF WETTABILITY OF INSULATOR SURFACES

FOREWORD

- 1) The IEC (International Electrotechnical Commission) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of the IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, the IEC publishes International Standards. Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. The IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of the IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested National Committees.
- 3) The documents produced have the form of recommendations for international use and are published in the form of standards, technical specifications, technical reports or guides and they are accepted by the National Committees in that sense.
- 4) In order to promote international unification, IEC National Committees undertake to apply IEC International Standards transparently to the maximum extent possible in their national and regional standards. Any divergence between the IEC Standard and the corresponding national or regional standard shall be clearly indicated in the latter.
- 5) The IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with one of its standards.
- 6) Attention is drawn to the possibility that some of the elements of this technical specification may be the subject of patent rights. The IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC 62073, which is a technical specification, has been prepared by IEC technical committee 36: Insulators.

The text of this technical specification is based on the following documents:

Enquiry draft	Report on voting
36/185/DTS	36/197A/RVC

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until 2006. At this date, the publication will be

- transformed into an International standard;
- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

IECNORM.COM: Click to view the full PDF of IEC TS 62073:2003

Withdrawn

INTRODUCTION

The wetting properties of a surface by water are commonly described by the terms hydrophobic (or hydrophobicity) and hydrophilic (or hydrophilicity). A hydrophobic surface is water-repellent, while a surface that is easily wetted by water is hydrophilic.

The wetting phenomenon of a surface is complex and many different parameters can influence its apparent wettability. Some important parameters include: type of insulator material, surface roughness, heterogeneities of the surface, chemical composition (e.g. due to ageing) and presence of pollution. For some of the insulator materials in common use, the wetting properties can change over time, due to the influence of the ambient conditions. This change can be either reversible or irreversible. Thus, the result of the measurement of the wettability may be influenced by the ambient conditions and the HV corona or dry-band arcing to which the insulator has been previously exposed. This dynamic wetting behaviour is more or less specific to different insulator materials.

The dynamic wetting behaviour exhibited by insulator materials is due to their chemical composition. Different processes such as oxidation, hydrolysis, migration of low molecular weight compounds, formation of complex compounds between e.g. siloxanes and water, rotation of flexible polymer chains, inter- and intra-molecular rearrangements, microbial growth, deposition of contaminants, adhesion and encapsulation of contaminant particles, may take place at different rates, depending on material and ambient conditions. Thus, wettability along and around an insulator can vary, due to differences in the exposure to solar radiation, rain, corona discharges, deposited pollution, etc. Therefore, wettability measurement of insulators should be performed on several separate areas of the insulator.

Measurement of the wettability of a surface is readily performed in the laboratory on well defined, homogeneous, smooth and planar surfaces of prepared specimens. In the case of insulators, for which non-destructive measurements are usually required (and where cut-out of material samples is usually not desired), these conditions do not exist and measurement with high precision is a difficult task. This is especially true when the measurement has to be performed on an insulator installed in an overhead line, substation or even in a high voltage test set-up in the laboratory.

GUIDANCE ON THE MEASUREMENT OF WETTABILITY OF INSULATOR SURFACES

1 Scope and object

The methods described in this technical specification can be used for the measurement of the wettability of the shed and housing material of composite insulators for overhead lines, substations and equipment or ceramic insulators covered or not covered by a coating. The obtained value represents the wettability at the time of the measurement.

The object of this standard is to describe three methods that can be used to determine the wettability of insulators. The determination of the ability of water to wet the surface of insulators may be useful to evaluate the condition of the surface of insulators in service, or as part of the insulator testing in the laboratory.

2 Terms and definitions

For the purposes of this document, the following definitions apply.

2.1

wettability

ability of a surface to be wetted by a liquid (e.g. water)

2.2

hydrophobicity and hydrophilicity

2.2.1

hydrophobicity

low level of wettability by water of a surface. A hydrophobic surface has a low surface tension and thus is water-repellent

2.2.2

hydrophilicity

high level of wettability by water of a surface. A hydrophilic surface has a high surface tension and thus is wetted by water (in the form of a film)

2.3

surface tension

interface tension

region of finite thickness (usually less than 0,1 µm) in which the composition and energy vary continuously from one bulk phase to the other. The pressure (force field) in the interfacial zone has a gradient perpendicular to the interfacial boundary. A net energy is required to create an interface (surface) by transporting the matter from the bulk phase to the interfacial (surface) zone. The reversible work required to create a unit interfacial (surface) area is the surface tension and is defined thermodynamically as follows:

$$\gamma = \left(\frac{\partial G}{\partial A} \right)_{T,P,n}$$

where

γ is the surface (interfacial) tension or surface energy;

G is the Gibbs free energy of the total system;

A is the surface (interfacial) area;

T is the temperature;

P is the pressure;

n is the total number of moles of matter in the system.

The surface tension (γ) is usually expressed in mN/m (1 mN/m = 1 dyn/cm).

2.4

static contact angle

when a drop of liquid rests on the surface of a solid, and a gas is in contact with both, the forces acting at the interfaces must be in balance. These forces are due to surface tensions acting in the direction of the respective surfaces. From Figure 1 it follows that:

$$\gamma_{GL} \cos \theta_s = \gamma_{GS} - \gamma_{SL}$$

where

θ_s is the static contact angle of the edge of the drop with the solid surface,

γ_{GL} is the surface tension of the gas-liquid interface,

γ_{GS} is the surface tension of the gas-solid interface, and

γ_{SL} is the surface tension of the solid-liquid interface.

NOTE The above equation (Young's equation) is only valid for ideal and smooth surfaces.




Figure 1 – Definition of the static contact angle

The right side of the above equation (the difference between the surface tensions of the gas-solid and the solid-liquid interfaces) is defined as the surface tension of the solid surface. It is not a fundamental property of the surface but depends on the interaction between the solid and a particular environment.

When the gas is air saturated with vapour of the liquid, γ_{GL} will be the surface tension of the liquid. If the contact angle is 0° , the liquid is said to just wet the surface of the solid, and in this particular case (since $\cos \theta_s = 1$), the surface tension of the solid will be equal to the surface tension of the liquid.

2.5

advancing and receding contact angle

droplet on an inclined solid surface exhibits two different angles. The advancing contact angle (θ_a) is the angle inside the water droplet between the solid surface and the droplet surface at the lower part of the droplet on the inclined surface (see Figure 2).

The receding contact angle (θ_r) of a droplet on an inclined surface is the angle inside the droplet between the solid surface and the droplet surface at the droplet rear (highest part on the inclined surface). If the receding contact angle is zero, a completely wetted trace of water is formed as the drop moves along the solid inclined surface (see Figure 2).

The general physical relation between the advancing and receding contact angle and the static contact angle defined in 2.4 is: $\theta_r \leq \theta_s \leq \theta_a$




Figure 2 – Definition of the advancing angle (θ_a) and the receding angle (θ_r) inside a liquid drop resting on an inclined solid surface

2.6

wettability class

WC

hydrophobicity class

specific level of the scale used in the spray method (Method C)

NOTE Seven (7) classes, WC/1 to WC/7, have been defined. WC/1 corresponds to the most hydrophobic surface and WC/7 to the most hydrophilic surface.

3 Methods for measurement of wetting properties

Three methods for wettability measurement, differing in accuracy, simplicity, size of measured surface area and applicability, are described in this standard and are as follows:

- the contact angle method;
- the surface tension method;
- the spray method.

Guidance relative to the specific use of the three methods is found in Annex A.

4 Method A – Contact angle method

4.1 General

The contact angle method is a measurement that involves the evaluation of the contact angle formed between the edge of a single droplet of water and the surface of a solid material. If done on a horizontal surface, the advancing and receding contact angles can be measured by adding water to or withdrawing water from the droplet.

The contact angles depend strongly on the surface roughness and contact angles measured on polluted surfaces may differ significantly from contact angles measured on smooth, clean and planar surfaces.

4.2 Equipment

Different commercial equipment for measuring the contact angle is available. Simple measurements are made using a magnifying device with a graduated reticle (goniometer) fixed on a frame with a syringe for application of the droplet on the test specimen. Another method involves magnifying the droplet using a light projector (behind the droplet) and projecting an image of the droplet onto a graduated background. Some equipment includes camera, display and computer for analysis of the measurements.

4.3 Measurement procedure

4.3.1 General recommendations

General recommendations include:

- a) the receding contact angle (θ_r) reflects the wetting properties of an insulator more than the advancing contact angle (θ_a) and the static contact angle (θ_s);
- b) it is often necessary to cut out a test specimen from the insulator under investigation. The test specimen selected should be as planar as possible and the size should allow for the application of at least three droplets on separate surface areas adjacent to each other. The surface to be measured should not be touched and the specimen should be carefully stored until the measurement has been performed. The measurement should be performed as soon as possible;
- c) the water used should not contain impurities affecting the water surface tension (e.g. tensides, solvents, oil residues, etc.). De-ionized water is suitable;
- d) the volume of water in the droplet is not very critical. Volumes in the range 5 μl to 50 μl may be used. 50 μl is the recommended volume. For rough surfaces, a larger droplet volume may be needed. To limit a possible influence of the water droplet volume, the volume should be kept as constant as possible when comparing different specimens;
- e) the measurement of the contact angles should be performed as soon as possible (within a minute) after the application of the droplet on the surface. This is especially important when the ambient temperature is high and the relative humidity is low, which increases the rate of evaporation of the droplet. If the measurement is performed in a chamber with saturated water vapour, it eliminates the influence of evaporation.

NOTE Small droplet volumes have the advantage that the contact angle is less influenced by gravity. On the other hand, for rough surfaces and other surfaces that could have high advancing contact angles and low receding angles, a too small droplet volume makes the measurement of the dynamic contact angles very difficult. A small droplet volume will also be more sensitive to evaporation, which could affect the measurement. The optimal droplet volume may thus be dependent on type of surface and ambient temperature and humidity

4.3.2 Static contact angle measurements

The measurement of the static contact angle (θ_s) can be performed by applying a water droplet to the horizontal surface of a test specimen, using a pipette or a syringe with a scale.

4.3.3 Dynamic contact angle measurements

The measurement of the receding contact angle (θ_r) can be performed on a horizontal plane by withdrawing water from the droplet by using a syringe with a scale (see Figure 3). θ_r is the angle at the moment when the liquid front recedes. Measurement of θ_r should be performed on both projected sides of the droplet. At least three measurements on droplets applied on adjacent areas on the test specimen shall be performed. If three droplets are applied, this gives a total of six values.




Figure 3 – Measurements of the advancing angle (θ_a) and the receding angle (θ_r) by adding or withdrawing water from a droplet

It is recommended to keep the capillary pipette of the syringe immersed in the droplet during the entire measurement in order to avoid vibrations and distortions of the droplet that otherwise may affect the result.

There exist other methods to measure the dynamic contact angles. Examples of such methods are given in Annex B.

NOTE Prior to the measurement of θ_r the advancing contact angle (θ_a) may be measured by adding water to the droplet. θ_a is the angle at the moment when the water droplet front starts to advance on the surface.

4.4 Evaluation

To obtain a good indication of the wettability of the whole insulator, several contact angle measurements should be performed on different areas along and around the insulator. Low or zero receding angles on all measured areas indicate an easily wetted insulator, especially if also the advancing angles are low or zero. On the contrary, high receding (and advancing) angles indicate that the insulator is hydrophobic. Measurement on a single spot of the insulator surface is only valid for that location and is not sufficient to draw conclusions on the wettability of the whole insulator.

5 Method B – Surface tension method

5.1 General

The determination of the surface tension of an insulator surface is based on the phenomenon that drops of a series of organic liquid mixtures, with gradually increasing surface tension, have different ability to wet the insulator surface. Any trace of surface-active impurities in the liquid reagents or on the surface may affect the results. It is, therefore, important that the surface to be tested should not be touched or rubbed, that all equipment is clean and that reagent purity is carefully controlled.

This method is an extension of IEC 60674-21, which is used for the determination of the surface tension of polyethylene and polypropylene films. In particular this method implies the adoption of a larger number of liquids to cover a wider range of surface tension, which is needed to perform measurements on both hydrophobic and hydrophilic insulators. There may be restrictions in using this method on polluted insulator surfaces (see Annex A).

5.2 Safety precautions

The organic liquids used as reagents may affect health if not used properly. Formamide (HCONH_2) may cause skin irritation and is particularly dangerous in direct contact with eyes. Ethylene-glycolmonoethyl-ether ($\text{CH}_3\text{OCH}_2\text{CH}_2\text{OH}$) (or ethyl cellosolve) is a highly flammable solvent. Both formamide and ethyl cellosolve are toxic. Adequate safety precautions should be adopted, e.g. safety goggles should be worn and there should be adequate ventilation when handling these liquids and performing the measurements.

5.3 Equipment and reagents

5.3.1 Preparation of reagents

Tables C.1, C.2 and C.3 of Annex C are used for the preparation of the required mixtures. For surface tension outside the range 30 mN/m to 56 mN/m, reference is made to mixtures in Tables C.2 and C.3 of Annex C. Commercially available marker pens already prepared with solutions of different surface tension may be an alternative to making own mixtures.

5.3.2 Equipment

Three different applicators are available to apply the reagent solutions on the insulator surface:

- cotton-tipped wooden applicators;
- small soft paintbrushes fixed into the caps of the bottles with the reagents;
- commercially available marker pens already prepared with solutions of different surface tension.

For applicators a) and b), additional equipment is required:

- two graduated bottles of 50 ml;
- other bottles, 100 ml with caps and labels. The bottles should be cleaned with chrome-sulfuric acid and rinsed with distilled water.

NOTE 1 If desired, add dye (e.g. Victoria Pure Blue BO at a maximum concentration of 0,03 %) to each of the different reagent mixtures. The dye used should be of such a colour as to make drops clearly visible on the surface of the organic material considered. Furthermore, the dye must be of such a chemical composition that it will not measurably affect the wetting tension of the liquid mixtures.

NOTE 2 It is recommended that the surface tension of the liquid mixture be checked weekly. Any surface tension method applied in the laboratory is suitable. Although the shown liquid mixtures are relatively stable, exposure to temperatures above 30 °C and a relative humidity in excess of 70 % should be avoided.

5.4 Measurement procedure

Wet the extreme tip of the cotton applicator (if cotton applicators are used) with one of the reagent mixtures or remove the soft paintbrush fixed into the cap of the bottle with the reagent. Use only a minimum amount of liquid as an excess of reagent may affect the result.

The same measurement procedure is then used with any of the three applicators.

¹ IEC 60674-2:1988, *Specification for plastic films for electrical purposes – Part 2: Methods of test*.

Spread the liquid lightly over an area of approximately 5 cm^2 (25 mm of diameter) of the insulator surface at the selected location. Note the time required for the continuous liquid coverage formed on the surface to break up into droplets. If the continuous liquid coverage holds for more than 2 s, proceed to a higher surface tension mixture, but if the continuous liquid coverage breaks into droplets in less than 2 s proceed to a lower surface tension mixture. For each application of a new reagent mixture, a new adjacent surface should be selected to avoid contamination from the previously applied reagent. If measurements on the same surface area are desirable and possible without disturbance, the surface may be gently cleaned with a dry cloth (without the use of any detergent) to remove the remaining reagent previously applied. If cleaning is not performed, it is recommended to start with the lower surface tension mixtures and progressively continue to higher surface tension mixtures to minimize erroneous results due to contamination from the previously applied reagent mixture. When a cotton applicator is used, a clean, new applicator shall be used each time to avoid contamination of the solution. If the soft paintbrushes fixed into the caps are used, the brush may be cleaned in a small volume of the reagent before it is re-inserted into the reagent bottle again.

Proceed in the direction indicated above continually repeating the prescribed steps until it is possible to select the right mixture according to the evaluation in 5.5.

5.5 Evaluation

The mixture is considered as wetting the insulator surface when it remains intact as a continuous coverage of the liquid for at least 2 s. Shrinkage of the periphery of the continuous liquid coverage does not indicate lack of wetting. Only breaking into droplets within 2 s indicates lack of wetting. Severe peripheral shrinking may be caused when too much liquid is placed upon the surface. The surface tension of the applied mixture (in mN/m), which remains intact during 2 s as close as possible, is called the surface tension of the measured insulator surface.

6 Method C – The spray method

6.1 General

The spray method is based on the wetting response that an insulator surface gives after exposure to a fine water mist for a short period. The wettability after the mist exposure is evaluated.

6.2 Equipment

The equipment needed is a device that can produce a fine mist, such as a common spray bottle. The spray bottle is filled with water. The water shall not contain any impurities, which could influence the surface tension of the water, such as detergents, solvents, etc.

NOTE 1 Additional equipment which may facilitate the measurement include a magnification glass (for an easier judgement of droplet shape) and a lamp.

NOTE 2 Tap water of high quality does usually not contain impurities that significantly influence the surface tension of the water. Tap water of high quality could thus be used for the measurement. If there are any uncertainties about the water quality, de-ionized water or distilled water should be used.

6.3 Measurement procedure

The test area should preferably be approximately 50 cm^2 to 100 cm^2 . The ratio between the length and width of the test area should not be larger than 1:3. If this requirement cannot be met, this should be noted in the measurement report. Apply the mist from a distance of $25 \text{ cm} \pm 10 \text{ cm}$. The surface shall be exposed to the mist for a period of 20 s to 30 s. Typically, the amount of water sprayed during the 20 s to 30 s should be within 10 ml to 30 ml. The measurements of the wettability shall be performed within 10 s after the spraying has been completed.

The measurement should be performed in such a way that a clear picture of the variation of the wettability along and around the insulator is obtained.

NOTE 1 For long insulators only some selected sheds from the upper, middle and lower part of the insulator may be examined.

NOTE 2 The measurement might be difficult to perform in high winds. If such difficulties are present it may be necessary to perform the spraying from a shorter distance than $25 \text{ cm} \pm 10 \text{ cm}$. This should be noted in the measurement report, together with any other possible deviations from given recommendations, e.g. smaller test area.

6.4 Evaluation

The appearance on the insulator surface after mist exposure has to be identified with one of the seven wettability (hydrophobicity) classes (WC), which is a value between 1 and 7. The criteria for the different WCs are given in Table 1. Typical photos of surfaces with different WCs are shown in Annex D.

A surface with the WC value 1 is the most hydrophobic surface and a surface with the WC value 7 is the most hydrophilic surface.

Two visual criteria are used to judge the WC value:

- the shape of droplets;
- the percentage part of the surface which is wetted.

NOTE The uncertainty in the visual evaluation is usually not larger than ± 1 wettability class.

Table 1 – Criteria for the determination of wettability class (WC)

WC	Description
1	Only discrete droplets are formed. Their shape when viewed perpendicular to the surface is practically circular. This corresponds to $\theta_r = 80^\circ$ or larger for the droplets.
2	Only discrete droplets are formed. The major part of the surface is covered by droplets with a shape, as seen perpendicular to the surface, still regular but deviates from circular form. This corresponds to $50^\circ < \theta_r < 80^\circ$ for the majority of droplets.
3	Only discrete droplets are formed. The major part of the surface is covered by droplets with an irregular shape. This corresponds to $20^\circ < \theta_r < 50^\circ$ for the majority of droplets.
4	Both discrete droplets and wetted traces from the water runnels or water film are observed (i.e. $\theta_r = 0^\circ$ for some of the droplets). Less than 10 % of the observed area is covered by water runnels or film.
5	Both discrete droplets and wetted traces from the water runnels or water film are observed (i.e. $\theta_r = 0^\circ$ for some of the droplets). More than 10 % but less than 90 % of the observed area is covered by water runnels or film.
6	More than 90 % but less than 100 % of the observed area is covered by water runnels or film (i.e. small non-wetted areas/spots/traces are still observed).
7	Continuous water film is formed over the whole-observed area.

7 Documentation

The measurement report should include the following information:

a) General information

- 1) location, station, line or laboratory conditions;
- 2) method used (A, B or C);
- 3) date and time of the measurement and sample collection date and droplet volume for method A;
- 4) weather conditions (temperature, wind, precipitation);
- 5) who performed the test.

b) Test object

- 6) type of insulator or apparatus;
- 7) insulator material and shed profile;
- 8) identity (item No., position in substation or tower No.);
- 9) voltage class, arcing distance, creepage distance;
- 10) date of installation or application of coating (type of coating);
- 11) installation position (vertical, horizontal, angle);
- 12) information on the pollution state of the insulator.

c) Result

The results of the measurement performed at different positions should be documented, e.g. along the insulator (shed No.), along the surface within each shed sequence (top, bottom, large shed, small shed, trunk, etc.) and differences (if any) around the insulator circumference should be noted.

Annex A (normative)

Guidelines regarding the applicability and comments on the limitations of the different methods described in this technical specification

A.1 General

The suitability of each method and its applicability depends not only on its associated procedure but also on the specific case to be evaluated. All three methods are well suited for wettability measurements in the laboratory. In the field, it may be difficult to use method A. Method B can be used without too much difficulty while Method C can readily be used. Some considerations relevant to each method are outlined below:

a) **Method A** : Contact angle measurement

- gives an accurate value of the wettability of the area measured,
- is more accurately performed in the laboratory than in the field,
- the measurement is easily performed on practically flat surfaces,
- if aging has affected the surface morphology, i.e. presence of cracks, fissures or filler, the measurement may be adversely affected, and
- requires many measurements if a complete evaluation of the insulator surface is required.

b) **Method B** : Surface tension measurement

- gives an accurate value of the wettability of the area measured provided the spatial variation in the wettability is compatible with the area required for the measurement,
- is fairly easy to perform,
- requires certain safety precautions,
- may be difficult to use if the surface is covered with a layer of loosely adhering pollution,
- may be affected by interaction between certain types of surface pollution and the measuring agents may occur, and
- requires many measurements if a complete evaluation of the insulator surface is required.

c) **Method C** : Spray method

- gives a global assessment of the wettability of the insulator surface and its variation along and around the insulator,
- is easy to perform and requires simple equipment,
- depends on subjective visual examination of the surface,
- can be used to evaluate bare and polluted surfaces, and
- may be affected by an interaction between certain types of surface pollution and the spray water (i.e. modification of the equivalent salt deposit density (ESDD) level of the surface contaminant applied for laboratory pollution tests).

A.2 Typical results obtained with the three methods

Typical results obtained with the three methods are as follows:

- a) Hydrophobic surface (not wettable)
 - high value of receding contact angle ($> 80^\circ$),
 - low value of surface tension (< 30 mN/m),
 - low WC value (WC = 1 or WC = 2).
- b) Intermediate surface (semi-wettable)
 - intermediate value of receding contact angle (10° to 80°),
 - intermediate value of surface tension (30 mN/m to 60 mN/m),
 - intermediate WC value (WC = 3 to WC = 5).
- c) Hydrophilic surface (wettable)
 - low value of receding contact angle ($< 10^\circ$),
 - high value of surface tension (> 60 mN/m),
 - high WC value (WC = 6 or WC = 7).