
**Leather — Chemical determination
of chromium(VI) content in leather
— Thermal pre-ageing of leather
and determination of hexavalent
chromium**

*Cuir — Détermination chimique de la teneur en chrome(VI) du cuir
— Vieillissement thermique du cuir et détermination de la teneur en
chrome hexavalent*

STANDARDSISO.COM : Click to view the full PDF of ISO 10195:2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Apparatus.....	1
6 Procedure.....	2
7 Test report.....	3
Annex A (informative) Accuracy.....	4
Annex B (informative) Natural ageing and development of hexavalent chromium.....	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by the Chemical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, and the European Committee for Standardization (CEN) Technical Committee CEN/TC 309, *Footwear*, the secretariat of which is held by AENOR, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

Introduction

More than 80 % of leather is tanned using chromium(III) salts. The industry recommends manufacturing procedures to avoid oxidative conditions that could allow the formation of traces of hexavalent chromium [chromium(VI)] in the leather.

It is difficult to reproduce the natural ageing process. Therefore, in order to predict the tendency for trace levels of hexavalent chromium to develop in chromium(III) tanned leather, a number of pre-ageing tests have been proposed, some of which are being used in commercial leather specifications.

Following an inter-laboratory trial (see [Annex A](#)), thermal pre-ageing was selected as a suitable pre-ageing test procedure. The method is presented in this document.

Information on the development of hexavalent chromium during the natural ageing of chromium(III) tanned leather is given in [Annex B](#).

STANDARDSISO.COM : Click to view the full PDF of ISO 10195:2018

STANDARDSISO.COM : Click to view the full PDF of ISO 10195:2018

Leather — Chemical determination of chromium(VI) content in leather — Thermal pre-ageing of leather and determination of hexavalent chromium

1 Scope

This document specifies a thermal pre-ageing procedure for leather to obtain indications about the tendency to the formation of hexavalent chromium under specified conditions and the determination of hexavalent chromium according to ISO 17075-1 or ISO 17075-2.

This thermal pre-ageing procedure does not simulate any real condition in leather production or use.

It is applicable to all types of chromium tanned leather.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 4044:2017, *Leather — Chemical tests — Preparation of chemical test samples*

ISO 17075-1:2017, *Leather — Chemical determination of chromium(VI) content in leather — Part 1: Colorimetric method*

ISO 17075-2:2017, *Leather — Chemical determination of chromium(VI) content in leather — Part 2: Chromatographic method*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

A test specimen of leather is heated in an oven for a specified period of time. The sample is then cooled and the chemical determination of hexavalent chromium [chromium(VI)] is carried out according to ISO 17075-1 or ISO 17075-2.

5 Apparatus

5.1 Static oven, capable of maintaining the required temperature within a tolerance of ± 2 °C. The oven shall not have a fan or any other air circulating system, nor openings that allow active air exchange. The oven should have an interior made of inert materials. An oven with natural convection should be used.

5.2 250 ml Erlenmeyer glass flask with stopper, for containing the specimen, able to be maintained at 80 °C for 24 h and cooled at ambient temperature. This vessel allows the procedure of ISO 17075-1 or ISO 17075-2 to start from 7.2 (see 6.9).

5.3 Apparatus for temperature and humidity measurement.

5.4 Analytical balance, with an accuracy of 0,1 mg.

6 Procedure

6.1 Pre-heat the oven (5.1) to the desired temperature, see Table 1.

Table 1 — Definition of the pre-ageing temperature

Method	Conditions	Recommended use
A1	At $(60 \pm 2) ^\circ\text{C}$ and relative humidity less than 20 %	General purpose ageing for leathers not subjected to critical conditions in manufacturing (gloves, garments, leather goods, handmade and fashion articles) and/or transportation
A2	At $(80 \pm 2) ^\circ\text{C}$ and relative humidity less than 10 %	Ageing for leathers subjected to critical conditions in manufacturing (footwear, automotive, upholstery) and/or transportation

6.2 Cut a leather sample in accordance with ISO 2418. If sampling in accordance with ISO 2418 is not possible (e.g. leathers from articles like shoes, garments), details about sampling shall be given in the test report.

6.3 Prepare the leather test specimen according to ISO 4044:2017, 6.3. Cut it into pieces of 3 mm to 5 mm with a sharp blade.

6.4 Weigh accurately $(2,0 \pm 0,1)$ g of leather test specimen, to 0,1 mg accuracy, into the vessel (5.2). Record the mass, *m*.

6.5 The vessel shall be closed immediately after weighing.

6.6 Open the vessel and place it in the oven.

6.7 The oven door shall not be opened during the ageing time. The temperature and humidity shall be checked (5.3) at least three times during the ageing process.

NOTE If the oven with natural convection is kept closed:

- at a temperature of 60 °C, the relative humidity will be physically lower than 20 %;
- at a temperature of 80 °C, the relative humidity will be physically lower than 10 %.

6.8 After (24 ± 1) h, remove the Erlenmeyer flask (5.2) from the oven, close it immediately and allow the leather test specimen to cool at ambient room temperature for $2 \text{ h} \pm 15 \text{ min}$.

6.9 Immediately after cooling, determine the hexavalent chromium content in the aged leather test specimen according to either ISO 17075-1 or ISO 17075-2.

Using the Erlenmeyer flask (5.2) allows the procedure to start from ISO 17075-1:2017, 7.2 or ISO 17075-2:2017, 7.2. Add by pipetting 100 ml of degassed solution (ISO 17075-1:2017, 5.1 or ISO 17075-2:2017, 5.1) into the flask and then displace the oxygen according to ISO 17075-1:2017, 7.2 or ISO 17075-2:2017, 7.2.

6.10 Calculate hexavalent chromium content in accordance with ISO 17075-1 or ISO 17075-2.

7 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 10195;
- b) a description of the type of leather tested and details about sampling if necessary ([6.2](#));
- c) the pre-ageing method selected;
- d) the amount of hexavalent chromium as defined in [6.10](#);
- e) the test method used for hexavalent chromium determination.

STANDARDSISO.COM : Click to view the full PDF of ISO 10195:2018