

# INTERNATIONAL STANDARD

**ISO**  
**10405**

First edition  
1993-08-01

---

---

## **Petroleum and natural gas industries – Care and use of casing and tubing**

*Industries du pétrole et du gaz naturel – Entretien et utilisation des tubes de  
cuvelage et de production*



Reference number  
ISO 10405:1993(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10405 was prepared by the American Petroleum Institute (API) (as RP 5C1) and was adopted, under a special "fast-track procedure", by Technical Committee ISO/TC 67, *Materials and equipment for petroleum and natural gas industries*, in parallel with its approval by the ISO member bodies.

© ISO 1993

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

## Introduction

International Standard ISO 10405:1993 reproduces the content of API RP 5C1, 16th edition, 1988. ISO, in endorsing this API document, recognizes that in certain respects the latter does not comply with all current ISO rules on the presentation and content of an International Standard. Therefore, the relevant technical body, within ISO/TC 67, will review ISO 10405:1993 and reissue it, when practicable, in a form complying with these rules.

This International Standard is not intended to obviate the need for sound engineering judgement as to when and where this International Standard should be utilized and users should be aware that additional or differing requirements may be needed to meet the needs for the particular service intended.

Standards referenced herein may be replaced by other international or national standards that can be shown to meet or exceed the requirements of the referenced standards.

STANDARDSISO.COM : Click to view the full PDF of ISO 10405:1993

This page intentionally left blank



# Petroleum and natural gas industries – Care and use of casing and tubing

## 1 Scope

This International Standard contains guiding principles for care and use of casing and tubing for the petroleum and natural gas industries.

## 2 Requirements

Requirements are specified in:

"API Recommended Practice 5C1 (RP 5C1), Sixteenth Edition, May 31, 1988, *Recommended Practice for Care and Use of Casing and Tubing*",

which is adopted as ISO 10405.

For the purposes of international standardization, however, modifications shall apply to specific clauses and paragraphs of API RP 5C1. These modifications are outlined below.

NOTE – A wavy line in the margin indicates the location of a modification to the text of the API publication.

Page 3

Information given in the POLICY statement is relevant to the API publication only.

Page 6

### Subclause 1.1, item b

Second line: delete "API" before "tubular goods".

### Subclause 1.7, item c

Second sentence shall read: "A steel tape calibrated in millimetres should be used."

Page 7

### Subclause 1.13

17th line from bottom shall read: "All values are rounded to the nearest 10 N·m."

6th line from bottom: Delete the asterisk after the parenthesis and the corresponding footnote.

### Subclause 1.14

Subheading above item a shall read: "**Round thread, 114 mm through 340 mm OD**"

Subheading above item g shall read: "**Buttress thread, 114 mm through 340 mm OD**"

Item g, 2nd line shall read: "... sizes 114,3 mm through 339,7 mm OD..."

Page 8

Subheading on 1st line shall read: "**Round thread and buttress thread, 406 mm, 473 mm and 508 mm OD**"

Item h, 1st line shall read:

"Make-up of 406,4 mm, 473 mm and 508 mm OD shall be to a..."

Item h, second paragraph, first sentence shall read:

"On 8-round thread casing a 9,5 mm equilateral triangle is die stamped at a distance of  $L_1 + 1,6$  mm from each end."

Item h, third paragraph, 4th line shall read: "(67 800 N·m)"

**Subclause 1.15**

Second sentence shall read:

"The joint should be made up beyond the hand-tight position at least three turns for sizes 114,3 mm through 177,8 mm and at least three and a half turns for sizes 193,7 mm and larger, except 244,5 mm and 273,1 mm grade P-110 and 508 mm grade J-55 and K-55 which should be made up for turns beyond hand-tight position."

*Page 9*

**Subclause 1.28**

Delete the first sentence starting "When thorough..." and ending "... Dallas, Texas."

*Pages 11 to 18, inclusive*

Replace part of the existing tables by new table 1.1 and table 1.2.

*Page 19*

**Subclause 2.1, item b**

2nd line: Delete "API" before "tubular goods".

**Subclause 2.3**

2nd line: Delete "API" before "drift mandrel".

**Subclause 2.9, item c**

Second sentence shall read: "A steel tape calibrated in millimetres should be used."

*Page 20*

**Subclause 2.15**

Last line shall read: "... coupling is made up with a torque of 68 N·m."

**Subclause 2.16**

13th line from bottom shall read: "All values are rounded to the nearest 10 N·m."

6th and 3rd lines from bottom: Delete the asterisk after the parenthesis (twice), and the corresponding footnote.

**Subclause 2.24**

Second sentence shall read:

"Tubing 60 mm OD and larger, preferably should be pulled in stands approximately 18 300 mm long or in doubles of range 2. Stands of tubing 48,3 mm OD or smaller and stands longer than 18 300 mm, should have intermediate support."

*Page 21*

**Subclause 2.33**

Delete the third sentence starting "When thorough..." and ending "... Dallas, Texas."

*Pages 22 to 24, inclusive*

Replace the existing table by new table 2.1.

*Page 25*

**Subclause 3.1**

1st line: Delete "API" before "tubular goods".

**Subclause 3.3**

2nd line: Delete the words "..., in addition to I.C.C. requirement, ..."

**Subclause 3.6, item a**

3rd line shall read: "less than 500 mm from the ground."

**Subclause 3.6, item g**

3rd line shall read: "higher than 3 000 mm."

Page 26

**Subclause 4.4**

2nd line below table 4.1: Delete "API" before "specified pipe wall thickness".

Page 27

**Subclause 6.3**

1st line: Substitute "should" for "shall".

**Subclause 6.5**

3rd and 7th lines: Substitute "should" for "shall".

Page 28

**Subclause 6.10**

3rd line: Replace "1 200 F" by "650 °C".

**Subclause 6.11**

Replace the present wording with the following:

"When using the metal arc process, low hydrogen electrodes should be used. These include all electrodes with the AWS classifications Exx15, Exx16, and Exx18 in AWS Specification A5.1, "*Covered Carbon Steel Arc Welding Electrodes*" (latest edition\*). Low-hydrogen electrodes should not be exposed to the atmosphere until ready for use. Electrodes must be stored in holding ovens at 65 °C to 150 °C immediately after their containers have been opened. Once removed from the holding oven, electrodes must be used within 30 min. Electrodes not used within this time limit must be discarded or re-conditioned by baking at 315 °C to 370 °C for 1 h. After re-conditioning, electrodes must be placed into the holding oven."

**Subclause 6.13**

2nd line: Replace "3 in" by "75 mm".

3rd line: Replace "400 to 600 F" by "205 °C to 315 °C".

**Subclause 6.14**

3rd line from bottom: Replace "205 F" by "121 °C".

**Subclause 6.16**

2nd line shall read: "4,8 mm diameter or smaller should be used."

**Subclause 6.22**

Second sentence shall read:

"If the top side of the float collar and casing collars are welded while the casing is in the rotary or if the practice is not to make a complete weld, three 75 mm welds should be placed at 120° intervals around 244,5 mm casing, three 100 mm welds should be placed on larger casing, and three 50 mm welds on smaller casings."

**Subclause 6.23**

1st line shall read: "If welds longer than 100 mm to 150 mm are made,"

2nd line shall read: "For example: If 150 mm..."

5th line shall read: "...150 mm to the left of the weld..."

**Subclause 6.26**

2nd line shall read: "... welds should be a minimum length of 50 mm at 50 mm intervals."

**Subclause 6.27**

End of 2nd line shall read: "..., with 19 mm welds at two equal spacings on the front edge and on 19 mm weld ..."

**New tables**

- 1.1 Recommended casing make-up torque 8-round-thread casing**
- 1.2 Torque values for extremeline casing**
- 2.1 Recommended tubing make-up torque round thread tubing**

NOTE – In tables 1.1 and 2.1, the values expressed in pounds per foot (column 2) must be multiplied by 1,488 to determine the linear density  $\rho_l$ .

STANDARDSISO.COM : Click to view the full PDF of ISO 10405:1993

**TABLE 1.1**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                     |         | 2                                           | 2     | 4      | 5                    |        | 6       |        | 7       |        |
|-----------------------|---------|---------------------------------------------|-------|--------|----------------------|--------|---------|--------|---------|--------|
| Size Outside Diameter |         | Nominal Weight, Threads and Coupling lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |        |         |        |         |        |
| in.                   | (mm)    |                                             |       |        | Optimum              |        | Minimum |        | Maximum |        |
| 4.500                 | (114,3) | 9.50                                        | H-40  | ST&C   | 770                  | (1040) | 570     | (780)  | 960     | (1300) |
| 4.500                 | (114,3) | 9.50                                        | J-55  | ST&C   | 1010                 | (1380) | 760     | (1030) | 1270    | (1720) |
| 4.500                 | (114,3) | 10.50                                       | J-55  | ST&C   | 1320                 | (1790) | 990     | (1350) | 1650    | (2240) |
| 4.500                 | (114,3) | 11.60                                       | J-55  | ST&C   | 1540                 | (2090) | 1150    | (1560) | 1920    | (2610) |
| 4.500                 | (114,3) | 9.50                                        | K-55  | ST&C   | 1120                 | (1520) | 840     | (1140) | 1400    | (1900) |
| 4.500                 | (114,3) | 10.50                                       | K-55  | ST&C   | 1460                 | (1980) | 1100    | (1490) | 1830    | (2480) |
| 4.500                 | (114,3) | 11.60                                       | K-55  | ST&C   | 1700                 | (2310) | 1280    | (1730) | 2130    | (2890) |
| 4.500                 | (114,3) | 11.60                                       | J-55  | LT&C   | 1620                 | (2200) | 1210    | (1650) | 2020    | (2750) |
| 4.500                 | (114,3) | 11.60                                       | K-55  | LT&C   | 1800                 | (2430) | 1350    | (1830) | 2240    | (3040) |
| 4.500                 | (114,3) | 11.60                                       | C-75  | LT&C   | 2150                 | (2910) | 1610    | (2180) | 2680    | (3640) |
| 4.500                 | (114,3) | 13.50                                       | C-75  | LT&C   | 2600                 | (3530) | 1950    | (2640) | 3250    | (4410) |
| 4.500                 | (114,3) | 11.60                                       | L-80  | LT&C   | 2230                 | (3030) | 1670    | (2270) | 2790    | (3780) |
| 4.500                 | (114,3) | 13.50                                       | L-80  | LT&C   | 2710                 | (3670) | 2030    | (2750) | 3380    | (4590) |
| 4.500                 | (114,3) | 11.60                                       | N-80  | LT&C   | 2280                 | (3090) | 1710    | (2310) | 2850    | (3860) |
| 4.500                 | (114,3) | 13.50                                       | N-80  | LT&C   | 2760                 | (3740) | 2070    | (2810) | 3450    | (4680) |
| 4.500                 | (114,3) | 11.60                                       | C-90  | LT&C   | 2450                 | (3320) | 1840    | (2490) | 3060    | (4150) |
| 4.500                 | (114,3) | 13.50                                       | C-90  | LT&C   | 2970                 | (4030) | 2230    | (3020) | 3710    | (5040) |
| 4.500                 | (114,3) | 11.60                                       | C-95  | LT&C   | 2580                 | (3500) | 1940    | (2630) | 3230    | (4380) |
| 4.500                 | (114,3) | 13.50                                       | C-95  | LT&C   | 3130                 | (4240) | 2350    | (3180) | 3910    | (5310) |
| 4.500                 | (114,3) | 11.60                                       | P-110 | LT&C   | 3020                 | (4100) | 2270    | (3070) | 3780    | (5120) |
| 4.500                 | (114,3) | 13.50                                       | P-110 | LT&C   | 3660                 | (4960) | 2750    | (3720) | 4580    | (6200) |
| 4.500                 | (114,3) | 15.10                                       | P-110 | LT&C   | 4400                 | (5960) | 3300    | (4470) | 5500    | (7450) |
| 4.500                 | (114,3) | 15.10                                       | Q-125 | LT&C   | 4910                 | (6650) | 3680    | (4990) | 6130    | (8320) |
| 5.000                 | (127,0) | 11.50                                       | J-55  | ST&C   | 1330                 | (1810) | 1000    | (1350) | 1660    | (2260) |
| 5.000                 | (127,0) | 13.00                                       | J-55  | ST&C   | 1690                 | (2290) | 1260    | (1710) | 2110    | (2860) |
| 5.000                 | (127,0) | 15.00                                       | J-55  | ST&C   | 2070                 | (2800) | 1550    | (2100) | 2580    | (3500) |
| 5.000                 | (127,0) | 11.50                                       | K-55  | ST&C   | 1470                 | (1990) | 1100    | (1490) | 1830    | (2490) |
| 5.000                 | (127,0) | 13.00                                       | K-55  | ST&C   | 1860                 | (2520) | 1390    | (1890) | 2320    | (3150) |
| 5.000                 | (127,0) | 15.00                                       | K-55  | ST&C   | 2280                 | (3090) | 1710    | (2320) | 2850    | (3860) |
| 5.000                 | (127,0) | 13.00                                       | J-55  | LT&C   | 1820                 | (2470) | 1360    | (1850) | 2270    | (3080) |
| 5.000                 | (127,0) | 15.00                                       | J-55  | LT&C   | 2230                 | (3020) | 1670    | (2270) | 2790    | (3780) |
| 5.000                 | (127,0) | 13.00                                       | K-55  | LT&C   | 2010                 | (2730) | 1510    | (2040) | 2510    | (3410) |
| 5.000                 | (127,0) | 15.00                                       | K-55  | LT&C   | 2460                 | (3340) | 1850    | (2500) | 3080    | (4170) |
| 5.000                 | (127,0) | 15.00                                       | C-75  | LT&C   | 2960                 | (4010) | 2220    | (3010) | 3690    | (5010) |
| 5.000                 | (127,0) | 18.00                                       | C-75  | LT&C   | 3770                 | (5110) | 2830    | (3830) | 4710    | (6390) |
| 5.000                 | (127,0) | 21.40                                       | C-75  | LT&C   | 4660                 | (6320) | 3500    | (4740) | 5830    | (7900) |
| 5.000                 | (127,0) | 24.10                                       | C-75  | LT&C   | 5390                 | (7310) | 4040    | (5480) | 6740    | (9140) |
| 5.000                 | (127,0) | 15.00                                       | L-80  | LT&C   | 3080                 | (4170) | 2310    | (3130) | 3850    | (5220) |
| 5.000                 | (127,0) | 18.00                                       | L-80  | LT&C   | 3930                 | (5320) | 2940    | (3990) | 4910    | (6650) |
| 5.000                 | (127,0) | 21.40                                       | L-80  | LT&C   | 4860                 | (6590) | 3640    | (4940) | 6070    | (8230) |
| 5.000                 | (127,0) | 24.10                                       | L-80  | LT&C   | 5610                 | (7610) | 4210    | (5710) | 7020    | (9520) |
| 5.000                 | (127,0) | 15.00                                       | N-80  | LT&C   | 3140                 | (4250) | 2350    | (3190) | 3920    | (5320) |
| 5.000                 | (127,0) | 18.00                                       | N-80  | LT&C   | 4000                 | (5420) | 3000    | (4070) | 5000    | (6780) |
| 5.000                 | (127,0) | 21.40                                       | N-80  | LT&C   | 4950                 | (6710) | 3710    | (5030) | 6190    | (8390) |
| 5.000                 | (127,0) | 24.10                                       | N-80  | LT&C   | 5720                 | (7760) | 4290    | (5820) | 7150    | (9700) |

**TABLE 1.1 (cont.)**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                     |         | 2                                           | 2     | 4      | 5                    | 6       | 7       |        |         |         |
|-----------------------|---------|---------------------------------------------|-------|--------|----------------------|---------|---------|--------|---------|---------|
| Size Outside Diameter |         | Nominal Weight, Threads and Coupling lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |         |         |        |         |         |
| in.                   | (mm)    |                                             |       |        | Optimum              |         | Minimum |        | Maximum |         |
| 5.000                 | (127,0) | 15.00                                       | C-90  | LT&C   | 3380                 | (4590)  | 2540    | (3440) | 4230    | (5730)  |
| 5.000                 | (127,0) | 18.00                                       | C-90  | LT&C   | 4310                 | (5850)  | 3240    | (4390) | 5390    | (7310)  |
| 5.000                 | (127,0) | 21.40                                       | C-90  | LT&C   | 5340                 | (7240)  | 4000    | (5430) | 6670    | (9050)  |
| 5.000                 | (127,0) | 23.20                                       | C-90  | LT&C   | 5880                 | (7980)  | 4410    | (5980) | 7350    | (9970)  |
| 5.000                 | (127,0) | 24.10                                       | C-90  | LT&C   | 6170                 | (8370)  | 4630    | (6270) | 7710    | (10460) |
| 5.000                 | (127,0) | 15.00                                       | C-95  | LT&C   | 3560                 | (4830)  | 2670    | (3630) | 4460    | (6040)  |
| 5.000                 | (127,0) | 18.00                                       | C-95  | LT&C   | 4550                 | (6160)  | 3410    | (4620) | 5680    | (7700)  |
| 5.000                 | (127,0) | 21.40                                       | C-95  | LT&C   | 5620                 | (7630)  | 4220    | (5720) | 7030    | (9530)  |
| 5.000                 | (127,0) | 24.10                                       | C-95  | LT&C   | 6500                 | (8810)  | 4880    | (6610) | 8130    | (11020) |
| 5.500                 | (139,7) | 14.00                                       | H-40  | ST&C   | 1300                 | (1760)  | 970     | (1320) | 1620    | (2200)  |
| 5.500                 | (139,7) | 14.00                                       | J-55  | ST&C   | 1720                 | (2330)  | 1290    | (1750) | 2150    | (2920)  |
| 5.500                 | (139,7) | 15.50                                       | J-55  | ST&C   | 2020                 | (2730)  | 1510    | (2050) | 2520    | (3420)  |
| 5.500                 | (139,7) | 17.00                                       | J-55  | ST&C   | 2290                 | (3110)  | 1720    | (2330) | 2860    | (3880)  |
| 5.500                 | (139,7) | 14.00                                       | K-55  | ST&C   | 1890                 | (2560)  | 1420    | (1920) | 2360    | (3200)  |
| 5.500                 | (139,7) | 15.50                                       | K-55  | ST&C   | 2220                 | (3000)  | 1660    | (2250) | 2770    | (3750)  |
| 5.500                 | (139,7) | 17.00                                       | K-55  | ST&C   | 2520                 | (3410)  | 1890    | (2560) | 3150    | (4260)  |
| 5.500                 | (139,7) | 15.50                                       | J-55  | LT&C   | 2170                 | (2940)  | 1630    | (2210) | 2710    | (3680)  |
| 5.500                 | (139,7) | 17.00                                       | J-55  | LT&C   | 2470                 | (3340)  | 1850    | (2510) | 3080    | (4180)  |
| 5.500                 | (139,7) | 15.50                                       | K-55  | LT&C   | 2390                 | (3240)  | 1790    | (2430) | 2990    | (4050)  |
| 5.500                 | (139,7) | 17.00                                       | K-55  | LT&C   | 2720                 | (3680)  | 2040    | (2760) | 3390    | (4600)  |
| 5.500                 | (139,7) | 17.00                                       | C-75  | LT&C   | 3270                 | (4440)  | 2460    | (3330) | 4090    | (5550)  |
| 5.500                 | (139,7) | 20.00                                       | C-75  | LT&C   | 4030                 | (5460)  | 3020    | (4100) | 5040    | (6830)  |
| 5.500                 | (139,7) | 23.00                                       | C-75  | LT&C   | 4730                 | (6410)  | 3550    | (4810) | 5910    | (8020)  |
| 5.500                 | (139,7) | 17.00                                       | L-80  | LT&C   | 3410                 | (4630)  | 2560    | (3470) | 4270    | (5790)  |
| 5.500                 | (139,7) | 20.00                                       | L-80  | LT&C   | 4200                 | (5700)  | 3150    | (4270) | 5250    | (7120)  |
| 5.500                 | (139,7) | 23.00                                       | L-80  | LT&C   | 4930                 | (6690)  | 3700    | (5020) | 6170    | (8360)  |
| 5.500                 | (139,7) | 17.00                                       | N-80  | LT&C   | 3480                 | (4710)  | 2610    | (3530) | 4340    | (5890)  |
| 5.500                 | (139,7) | 20.00                                       | N-80  | LT&C   | 4280                 | (5800)  | 3210    | (4350) | 5350    | (7250)  |
| 5.500                 | (139,7) | 23.00                                       | N-80  | LT&C   | 5020                 | (6810)  | 3770    | (5110) | 6280    | (8510)  |
| 5.500                 | (139,7) | 17.00                                       | C-90  | LT&C   | 3750                 | (5090)  | 2820    | (3820) | 4690    | (6360)  |
| 5.500                 | (139,7) | 20.00                                       | C-90  | LT&C   | 4620                 | (6270)  | 3470    | (4700) | 5780    | (7830)  |
| 5.500                 | (139,7) | 23.00                                       | C-90  | LT&C   | 5430                 | (7360)  | 4070    | (5520) | 6780    | (9190)  |
| 5.500                 | (139,7) | 17.00                                       | C-95  | LT&C   | 3960                 | (5360)  | 2970    | (4020) | 4950    | (6710)  |
| 5.500                 | (139,7) | 20.00                                       | C-95  | LT&C   | 4870                 | (6600)  | 3650    | (4950) | 6090    | (8250)  |
| 5.500                 | (139,7) | 23.00                                       | C-95  | LT&C   | 5720                 | (7750)  | 4290    | (5810) | 7150    | (9690)  |
| 5.500                 | (139,7) | 17.00                                       | P-110 | LT&C   | 4620                 | (6270)  | 3470    | (4700) | 5780    | (7840)  |
| 5.500                 | (139,7) | 20.00                                       | P-110 | LT&C   | 5690                 | (7720)  | 4270    | (5790) | 7110    | (9650)  |
| 5.500                 | (139,7) | 23.00                                       | P-110 | LT&C   | 6680                 | (9060)  | 5010    | (6790) | 8350    | (11320) |
| 5.500                 | (139,7) | 23.00                                       | Q-125 | LT&C   | 7470                 | (10120) | 5600    | (7590) | 9330    | (12650) |
| 6.625                 | (168,3) | 20.00                                       | H-40  | ST&C   | 1840                 | (2490)  | 1380    | (1870) | 2300    | (3120)  |
| 6.625                 | (168,3) | 20.00                                       | J-55  | ST&C   | 2450                 | (3320)  | 1830    | (2490) | 3060    | (4150)  |
| 6.625                 | (168,3) | 24.00                                       | J-55  | ST&C   | 3140                 | (4250)  | 2350    | (3190) | 3920    | (5320)  |
| 6.625                 | (168,3) | 20.00                                       | K-55  | ST&C   | 2670                 | (3620)  | 2000    | (2710) | 3340    | (4520)  |
| 6.625                 | (168,3) | 24.00                                       | K-55  | ST&C   | 3420                 | (4640)  | 2570    | (3480) | 4280    | (5800)  |
| 6.625                 | (168,3) | 20.00                                       | J-55  | LT&C   | 2660                 | (3600)  | 1990    | (2700) | 3320    | (4500)  |
| 6.625                 | (168,3) | 24.00                                       | J-55  | LT&C   | 3400                 | (4620)  | 2550    | (3460) | 4250    | (5770)  |

TABLE 1.1 (cont.)  
RECOMMENDED CASING MAKE-UP TORQUE  
8-ROUND-THREAD CASING

| 1                           |         | 2                                                          | 2     | 4      | 5                    | 6       |      | 7       |       |         |
|-----------------------------|---------|------------------------------------------------------------|-------|--------|----------------------|---------|------|---------|-------|---------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |         |      |         |       |         |
| in.                         | (mm)    |                                                            |       |        | Optimum              | Minimum |      | Maximum |       |         |
| 6.625                       | (168,3) | 20.00                                                      | K-55  | LT&C   | 2900                 | (3940)  | 2180 | (2950)  | 3630  | (4920)  |
| 6.625                       | (168,3) | 24.00                                                      | K-55  | LT&C   | 3720                 | (5050)  | 2790 | (3780)  | 4650  | (6310)  |
| 6.625                       | (168,3) | 24.00                                                      | C-75  | LT&C   | 4530                 | (6140)  | 3390 | (4600)  | 5660  | (7670)  |
| 6.625                       | (168,3) | 28.00                                                      | C-75  | LT&C   | 5520                 | (7480)  | 4140 | (5610)  | 6890  | (9350)  |
| 6.625                       | (168,3) | 32.00                                                      | C-75  | LT&C   | 6380                 | (8650)  | 4780 | (6490)  | 7970  | (10810) |
| 6.625                       | (168,3) | 24.00                                                      | L-80  | LT&C   | 4730                 | (6410)  | 3550 | (4810)  | 5910  | (8010)  |
| 6.625                       | (168,3) | 28.00                                                      | L-80  | LT&C   | 5760                 | (7810)  | 4320 | (5860)  | 7200  | (9760)  |
| 6.625                       | (168,3) | 32.00                                                      | L-80  | LT&C   | 6660                 | (9030)  | 5000 | (6780)  | 8330  | (11290) |
| 6.625                       | (168,3) | 24.00                                                      | N-80  | LT&C   | 4810                 | (6520)  | 3600 | (4890)  | 6010  | (8150)  |
| 6.625                       | (168,3) | 28.00                                                      | N-80  | LT&C   | 5860                 | (7940)  | 4390 | (5960)  | 7320  | (9930)  |
| 6.625                       | (168,3) | 32.00                                                      | N-80  | LT&C   | 6780                 | (9190)  | 5080 | (6890)  | 8470  | (11480) |
| 6.625                       | (168,3) | 24.00                                                      | C-90  | LT&C   | 5210                 | (7060)  | 3910 | (5300)  | 6510  | (8830)  |
| 6.625                       | (168,3) | 28.00                                                      | C-90  | LT&C   | 6350                 | (8610)  | 4760 | (6450)  | 7930  | (10760) |
| 6.625                       | (168,3) | 32.00                                                      | C-90  | LT&C   | 7340                 | (9950)  | 5510 | (7470)  | 9180  | (12440) |
| 6.625                       | (168,3) | 24.00                                                      | C-95  | LT&C   | 5490                 | (7440)  | 4120 | (5580)  | 6860  | (9300)  |
| 6.625                       | (168,3) | 28.00                                                      | C-95  | LT&C   | 6690                 | (9070)  | 5020 | (6800)  | 8360  | (11340) |
| 6.625                       | (168,3) | 32.00                                                      | C-95  | LT&C   | 7740                 | (10490) | 5800 | (7870)  | 9670  | (13110) |
| 6.625                       | (168,3) | 24.00                                                      | P-110 | LT&C   | 6410                 | (8690)  | 4810 | (6520)  | 8010  | (10860) |
| 6.625                       | (168,3) | 28.00                                                      | P-110 | LT&C   | 7810                 | (10590) | 5860 | (7940)  | 9760  | (13240) |
| 6.625                       | (168,3) | 32.00                                                      | P-110 | LT&C   | 9040                 | (12250) | 6780 | (9190)  | 11290 | (15310) |
| 6.625                       | (168,3) | 32.00                                                      | Q-125 | LT&C   | 10110                | (13710) | 7580 | (10280) | 12640 | (17130) |
| 7.000                       | (177,8) | 17.00                                                      | H-40  | ST&C   | 1220                 | (1650)  | 910  | (1240)  | 1520  | (2070)  |
| 7.000                       | (177,8) | 20.00                                                      | H-40  | ST&C   | 1760                 | (2380)  | 1320 | (1790)  | 2200  | (2980)  |
| 7.000                       | (177,8) | 20.00                                                      | J-55  | ST&C   | 2340                 | (3170)  | 1750 | (2380)  | 2920  | (3960)  |
| 7.000                       | (177,8) | 23.00                                                      | J-55  | ST&C   | 2840                 | (3850)  | 2130 | (2890)  | 3550  | (4820)  |
| 7.000                       | (177,8) | 26.00                                                      | J-55  | ST&C   | 3340                 | (4530)  | 2500 | (3400)  | 4170  | (5660)  |
| 7.000                       | (177,8) | 20.00                                                      | K-55  | ST&C   | 2540                 | (3450)  | 1910 | (2590)  | 3180  | (4310)  |
| 7.000                       | (177,8) | 23.00                                                      | K-55  | ST&C   | 3090                 | (4190)  | 2320 | (3150)  | 3870  | (5240)  |
| 7.000                       | (177,8) | 26.00                                                      | K-55  | ST&C   | 3640                 | (4930)  | 2730 | (3700)  | 4540  | (6160)  |
| 7.000                       | (177,8) | 23.00                                                      | J-55  | LT&C   | 3130                 | (4240)  | 2350 | (3180)  | 3910  | (5300)  |
| 7.000                       | (177,8) | 26.00                                                      | J-55  | LT&C   | 3670                 | (4980)  | 2760 | (3740)  | 4590  | (6230)  |
| 7.000                       | (177,8) | 23.00                                                      | K-55  | LT&C   | 3410                 | (4630)  | 2560 | (3470)  | 4270  | (5780)  |
| 7.000                       | (177,8) | 26.00                                                      | K-55  | LT&C   | 4010                 | (5440)  | 3010 | (4080)  | 5010  | (6800)  |
| 7.000                       | (177,8) | 23.00                                                      | C-75  | LT&C   | 4160                 | (5640)  | 3120 | (4230)  | 5200  | (7050)  |
| 7.000                       | (177,8) | 26.00                                                      | C-75  | LT&C   | 4890                 | (6630)  | 3670 | (4970)  | 6110  | (8280)  |
| 7.000                       | (177,8) | 29.00                                                      | C-75  | LT&C   | 5620                 | (7620)  | 4220 | (5720)  | 7030  | (9530)  |
| 7.000                       | (177,8) | 32.00                                                      | C-75  | LT&C   | 6330                 | (8580)  | 4750 | (6440)  | 7910  | (10730) |
| 7.000                       | (177,8) | 35.00                                                      | C-75  | LT&C   | 7030                 | (9530)  | 5270 | (7140)  | 8780  | (11910) |
| 7.000                       | (177,8) | 38.00                                                      | C-75  | LT&C   | 7670                 | (10400) | 5750 | (7800)  | 9580  | (12990) |
| 7.000                       | (177,8) | 23.00                                                      | L-80  | LT&C   | 4350                 | (5890)  | 3260 | (4420)  | 5430  | (7370)  |
| 7.000                       | (177,8) | 26.00                                                      | L-80  | LT&C   | 5110                 | (6930)  | 3830 | (5190)  | 6380  | (8660)  |
| 7.000                       | (177,8) | 29.00                                                      | L-80  | LT&C   | 5870                 | (7960)  | 4410 | (5970)  | 7340  | (9960)  |
| 7.000                       | (177,8) | 32.00                                                      | L-80  | LT&C   | 6610                 | (8970)  | 4960 | (6720)  | 8270  | (11210) |
| 7.000                       | (177,8) | 35.00                                                      | L-80  | LT&C   | 7340                 | (9950)  | 5510 | (7470)  | 9180  | (12440) |
| 7.000                       | (177,8) | 38.00                                                      | L-80  | LT&C   | 8010                 | (10860) | 6010 | (8150)  | 10010 | (13580) |



TABLE 1.1 (cont.)  
RECOMMENDED CASING MAKE-UP TORQUE  
8-ROUND-THREAD CASING

| 1                           |         | 2                                                          | 2     | 4      | 5                    | 6            | 7             |
|-----------------------------|---------|------------------------------------------------------------|-------|--------|----------------------|--------------|---------------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |              |               |
| in.                         | (mm)    |                                                            |       |        | Optimum              | Minimum      | Maximum       |
| 7.000                       | (177,8) | 23.00                                                      | N-80  | LT&C   | 4420 (5990)          | 3310 (4490)  | 5520 (7490)   |
| 7.000                       | (177,8) | 26.00                                                      | N-80  | LT&C   | 5190 (7040)          | 3890 (5280)  | 6490 (8800)   |
| 7.000                       | (177,8) | 29.00                                                      | N-80  | LT&C   | 5970 (8100)          | 4480 (6070)  | 7460 (10120)  |
| 7.000                       | (177,8) | 32.00                                                      | N-80  | LT&C   | 6720 (9110)          | 5040 (6840)  | 8400 (11390)  |
| 7.000                       | (177,8) | 35.00                                                      | N-80  | LT&C   | 7460 (10120)         | 5600 (7590)  | 9330 (12650)  |
| 7.000                       | (177,8) | 38.00                                                      | N-80  | LT&C   | 8140 (11040)         | 6110 (8280)  | 10180 (13800) |
| 7.000                       | (177,8) | 23.00                                                      | C-90  | LT&C   | 4790 (6500)          | 3590 (4870)  | 5990 (8120)   |
| 7.000                       | (177,8) | 26.00                                                      | C-90  | LT&C   | 5630 (7630)          | 4220 (5730)  | 7040 (9540)   |
| 7.000                       | (177,8) | 29.00                                                      | C-90  | LT&C   | 6480 (8780)          | 4860 (6590)  | 8100 (10980)  |
| 7.000                       | (177,8) | 32.00                                                      | C-90  | LT&C   | 7290 (9880)          | 5470 (7410)  | 9110 (12360)  |
| 7.000                       | (177,8) | 35.00                                                      | C-90  | LT&C   | 8090 (10970)         | 6070 (8230)  | 10120 (13720) |
| 7.000                       | (177,8) | 38.00                                                      | C-90  | LT&C   | 8830 (11970)         | 6620 (8980)  | 11040 (14970) |
| 7.000                       | (177,8) | 23.00                                                      | C-95  | LT&C   | 5050 (6850)          | 3790 (5140)  | 6310 (8560)   |
| 7.000                       | (177,8) | 26.00                                                      | C-95  | LT&C   | 5930 (8050)          | 4450 (6030)  | 7420 (10060)  |
| 7.000                       | (177,8) | 29.00                                                      | C-95  | LT&C   | 6830 (9250)          | 5120 (6940)  | 8530 (11570)  |
| 7.000                       | (177,8) | 32.00                                                      | C-95  | LT&C   | 7680 (10420)         | 5760 (7810)  | 9600 (13020)  |
| 7.000                       | (177,8) | 35.00                                                      | C-95  | LT&C   | 8530 (11560)         | 6400 (8670)  | 10660 (14460) |
| 7.000                       | (177,8) | 38.00                                                      | C-95  | LT&C   | 9310 (12620)         | 6980 (9470)  | 11640 (15780) |
| 7.000                       | (177,8) | 26.00                                                      | P-110 | LT&C   | 6930 (9390)          | 5200 (7050)  | 8660 (11740)  |
| 7.000                       | (177,8) | 29.00                                                      | P-110 | LT&C   | 7970 (10800)         | 7980 (8100)  | 9960 (13510)  |
| 7.000                       | (177,8) | 32.00                                                      | P-110 | LT&C   | 8970 (12160)         | 6730 (9120)  | 11210 (15200) |
| 7.000                       | (177,8) | 35.00                                                      | P-110 | LT&C   | 9960 (13500)         | 7470 (10130) | 12450 (16880) |
| 7.000                       | (177,8) | 38.00                                                      | P-110 | LT&C   | 10870 (14730)        | 8150 (11050) | 13580 (18420) |
| 7.000                       | (177,8) | 35.00                                                      | Q-125 | LT&C   | 11150 (15110)        | 8360 (11340) | 13930 (18890) |
| 7.000                       | (177,8) | 38.00                                                      | Q-125 | LT&C   | 12160 (16490)        | 9120 (12370) | 15210 (20620) |
| 7.625                       | (193,7) | 24.00                                                      | H-40  | ST&C   | 2120 (2870)          | 1590 (2150)  | 2640 (3590)   |
| 7.625                       | (193,7) | 26.40                                                      | J-55  | ST&C   | 3150 (4270)          | 2360 (3200)  | 3940 (5340)   |
| 7.625                       | (193,7) | 26.40                                                      | K-55  | ST&C   | 3420 (4640)          | 2570 (3480)  | 4280 (5800)   |
| 7.625                       | (193,7) | 26.40                                                      | J-55  | LT&C   | 3460 (4690)          | 2600 (3520)  | 4330 (5870)   |
| 7.625                       | (193,7) | 26.40                                                      | K-55  | LT&C   | 3770 (5110)          | 2820 (3830)  | 4710 (6380)   |
| 7.625                       | (193,7) | 26.40                                                      | C-75  | LT&C   | 4610 (6250)          | 3460 (4690)  | 5760 (7810)   |
| 7.625                       | (193,7) | 29.70                                                      | C-75  | LT&C   | 5420 (7340)          | 4060 (5510)  | 6770 (9180)   |
| 7.625                       | (193,7) | 33.70                                                      | C-75  | LT&C   | 6350 (8610)          | 4760 (6460)  | 7940 (10760)  |
| 7.625                       | (193,7) | 39.00                                                      | C-75  | LT&C   | 7510 (10190)         | 5640 (7640)  | 9390 (12730)  |
| 7.625                       | (193,7) | 42.80                                                      | C-75  | LT&C   | 8520 (11560)         | 6390 (8670)  | 10660 (14450) |
| 7.625                       | (193,7) | 47.10                                                      | C-75  | LT&C   | 9530 (12920)         | 7150 (9690)  | 11910 (16150) |
| 7.625                       | (193,7) | 26.40                                                      | L-80  | LT&C   | 4820 (6530)          | 3610 (4900)  | 6020 (8170)   |
| 7.625                       | (193,7) | 29.70                                                      | L-80  | LT&C   | 5670 (7680)          | 4250 (5760)  | 7080 (9600)   |
| 7.625                       | (193,7) | 33.70                                                      | L-80  | LT&C   | 6640 (9000)          | 4980 (6750)  | 8300 (11250)  |
| 7.625                       | (193,7) | 39.00                                                      | L-80  | LT&C   | 7860 (10650)         | 5890 (7990)  | 9820 (13320)  |
| 7.625                       | (193,7) | 42.80                                                      | L-80  | LT&C   | 8910 (12090)         | 6690 (9060)  | 11140 (15110) |
| 7.625                       | (193,7) | 47.10                                                      | L-80  | LT&C   | 9970 (13520)         | 7480 (10140) | 12460 (16890) |
| 7.625                       | (193,7) | 26.40                                                      | N-80  | LT&C   | 4900 (6640)          | 3670 (4980)  | 6120 (8300)   |
| 7.625                       | (193,7) | 29.70                                                      | N-80  | LT&C   | 5750 (7800)          | 4320 (5850)  | 7190 (9750)   |
| 7.625                       | (193,7) | 33.70                                                      | N-80  | LT&C   | 6740 (9140)          | 5060 (6860)  | 8430 (11430)  |
| 7.625                       | (193,7) | 39.00                                                      | N-80  | LT&C   | 7980 (10820)         | 5990 (8120)  | 9980 (13530)  |
| 7.625                       | (193,7) | 42.80                                                      | N-80  | LT&C   | 9060 (12280)         | 6790 (9210)  | 11320 (15350) |
| 7.625                       | (193,7) | 47.10                                                      | N-80  | LT&C   | 10130 (13730)        | 7590 (10300) | 12660 (17160) |



TABLE 1.1 (cont.)  
RECOMMENDED CASING MAKE-UP TORQUE  
8-ROUND-THREAD CASING

| 1                           |         | 2                                                          | 2     | 4      | 5                    | 6             | 7             |
|-----------------------------|---------|------------------------------------------------------------|-------|--------|----------------------|---------------|---------------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |               |               |
| in.                         | (mm)    |                                                            |       |        | Optimum              | Minimum       | Maximum       |
| 7.625                       | (193,7) | 26.40                                                      | C-90  | LT&C   | 5320 (7210)          | 3990 (5410)   | 6650 (9010)   |
| 7.625                       | (193,7) | 29.70                                                      | C-90  | LT&C   | 6250 (8470)          | 4690 (6360)   | 7810 (10590)  |
| 7.625                       | (193,7) | 33.70                                                      | C-90  | LT&C   | 7330 (9930)          | 5490 (7450)   | 9160 (12420)  |
| 7.625                       | (193,7) | 39.00                                                      | C-90  | LT&C   | 8670 (11750)         | 6500 (8820)   | 10840 (14690) |
| 7.625                       | (193,7) | 42.80                                                      | C-90  | LT&C   | 9840 (13330)         | 7380 (10000)  | 12290 (16670) |
| 7.625                       | (193,7) | 45.30                                                      | C-90  | LT&C   | 10450 (14160)        | 7840 (10620)  | 13060 (17710) |
| 7.625                       | (193,7) | 47.10                                                      | C-90  | LT&C   | 11000 (14910)        | 8250 (11180)  | 13750 (18640) |
| 7.625                       | (193,7) | 26.40                                                      | C-95  | LT&C   | 5600 (7600)          | 4200 (5700)   | 7010 (9500)   |
| 7.625                       | (193,7) | 29.70                                                      | C-95  | LT&C   | 6590 (8930)          | 4940 (6700)   | 8230 (11160)  |
| 7.625                       | (193,7) | 33.70                                                      | C-95  | LT&C   | 7720 (10470)         | 5790 (7850)   | 9650 (13090)  |
| 7.625                       | (193,7) | 39.00                                                      | C-95  | LT&C   | 9140 (12390)         | 6850 (9290)   | 11420 (15480) |
| 7.625                       | (193,7) | 42.80                                                      | C-95  | LT&C   | 10370 (14050)        | 7770 (10540)  | 12960 (17570) |
| 7.625                       | (193,7) | 47.10                                                      | C-95  | LT&C   | 11590 (15720)        | 8690 (11790)  | 14490 (19640) |
| 7.625                       | (193,7) | 29.70                                                      | P-110 | LT&C   | 7690 (10420)         | 5770 (7820)   | 9610 (13030)  |
| 7.625                       | (193,7) | 33.70                                                      | P-110 | LT&C   | 9010 (12220)         | 6760 (9160)   | 11260 (15270) |
| 7.625                       | (193,7) | 39.00                                                      | P-110 | LT&C   | 10660 (14460)        | 8000 (10840)  | 13330 (18070) |
| 7.625                       | (193,7) | 42.80                                                      | P-110 | LT&C   | 12100 (16400)        | 9070 (12300)  | 15120 (20510) |
| 7.625                       | (193,7) | 47.10                                                      | P-110 | LT&C   | 13530 (18340)        | 10150 (13760) | 16910 (22930) |
| 7.625                       | (193,7) | 39.00                                                      | Q-125 | LT&C   | 11940 (16190)        | 8960 (12150)  | 14930 (20240) |
| 7.625                       | (193,7) | 42.80                                                      | Q-125 | LT&C   | 13550 (18370)        | 10160 (13780) | 16940 (22970) |
| 7.625                       | (193,7) | 45.30                                                      | Q-125 | LT&C   | 14390 (19520)        | 10800 (14640) | 17990 (24390) |
| 7.625                       | (193,7) | 47.10                                                      | Q-125 | LT&C   | 15150 (20540)        | 11360 (15410) | 18940 (25680) |
| 8.625                       | (219,1) | 28.00                                                      | H-40  | ST&C   | 2330 (3150)          | 1740 (2370)   | 2910 (3940)   |
| 8.625                       | (219,1) | 32.00                                                      | H-40  | ST&C   | 2790 (3780)          | 2090 (2840)   | 3490 (4730)   |
| 8.625                       | (219,1) | 24.00                                                      | J-55  | ST&C   | 2440 (3310)          | 1830 (2480)   | 3050 (4140)   |
| 8.625                       | (219,1) | 32.00                                                      | J-55  | ST&C   | 3720 (5050)          | 2790 (3790)   | 4660 (6310)   |
| 8.625                       | (219,1) | 36.00                                                      | J-55  | ST&C   | 4340 (5880)          | 3250 (4410)   | 5420 (7350)   |
| 8.625                       | (219,1) | 24.00                                                      | K-55  | ST&C   | 2630 (3570)          | 1970 (2680)   | 3290 (4460)   |
| 8.625                       | (219,1) | 32.00                                                      | K-55  | ST&C   | 4020 (5460)          | 3020 (4090)   | 5030 (6820)   |
| 8.625                       | (219,1) | 36.00                                                      | K-55  | ST&C   | 4680 (6350)          | 3510 (4760)   | 5850 (7940)   |
| 8.625                       | (219,1) | 32.00                                                      | J-55  | LT&C   | 4170 (5660)          | 3130 (4240)   | 5220 (7070)   |
| 8.625                       | (219,1) | 36.00                                                      | J-55  | LT&C   | 4860 (6590)          | 3640 (4940)   | 6070 (8230)   |
| 8.625                       | (219,1) | 32.00                                                      | K-55  | LT&C   | 4520 (6130)          | 3390 (4600)   | 5650 (7660)   |
| 8.625                       | (219,1) | 36.00                                                      | K-55  | LT&C   | 5260 (7140)          | 3950 (5350)   | 6580 (8920)   |
| 8.625                       | (219,1) | 36.00                                                      | C-75  | LT&C   | 6480 (8780)          | 4860 (6590)   | 8100 (10980)  |
| 8.625                       | (219,1) | 40.00                                                      | C-75  | LT&C   | 7420 (10060)         | 5560 (7540)   | 9270 (12570)  |
| 8.625                       | (219,1) | 44.00                                                      | C-75  | LT&C   | 8340 (11310)         | 6260 (8490)   | 10430 (14140) |
| 8.625                       | (219,1) | 49.00                                                      | C-75  | LT&C   | 9390 (12730)         | 7040 (9550)   | 11730 (15910) |
| 8.625                       | (219,1) | 36.00                                                      | L-80  | LT&C   | 6780 (9190)          | 5090 (6900)   | 8480 (11490)  |
| 8.625                       | (219,1) | 40.00                                                      | L-80  | LT&C   | 7760 (10530)         | 5820 (7900)   | 9710 (13160)  |
| 8.625                       | (219,1) | 44.00                                                      | L-80  | LT&C   | 8740 (11840)         | 6550 (8880)   | 10920 (14800) |
| 8.625                       | (219,1) | 49.00                                                      | L-80  | LT&C   | 9830 (13320)         | 7370 (9990)   | 12280 (16650) |
| 8.625                       | (219,1) | 36.00                                                      | N-80  | LT&C   | 6880 (9330)          | 5160 (7000)   | 8600 (11660)  |
| 8.625                       | (219,1) | 40.00                                                      | N-80  | LT&C   | 7880 (10680)         | 5910 (8010)   | 9850 (13360)  |
| 8.625                       | (219,1) | 44.00                                                      | N-80  | LT&C   | 8870 (12020)         | 6650 (9020)   | 11080 (15030) |
| 8.625                       | (219,1) | 49.00                                                      | N-80  | LT&C   | 9970 (13520)         | 7480 (10140)  | 12470 (16900) |
| 8.625                       | (219,1) | 36.00                                                      | C-90  | LT&C   | 7490 (10150)         | 5620 (7620)   | 9360 (12690)  |
| 8.625                       | (219,1) | 40.00                                                      | C-90  | LT&C   | 8580 (11630)         | 6430 (8720)   | 10720 (14530) |
| 8.625                       | (219,1) | 44.00                                                      | C-90  | LT&C   | 9650 (13080)         | 7240 (9810)   | 12060 (16350) |
| 8.625                       | (219,1) | 49.00                                                      | C-90  | LT&C   | 10850 (14710)        | 8140 (11040)  | 13570 (18390) |

TABLE 1.1 (cont.)  
RECOMMENDED CASING MAKE-UP TORQUE  
8-ROUND-THREAD CASING

| 1                           |         | 2                                                          | 2     | 4      | 5                    | 6             | 7             |
|-----------------------------|---------|------------------------------------------------------------|-------|--------|----------------------|---------------|---------------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |               |               |
| in.                         | (mm)    |                                                            |       |        | Optimum              | Minimum       | Maximum       |
| 8.625                       | (219,1) | 36.00                                                      | C-95  | LT&C   | 7890 (10700)         | 5920 (8030)   | 9870 (13380)  |
| 8.625                       | (219,1) | 40.00                                                      | C-95  | LT&C   | 9040 (12260)         | 6780 (9190)   | 11300 (15320) |
| 8.625                       | (219,1) | 44.00                                                      | C-95  | LT&C   | 10170 (13790)        | 7630 (10340)  | 12710 (17230) |
| 8.625                       | (219,1) | 49.00                                                      | C-95  | LT&C   | 11440 (15510)        | 8580 (11630)  | 14300 (19390) |
| 8.625                       | (219,1) | 40.00                                                      | P-110 | LT&C   | 10550 (14300)        | 7910 (10720)  | 13180 (17870) |
| 8.625                       | (219,1) | 44.00                                                      | P-110 | LT&C   | 11860 (16090)        | 8900 (12060)  | 14830 (20110) |
| 8.625                       | (219,1) | 49.00                                                      | P-110 | LT&C   | 13350 (18100)        | 10010 (13570) | 16680 (22620) |
| 8.625                       | (219,1) | 49.00                                                      | Q-125 | LT&C   | 14960 (20280)        | 11220 (15210) | 18700 (25350) |
| 9.625                       | (244,5) | 32.30                                                      | H-40  | ST&C   | 2540 (3440)          | 1900 (2580)   | 3170 (4300)   |
| 9.625                       | (244,5) | 36.00                                                      | H-40  | ST&C   | 2940 (3990)          | 2210 (2990)   | 3680 (4990)   |
| 9.625                       | (244,5) | 36.00                                                      | J-55  | ST&C   | 3940 (5340)          | 2950 (4000)   | 4920 (6670)   |
| 9.625                       | (244,5) | 40.00                                                      | J-55  | ST&C   | 4520 (6120)          | 3390 (4590)   | 5650 (7660)   |
| 9.625                       | (244,5) | 36.00                                                      | K-55  | ST&C   | 4230 (5740)          | 3180 (4310)   | 5290 (7180)   |
| 9.625                       | (244,5) | 40.00                                                      | K-55  | ST&C   | 4860 (6590)          | 3640 (4940)   | 6070 (8240)   |
| 9.625                       | (244,5) | 36.00                                                      | J-55  | LT&C   | 4530 (6140)          | 3400 (4610)   | 5660 (7680)   |
| 9.625                       | (244,5) | 40.00                                                      | J-55  | LT&C   | 5200 (7050)          | 3900 (5290)   | 6500 (8810)   |
| 9.625                       | (244,5) | 36.00                                                      | K-55  | LT&C   | 4890 (6630)          | 3670 (4970)   | 6110 (8290)   |
| 9.625                       | (244,5) | 40.00                                                      | K-55  | LT&C   | 5610 (7610)          | 4210 (5710)   | 7020 (9510)   |
| 9.625                       | (244,5) | 40.00                                                      | C-75  | LT&C   | 6940 (9410)          | 5200 (7060)   | 8670 (11760)  |
| 9.625                       | (244,5) | 43.50                                                      | C-75  | LT&C   | 7760 (10530)         | 5820 (7890)   | 9700 (13160)  |
| 9.625                       | (244,5) | 47.00                                                      | C-75  | LT&C   | 8520 (11550)         | 6390 (8660)   | 10650 (14440) |
| 9.625                       | (244,5) | 53.50                                                      | C-75  | LT&C   | 9990 (13540)         | 7490 (10160)  | 12490 (16930) |
| 9.625                       | (244,5) | 40.00                                                      | L-80  | LT&C   | 7270 (9860)          | 5450 (7390)   | 9090 (12320)  |
| 9.625                       | (244,5) | 43.50                                                      | L-80  | LT&C   | 8130 (11030)         | 6100 (8270)   | 10170 (13790) |
| 9.625                       | (244,5) | 47.00                                                      | L-80  | LT&C   | 8930 (12100)         | 6690 (9080)   | 11160 (15130) |
| 9.625                       | (244,5) | 53.50                                                      | L-80  | LT&C   | 10470 (14190)        | 7850 (10640)  | 13080 (17740) |
| 9.625                       | (244,5) | 40.00                                                      | N-80  | LT&C   | 7370 (10000)         | 5530 (7500)   | 9220 (12500)  |
| 9.625                       | (244,5) | 43.50                                                      | N-80  | LT&C   | 8250 (11190)         | 6190 (8390)   | 10310 (13980) |
| 9.625                       | (244,5) | 47.00                                                      | N-80  | LT&C   | 9050 (12270)         | 6790 (9200)   | 11320 (15340) |
| 9.625                       | (244,5) | 53.50                                                      | N-80  | LT&C   | 10620 (14390)        | 7960 (10790)  | 13270 (17990) |
| 9.625                       | (244,5) | 40.00                                                      | C-90  | LT&C   | 8040 (10900)         | 6030 (8170)   | 10050 (13620) |
| 9.625                       | (244,5) | 43.50                                                      | C-90  | LT&C   | 8990 (12190)         | 6740 (9140)   | 11240 (15240) |
| 9.625                       | (244,5) | 47.00                                                      | C-90  | LT&C   | 9870 (13380)         | 7400 (10030)  | 12330 (16720) |
| 9.625                       | (244,5) | 53.50                                                      | C-90  | LT&C   | 11570 (15690)        | 8680 (11770)  | 14460 (19610) |
| 9.625                       | (244,5) | 40.00                                                      | C-95  | LT&C   | 8470 (11490)         | 6360 (8620)   | 10590 (14360) |
| 9.625                       | (244,5) | 43.50                                                      | C-95  | LT&C   | 9480 (12850)         | 7110 (9640)   | 11850 (16060) |
| 9.625                       | (244,5) | 47.00                                                      | C-95  | LT&C   | 10400 (14100)        | 7800 (10580)  | 13000 (17630) |
| 9.625                       | (244,5) | 53.50                                                      | C-95  | LT&C   | 12200 (16540)        | 9150 (12400)  | 15250 (20670) |
| 9.625                       | (244,5) | 43.50                                                      | P-110 | LT&C   | 11050 (14980)        | 8290 (11240)  | 13810 (18730) |
| 9.625                       | (244,5) | 47.00                                                      | P-110 | LT&C   | 12130 (16440)        | 9090 (12330)  | 15160 (20550) |
| 9.625                       | (244,5) | 53.50                                                      | P-110 | LT&C   | 14220 (19280)        | 10670 (14460) | 17780 (24100) |
| 9.625                       | (244,5) | 47.00                                                      | Q-125 | LT&C   | 13600 (18440)        | 10200 (13830) | 17000 (23050) |
| 9.625                       | (244,5) | 53.50                                                      | Q-125 | LT&C   | 15950 (21620)        | 11960 (16220) | 19940 (27030) |

TABLE 1.1 (cont.)  
RECOMMENDED CASING MAKE-UP TORQUE  
8-ROUND-THREAD CASING

| 1                           |         | 2                                                          | 2     | 4      | 5                    | 6       | 7       |         |         |         |
|-----------------------------|---------|------------------------------------------------------------|-------|--------|----------------------|---------|---------|---------|---------|---------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft |       |        | Torque, ft-lbs (N·m) |         |         |         |         |         |
| in.                         | (mm)    |                                                            | Grade | Thread | Optimum              |         | Minimum |         | Maximum |         |
| 10.750                      | (273,1) | 32.75                                                      | H-40  | ST&C   | 2050                 | (2790)  | 1540    | (2090)  | 2570    | (3480)  |
| 10.750                      | (273,1) | 40.50                                                      | H-40  | ST&C   | 3140                 | (4250)  | 2350    | (3190)  | 3920    | (5320)  |
| 10.750                      | (273,1) | 40.50                                                      | J-55  | ST&C   | 4200                 | (5700)  | 3150    | (4270)  | 5250    | (7120)  |
| 10.750                      | (273,1) | 45.55                                                      | J-55  | ST&C   | 4930                 | (6680)  | 3700    | (5010)  | 6160    | (8360)  |
| 10.750                      | (273,1) | 51.00                                                      | J-55  | ST&C   | 5650                 | (7660)  | 4240    | (5750)  | 7070    | (9580)  |
| 10.750                      | (273,1) | 40.50                                                      | K-55  | ST&C   | 4500                 | (6100)  | 3380    | (4580)  | 5630    | (7630)  |
| 10.750                      | (273,1) | 45.55                                                      | K-55  | ST&C   | 5280                 | (7160)  | 3960    | (5370)  | 6600    | (8960)  |
| 10.750                      | (273,1) | 51.00                                                      | K-55  | ST&C   | 6060                 | (8210)  | 4540    | (6160)  | 7570    | (10270) |
| 10.750                      | (273,1) | 51.00                                                      | C-75  | ST&C   | 7560                 | (10250) | 5670    | (7690)  | 9450    | (12810) |
| 10.750                      | (273,1) | 55.50                                                      | C-75  | ST&C   | 8420                 | (11420) | 6320    | (8560)  | 10530   | (14270) |
| 10.750                      | (273,1) | 51.00                                                      | L-80  | ST&C   | 7940                 | (10760) | 5950    | (8070)  | 9920    | (13450) |
| 10.750                      | (273,1) | 55.50                                                      | L-80  | ST&C   | 8840                 | (11990) | 6630    | (8990)  | 11050   | (14980) |
| 10.750                      | (273,1) | 51.00                                                      | N-80  | ST&C   | 8040                 | (10900) | 6030    | (8170)  | 10050   | (13620) |
| 10.750                      | (273,1) | 55.50                                                      | N-80  | ST&C   | 8950                 | (12140) | 6710    | (9100)  | 11190   | (15170) |
| 10.750                      | (273,1) | 51.00                                                      | C-90  | ST&C   | 8790                 | (11920) | 6590    | (8940)  | 10990   | (14890) |
| 10.750                      | (273,1) | 55.50                                                      | C-90  | ST&C   | 9790                 | (13270) | 7340    | (9950)  | 12240   | (16590) |
| 10.750                      | (273,1) | 51.00                                                      | C-95  | ST&C   | 9270                 | (12560) | 6950    | (9420)  | 11580   | (15700) |
| 10.750                      | (273,1) | 55.50                                                      | C-95  | ST&C   | 10320                | (13990) | 7740    | (10490) | 12900   | (17490) |
| 10.750                      | (273,1) | 51.00                                                      | P-110 | ST&C   | 10790                | (14630) | 8090    | (10970) | 13490   | (18290) |
| 10.750                      | (273,1) | 55.50                                                      | P-110 | ST&C   | 12020                | (16300) | 9020    | (12220) | 15030   | (20370) |
| 10.750                      | (273,1) | 60.70                                                      | P-110 | ST&C   | 13370                | (18130) | 10030   | (13600) | 16720   | (22660) |
| 10.750                      | (273,1) | 65.70                                                      | P-110 | ST&C   | 14710                | (19950) | 11030   | (14960) | 18390   | (24930) |
| 10.750                      | (273,1) | 60.70                                                      | Q-125 | ST&C   | 15020                | (20360) | 11260   | (15270) | 18770   | (25460) |
| 10.750                      | (273,1) | 65.70                                                      | Q-125 | ST&C   | 16520                | (22400) | 12390   | (16800) | 20650   | (28000) |
| 11.750                      | (298,5) | 42.00                                                      | H-40  | ST&C   | 3070                 | (4170)  | 2310    | (3130)  | 3840    | (5210)  |
| 11.750                      | (298,5) | 47.00                                                      | J-55  | ST&C   | 4770                 | (6460)  | 3570    | (4850)  | 5960    | (8080)  |
| 11.750                      | (298,5) | 54.00                                                      | J-55  | ST&C   | 5680                 | (7700)  | 4260    | (5770)  | 7100    | (9620)  |
| 11.750                      | (298,5) | 60.00                                                      | J-55  | ST&C   | 6490                 | (8800)  | 4870    | (6600)  | 8110    | (11000) |
| 11.750                      | (298,5) | 47.00                                                      | K-55  | ST&C   | 5090                 | (6900)  | 3820    | (5180)  | 6360    | (8630)  |
| 11.750                      | (298,5) | 54.00                                                      | K-55  | ST&C   | 6060                 | (8220)  | 4550    | (6170)  | 7580    | (10280) |
| 11.750                      | (298,5) | 60.00                                                      | K-55  | ST&C   | 6930                 | (9400)  | 5200    | (7050)  | 8660    | (11750) |
| 11.750                      | (298,5) | 60.00                                                      | C-75  | ST&C   | 8690                 | (11780) | 6520    | (8830)  | 10860   | (14720) |
| 11.750                      | (298,5) | 60.00                                                      | L-80  | ST&C   | 9130                 | (12370) | 6840    | (9280)  | 11410   | (15470) |
| 11.750                      | (298,5) | 60.00                                                      | N-80  | ST&C   | 9240                 | (12420) | 6930    | (9390)  | 11550   | (15650) |
| 11.750                      | (298,5) | 60.00                                                      | C-90  | ST&C   | 10110                | (13710) | 7590    | (10290) | 12640   | (17140) |
| 11.750                      | (298,5) | 60.00                                                      | C-95  | ST&C   | 10660                | (14460) | 8000    | (10840) | 13330   | (18070) |
| 11.750                      | (298,5) | 60.00                                                      | P-110 | ST&C   | 12420                | (16830) | 9310    | (12630) | 15520   | (21040) |
| 11.750                      | (298,5) | 60.00                                                      | Q-125 | ST&C   | 13950                | (18920) | 10470   | (14190) | 17440   | (23650) |
| 13.375                      | (339,7) | 48.00                                                      | H-40  | ST&C   | 3220                 | (4370)  | 2420    | (3280)  | 4030    | (5460)  |
| 13.375                      | (339,7) | 54.50                                                      | J-55  | ST&C   | 5140                 | (6970)  | 3860    | (5230)  | 6430    | (8710)  |
| 13.375                      | (339,7) | 61.00                                                      | J-55  | ST&C   | 5950                 | (8070)  | 4460    | (6050)  | 7440    | (10090) |
| 13.375                      | (339,7) | 68.00                                                      | J-55  | ST&C   | 6750                 | (9160)  | 5070    | (6870)  | 8440    | (11450) |

**TABLE 1.1 (cont.)**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                           |         | 2                                                          | 2     | 4      | 5                    | 6             | 7             |
|-----------------------------|---------|------------------------------------------------------------|-------|--------|----------------------|---------------|---------------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |               |               |
| in.                         | (mm)    |                                                            |       |        | Optimum              | Minimum       | Maximum       |
| 13.375                      | (339,7) | 54.50                                                      | K-55  | ST&C   | 5470 (7410)          | 4100 (5560)   | 6840 (9270)   |
| 13.375                      | (339,7) | 61.00                                                      | K-55  | ST&C   | 6330 (8580)          | 4750 (6440)   | 7910 (10730)  |
| 13.375                      | (339,7) | 68.00                                                      | K-55  | ST&C   | 7180 (9740)          | 5390 (7300)   | 8980 (12170)  |
| 13.375                      | (339,7) | 68.00                                                      | C-75  | ST&C   | 9060 (12280)         | 6790 (9210)   | 11320 (15350) |
| 13.375                      | (339,7) | 72.00                                                      | C-75  | ST&C   | 9780 (13260)         | 7340 (9950)   | 12230 (16580) |
| 13.375                      | (339,7) | 68.00                                                      | L-80  | ST&C   | 9520 (12910)         | 7140 (9680)   | 11900 (16140) |
| 13.375                      | (339,7) | 72.00                                                      | L-80  | ST&C   | 10290 (13950)        | 7720 (10460)  | 12860 (17440) |
| 13.375                      | (339,7) | 68.00                                                      | N-80  | ST&C   | 9630 (13060)         | 7220 (9790)   | 12040 (16320) |
| 13.375                      | (339,7) | 72.00                                                      | N-80  | ST&C   | 10400 (14110)        | 7800 (10580)  | 13010 (17630) |
| 13.375                      | (339,7) | 68.00                                                      | C-90  | ST&C   | 10570 (14330)        | 7930 (10750)  | 13210 (17910) |
| 13.375                      | (339,7) | 72.00                                                      | C-90  | ST&C   | 11420 (15480)        | 8560 (11610)  | 14270 (19350) |
| 13.375                      | (339,7) | 68.00                                                      | C-95  | ST&C   | 11140 (15110)        | 8360 (11330)  | 13930 (18880) |
| 13.375                      | (339,7) | 72.00                                                      | C-95  | ST&C   | 12040 (16320)        | 9030 (12240)  | 15050 (20400) |
| 13.375                      | (339,7) | 68.00                                                      | P-110 | ST&C   | 12970 (17580)        | 9720 (13190)  | 16210 (21980) |
| 13.375                      | (339,7) | 72.00                                                      | P-110 | ST&C   | 14010 (18990)        | 10510 (14240) | 17510 (23740) |
| 13.375                      | (339,7) | 72.00                                                      | Q-125 | ST&C   | 15770 (21370)        | 11820 (16030) | 19710 (26720) |
| 16.000                      | (406,4) | 65.00                                                      | H-40  | ST&C   | 4390 (5950)          | 3290 (4460)   | 5490 (7440)   |
| 16.000                      | (406,4) | 75.00                                                      | J-55  | ST&C   | 7100 (9630)          | 5330 (7220)   | 8880 (12040)  |
| 16.000                      | (406,4) | 84.00                                                      | J-55  | ST&C   | 8170 (11080)         | 6130 (8310)   | 10220 (13850) |
| 16.000                      | (406,4) | 75.00                                                      | K-55  | ST&C   | 7520 (10190)         | 5640 (7640)   | 9390 (12740)  |
| 16.000                      | (406,4) | 84.00                                                      | K-55  | ST&C   | 8650 (11730)         | 6490 (8800)   | 10810 (14660) |
| 18.625                      | (473,0) | 87.50                                                      | H-40  | ST&C   | 5590 (7580)          | 4200 (5690)   | 6990 (9480)   |
| 18.625                      | (473,0) | 87.50                                                      | J-55  | ST&C   | 7540 (10220)         | 5660 (7670)   | 9430 (12780)  |
| 18.625                      | (473,0) | 87.50                                                      | K-55  | ST&C   | 7940 (10770)         | 5960 (8080)   | 9930 (13460)  |
| 20.000                      | (508,0) | 94.00                                                      | H-40  | ST&C   | 5810 (7870)          | 4360 (5910)   | 7260 (9840)   |
| 20.000                      | (508,0) | 94.00                                                      | J-55  | ST&C   | 7830 (10620)         | 5870 (7960)   | 9790 (13270)  |
| 20.000                      | (508,0) | 105.50                                                     | J-55  | ST&C   | 9130 (12370)         | 6850 (9280)   | 11410 (15470) |
| 20.000                      | (508,0) | 133.00                                                     | J-55  | ST&C   | 11920 (16160)        | 8940 (12120)  | 14900 (20200) |
| 20.000                      | (508,0) | 94.00                                                      | K-55  | ST&C   | 8230 (11160)         | 6170 (8370)   | 10290 (13950) |
| 20.000                      | (508,0) | 106.50                                                     | K-55  | ST&C   | 9590 (13000)         | 7190 (9750)   | 11990 (16260) |
| 20.000                      | (508,0) | 133.00                                                     | K-55  | ST&C   | 12520 (16980)        | 9390 (12740)  | 15660 (21230) |
| 20.000                      | (508,0) | 94.00                                                      | J-55  | LT&C   | 9070 (12290)         | 6800 (9220)   | 11330 (15360) |
| 20.000                      | (508,0) | 106.50                                                     | J-55  | LT&C   | 10560 (14320)        | 7920 (10740)  | 13210 (17900) |
| 20.000                      | (508,0) | 133.00                                                     | J-55  | LT&C   | 13790 (18700)        | 10350 (14030) | 17240 (23380) |
| 20.000                      | (508,0) | 94.00                                                      | K-55  | LT&C   | 9550 (12950)         | 7160 (9710)   | 11940 (16180) |
| 20.000                      | (508,0) | 106.50                                                     | K-55  | LT&C   | 11130 (15090)        | 8350 (11310)  | 13910 (18860) |
| 20.000                      | (508,0) | 133.00                                                     | K-55  | LT&C   | 14530 (19700)        | 10900 (14770) | 18160 (24620) |

**TABLE 1.2**  
**TORQUE VALUES FOR EXTREMELINE CASING**

The torque values listed below are recommended for use in conjunction with close visual examination to be sure the shoulder closes and to avoid excessive box swelling.

TORQUE, ft.-lbf (N·m)

| Size<br>Outside<br>Dia. | J-55 &<br>K-55 |                |                | C-75, L-80,<br>N-80, C-90 |                |                | C-95,<br>P-110 |                |                | Q-125          |                |                |
|-------------------------|----------------|----------------|----------------|---------------------------|----------------|----------------|----------------|----------------|----------------|----------------|----------------|----------------|
| In.<br>(mm)             | Min.           | Aim            | Max.           | Min.                      | Aim            | Max.           | Min.           | Aim            | Max.           | Min.           | Aim            | Max.           |
| 5<br>(127)              | 2500<br>(3390) | 2700<br>(3660) | 3000<br>(4070) | 3000<br>(4070)            | 3200<br>(4340) | 3500<br>(4750) | 3500<br>(4750) | 3700<br>(5020) | 4000<br>(5420) | 4000<br>(5420) | 4200<br>(5690) | 4500<br>(6100) |
| 5 1/2<br>(139,7)        | 2500<br>(3390) | 2700<br>(3660) | 3000<br>(4070) | 3000<br>(4070)            | 3200<br>(4340) | 3500<br>(4750) | 3500<br>(4750) | 3700<br>(5020) | 4000<br>(5420) | 4000<br>(5420) | 4200<br>(5690) | 4500<br>(6100) |
| 6 5/8<br>(168,3)        | 3000<br>(4070) | 3200<br>(4340) | 3500<br>(4750) | 3500<br>(4750)            | 3700<br>(5020) | 4000<br>(5420) | 4000<br>(5420) | 4200<br>(5690) | 4500<br>(6100) | 4500<br>(6100) | 4700<br>(6370) | 5000<br>(6780) |
| 7<br>(177,8)            | 3000<br>(4070) | 3200<br>(4340) | 3500<br>(4750) | 3500<br>(4750)            | 3700<br>(5020) | 4000<br>(5420) | 4000<br>(5420) | 4200<br>(5690) | 4500<br>(6100) | 4500<br>(6100) | 4700<br>(6370) | 5000<br>(6780) |
| 7 5/8<br>(193,7)        | 3500<br>(4750) | 3700<br>(5020) | 4000<br>(5420) | 4000<br>(5420)            | 4200<br>(5690) | 4500<br>(6100) | 4500<br>(6100) | 4700<br>(6370) | 5000<br>(6780) | 5000<br>(6780) | 5200<br>(7050) | 5500<br>(7460) |
| 8 5/8<br>(219,1)        | 4000<br>(5420) | 4200<br>(5690) | 4500<br>(6100) | 4500<br>(6100)            | 4700<br>(6370) | 5000<br>(6780) | 5000<br>(6780) | 5200<br>(7050) | 5500<br>(7460) | 5500<br>(7460) | 5700<br>(7730) | 6000<br>(8130) |
| 9 5/8<br>(244,5)        | 4500<br>(6100) | 4700<br>(6370) | 5000<br>(6780) | 5000<br>(6780)            | 5200<br>(7050) | 5500<br>(7460) | 6000<br>(8130) | 6200<br>(8410) | 6500<br>(8810) | 6500<br>(8810) | 6700<br>(9080) | 7000<br>(9490) |

**NOTES:**

- (1) The outside shoulder is not a sealing surface; serves as a stop only.
- (2) Torque values higher than those listed above may be considered under certain conditions, providing box swelling does not occur.
- (3) Increased axial tension stress due to higher torque values could be excessive for sulfide service.
- (4) If the connection does not shoulder when maximum torque is applied, it should be treated as a questionable joint as provided under Par. 1.16.
- (5) Recommended make-up torque values for 273,1 mm (10 3/4") are not available due to lack of data.



TABLE 2.1  
RECOMMENDED TUBING MAKE-UP TORQUE  
ROUND THREAD TUBING

| 1                           |         | 2                                                          | 2     | 4      | 5                    | 6          | 7           |
|-----------------------------|---------|------------------------------------------------------------|-------|--------|----------------------|------------|-------------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |            |             |
| in.                         | (mm)    |                                                            |       |        | Optimum              | Minimum    | Maximum     |
| 1.050                       | ( 26,7) | 1.14                                                       | H-40  | NU     | 140 (190)            | 100 (140)  | 170 (240)   |
| 1.050                       | ( 26,7) | 1.14                                                       | J-55  | NU     | 180 (240)            | 130 (180)  | 220 (300)   |
| 1.050                       | ( 26,7) | 1.14                                                       | C-75  | NU     | 230 (320)            | 180 (240)  | 290 (400)   |
| 1.050                       | ( 26,7) | 1.14                                                       | L-80  | NU     | 240 (330)            | 180 (240)  | 300 (410)   |
| 1.050                       | ( 26,7) | 1.14                                                       | N-80  | NU     | 250 (340)            | 190 (250)  | 310 (420)   |
| 1.050                       | ( 26,7) | 1.14                                                       | C-90  | NU     | 260 (350)            | 200 (260)  | 330 (440)   |
| 1.050                       | ( 26,7) | 1.20                                                       | H-40  | EUE    | 460 (630)            | 350 (470)  | 580 (780)   |
| 1.050                       | ( 26,7) | 1.20                                                       | J-55  | EUE    | 600 (810)            | 450 (610)  | 750 (1020)  |
| 1.050                       | ( 26,7) | 1.20                                                       | C-75  | EUE    | 780 (1060)           | 590 (800)  | 980 (1330)  |
| 1.050                       | ( 26,7) | 1.20                                                       | L-80  | EUE    | 810 (1090)           | 610 (820)  | 1010 (1370) |
| 1.050                       | ( 26,7) | 1.20                                                       | N-80  | EUE    | 830 (1130)           | 620 (840)  | 1040 (1410) |
| 1.050                       | ( 26,7) | 1.20                                                       | C-90  | EUE    | 880 (1190)           | 660 (890)  | 1100 (1480) |
| 1.315                       | ( 33,4) | 1.70                                                       | H-40  | NU     | 210 (280)            | 160 (210)  | 260 (350)   |
| 1.315                       | ( 33,4) | 1.70                                                       | J-55  | NU     | 270 (370)            | 200 (280)  | 340 (460)   |
| 1.315                       | ( 33,4) | 1.70                                                       | C-75  | NU     | 360 (480)            | 270 (360)  | 440 (600)   |
| 1.315                       | ( 33,4) | 1.70                                                       | L-80  | NU     | 370 (500)            | 270 (370)  | 460 (620)   |
| 1.315                       | ( 33,4) | 1.70                                                       | N-80  | NU     | 380 (510)            | 280 (380)  | 470 (640)   |
| 1.315                       | ( 33,4) | 1.70                                                       | C-90  | NU     | 400 (540)            | 300 (400)  | 500 (670)   |
| 1.315                       | ( 33,4) | 1.80                                                       | H-40  | EUE    | 440 (590)            | 330 (440)  | 550 (740)   |
| 1.315                       | ( 33,4) | 1.80                                                       | J-55  | EUE    | 570 (770)            | 430 (580)  | 710 (960)   |
| 1.315                       | ( 33,4) | 1.80                                                       | C-75  | EUE    | 740 (1010)           | 560 (750)  | 930 (1260)  |
| 1.315                       | ( 33,4) | 1.80                                                       | L-80  | EUE    | 760 (1040)           | 570 (780)  | 960 (1300)  |
| 1.315                       | ( 33,4) | 1.80                                                       | N-80  | EUE    | 790 (1070)           | 590 (800)  | 980 (1330)  |
| 1.315                       | ( 33,4) | 1.80                                                       | C-90  | EUE    | 830 (1130)           | 620 (840)  | 1040 (1410) |
| 1.315                       | ( 33,4) | 1.72                                                       | H-40  | IJ     | 310 (410)            | 230 (310)  | 380 (520)   |
| 1.315                       | ( 33,4) | 1.72                                                       | J-55  | IJ     | 400 (540)            | 300 (400)  | 500 (670)   |
| 1.315                       | ( 33,4) | 1.72                                                       | C-75  | IJ     | 520 (700)            | 390 (530)  | 650 (880)   |
| 1.315                       | ( 33,4) | 1.72                                                       | L-80  | IJ     | 530 (720)            | 400 (540)  | 670 (900)   |
| 1.315                       | ( 33,4) | 1.72                                                       | N-80  | IJ     | 550 (740)            | 410 (560)  | 690 (930)   |
| 1.315                       | ( 33,4) | 1.72                                                       | C-90  | IJ     | 580 (780)            | 430 (590)  | 720 (980)   |
| 1.660                       | ( 42,2) | 2.30                                                       | H-40  | NU     | 270 (360)            | 200 (270)  | 340 (450)   |
| 1.660                       | ( 42,2) | 2.30                                                       | J-55  | NU     | 350 (470)            | 260 (360)  | 440 (590)   |
| 1.660                       | ( 42,2) | 2.30                                                       | C-75  | NU     | 460 (620)            | 340 (470)  | 570 (780)   |
| 1.660                       | ( 42,2) | 2.30                                                       | L-80  | NU     | 470 (640)            | 350 (480)  | 590 (800)   |
| 1.660                       | ( 42,2) | 2.30                                                       | N-80  | NU     | 490 (660)            | 360 (490)  | 610 (820)   |
| 1.660                       | ( 42,2) | 2.30                                                       | C-90  | NU     | 510 (700)            | 390 (520)  | 640 (870)   |
| 1.660                       | ( 42,2) | 2.30                                                       | H-40  | EUE    | 530 (720)            | 400 (540)  | 660 (900)   |
| 1.660                       | ( 42,2) | 2.40                                                       | J-55  | EUE    | 690 (940)            | 520 (700)  | 860 (1170)  |
| 1.660                       | ( 42,2) | 2.40                                                       | C-75  | EUE    | 910 (1230)           | 680 (920)  | 1130 (1540) |
| 1.660                       | ( 42,2) | 2.40                                                       | L-80  | EUE    | 940 (1270)           | 700 (950)  | 1170 (1590) |
| 1.660                       | ( 42,2) | 2.40                                                       | N-80  | EUE    | 960 (1300)           | 720 (980)  | 1200 (1630) |
| 1.660                       | ( 42,2) | 2.40                                                       | C-90  | EUE    | 1020 (1380)          | 760 (1040) | 1270 (1730) |
| 1.660                       | ( 42,2) | 2.10                                                       | H-40  | IJ     | 380 (520)            | 290 (390)  | 480 (650)   |
| 1.660                       | ( 42,2) | 2.33                                                       | H-40  | IJ     | 380 (520)            | 290 (390)  | 480 (650)   |
| 1.660                       | ( 42,2) | 2.10                                                       | J-55  | IJ     | 500 (680)            | 370 (510)  | 620 (850)   |
| 1.660                       | ( 42,2) | 2.33                                                       | J-55  | IJ     | 500 (680)            | 370 (510)  | 620 (850)   |
| 1.660                       | ( 42,2) | 2.33                                                       | C-75  | IJ     | 650 (890)            | 490 (670)  | 820 (1110)  |
| 1.660                       | ( 42,2) | 2.33                                                       | L-80  | IJ     | 680 (920)            | 510 (690)  | 840 (1140)  |
| 1.660                       | ( 42,2) | 2.33                                                       | N-80  | IJ     | 690 (940)            | 520 (710)  | 870 (1180)  |
| 1.660                       | ( 42,2) | 2.33                                                       | C-90  | IJ     | 730 (1000)           | 550 (750)  | 920 (1240)  |

TABLE 2.1 (cont.)  
RECOMMENDED TUBING MAKE-UP TORQUE  
ROUND THREAD TUBING

| 1                           |         | 2                                                          | 2     | 4      | 5                    | 6          | 7           |
|-----------------------------|---------|------------------------------------------------------------|-------|--------|----------------------|------------|-------------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |            |             |
| in.                         | (mm)    |                                                            |       |        | Optimum              | Minimum    | Maximum     |
| 1.900                       | ( 48,3) | 2.75                                                       | H-40  | NU     | 320 (430)            | 240 (320)  | 400 (540)   |
| 1.900                       | ( 48,3) | 2.75                                                       | J-55  | NU     | 410 (560)            | 310 (420)  | 520 (700)   |
| 1.900                       | ( 48,3) | 2.75                                                       | C-75  | NU     | 540 (730)            | 410 (550)  | 680 (920)   |
| 1.900                       | ( 48,3) | 2.75                                                       | L-80  | NU     | 560 (760)            | 420 (570)  | 700 (950)   |
| 1.900                       | ( 48,3) | 2.75                                                       | N-80  | NU     | 570 (780)            | 430 (580)  | 720 (970)   |
| 1.900                       | ( 48,3) | 2.75                                                       | C-90  | NU     | 610 (830)            | 460 (620)  | 760 (1030)  |
| 1.900                       | ( 48,3) | 2.90                                                       | H-40  | EUE    | 670 (910)            | 500 (680)  | 840 (1130)  |
| 1.900                       | ( 48,3) | 2.90                                                       | J-55  | EUE    | 880 (1190)           | 660 (890)  | 1090 (1480) |
| 1.900                       | ( 48,3) | 2.90                                                       | C-75  | EUE    | 1150 (1560)          | 860 (1170) | 1440 (1950) |
| 1.900                       | ( 48,3) | 2.90                                                       | L-80  | EUE    | 1190 (1610)          | 890 (1210) | 1490 (2010) |
| 1.900                       | ( 48,3) | 2.90                                                       | N-80  | EUE    | 1220 (1650)          | 910 (1240) | 1520 (2060) |
| 1.900                       | ( 48,3) | 2.90                                                       | C-90  | EUE    | 1300 (1760)          | 970 (1320) | 1620 (2200) |
| 1.900                       | ( 48,3) | 2.40                                                       | H-40  | IJ     | 450 (600)            | 330 (450)  | 560 (750)   |
| 1.900                       | ( 48,3) | 2.76                                                       | H-40  | IJ     | 450 (600)            | 330 (450)  | 560 (750)   |
| 1.900                       | ( 48,3) | 2.40                                                       | J-55  | IJ     | 580 (790)            | 440 (590)  | 730 (990)   |
| 1.900                       | ( 48,3) | 2.76                                                       | J-55  | IJ     | 580 (790)            | 440 (590)  | 730 (990)   |
| 1.900                       | ( 48,3) | 2.76                                                       | C-75  | IJ     | 760 (1030)           | 570 (780)  | 950 (1290)  |
| 1.900                       | ( 48,3) | 2.76                                                       | L-80  | IJ     | 790 (1070)           | 590 (800)  | 990 (1340)  |
| 1.900                       | ( 48,3) | 2.76                                                       | N-80  | IJ     | 810 (1100)           | 610 (820)  | 1010 (1370) |
| 1.900                       | ( 48,3) | 2.76                                                       | C-90  | Ij     | 860 (1160)           | 640 (870)  | 1070 (1450) |
| 2.063                       | ( 52,4) | 3.25                                                       | H-40  | IJ     | 570 (770)            | 430 (580)  | 710 (960)   |
| 2.063                       | ( 52,4) | 3.25                                                       | J-55  | IJ     | 740 (1010)           | 560 (750)  | 930 (1260)  |
| 2.063                       | ( 52,4) | 3.25                                                       | C-75  | IJ     | 970 (1320)           | 730 (990)  | 1220 (1650) |
| 2.063                       | ( 52,4) | 3.25                                                       | L-80  | IJ     | 1010 (1370)          | 760 (1020) | 1260 (1710) |
| 2.063                       | ( 52,4) | 3.25                                                       | N-80  | IJ     | 1030 (1400)          | 770 (1050) | 1290 (1750) |
| 2.063                       | ( 52,4) | 3.25                                                       | C-90  | IJ     | 1100 (1490)          | 820 (1120) | 1370 (1860) |

TABLE 2.1 (cont.)  
RECOMMENDED TUBING MAKE-UP TORQUE  
ROUND THREAD TUBING

| 1                           |        | 2                                                          | 2     | 4      | 5                    | 6           | 7           |
|-----------------------------|--------|------------------------------------------------------------|-------|--------|----------------------|-------------|-------------|
| Size<br>Outside<br>Diameter |        | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |             |             |
| in.                         | (mm)   |                                                            |       |        | Optimum              | Minimum     | Maximum     |
| 2.375                       | (60,3) | 4.00                                                       | H-40  | NU     | 470 (630)            | 350 (480)   | 580 (790)   |
| 2.375                       | (60,3) | 4.60                                                       | H-40  | NU     | 560 (760)            | 420 (570)   | 700 (950)   |
| 2.375                       | (60,3) | 4.00                                                       | J-55  | NU     | 610 (830)            | 460 (620)   | 760 (1040)  |
| 2.375                       | (60,3) | 4.60                                                       | J-55  | NU     | 730 (990)            | 550 (740)   | 910 (1240)  |
| 2.375                       | (60,3) | 4.00                                                       | C-75  | NU     | 800 (1090)           | 600 (820)   | 1010 (1360) |
| 2.375                       | (60,3) | 4.60                                                       | C-75  | NU     | 960 (1300)           | 720 (980)   | 1200 (1630) |
| 2.375                       | (60,3) | 5.80                                                       | C-75  | NU     | 1380 (1860)          | 1030 (1400) | 1720 (2330) |
| 2.375                       | (60,3) | 4.00                                                       | L-80  | NU     | 830 (1130)           | 620 (850)   | 1040 (1410) |
| 2.375                       | (60,3) | 4.60                                                       | L-80  | NU     | 990 (1350)           | 750 (1010)  | 1240 (1680) |
| 2.375                       | (60,3) | 5.80                                                       | L-80  | NU     | 1420 (1930)          | 1070 (1450) | 1780 (2410) |
| 2.375                       | (60,3) | 4.00                                                       | N-80  | NU     | 850 (1160)           | 640 (870)   | 1070 (1450) |
| 2.375                       | (60,3) | 4.60                                                       | N-80  | NU     | 1020 (1380)          | 760 (1040)  | 1270 (1730) |
| 2.375                       | (60,3) | 5.80                                                       | N-80  | NU     | 1460 (1980)          | 1090 (1480) | 1820 (2470) |
| 2.375                       | (60,3) | 4.00                                                       | C-90  | NU     | 910 (1230)           | 680 (920)   | 1140 (1540) |
| 2.375                       | (60,3) | 4.60                                                       | C-90  | NU     | 1080 (1470)          | 810 (1100)  | 1360 (1840) |
| 2.375                       | (60,3) | 5.80                                                       | C-90  | NU     | 1550 (2110)          | 1160 (1580) | 1940 (2630) |
| 2.375                       | (60,3) | 4.60                                                       | P-105 | NU     | 1280 (1740)          | 960 (1300)  | 1600 (2170) |
| 2.375                       | (60,3) | 5.80                                                       | P-105 | NU     | 1840 (2490)          | 1380 (1870) | 2290 (3110) |
| 2.375                       | (60,3) | 4.70                                                       | H-40  | EUE    | 990 (1340)           | 740 (1000)  | 1230 (1670) |
| 2.375                       | (60,3) | 4.70                                                       | J-55  | EUE    | 1290 (1750)          | 970 (1310)  | 1620 (2190) |
| 2.375                       | (60,3) | 4.70                                                       | C-75  | EUE    | 1700 (2310)          | 1280 (1730) | 2130 (2880) |
| 2.375                       | (60,3) | 5.95                                                       | C-75  | EUE    | 2120 (2870)          | 1590 (2150) | 2650 (3590) |
| 2.375                       | (60,3) | 4.70                                                       | L-80  | EUE    | 1760 (2390)          | 1320 (1790) | 2200 (2990) |
| 2.375                       | (60,3) | 5.95                                                       | L-80  | EUE    | 2190 (2970)          | 1640 (2230) | 2740 (3710) |
| 2.375                       | (60,3) | 4.70                                                       | N-80  | EUE    | 1800 (2450)          | 1350 (1830) | 2260 (3060) |
| 2.375                       | (60,3) | 5.95                                                       | N-80  | EUE    | 2240 (3040)          | 1680 (2280) | 2800 (3800) |
| 2.375                       | (60,3) | 4.70                                                       | C-90  | EUE    | 1920 (2610)          | 1440 (1960) | 2410 (3260) |
| 2.375                       | (60,3) | 5.95                                                       | C-90  | EUE    | 2390 (3250)          | 1800 (2430) | 2990 (4060) |
| 2.375                       | (60,3) | 4.70                                                       | P-105 | EUE    | 2270 (3080)          | 1710 (2310) | 2840 (3850) |
| 2.375                       | (60,3) | 5.95                                                       | P-105 | EUE    | 2830 (3830)          | 2120 (2870) | 3530 (4790) |
| 2.875                       | (73,0) | 6.40                                                       | H-40  | NU     | 800 (1080)           | 600 (810)   | 1000 (1360) |
| 2.875                       | (73,0) | 6.40                                                       | J-55  | NU     | 1050 (1420)          | 790 (1070)  | 1310 (1780) |
| 2.875                       | (73,0) | 6.40                                                       | C-75  | NU     | 1380 (1880)          | 1040 (1410) | 1730 (2350) |
| 2.875                       | (73,0) | 7.80                                                       | C-75  | NU     | 1850 (2500)          | 1390 (1880) | 2310 (3130) |
| 2.875                       | (73,0) | 8.60                                                       | C-75  | NU     | 2090 (2830)          | 1570 (2120) | 2610 (3540) |
| 2.875                       | (73,0) | 6.40                                                       | L-80  | NU     | 1430 (1940)          | 1080 (1460) | 1790 (2430) |
| 2.875                       | (73,0) | 7.80                                                       | L-80  | NU     | 1910 (2590)          | 1440 (1950) | 2390 (3240) |
| 2.875                       | (73,0) | 8.60                                                       | L-80  | NU     | 2160 (2930)          | 1620 (2200) | 2710 (3670) |
| 2.875                       | (73,0) | 6.40                                                       | N-80  | NU     | 1470 (1990)          | 1100 (1490) | 1830 (2490) |
| 2.875                       | (73,0) | 7.80                                                       | N-80  | NU     | 1960 (2650)          | 1470 (1990) | 2450 (3320) |
| 2.875                       | (73,0) | 8.60                                                       | N-80  | NU     | 2210 (3000)          | 1660 (2250) | 2770 (3750) |
| 2.875                       | (73,0) | 6.40                                                       | C-90  | NU     | 1570 (2130)          | 1180 (1590) | 1960 (2660) |
| 2.875                       | (73,0) | 7.80                                                       | C-90  | NU     | 2090 (2840)          | 1570 (2130) | 2620 (3550) |
| 2.875                       | (73,0) | 8.60                                                       | C-90  | NU     | 2370 (3210)          | 1770 (2410) | 2960 (4010) |
| 2.875                       | (73,0) | 6.40                                                       | P-105 | NU     | 1850 (2510)          | 1390 (1880) | 2310 (3140) |
| 2.875                       | (73,0) | 7.80                                                       | P-105 | NU     | 2470 (3350)          | 1850 (2510) | 3090 (4190) |
| 2.875                       | (73,0) | 8.60                                                       | P-105 | NU     | 2790 (3790)          | 2100 (2840) | 3490 (4730) |
| 2.875                       | (73,0) | 6.50                                                       | H-40  | EUE    | 1250 (1700)          | 940 (1270)  | 1570 (2120) |
| 2.875                       | (73,0) | 6.50                                                       | J-55  | EUE    | 1650 (2230)          | 1230 (1670) | 2060 (2790) |
| 2.875                       | (73,0) | 6.50                                                       | C-75  | EUE    | 2170 (2940)          | 1630 (2210) | 2710 (3680) |
| 2.875                       | (73,0) | 7.90                                                       | C-75  | EUE    | 2610 (3540)          | 1960 (2660) | 3270 (4430) |
| 2.875                       | (73,0) | 8.70                                                       | C-75  | EUE    | 2850 (3860)          | 2130 (2890) | 3560 (4820) |
| 2.875                       | (73,0) | 6.50                                                       | L-80  | EUE    | 2250 (3050)          | 1690 (2290) | 2810 (3820) |
| 2.875                       | (73,0) | 7.90                                                       | L-80  | EUE    | 2710 (3680)          | 2030 (2760) | 3390 (4600) |
| 2.875                       | (73,0) | 8.70                                                       | L-80  | EUE    | 2950 (4000)          | 2210 (3000) | 3690 (5000) |



TABLE 2.1 (cont.)  
RECOMMENDED TUBING MAKE-UP TORQUE  
ROUND THREAD TUBING

| 1                           |         | 2                                                          | 2     | 4      | 5                    | 6           | 7           |
|-----------------------------|---------|------------------------------------------------------------|-------|--------|----------------------|-------------|-------------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lbs/ft | Grade | Thread | Torque, ft-lbs (N·m) |             |             |
| in.                         | (mm)    |                                                            |       |        | Optimum              | Minimum     | Maximum     |
| 2.875                       | ( 73,0) | 6.50                                                       | N-80  | EUE    | 2300 (3120)          | 1730 (2340) | 2880 (3900) |
| 2.875                       | ( 73,0) | 7.90                                                       | N-80  | EUE    | 2770 (3760)          | 2080 (2820) | 3470 (4700) |
| 2.875                       | ( 73,0) | 8.70                                                       | N-80  | EUE    | 3020 (4090)          | 2260 (3070) | 3770 (5110) |
| 2.875                       | ( 73,0) | 6.50                                                       | C-90  | EUE    | 2460 (3340)          | 1850 (2510) | 3080 (4180) |
| 2.875                       | ( 73,0) | 7.90                                                       | C-90  | EUE    | 2970 (4020)          | 2230 (3020) | 3710 (5030) |
| 2.875                       | ( 73,0) | 8.70                                                       | C-90  | EUE    | 3230 (4380)          | 2420 (3280) | 4040 (5470) |
| 2.875                       | ( 73,0) | 6.50                                                       | P-105 | EUE    | 2910 (3940)          | 2180 (2960) | 3640 (4930) |
| 2.875                       | ( 73,0) | 7.90                                                       | P-105 | EUE    | 3500 (4750)          | 2630 (3560) | 4380 (5940) |
| 2.875                       | ( 73,0) | 8.70                                                       | P-105 | EUE    | 3810 (5170)          | 2860 (3880) | 4760 (6460) |
| 3.500                       | ( 88,9) | 7.70                                                       | H-40  | NU     | 920 (1250)           | 690 (930)   | 1150 (1560) |
| 3.500                       | ( 88,9) | 9.20                                                       | H-40  | NU     | 1120 (1520)          | 840 (1140)  | 1400 (1900) |
| 3.500                       | ( 88,9) | 10.20                                                      | H-40  | NU     | 1310 (1770)          | 980 (1330)  | 1630 (2220) |
| 3.500                       | ( 88,9) | 7.70                                                       | J-55  | NU     | 1210 (1640)          | 910 (1230)  | 1510 (2050) |
| 3.500                       | ( 88,9) | 9.20                                                       | J-55  | NU     | 1480 (2010)          | 1110 (1500) | 1850 (2510) |
| 3.500                       | ( 88,9) | 10.20                                                      | J-55  | NU     | 1720 (2330)          | 1290 (1750) | 2150 (2920) |
| 3.500                       | ( 88,9) | 7.70                                                       | C-75  | NU     | 1600 (2170)          | 1200 (1630) | 2000 (2710) |
| 3.500                       | ( 88,9) | 9.20                                                       | C-75  | NU     | 1950 (2650)          | 1470 (1990) | 2440 (3310) |
| 3.500                       | ( 88,9) | 10.20                                                      | C-75  | NU     | 2270 (3080)          | 1710 (2310) | 2840 (3850) |
| 3.500                       | ( 88,9) | 12.70                                                      | C-75  | NU     | 3030 (4100)          | 2270 (3080) | 3780 (5130) |
| 3.500                       | ( 88,9) | 7.70                                                       | L-80  | NU     | 1660 (2250)          | 1240 (1690) | 2070 (2810) |
| 3.500                       | ( 88,9) | 9.20                                                       | L-80  | NU     | 2030 (2750)          | 1520 (2060) | 2540 (3440) |
| 3.500                       | ( 88,9) | 10.20                                                      | L-80  | NU     | 2360 (3200)          | 1770 (2400) | 2950 (4000) |
| 3.500                       | ( 88,9) | 12.70                                                      | L-80  | NU     | 3140 (4260)          | 2360 (3200) | 3930 (5330) |
| 3.500                       | ( 88,9) | 7.70                                                       | N-80  | NU     | 1700 (2300)          | 1270 (1720) | 2120 (2870) |
| 3.500                       | ( 88,9) | 9.20                                                       | N-80  | NU     | 2070 (2810)          | 1550 (2110) | 2590 (3510) |
| 3.500                       | ( 88,9) | 10.20                                                      | N-80  | NU     | 2410 (3270)          | 1810 (2450) | 3010 (4090) |
| 3.500                       | ( 88,9) | 12.70                                                      | N-80  | NU     | 3210 (4350)          | 2410 (3260) | 4010 (5440) |
| 3.500                       | ( 88,9) | 7.70                                                       | C-90  | NU     | 1820 (2460)          | 1360 (1850) | 2270 (3080) |
| 3.500                       | ( 88,9) | 9.20                                                       | C-90  | NU     | 2220 (3010)          | 1670 (2260) | 2780 (3770) |
| 3.500                       | ( 88,9) | 10.20                                                      | C-90  | NU     | 2590 (3510)          | 1940 (2630) | 3230 (4380) |
| 3.500                       | ( 88,9) | 12.70                                                      | C-90  | NU     | 3440 (4670)          | 2580 (3500) | 4300 (5830) |
| 3.500                       | ( 88,9) | 9.20                                                       | P-105 | NU     | 2620 (3550)          | 1970 (2670) | 3280 (4440) |
| 3.500                       | ( 88,9) | 12.70                                                      | P-105 | NU     | 4060 (5510)          | 3050 (4130) | 5080 (6880) |
| 3.500                       | ( 88,9) | 9.30                                                       | H-40  | EUE    | 1730 (2340)          | 1300 (1760) | 2160 (2930) |
| 3.500                       | ( 88,9) | 9.30                                                       | J-55  | EUE    | 2280 (3090)          | 1710 (2320) | 2850 (3860) |
| 3.500                       | ( 88,9) | 9.30                                                       | C-75  | EUE    | 3010 (4080)          | 2260 (3060) | 3770 (5110) |
| 3.500                       | ( 88,9) | 12.95                                                      | C-75  | EUE    | 4040 (5480)          | 3030 (4110) | 5050 (6850) |
| 3.500                       | ( 88,9) | 9.30                                                       | L-80  | EUE    | 3130 (4240)          | 2350 (3180) | 3910 (5310) |
| 3.500                       | ( 88,9) | 12.95                                                      | L-80  | EUE    | 4200 (5700)          | 3150 (4270) | 5250 (7120) |
| 3.500                       | ( 88,9) | 9.30                                                       | N-80  | EUE    | 3200 (4330)          | 2400 (3250) | 4000 (5420) |
| 3.500                       | ( 88,9) | 12.95                                                      | N-80  | EUE    | 4290 (5820)          | 3220 (4360) | 5360 (7270) |
| 3.500                       | ( 88,9) | 9.30                                                       | C-90  | EUE    | 3430 (4650)          | 2570 (3490) | 4290 (5820) |
| 3.500                       | ( 88,9) | 12.95                                                      | C-90  | EUE    | 4610 (6250)          | 3450 (4680) | 5760 (7810) |
| 3.500                       | ( 88,9) | 9.30                                                       | P-105 | EUE    | 4050 (5490)          | 3040 (4120) | 5060 (6860) |
| 3.500                       | ( 88,9) | 12.95                                                      | P-105 | EUE    | 5430 (7370)          | 4070 (5520) | 6790 (9210) |
| 4.000                       | (101,6) | 9.50                                                       | H-40  | NU     | 930 (1260)           | 700 (940)   | 1160 (1570) |
| 4.000                       | (101,6) | 9.50                                                       | J-55  | NU     | 1220 (1660)          | 920 (1240)  | 1530 (2070) |
| 4.000                       | (101,6) | 9.50                                                       | C-75  | NU     | 1620 (2200)          | 1210 (1650) | 2020 (2740) |
| 4.000                       | (101,6) | 9.50                                                       | L-80  | NU     | 1680 (2280)          | 1260 (1710) | 2100 (2850) |
| 4.000                       | (101,6) | 9.50                                                       | N-80  | NU     | 1720 (2330)          | 1290 (1750) | 2150 (2910) |
| 4.000                       | (101,6) | 9.50                                                       | C-90  | NU     | 1850 (2500)          | 1390 (1880) | 2310 (3130) |
| 4.000                       | (101,6) | 11.00                                                      | H-40  | EUE    | 1940 (2630)          | 1450 (1970) | 2420 (3290) |
| 4.000                       | (101,6) | 11.00                                                      | J-55  | EUE    | 2560 (3470)          | 1920 (2600) | 3200 (4340) |

TABLE 2.1 (cont.)  
RECOMMENDED TUBING MAKE-UP TORQUE  
ROUND THREAD TUBING

| 1                           |         | 2                                                | 2     | 4      | 5                    | 6           | 7           |
|-----------------------------|---------|--------------------------------------------------|-------|--------|----------------------|-------------|-------------|
| Size<br>Outside<br>Diameter |         | Nominal<br>Weight,<br>Threads<br>and<br>Coupling | Grade | Thread | Torque, ft-lbs (N·m) |             |             |
| in.                         | (mm)    | lbs/ft                                           |       |        | Optimum              | Minimum     | Maximum     |
| 4.000                       | (101,6) | 11.00                                            | C-75  | EUE    | 3390 (4600)          | 2540 (3450) | 4240 (5750) |
| 4.000                       | (101,6) | 11.00                                            | L-80  | EUE    | 3530 (4780)          | 2650 (3590) | 4410 (5980) |
| 4.000                       | (101,6) | 11.00                                            | N-80  | EUE    | 3600 (4880)          | 2700 (3660) | 4500 (6100) |
| 4.000                       | (101,6) | 11.00                                            | C-90  | EUE    | 3870 (5250)          | 2900 (3940) | 4840 (6560) |
| 4.500                       | (114,3) | 12.60                                            | H-40  | NU     | 1320 (1780)          | 990 (1340)  | 1640 (2230) |
| 4.500                       | (114,3) | 12.60                                            | J-55  | NU     | 1740 (2360)          | 1300 (1770) | 2170 (2950) |
| 4.500                       | (114,3) | 12.60                                            | C-75  | NU     | 2300 (3120)          | 1730 (2340) | 2880 (3900) |
| 4.500                       | (114,3) | 12.60                                            | L-80  | NU     | 2400 (3250)          | 1800 (2440) | 3000 (4060) |
| 4.500                       | (114,3) | 12.60                                            | N-80  | NU     | 2440 (3310)          | 1830 (2490) | 3060 (4140) |
| 4.500                       | (114,3) | 12.60                                            | C-90  | NU     | 2630 (3570)          | 1980 (2680) | 3290 (4460) |
| 4.500                       | (114,3) | 12.75                                            | H-40  | EUE    | 2160 (2930)          | 1620 (2190) | 2700 (3660) |
| 4.500                       | (114,3) | 12.75                                            | J-55  | EUE    | 2860 (3870)          | 2140 (2900) | 3570 (4840) |
| 4.500                       | (114,3) | 12.75                                            | C-75  | EUE    | 3780 (5130)          | 2840 (3850) | 4730 (6410) |
| 4.500                       | (114,3) | 12.75                                            | L-80  | EUE    | 3940 (5340)          | 2960 (4010) | 4930 (6680) |
| 4.500                       | (114,3) | 12.75                                            | N-80  | EUE    | 4020 (5450)          | 3010 (4080) | 5020 (6810) |
| 4.500                       | (114,3) | 12.75                                            | C-90  | EUE    | 4330 (5870)          | 3250 (4400) | 5410 (7340) |

# **Recommended Practice for Care and Use of Casing and Tubing**

API RECOMMENDED PRACTICE 5C1 (RP 5C1)  
SIXTEENTH EDITION, MAY 31, 1988

STANDARDSISO.COM : Click to view the full PDF of ISO 10405:1993

**American Petroleum Institute**  
1220 L Street, Northwest  
Washington, DC 20005



This page intentionally left blank

Issued by  
**AMERICAN PETROLEUM INSTITUTE**  
Production Department

FOR INFORMATION CONCERNING TECHNICAL CONTENTS OF  
THIS PUBLICATION CONTACT THE API PRODUCTION DEPARTMENT,  
211 N. ERVAY, SUITE 1700, DALLAS, TX 75201 — (214) 220-9111.  
SEE BACK SIDE FOR INFORMATION CONCERNING HOW TO OBTAIN  
ADDITIONAL COPIES OF THIS PUBLICATION.

Users of this publication should become familiar with its scope  
and content. This document is intended to supplement rather  
than replace individual engineering judgment.

Additional copies available from  
**AMERICAN PETROLEUM INSTITUTE**  
Publications and Distribution Section  
1220 L Street, NW  
Washington, DC 20005  
(202) 682-8375

OFFICIAL PUBLICATION



REG. U.S. PATENT OFFICE

Copyright © 1988 American Petroleum Institute

## TABLE OF CONTENTS

|                                                                  | Page |
|------------------------------------------------------------------|------|
| Policy .....                                                     | 3    |
| Foreword.....                                                    | 4    |
| Scope .....                                                      | 5    |
| Sect. 1: Running and Pulling Casing                              |      |
| Preparation and Inspection before Running.....                   | 6    |
| Stabbing, Making Up, and Lowering .....                          | 7    |
| Field Make-Up.....                                               | 7    |
| Casing Landing Procedure .....                                   | 8    |
| Care of Casing in Hole .....                                     | 8    |
| Causes of Casing Troubles .....                                  | 9    |
| Sect. 2: Running and Pulling Tubing                              |      |
| Preparation and Inspection before Running .....                  | 19   |
| Stabbing, Making Up, and Lowering .....                          | 20   |
| Field Make-Up .....                                              | 20   |
| Pulling Tubing .....                                             | 20   |
| Causes of Tubing Troubles .....                                  | 21   |
| Sect. 3: Transportation, Handling, and Storage                   |      |
| Transportation .....                                             | 25   |
| Handling .....                                                   | 25   |
| Storage .....                                                    | 25   |
| Sect. 4: Inspection and Classification of Used Casing and Tubing |      |
| Inspection and Classification Procedures.....                    | 25   |
| General .....                                                    | 26   |
| Service Rating .....                                             | 27   |
| Sect. 5: Reconditioning .....                                    | 27   |
| Sect. 6: Field Welding of Attachments on Casing                  |      |
| Introduction .....                                               | 27   |
| Requirements of Welds .....                                      | 27   |
| Process .....                                                    | 28   |
| Filler for Arc Welding .....                                     | 28   |
| Preparation of Base Metal .....                                  | 28   |
| Preheating and Cooling .....                                     | 28   |
| Welding Technique .....                                          | 28   |

## Note

This edition supersedes the 15th edition dated May 31, 1987. It includes recommendations and revisions adopted at the 1987 Standardization Conference.

This recommended practice was originally adopted in 1928 and issued in 1929. Revised editions were issued in 1938, 1948, 1949, 1951, 1956, 1957, 1963, 1971, 1973, 1980, 1981, 1984, 1986 and 1987.

*Requests for permission to reproduce or translate all or any part of the material published herein should be addressed to the Director, American Petroleum Institute, Production Department, 211 N. Ervay, Suite 1700, Dallas TX 75201.*

## POLICY

(a) API PUBLICATIONS NECESSARILY ADDRESS PROBLEMS OF A GENERAL NATURE. WITH RESPECT TO PARTICULAR CIRCUMSTANCES, LOCAL, STATE AND FEDERAL LAWS AND REGULATIONS SHOULD BE REVIEWED.

(b) API IS NOT UNDERTAKING TO MEET DUTIES OF EMPLOYERS, MANUFACTURERS OR SUPPLIERS TO WARN AND PROPERLY TRAIN AND EQUIP THEIR EMPLOYEES, AND OTHERS EXPOSED, CONCERNING HEALTH AND SAFETY RISKS AND PRECAUTIONS, NOR UNDERTAKING THEIR OBLIGATIONS UNDER LOCAL, STATE, OR FEDERAL LAWS.

(c) NOTHING CONTAINED IN ANY API PUBLICATION IS TO BE CONSTRUED AS GRANTING ANY RIGHT, BY IMPLICATION OR OTHERWISE, FOR THE MANUFACTURE, SALE, OR USE OF ANY METHOD, APPARATUS, OR PRODUCT COVERED BY LETTERS PATENT. NEITHER

SHOULD ANYTHING CONTAINED IN THE PUBLICATION BE CONSTRUED AS INSURING ANYONE AGAINST LIABILITY FOR INFRINGEMENT OF LETTERS PATENT.

(d) GENERALLY, API STANDARDS ARE REVIEWED AND REVISED, REAFFIRMED, OR WITHDRAWN AT LEAST EVERY FIVE YEARS. SOMETIMES A ONE-TIME EXTENSION OF UP TO TWO YEARS WILL BE ADDED TO THIS REVIEW CYCLE. THIS PUBLICATION WILL NO LONGER BE IN EFFECT FIVE YEARS AFTER ITS PUBLICATION DATE AS AN OPERATIVE API STANDARD OR, WHERE AN EXTENSION HAS BEEN GRANTED, UPON REPUBLICATION. STATUS OF THE PUBLICATION CAN BE ASCERTAINED FROM THE API PRODUCTION DEPARTMENT (TEL. 214-220-9111). A CATALOG OF API PUBLICATIONS AND MATERIALS IS PUBLISHED ANNUALLY AND UPDATED QUARTERLY BY API, 1220 L ST., N.W., WASHINGTON, D.C. 20005.

STANDARDSISO.COM : Click to view the full PDF of ISO 10405:1993



## FOREWORD

(a) American Petroleum Institute (API) Recommended Practices are published to facilitate the broad availability of proven, sound engineering and operating practices. These Recommended Practices are not intended to obviate the need for applying sound judgment as to when and where these Recommended Practices should be utilized.

(b) The formulation and publication of API Recommended Practices is not intended to, in any way, inhibit anyone from using any other practices.

(c) Any Recommended Practice may be used by anyone desiring to do so, and a diligent effort has been made by API to assure the accuracy and reliability of the data contained herein. However, the Institute makes no representation, warranty, or guarantee in connection with the publication of any Recommended Practice and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use, for any violation of any federal, state, or municipal regulation with which an API recommendation may conflict, or for the infringement of any patent resulting from the use of this publication.

**Attention Users:** Portions of this publication have been changed from the previous edition. The locations of changes have been marked with a bar in the margin, as shown to the left of this paragraph. In some cases the changes are significant, while in other cases the changes reflect minor editorial adjustments. The bar notations in the margins are provided as an aid to users as to those parts of this publication that have been changed from the previous edition, but API makes no warranty as to the accuracy of such bar notations.

## SCOPE

a. This recommended practice is under the jurisdiction of the API Committee on Standardization of Tubular Goods.

1. *Shall* is used to indicate that a provision is mandatory.
2. *Should* is used to indicate that a provision is not mandatory, but recommended as good practice.
3. *May* is used to indicate that a provision is optional.

NOTE: No provision of this recommended practice shall be cause for rejection of casing or tubing provided the threads are in accordance with the requirements of the latest edition of API Std 5B.

b. The statements on corrosion of casing and tubing as given herein, were developed with the cooperation of the Technical Practices Committee on Corrosion of Oil and Gas Well Equipment, National Association of Corrosion Engineers.

c. It is suggested that the selection of a thread compound for casing and tubing be given careful consideration by the user, bearing in mind that a satisfactory compound should possess certain properties, the major of which are (1) to lubricate the thread surfaces to facilitate joint make-up and break-out without galling, and (2) to seal voids between the mating thread surfaces and effectively prevent leakage. Compounds which have given outstanding service for casing and tubing under both laboratory and field conditions are described in the latest edition of API Bul 5A2: *Bulletin on Thread Compounds*.

NOTE: Thread Compounds described in the latest edition of Bul 5A2 should not be used on rotary shouldered connections.

d. Some generalized suggestions on prevention of damage to casing and tubing by corrosive fluids are given herein (Par. 1.30-p and 2.34-o). It is not, however, within the scope of this bulletin to provide detailed suggestions for corrosion control under specific conditions. Many variables may be involved in a specific corrosion problem and inter-related in such a complex fashion as to require detailed attention to the specific problem. For more complete technical information on specific corrosion problems, the user should consult the official publication of the National Association of Corrosion Engineers, CORROSION, or contact: Chairman, Technical Practices Committee on Corrosion of Oil and Gas Well Equipment, T-1. NACE, 2400 West Loop South, Houston, Texas 77027.

e. This recommended practice may be used by anyone desiring to do so, and every effort has been made by the Institute to assure the accuracy and reliability of the

data obtained. However, the Institute makes no representation, warranty, or guarantee in connection with the publication of any API recommended practice and hereby expressly disclaims any liability or responsibility for loss or damage resulting from their use, for any violation of any federal, state, or municipal regulation with which an API recommended practice may conflict, or for the infringement of any patent resulting from the use of an API recommended practice.

## f. Referenced Standards

1. **General.** This specification includes by reference, either in total or in part, other API, industry and government standards listed in Table A.
2. **Requirements.** Requirements of other standards included by reference in this specification are essential to the safety and interchangeability of the equipment produced.
3. **Equivalent Standards.** Other nationally or internationally recognized standards shall be submitted to and approved by API for inclusion in this specification prior to their use as equivalent standards.

TABLE A  
REFERENCED STANDARDS

|                  |                                                                                                           |                |
|------------------|-----------------------------------------------------------------------------------------------------------|----------------|
| 1. API Spec 5CT: | <i>Specification for Casing and Tubing</i>                                                                | Latest Edition |
| 2. API Bul 5A2:  | <i>Bulletin on Thread Compounds</i>                                                                       | Latest Edition |
| 3. API Bul 5C2:  | <i>Bulletin on Performance Properties of Casing and Tubing</i>                                            | Latest Edition |
| 4. API Std 5B:   | <i>Specification for Threading, Gaging, and Thread Inspection of Casing, Tubing and Line Pipe Threads</i> | Latest Edition |
| 5. API Bul 5C3:  | <i>Bulletin on Formulas and Calculations for Casing, Tubing Drill Pipe and Line Pipe Properties</i>       | Latest Edition |
| 6. API RP7G:     | <i>Recommended Practice for Drill Stem Design and Operating Limits</i>                                    | Latest Edition |
| 7. ASTM A233:    | <i>Mild Steel Arc-Welding Electrodes</i>                                                                  | Latest Edition |
| 8. ASTM A316:    | <i>High Tensile and Low Alloy Steel Covered Arc-Welding Electrodes</i>                                    | Latest Edition |

## SECTION 1

### RUNNING AND PULLING CASING

#### Preparation and Inspection before Running

1.1 New casing is delivered free of injurious defects as defined in API Spec 5CT and within the practical limits of the inspection procedures therein prescribed. Some Users have found that, for a limited number of critical well applications, these procedures do not result in casing sufficiently free of defects to meet their needs for such critical applications. Various nondestructive inspection services have been employed by Users to assure that the desired quality of casing is being run. In view of this practice, it is suggested that the individual user:

- a. Familiarize himself with inspection practices specified in the standards and employed by the respective mills, and with the definition of "injurious defect" contained in the standards.
- b. Thoroughly evaluate any nondestructive inspection to be used by him on API tubular goods to assure himself that the inspection does in fact correctly locate and differentiate injurious defects from other variables which can be and frequently are sources of misleading "defect" signals with such inspection methods.

1.2 All casing, whether new, used, or reconditioned, should always be handled with thread protectors in place. Casing should be handled at all times on racks or on wooden or metal surfaces free of rocks, sand, or dirt other than normal drilling mud. When lengths of casing are inadvertently dragged in the dirt, the threads should be recleaned and serviced again as outlined in Par. 1.7.

1.3 Slip elevators are recommended for long strings. Both spider and elevator slips should be clean and sharp and should fit properly. Slips should be extra long for heavy casing strings. The spider must be level.

*NOTE: Slip and tong marks are injurious. Every possible effort should be made to keep such damage at a minimum by using proper up-to-date equipment.*

1.4 If collar-pull elevators are used, the bearing surface should be carefully inspected for (1) uneven wear which may produce a side lift on the coupling with danger of jumping it off, and (2) uniform distribution of the load when applied over the bearing face of the coupling.

1.5 Spider and elevator slips should be examined and watched to see that all lower together. If they lower unevenly, there is danger of denting the pipe or badly slip-cutting it.

1.6 Care shall be exercised, particularly when running long casing strings, to insure that the slip bushing or bowl is in good condition. Tongs should be examined for wear on hinge-pins and hinge-surfaces. The back-up line attachment to the back-up post should be corrected if necessary to be level with the tong in the back-up position, so as to avoid uneven load distribution on the gripping surfaces of the casing. The length of the back-up line should be such as to cause minimum bending stresses on the casing and to allow full stroke movement of the make-up tong.

1.7 The following precautions should be taken in the preparation of casing threads for make up in the casing strings:

- a. Immediately before running, remove thread protectors from both field and coupling ends and clean the threads thoroughly, repeating as additional rows become uncovered.

b. Carefully inspect the threads. Those found damaged, even slightly, should be laid aside unless satisfactory means are available for correcting thread damage.

c. The length of each piece of casing shall be measured prior to running. A steel tape calibrated in decimal feet to the nearest 0.01 ft should be used. The measurement should be made from the outermost face of the coupling or box to the position on the externally threaded end where the coupling or the box stops when the joint is made up power-tight. On round-thread joints, this position is to the plane of the vanish point on the pipe; on buttress-thread casing, this position is to the base of the triangle stamp on the pipe; and, on extreme line casing, to the shoulder on the externally threaded end. The total of the individual lengths so measured will represent the unloaded length of the casing string. The actual length under tension in the hole can be obtained by consulting graphs which are prepared for this purpose and which are available in most pipe handbooks.

d. Check each coupling for make-up. If the stand-off is abnormally great, check the coupling for tightness. Tighten any loose couplings after thoroughly cleaning the threads and applying fresh compound over entire thread surfaces, and before pulling the pipe into the derrick.

e. Before stabbing, liberally apply thread compound to the entire internally and externally threaded areas. It is recommended that high pressure modified thread compound as specified in the latest edition of API Bul 5A2: *Bulletin on Thread Compounds* be used, except in special cases where severe conditions are encountered, it is recommended that high pressure silicone thread compound as specified in the latest edition of Bul 5A2 be used.

f. Place a clean thread protector on the field end of the pipe so that the thread will not be damaged while rolling pipe on the rack and pulling into the derrick. Several thread protectors may be cleaned and used repeatedly for this operation.

g. If a mixed string is to be run, check to determine that appropriate casing will be accessible on the pipe rack when required according to program.

h. Connectors used as tensile and lifting members should have their thread capacity carefully checked to assure that the connector can safely support the load.

i. Care should be taken when making up pup joints and connectors to assure that the mating threads are of the same size and type.

1.8 **Drifting of Casing.** It is recommended that each length of casing be drifted for its entire length just before running, with mandrels conforming to Par. 5.20b of the latest edition of Spec 5CT. Casing which will not pass the drift test should be laid aside.

1.9 Lower or roll each piece of casing carefully to the walk without dropping. Use rope snubber if necessary. Avoid hitting casing against any part of derrick or other equipment. Provide a hold-back rope at window. For mixed or unmarked strings, a drift or "jack rabbit" should be run through each length of

casing when it is picked up from the catwalk and pulled onto the derrick floor, to avoid running a heavier length or one with a lesser inside diameter than called for in the casing string.

#### Stabbing, Making Up, and Lowering

1.10 Do not remove thread protector from field end of casing until ready to stab.

1.11 If necessary, apply thread compound over entire surface of threads just before stabbing. The brush or utensil used in applying thread compound should be kept free of foreign matter and the compound should never be thinned.

1.12 In stabbing, lower casing carefully to avoid injuring threads. Stab vertically, preferably with assistance of a man on the stabbing board. If the casing stand tilts to one side after stabbing, lift up, clean, and correct any damaged thread with three-cornered file, then carefully remove any filings and reapply compound over the thread surface. After stabbing, the casing should be rotated very slowly at first to insure that threads are engaging properly and not cross-threading. If spinning line is used, it should pull close to the coupling.

NOTE: Recommendations in Par. 1.13 and 1.14 for casing makeup apply to the use of power tongs. For recommendations on makeup of casing with spinning lines and conventional tongs, see Par. 1.15.

1.13 The use of power tongs for making up casing made desirable the establishment of recommended torque values for each size, weight, and grade of casing. Early studies and tests indicated that torque values are affected by a large number of variables, such as variations in taper, lead, thread height and thread form, surface finish, type of thread compound, length of thread, weight and grade of pipe, etc. In view of the number of variables and the extent that these variables, alone or in combination, could affect the relationship of torque values versus made-up position, it was evident that both applied torque and made-up position must be considered. Since the API joint pullout strength formula in the latest edition of API Bul 5C2: *Bulletin on Performance Properties of Casing and Tubing*, contains several of the variables believed to affect torque, the use of a modification of this formula to establish torque values was investigated. Torque values obtained by taking 1% of the calculated pull-out value were found to be generally comparable to values obtained by field make-up tests using API modified thread compound in accordance with the latest edition of API Bul 5A2. This procedure was therefore used to establish the optimum make up torque values listed in Table 1.1. Minimum torque values listed are 75% of optimum values and maximum values listed are 125% of optimum values. All values are rounded to the nearest 10 foot pounds. These values shall be considered a guide only, due to the very wide variations in torque requirements that can exist for a specific connection. Because of this, it is essential that torque be related to made-up position as outlined in Par. 1.14, following. The torque values listed in Table 1.1 apply to casing with zinc plated or phosphate coated couplings. When making up connections with tin plated couplings, 80% of the listed value can be used as a guide. The listed torque values are not applicable for making up couplings with PTFE (Polytetrafluoroethylene)\* rings. When making up round thread connections with PTFE (Polytetrafluoroethylene) rings, 70% of the listed values are recommended. Buttress connections with PTFE (Polytetrafluoroethylene) seal rings may make up at torque values different from those normally observed on standard buttress threads.

\*Teflon™ or equivalent.

NOTE: Thread galling of gall-prone materials (martensitic chromium steels—9Cr and 13Cr) occurs during movement — stabbing or pulling and make-up or break-out. Galling resistance of threads is primarily controlled in two areas — surface preparation and finishing during manufacture and careful handling practices during running and pulling. Threads and lubricant must be clean. Assembly in the horizontal position should be avoided. Connections should be turned by hand to the hand-tight position before slowly power tightening. The procedure should be reversed for disassembly.

#### Field Make-Up

1.14 The following practice is recommended for field make-up of casing.

#### Round Thread, 4½ through 13¾ in. OD

- a. It is advisable when starting to run casing from each particular mill shipment to make up sufficient joints to determine the torque necessary to provide proper make-up. See Par. 1.15 for proper number of turns beyond hand-tight position. These values may indicate that a departure from the recommended optimum values listed in Table 1.1 is advisable. If other optimum values are chosen, the minimum torque should be not less than 75 percent of the optimum selected. The maximum torque should be not more than 125 percent of the optimum torque.
- b. The power tong should be provided with a reliable torque gage of known accuracy. In the initial stages of make-up, any irregularities of make-up or in speed of make-up should be observed, since these may be indicative of crossed threads, dirty or damaged threads, or other unfavorable conditions. To prevent galling when making up connections in the field, the connections should be made up at a speed not to exceed 25 rpm.
- c. Continue the make-up, observing both the torque gage and the approximate position of the coupling face with respect to the thread vanish point position.
- d. The optimum torque values shown in the following tabulation have been selected to give optimum make-up under normal conditions and should be considered as satisfactory providing the face of the coupling is flush with the thread vanish point or within two thread turns plus or minus of the thread vanish point.
- e. If the make-up is such that the thread vanish point is buried two thread turns and the minimum torque shown in Table 1.1 is not reached, the joint should be treated as a questionable joint as provided under Par. 1.16.
- f. If several threads remain exposed when the optimum torque is reached, apply additional torque up to the maximum shown in Table 1.1. If the stand-off (distance from face of coupling to the thread vanish point) is greater than three thread turns when the maximum torque is reached, the joint should be treated as a questionable joint as provided under Par. 1.16.

#### Buttress Thread, 4½ through 13¾ in. OD

- g. Make-up torque values for buttress thread casing connections is sizes 4½ through 13¾ in. OD should be determined by carefully noting the torque required to make up each of several connections to the base of the triangle, then using the torque value thus established, make up the balance of the pipe of that particular weight and grade in the string.



**Round Thread and Buttress Thread, 16, 18% and 20 in. OD**

- h. Make-up of 16, 18% and 20 in. OD shall be to a position on each connection represented by the thread vanish point on 8-round thread and the base of the triangle on buttress thread using the minimum torque shown in Table 1.1 as a guide.

On 8-round thread casing a  $\frac{3}{8}$  in. equilateral triangle is die stamped at a distance of  $L_1 + \frac{1}{2}L_2$  in. from each end. The base of the triangle will aid in locating the thread vanish point for basic power tight make-up; however, the position of the coupling with respect to the base of the triangle shall not be a basis for acceptance or rejection of the product.

Care shall be taken to avoid cross-threading in starting these larger connections. The tongs selected should be capable of attaining high torques (50,000 ft-lbs) for the entire run. Anticipate that maximum torque values could be five times the minimum experienced in make-up to the recommended position.

- i. Joints that are questionable as to their proper make-up in Paragraph e or f should be unscrewed and laid down to determine the cause of improper make-up. Both the pipe thread and mating coupling thread should be inspected. Damaged threads, or threads which do not comply with the specification should be repaired. If damaged or threads out-of-tolerance are not found to be the cause of improper make-up, then the make-up torque should be adjusted to obtain proper make-up (see Paragraph a). It should be noted that a thread compound with a coefficient of friction substantially different from common values may be the cause of improper make-up.

1.15 When conventional tongs are used for casing make-up, tighten with tongs to proper degree of tightness. The joint should be made up beyond the hand-tight position at least 3 turns for sizes 4½ through 7 ins., and at least 3½ turns for sizes 7½ in. and larger, except 9½ in. and 10½ in. grade P-110 and 20 in. grade J-55 and K-55 which should be made up 4 turns beyond hand-tight position. When using a spinning line it is necessary to compare handtightness with spin-up tightness. In order to do this, make up the first few joints to the handtight position, then back off and spin up joints to the spin-up tight position. Compare relative position of these two make-ups and use this information to determine when the joint is made up the recommended number of turns beyond handtight.

1.16 Joints that are questionable as to their proper tightness should be unscrewed and the casing laid down for inspection and repair. When this is done, the mating coupling should be carefully inspected for damaged threads. Parted joints should never be re-used without shopping or regaging, even though the joints may have little appearance of damage.

1.17 If casing has a tendency to wobble unduly at its upper end when making up, indicating that the thread may not be in line with the axis of the casing, the speed of rotation should be decreased to prevent galling of threads. If wobbling should persist despite reduced rotational speed, the casing should be laid down for inspection. Serious consideration should be given before using such casing in a position in the string where a heavy tensile load is imposed.

1.18 In making up the field joint it is possible for the coupling to make up slightly on the mill end. This does not indicate that the coupling on the mill end is too loose, but simply that the field end has reached the tightness with which the coupling was screwed on at the Manufacturer's Facility.

1.19 Casing strings should be picked up and lowered carefully, and care exercised in setting slips to avoid shock loads. Dropping a string even a short distance may loosen couplings at the bottom of the string. Care should be exercised to prevent setting casing down on bottom, or otherwise placing it in compression because of the danger of buckling, particularly in that part of the well where hole enlargement has occurred.

1.20 Definite instructions should be available as to the design of the casing string, including the proper location of the various grades of steel, weights of casing, and types of joint. Care should be exercised to run the string in exactly the order in which it was designed. If any length cannot be clearly identified, it should be laid aside until its grade, weight, or type of joint can be positively established.

1.21 To facilitate running and to assure adequate hydrostatic head to contain reservoir pressures, the casing should be periodically filled with mud while being run. A number of things govern the frequency with which filling should be accomplished: weight of pipe in the hole, mud weight, reservoir pressure, etc. In most cases, filling every 6-10 lengths should suffice. In no case should the hydrostatic balance of reservoir pressure be jeopardized by too infrequent filling. Filling should be done with mud of the proper weight, using a conveniently located hose of adequate size to expedite the filling operation. A quick opening and closing plug valve on the mud hose will facilitate the operation and prevent overflow. If rubber hose is used, it is recommended that the quick-closing valve be mounted where the hose is connected to the mud line, rather than at the outlet end of the hose. It is also recommended that at least one other discharge connection be left open on the mud system to prevent build-up of excessive pressure when the quick-closing valve is closed while the pump is still running. A copper nipple at the end of the mud hose may be used to prevent damaging of the coupling threads during the filling operation.

NOTE: The foregoing mud fill-up practice will be unnecessary, if automatic fill-up casing shoes and collars are used.

**Casing Landing Procedure**

1.22 Definite instructions should be provided for the proper string tension, also on the proper landing procedure after the cement has set. The purpose is to avoid critical stresses or excessive and unsafe tensile stresses at any time during the life of the well. In arriving at the proper tension and landing procedure, consideration should be given to all factors such as well temperature and pressure, temperature developed due to cement hydration, mud temperature, and changes of temperature during producing operations. The adequacy of the original tension safety factor of the string as designed will influence the landing procedure and should be considered. If, however, after due consideration it is not considered necessary to develop special landing procedure instructions (and this probably applies to a very large majority of the wells drilled), then the procedure should be followed of landing the casing in the casing head at exactly the position in which it was hanging when the cement plug reached its lowest point or "as cemented."

**Care of Casing in Hole**

1.23 Drill pipe run inside casing should be equipped with suitable drill-pipe protectors.

**Recovery of Casing**

1.24 Break-out tongs should be positioned close to the coupling but not too close since a slight squashing effect where the tong dies contact the pipe surface cannot be avoided especially if the joint is

tight and/or the casing is light. Keeping a space of  $\frac{1}{8}$  to  $\frac{1}{4}$  of the diameter of the pipe between the tong and the coupling should normally prevent unnecessary friction in the threads. Hammering the coupling to break the joint is an injurious practice. If tapping is required, use the flat face, never the peen face of the hammer, and under no circumstances should a sledge hammer be used. Tap lightly near the middle and completely around the coupling, never near the end nor on opposite sides only.

1.25 Great care should be exercised to disengage all of the thread before lifting the casing out of the coupling. Do not jump casing out of coupling.

1.26 All threads should be cleaned and lubricated or should be coated with a material that will minimize corrosion. Clean protectors should be placed on the tubing before it is laid down.

1.27 Before casing is stored or re-used, pipe and thread should be inspected and defective joints marked for shopping and regaging.

1.28 When casing is being retrieved because of a casing failure, it is imperative to future prevention of such failures that a thorough metallurgical study be made. Every attempt should be made to retrieve the failed portion in the "as-failed" condition. When thorough metallurgical analysis reveals some facet of pipe quality to be involved in the failure, the results of the study should be reported to the API office in Dallas, Texas.

1.29 Casing stacked in the derrick should be set on a firm wooden platform and without the bottom thread protector since the design of most protectors is not such as to support the joint or stand without damage to the field thread.

#### Causes of Casing Troubles

1.30 The more common causes of casing troubles are as follows:

- a. Improper selection for depth and pressures encountered.
- b. Insufficient inspection of each length of casing or of field-shop threads.
- c. Abuse in mill, transportation, and field handling.
- d. Non-observance of good rules in running and pulling casing.
- e. Improper cutting of field-shop threads.
- f. The use of poorly manufactured couplings for replacements and additions.
- g. Improper care in storage.
- h. Excessive torquing of casing to force it through tight places in the hole.
- i. Pulling too hard on a string (to free it). This may loosen the couplings at the top of the string. They should be retightened with tongs before finally setting the string.
- j. Rotary drilling inside casing. Setting the casing with improper tension after cementing is one of the greatest contributing causes of such failures.
- k. Drill pipe wear while drilling inside casing is particularly significant in drifted holes. Excess dog legs in deviated holes or occasionally in straight holes where corrective measures are taken, result in concentrated bending of the casing which in turn results in excess internal wear, particularly when the dog legs are high in the hole.
- l. Wire-line cutting, by swabbing or cable-tool drilling.
- m. Buckling of casing in an enlarged, washed-out uncemented cavity if too much tension is released in landing.
- n. Dropping a string, even a very short distance.

o. Leaky joints, under external or internal pressure, are a common trouble, and may be due to:

1. Improper thread compound.
2. Undertonging.
3. Dirty threads.
4. Galled threads, due to dirt, careless stabbing, damaged threads, too rapid spinning, overtonging, or wobbling during spinning or tonging operations.
5. Improper cutting of field-shop threads.
6. Pulling too hard on string.
7. Dropping string.
8. Excessive making and breaking.
9. Tonging too high on casing, especially on breaking out. This gives a bending effect which tends to gall the threads.
10. Improper joint make-up at mill.
11. Casing ovality or out-of-roundness.
12. Improper landing practice which produces stresses in the threaded joint in excess of the yield point.

p. Corrosion. Both the inside and outside of casing can be damaged by corrosion which can be recognized by the presence of pits or holes in the pipe. Corrosion on the outside of casing can be caused by corrosive fluids or formations in contact with the casing, or by stray electric currents flowing out of the casing into the surrounding fluids or formations. Severe corrosion may also be caused by sulphate reducing bacteria. Corrosion damage on the inside is usually caused by corrosive fluids produced from the well, but the damage can be increased by the abrasive effects of casing and tubing pumping equipment, and by high fluid velocities such as those encountered in some gas-lifted wells. Internal corrosion might also be due to stray electrical currents (electrolysis) or to dissimilar metals in close contact (bimetallic galvanic corrosion). Because corrosion may result from so many different conditions, no simple or universal remedy can be given for its control. Each corrosion problem must be treated as an individual case and a solution attempted in the light of the known corrosion factors and operating conditions. The condition of the casing can be determined by visual or optical-instrument inspections. Where these are not practical, a casing-caliper survey can be made to determine the condition of the inside surfaces. No tools have yet been designed for determining the condition of the outside of casing in a well. Internal casing-caliper surveys indicate the extent, location, and severity of corrosion. On the basis of the industry's experience to date, the following practices and measures can be used to control corrosion of casing.

1. Where external casing corrosion is known to occur or stray electrical current surveys indicate that relatively high currents are entering the well, the following practices can be employed.
  - a. Good cementing practices, including the use of centralizers, scratchers, and adequate amounts of cement to keep corrosive fluids from contact with the outside of the casing.
  - b. Electrical insulation of flow lines from wells by the use of nonconducting flange assemblies to reduce or prevent electrical currents from entering the well.
  - c. The use of highly alkaline mud or mud treated with a bactericide as a comple-

- tion fluid will help alleviate corrosion caused by sulfate-reducing bacteria.
- d. A properly designed cathodic protection system similar to that used for line pipe can alleviate external casing corrosion. Protection criteria for casing differs somewhat from the criteria used for line pipe. Literature on external casing corrosion or persons competent in this field should be consulted for proper protection criteria.
2. Where internal corrosion is known to exist, the following practices can be employed.
    - a. In flowing wells, packing the annulus with fresh water or low-salinity alkaline muds. (It may be preferable in some flowing wells to depend upon inhibitors to protect the inside of the casing and the tubing.)
    - b. In pumping wells, avoiding the use of casing pumps. Ordinarily, pumping wells should be tubed as close to bottom as practical, regardless of the position of the pump, to minimize the damage to the casing from corrosive fluids.
    - c. Using inhibitors to protect the inside of the casing against corrosion.
  3. To determine the value and effectiveness of the above practices and measures, cost and equipment-failure records can be compared before and after application of control measures. Inhibitor effectiveness may be checked also by means of caliper surveys, visual examinations of readily accessible pieces of equipment, and by water analyses for iron content. Coupons may also be helpful in determining whether sufficient inhibitor is being used. When lacking previous experience with any of the above measures, they should be used cautiously and on a limited scale until appraised for the particular operating conditions.
  4. In general, all new areas should be considered as being potentially corrosive and investigations should be initiated early in the life of a field, and repeated periodically, to detect and localize corrosion before it has done destructive damage. These investigations should cover: (a) a complete chemical analysis of the effluent water, including pH, iron, hydrogen sulfide, organic acids, and any other substances which influence or indicate the degree of corrosion. An analysis of the produced gas for carbon dioxide and hydrogen sulfide is also desirable; (b) corrosion rate tests by using coupons of the same materials as in the well; and (c) the use of caliper or optical-instrument inspections. Where conditions favorable to corrosion exist, a qualified corrosion engineer should be consulted. Particular attention should be given to mitigation of corrosion where the probable life of subsurface equipment is less than the time expected to deplete a well.
  5. When  $H_2S$  is present in the well fluids, casing of high yield strength may be subject to sulfide corrosion cracking. The concentration of  $H_2S$  necessary to cause cracking in different strength materials is not yet well defined. Literature on sulfide corrosion or persons competent in this field should be consulted.

STANDARDSISO.COM : Click to view the full text of the standard



**TABLE 1.1**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                                   | 2                                                               | 3     | 4             | 5       | 6       | 7           | 8       | 9       |
|-------------------------------------|-----------------------------------------------------------------|-------|---------------|---------|---------|-------------|---------|---------|
| Size:<br>Outside<br>Diameter<br>in. | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lb. per ft. | Grade | Torque, ft-lb |         |         |             |         |         |
|                                     |                                                                 |       | Short Thread  |         |         | Long Thread |         |         |
|                                     |                                                                 |       | Optimum       | Minimum | Maximum | Optimum     | Minimum | Maximum |
| 4½                                  | 9.50                                                            | H-40  | 770           | 580     | 960     | —           | —       | —       |
|                                     | 9.50                                                            | J-55  | 1010          | 760     | 1260    | —           | —       | —       |
|                                     | 10.50                                                           | J-55  | 1320          | 990     | 1650    | —           | —       | —       |
|                                     | 11.60                                                           | J-55  | 1540          | 1160    | 1930    | 1620        | 1220    | 2030    |
|                                     | 9.50                                                            | K-55  | 1120          | 840     | 1400    | —           | —       | —       |
|                                     | 10.50                                                           | K-55  | 1460          | 1100    | 1830    | —           | —       | —       |
|                                     | 11.60                                                           | K-55  | 1700          | 1280    | 2130    | 1800        | 1350    | 2250    |
|                                     | 11.60                                                           | C-75  | —             | —       | —       | 2150        | 1610    | 2690    |
|                                     | 13.50                                                           | C-75  | —             | —       | —       | 2600        | 1950    | 3250    |
|                                     | 11.60                                                           | L-80  | —             | —       | —       | 2230        | 1670    | 2790    |
|                                     | 13.50                                                           | L-80  | —             | —       | —       | 2710        | 2030    | 3390    |
|                                     | 11.60                                                           | N-80  | —             | —       | —       | 2280        | 1710    | 2850    |
|                                     | 13.50                                                           | N-80  | —             | —       | —       | 2760        | 2070    | 3450    |
|                                     | 11.60                                                           | C-90  | —             | —       | —       | 2450        | 1840    | 3060    |
|                                     | 13.50                                                           | C-90  | —             | —       | —       | 2970        | 2230    | 3710    |
|                                     | 11.60                                                           | C-95  | —             | —       | —       | 2580        | 1940    | 3230    |
|                                     | 13.50                                                           | C-95  | —             | —       | —       | 3130        | 2350    | 3910    |
|                                     | 11.60                                                           | P-110 | —             | —       | —       | 3020        | 2270    | 3780    |
|                                     | 13.50                                                           | P-110 | —             | —       | —       | 3660        | 2750    | 4580    |
|                                     | 15.10                                                           | P-110 | —             | —       | —       | 4400        | 3300    | 5500    |
|                                     | 15.10                                                           | Q125  | —             | —       | —       | 4910        | 3680    | 6140    |
| 5                                   | 11.50                                                           | J-55  | 1330          | 1000    | 1660    | —           | —       | —       |
|                                     | 13.00                                                           | J-55  | 1690          | 1270    | 2110    | 1820        | 1370    | 2280    |
|                                     | 15.00                                                           | J-55  | 2070          | 1550    | 2590    | 2230        | 1670    | 2790    |
|                                     | 11.50                                                           | K-55  | 1470          | 1100    | 1840    | —           | —       | —       |
|                                     | 13.00                                                           | K-55  | 1860          | 1400    | 2330    | 2010        | 1510    | 2510    |
|                                     | 15.00                                                           | K-55  | 2280          | 1710    | 2850    | 2460        | 1850    | 3080    |
|                                     | 15.00                                                           | C-75  | —             | —       | —       | 2960        | 2220    | 3700    |
|                                     | 18.00                                                           | C-75  | —             | —       | —       | 3770        | 2830    | 4710    |
|                                     | 21.40                                                           | C-75  | —             | —       | —       | 4660        | 3500    | 5830    |
|                                     | 24.10                                                           | C-75  | —             | —       | —       | 5390        | 4040    | 6740    |
|                                     | 15.00                                                           | L-80  | —             | —       | —       | 3080        | 2310    | 3850    |
|                                     | 18.00                                                           | L-80  | —             | —       | —       | 3950        | 2950    | 4910    |
|                                     | 21.40                                                           | L-80  | —             | —       | —       | 4860        | 3650    | 6080    |
|                                     | 24.10                                                           | L-80  | —             | —       | —       | 5610        | 4210    | 7010    |
|                                     | 15.00                                                           | N-80  | —             | —       | —       | 3140        | 2360    | 3930    |
|                                     | 18.00                                                           | N-80  | —             | —       | —       | 4000        | 3000    | 5000    |
|                                     | 21.40                                                           | N-80  | —             | —       | —       | 4950        | 3710    | 6190    |
|                                     | 24.10                                                           | N-80  | —             | —       | —       | 5720        | 4290    | 7150    |
|                                     | 15.00                                                           | C-90  | —             | —       | —       | 3380        | 2540    | 4230    |
|                                     | 18.00                                                           | C-90  | —             | —       | —       | 4310        | 3240    | 5390    |
|                                     | 21.40                                                           | C-90  | —             | —       | —       | 5340        | 4000    | 6670    |
|                                     | 23.20                                                           | C-90  | —             | —       | —       | 5880        | 4410    | 7350    |
|                                     | 24.10                                                           | C-90  | —             | —       | —       | 6170        | 4630    | 7710    |
|                                     | 15.00                                                           | C-95  | —             | —       | —       | 3560        | 2670    | 4450    |
|                                     | 18.00                                                           | C-95  | —             | —       | —       | 4550        | 3410    | 5690    |
|                                     | 21.40                                                           | C-95  | —             | —       | —       | 5620        | 4220    | 7030    |
|                                     | 24.10                                                           | C-95  | —             | —       | —       | 6500        | 4880    | 8130    |

**TABLE 1.1 (cont.)**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                                   | 2                                                               | 3     | 4             | 5       | 6       | 7           | 8       | 9       |
|-------------------------------------|-----------------------------------------------------------------|-------|---------------|---------|---------|-------------|---------|---------|
| Size:<br>Outside<br>Diameter<br>in. | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lb. per ft. | Grade | Torque, ft-lb |         |         |             |         |         |
|                                     |                                                                 |       | Short Thread  |         |         | Long Thread |         |         |
|                                     |                                                                 |       | Optimum       | Minimum | Maximum | Optimum     | Minimum | Maximum |
|                                     | 15.00                                                           | P-110 | —             | —       | —       | 4170        | 3130    | 5210    |
|                                     | 18.00                                                           | P-110 | —             | —       | —       | 5310        | 3980    | 6640    |
|                                     | 21.40                                                           | P-110 | —             | —       | —       | 6580        | 4940    | 8230    |
|                                     | 24.10                                                           | P-110 | —             | —       | —       | 7600        | 5700    | 9500    |
|                                     | 18.00                                                           | Q125  | —             | —       | —       | 5930        | 4450    | 7410    |
|                                     | 21.40                                                           | Q125  | —             | —       | —       | 7340        | 5510    | 9180    |
|                                     | 23.20                                                           | Q125  | —             | —       | —       | 8090        | 6070    | 10110   |
|                                     | 24.10                                                           | Q125  | —             | —       | —       | 8490        | 6370    | 10610   |
| 5½                                  | 14.00                                                           | H-40  | 1300          | 980     | 1630    | —           | —       | —       |
|                                     | 14.00                                                           | J-55  | 1720          | 1290    | 2150    | —           | —       | —       |
|                                     | 15.50                                                           | J-55  | 2020          | 1520    | 2530    | 2170        | 1630    | 2710    |
|                                     | 17.00                                                           | J-55  | 2290          | 1720    | 2860    | 2470        | 1850    | 3090    |
|                                     | 14.00                                                           | K-55  | 1890          | 1420    | 2360    | —           | —       | —       |
|                                     | 15.50                                                           | K-55  | 2220          | 1670    | 2780    | 2390        | 1790    | 2990    |
|                                     | 17.00                                                           | K-55  | 2520          | 1890    | 3150    | 2720        | 2040    | 3400    |
|                                     | 17.00                                                           | C-75  | —             | —       | —       | 3270        | 2450    | 4090    |
|                                     | 20.00                                                           | C-75  | —             | —       | —       | 4030        | 3020    | 5040    |
|                                     | 23.00                                                           | C-75  | —             | —       | —       | 4730        | 3550    | 5910    |
|                                     | 17.00                                                           | L-80  | —             | —       | —       | 3410        | 2560    | 4260    |
|                                     | 20.00                                                           | L-80  | —             | —       | —       | 4200        | 3150    | 5250    |
|                                     | 23.00                                                           | L-80  | —             | —       | —       | 4930        | 3700    | 6160    |
|                                     | 17.00                                                           | N-80  | —             | —       | —       | 3480        | 2610    | 4350    |
|                                     | 20.00                                                           | N-80  | —             | —       | —       | 4280        | 3210    | 5350    |
|                                     | 23.00                                                           | N-80  | —             | —       | —       | 5020        | 3770    | 6280    |
|                                     | 17.00                                                           | C-90  | —             | —       | —       | 3750        | 2820    | 4690    |
|                                     | 20.00                                                           | C-90  | —             | —       | —       | 4620        | 3470    | 5780    |
|                                     | 23.00                                                           | C-90  | —             | —       | —       | 5420        | 4070    | 6780    |
|                                     | 26.80                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 29.70                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 32.60                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 35.30                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 38.00                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 40.50                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 43.10                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 17.00                                                           | C-95  | —             | —       | —       | 3960        | 2970    | 4950    |
|                                     | 20.00                                                           | C-95  | —             | —       | —       | 4870        | 3650    | 6090    |
|                                     | 23.00                                                           | C-95  | —             | —       | —       | 5720        | 4290    | 7150    |
|                                     | 17.00                                                           | P-110 | —             | —       | —       | 4620        | 3470    | 5780    |
|                                     | 20.00                                                           | P-110 | —             | —       | —       | 5690        | 4270    | 7110    |
|                                     | 23.00                                                           | P-110 | —             | —       | —       | 6680        | 5010    | 8350    |
|                                     | 23.00                                                           | Q125  | —             | —       | —       | 7460        | 5600    | 9330    |
| 6%                                  | 20.00                                                           | H-40  | 1840          | 1380    | 2300    | —           | —       | —       |
|                                     | 20.00                                                           | J-55  | 2450          | 1840    | 3060    | 2660        | 2000    | 3330    |
|                                     | 24.00                                                           | J-55  | 3140          | 2360    | 3930    | 3400        | 2550    | 4250    |
|                                     | 20.00                                                           | K-55  | 2670          | 2000    | 3340    | 2900        | 2180    | 3630    |
|                                     | 24.00                                                           | K-55  | 3420          | 2570    | 4280    | 3720        | 2790    | 4650    |

**TABLE 1.1 (cont.)**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                                   | 2                                                               | 3     | 4             | 5       | 6       | 7           | 8       | 9       |
|-------------------------------------|-----------------------------------------------------------------|-------|---------------|---------|---------|-------------|---------|---------|
| Size:<br>Outside<br>Diameter<br>in. | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lb. per ft. | Grade | Torque, ft-lb |         |         |             |         |         |
|                                     |                                                                 |       | Short Thread  |         |         | Long Thread |         |         |
|                                     |                                                                 |       | Optimum       | Minimum | Maximum | Optimum     | Minimum | Maximum |
|                                     | 24.00                                                           | C-75  | —             | —       | —       | 4530        | 3400    | 5660    |
|                                     | 28.00                                                           | C-75  | —             | —       | —       | 5520        | 4140    | 6900    |
|                                     | 32.00                                                           | C-75  | —             | —       | —       | 6380        | 4790    | 7980    |
|                                     | 24.00                                                           | L-80  | —             | —       | —       | 4730        | 3550    | 5910    |
|                                     | 28.00                                                           | L-80  | —             | —       | —       | 5760        | 4320    | 7200    |
|                                     | 32.00                                                           | L-80  | —             | —       | —       | 6660        | 5000    | 8330    |
|                                     | 24.00                                                           | N-80  | —             | —       | —       | 4810        | 3610    | 6010    |
|                                     | 28.00                                                           | N-80  | —             | —       | —       | 5860        | 4400    | 7330    |
|                                     | 32.00                                                           | N-80  | —             | —       | —       | 6770        | 5080    | 8460    |
|                                     | 24.00                                                           | C-90  | —             | —       | —       | 5210        | 3910    | 6510    |
|                                     | 28.00                                                           | C-90  | —             | —       | —       | 6350        | 4760    | 7930    |
|                                     | 32.00                                                           | C-90  | —             | —       | —       | 7340        | 5510    | 9180    |
|                                     | 24.00                                                           | C-95  | —             | —       | —       | 5490        | 4120    | 6860    |
|                                     | 28.00                                                           | C-95  | —             | —       | —       | 6690        | 5020    | 8360    |
|                                     | 32.00                                                           | C-95  | —             | —       | —       | 7740        | 5810    | 9680    |
|                                     | 24.00                                                           | P-110 | —             | —       | —       | 6410        | 4810    | 8010    |
|                                     | 28.00                                                           | P-110 | —             | —       | —       | 7810        | 5860    | 9760    |
|                                     | 32.00                                                           | P-110 | —             | —       | —       | 9040        | 6780    | 11300   |
|                                     | 32.00                                                           | Q125  | —             | —       | —       | 10110       | 7580    | 12640   |
| 7                                   | 17.00                                                           | H-40  | 1220          | 920     | 1530    | —           | —       | —       |
|                                     | 20.00                                                           | H-40  | 1760          | 1320    | 2200    | —           | —       | —       |
|                                     | 20.00                                                           | J-55  | 2340          | 1760    | 2930    | —           | —       | —       |
|                                     | 23.00                                                           | J-55  | 2840          | 2130    | 3550    | 3130        | 2350    | 3910    |
|                                     | 26.00                                                           | J-55  | 3340          | 2510    | 4180    | 3670        | 2750    | 4590    |
|                                     | 20.00                                                           | K-55  | 2540          | 1910    | 3180    | —           | —       | —       |
|                                     | 23.00                                                           | K-55  | 3090          | 2320    | 3860    | 3410        | 2560    | 4260    |
|                                     | 26.00                                                           | K-55  | 3640          | 2730    | 4550    | 4010        | 3010    | 5010    |
|                                     | 23.00                                                           | C-75  | —             | —       | —       | 4160        | 3120    | 5200    |
|                                     | 26.00                                                           | C-75  | —             | —       | —       | 4890        | 3670    | 6110    |
|                                     | 29.00                                                           | C-75  | —             | —       | —       | 5620        | 4220    | 7030    |
|                                     | 32.00                                                           | C-75  | —             | —       | —       | 6330        | 4750    | 7910    |
|                                     | 35.00                                                           | C-75  | —             | —       | —       | 7030        | 5270    | 8790    |
|                                     | 38.00                                                           | C-75  | —             | —       | —       | 7670        | 5750    | 9590    |
|                                     | 23.00                                                           | L-80  | —             | —       | —       | 4350        | 3260    | 5440    |
|                                     | 26.00                                                           | L-80  | —             | —       | —       | 5110        | 3830    | 6390    |
|                                     | 29.00                                                           | L-80  | —             | —       | —       | 5870        | 4400    | 7340    |
|                                     | 32.00                                                           | L-80  | —             | —       | —       | 6610        | 4960    | 8260    |
|                                     | 35.00                                                           | L-80  | —             | —       | —       | 7340        | 5510    | 9180    |
|                                     | 38.00                                                           | L-80  | —             | —       | —       | 8010        | 6010    | 10010   |
|                                     | 23.00                                                           | N-80  | —             | —       | —       | 4420        | 3320    | 5530    |
|                                     | 26.00                                                           | N-80  | —             | —       | —       | 5190        | 3890    | 6490    |
|                                     | 29.00                                                           | N-80  | —             | —       | —       | 5970        | 4480    | 7460    |
|                                     | 32.00                                                           | N-80  | —             | —       | —       | 6720        | 5040    | 8400    |
|                                     | 35.00                                                           | N-80  | —             | —       | —       | 7460        | 5600    | 9330    |
|                                     | 38.00                                                           | N-80  | —             | —       | —       | 8140        | 6110    | 10180   |
|                                     | 23.00                                                           | C-90  | —             | —       | —       | 4790        | 3590    | 5990    |
|                                     | 26.00                                                           | C-90  | —             | —       | —       | 5630        | 4220    | 7040    |
|                                     | 29.00                                                           | C-90  | —             | —       | —       | 6480        | 4860    | 8100    |
|                                     | 32.00                                                           | C-90  | —             | —       | —       | 7290        | 5470    | 9110    |
|                                     | 35.00                                                           | C-90  | —             | —       | —       | 8090        | 6070    | 10110   |

**TABLE 1.1 (cont.)**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                                   | 2                                                               | 3     | 4             | 5       | 6       | 7           | 8       | 9       |
|-------------------------------------|-----------------------------------------------------------------|-------|---------------|---------|---------|-------------|---------|---------|
| Size:<br>Outside<br>Diameter<br>in. | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lb. per ft. | Grade | Torque, ft-lb |         |         |             |         |         |
|                                     |                                                                 |       | Short Thread  |         |         | Long Thread |         |         |
|                                     |                                                                 |       | Optimum       | Minimum | Maximum | Optimum     | Minimum | Maximum |
|                                     | 38.00                                                           | C-90  | —             | —       | —       | 8830        | 6620    | 11040   |
|                                     | 42.70                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 46.40                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 50.10                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 53.60                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 57.10                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 23.00                                                           | C-95  | —             | —       | —       | 5050        | 3790    | 6310    |
|                                     | 26.00                                                           | C-95  | —             | —       | —       | 5930        | 4450    | 7410    |
|                                     | 29.00                                                           | C-95  | —             | —       | —       | 6830        | 5120    | 8540    |
|                                     | 32.00                                                           | C-95  | —             | —       | —       | 7680        | 5760    | 9600    |
|                                     | 35.00                                                           | C-95  | —             | —       | —       | 8530        | 6400    | 10660   |
|                                     | 38.00                                                           | C-95  | —             | —       | —       | 9310        | 6980    | 11640   |
|                                     | 26.00                                                           | P-110 | —             | —       | —       | 6930        | 5200    | 8660    |
|                                     | 29.00                                                           | P-110 | —             | —       | —       | 7970        | 5980    | 9960    |
|                                     | 32.00                                                           | P-110 | —             | —       | —       | 8970        | 6730    | 11210   |
|                                     | 35.00                                                           | P-110 | —             | —       | —       | 9960        | 7470    | 12450   |
|                                     | 38.00                                                           | P-110 | —             | —       | —       | 10870       | 8150    | 13590   |
|                                     | 35.00                                                           | Q125  | —             | —       | —       | 11150       | 8360    | 13940   |
|                                     | 38.00                                                           | Q125  | —             | —       | —       | 12160       | 9120    | 15200   |
| 7%                                  | 24.00                                                           | H-40  | 2120          | 1590    | 2650    | —           | —       | —       |
|                                     | 26.40                                                           | J-55  | 3150          | 2360    | 3940    | 3460        | 2600    | 4330    |
|                                     | 26.40                                                           | K-55  | 3420          | 2570    | 4280    | 3770        | 2830    | 4710    |
|                                     | 26.40                                                           | C-75  | —             | —       | —       | 4610        | 3460    | 5760    |
|                                     | 29.70                                                           | C-75  | —             | —       | —       | 5420        | 4070    | 6780    |
|                                     | 33.70                                                           | C-75  | —             | —       | —       | 6350        | 4760    | 7940    |
|                                     | 39.00                                                           | C-75  | —             | —       | —       | 7510        | 5630    | 9390    |
|                                     | 42.80                                                           | C-75  | —             | —       | —       | 8520        | 6390    | 10650   |
|                                     | 47.10                                                           | C-75  | —             | —       | —       | 9530        | 7150    | 11910   |
|                                     | 26.40                                                           | L-80  | —             | —       | —       | 4820        | 3620    | 6030    |
|                                     | 29.70                                                           | L-80  | —             | —       | —       | 5670        | 4250    | 7090    |
|                                     | 33.70                                                           | L-80  | —             | —       | —       | 6640        | 4980    | 8300    |
|                                     | 39.00                                                           | L-80  | —             | —       | —       | 7860        | 5900    | 9830    |
|                                     | 42.80                                                           | L-80  | —             | —       | —       | 8910        | 6680    | 11140   |
|                                     | 47.10                                                           | L-80  | —             | —       | —       | 9970        | 7480    | 12460   |
|                                     | 26.40                                                           | N-80  | —             | —       | —       | 4900        | 3680    | 6130    |
|                                     | 29.70                                                           | N-80  | —             | —       | —       | 5750        | 4310    | 7190    |
|                                     | 33.70                                                           | N-80  | —             | —       | —       | 6740        | 5060    | 8430    |
|                                     | 39.00                                                           | N-80  | —             | —       | —       | 7980        | 5980    | 9980    |
|                                     | 42.80                                                           | N-80  | —             | —       | —       | 9060        | 6800    | 11330   |
|                                     | 47.10                                                           | N-80  | —             | —       | —       | 10130       | 7600    | 12660   |
|                                     | 26.40                                                           | C-90  | —             | —       | —       | 5320        | 3990    | 6650    |
|                                     | 29.70                                                           | C-90  | —             | —       | —       | 6250        | 4690    | 7810    |
|                                     | 33.70                                                           | C-90  | —             | —       | —       | 7330        | 5500    | 9160    |
|                                     | 39.00                                                           | C-90  | —             | —       | —       | 8670        | 6500    | 10840   |
|                                     | 42.80                                                           | C-90  | —             | —       | —       | 9840        | 7380    | 12300   |
|                                     | 45.30                                                           | C-90  | —             | —       | —       | 10450       | 7840    | 13060   |
|                                     | 47.10                                                           | C-90  | —             | —       | —       | 11000       | 8250    | 13750   |
|                                     | 51.20                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 55.30                                                           | C-90  | **            | **      | **      | **          | **      | **      |
|                                     | 26.40                                                           | C-95  | —             | —       | —       | 5600        | 4200    | 7000    |
|                                     | 29.70                                                           | C-95  | —             | —       | —       | 6590        | 4940    | 8240    |
|                                     | 33.70                                                           | C-95  | —             | —       | —       | 7720        | 5790    | 9650    |
|                                     | 39.00                                                           | C-95  | —             | —       | —       | 9140        | 6860    | 11430   |
|                                     | 42.80                                                           | C-95  | —             | —       | —       | 10370       | 7780    | 12960   |
|                                     | 47.10                                                           | C-95  | —             | —       | —       | 11590       | 8690    | 14490   |

**TABLE 1.1 (cont.)**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                                   | 2                                                               | 3     | 4             | 5       | 6       | 7           | 8       | 9       |
|-------------------------------------|-----------------------------------------------------------------|-------|---------------|---------|---------|-------------|---------|---------|
| Size:<br>Outside<br>Diameter<br>in. | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lb. per ft. | Grade | Torque, ft-lb |         |         |             |         |         |
|                                     |                                                                 |       | Short Thread  |         |         | Long Thread |         |         |
|                                     |                                                                 |       | Optimum       | Minimum | Maximum | Optimum     | Minimum | Maximum |
|                                     | 29.70                                                           | P-110 | —             | —       | —       | 7690        | 5770    | 9610    |
|                                     | 33.70                                                           | P-110 | —             | —       | —       | 9010        | 6760    | 11260   |
|                                     | 39.00                                                           | P-110 | —             | —       | —       | 10660       | 8000    | 13330   |
|                                     | 42.80                                                           | P-110 | —             | —       | —       | 12100       | 9080    | 15130   |
|                                     | 47.10                                                           | P-110 | —             | —       | —       | 13530       | 10150   | 16910   |
|                                     | 39.00                                                           | Q125  | —             | —       | —       | 11940       | 8960    | 14930   |
|                                     | 42.80                                                           | Q125  | —             | —       | —       | 13550       | 10160   | 16940   |
|                                     | 45.30                                                           | Q125  | —             | —       | —       | 14390       | 10790   | 17990   |
|                                     | 47.10                                                           | Q125  | —             | —       | —       | 15150       | 11360   | 18940   |
| 7¾                                  | 46.10                                                           | C-75  | —             | —       | —       | —           | —       | —       |
|                                     |                                                                 | L-80  | —             | —       | —       | —           | —       | —       |
|                                     |                                                                 | N-80  | —             | —       | —       | —           | —       | —       |
|                                     |                                                                 | C-90  | —             | —       | —       | —           | —       | —       |
|                                     |                                                                 | C-95  | —             | —       | —       | —           | —       | —       |
|                                     |                                                                 | P-110 | —             | —       | —       | —           | —       | —       |
|                                     |                                                                 | Q125  | —             | —       | —       | —           | —       | —       |
| 8%                                  | 28.00                                                           | H-40  | 2330          | 1750    | 2910    | —           | —       | —       |
|                                     | 32.00                                                           | H-40  | 2790          | 2090    | 3490    | —           | —       | —       |
|                                     | 24.00                                                           | J-55  | 2440          | 1830    | 3050    | —           | —       | —       |
|                                     | 32.00                                                           | J-55  | 3720          | 2790    | 4650    | 4170        | 3130    | 5210    |
|                                     | 36.00                                                           | J-55  | 4340          | 3260    | 5430    | 4860        | 3650    | 6080    |
|                                     | 24.00                                                           | K-55  | 2630          | 1970    | 3290    | —           | —       | —       |
|                                     | 32.00                                                           | K-55  | 4020          | 3020    | 5030    | 4520        | 3390    | 5650    |
|                                     | 36.00                                                           | K-55  | 4680          | 3510    | 5850    | 5260        | 3950    | 6580    |
|                                     | 36.00                                                           | C-75  | —             | —       | —       | 6480        | 4860    | 8100    |
|                                     | 40.00                                                           | C-75  | —             | —       | —       | 7420        | 5570    | 9280    |
|                                     | 44.00                                                           | C-75  | —             | —       | —       | 8340        | 6260    | 10430   |
|                                     | 49.00                                                           | C-75  | —             | —       | —       | 9390        | 7040    | 11740   |
|                                     | 36.00                                                           | L-80  | —             | —       | —       | 6780        | 5090    | 8480    |
|                                     | 40.00                                                           | L-80  | —             | —       | —       | 7760        | 5820    | 9700    |
|                                     | 44.00                                                           | L-80  | —             | —       | —       | 8740        | 6560    | 10930   |
|                                     | 49.00                                                           | L-80  | —             | —       | —       | 9830        | 7370    | 12290   |
|                                     | 36.00                                                           | N-80  | —             | —       | —       | 6880        | 5160    | 8600    |
|                                     | 40.00                                                           | N-80  | —             | —       | —       | 7880        | 5910    | 9850    |
|                                     | 44.00                                                           | N-80  | —             | —       | —       | 8870        | 6650    | 11090   |
|                                     | 49.00                                                           | N-80  | —             | —       | —       | 9970        | 7480    | 12460   |
|                                     | 36.00                                                           | C-90  | —             | —       | —       | 7490        | 5620    | 9360    |
|                                     | 40.00                                                           | C-90  | —             | —       | —       | 8580        | 6440    | 10730   |
|                                     | 44.00                                                           | C-90  | —             | —       | —       | 9650        | 7240    | 12060   |
|                                     | 49.00                                                           | C-90  | —             | —       | —       | 10850       | 8140    | 13560   |
|                                     | 36.00                                                           | C-95  | —             | —       | —       | 7890        | 5920    | 9860    |
|                                     | 40.00                                                           | C-95  | —             | —       | —       | 9040        | 6780    | 11300   |
|                                     | 44.00                                                           | C-95  | —             | —       | —       | 10170       | 7630    | 12710   |
|                                     | 49.00                                                           | C-95  | —             | —       | —       | 11440       | 8580    | 14300   |
|                                     | 40.00                                                           | P-110 | —             | —       | —       | 10550       | 7910    | 13190   |
|                                     | 44.00                                                           | P-110 | —             | —       | —       | 11860       | 8900    | 14830   |
|                                     | 49.00                                                           | P-110 | —             | —       | —       | 13350       | 10010   | 16690   |
|                                     | 49.00                                                           | Q125  | —             | —       | —       | 14960       | 11220   | 18700   |
| 9%                                  | 32.30                                                           | H-40  | 2540          | 1910    | 3180    | —           | —       | —       |
|                                     | 36.00                                                           | H-40  | 2940          | 2210    | 3680    | —           | —       | —       |
|                                     | 36.00                                                           | J-55  | 3940          | 2960    | 4930    | 4530        | 3400    | 5660    |
|                                     | 40.00                                                           | J-55  | 4520          | 3390    | 5650    | 5200        | 3900    | 6500    |

**TABLE 1.1 (cont.)**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                                   | 2                                                               | 3     | 4               | 5       | 6       | 7           | 8       | 9       |
|-------------------------------------|-----------------------------------------------------------------|-------|-----------------|---------|---------|-------------|---------|---------|
| Size:<br>Outside<br>Diameter<br>in. | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lb. per ft. | Grade | Torque, ft.-lb. |         |         |             |         |         |
|                                     |                                                                 |       | Short Thread    |         |         | Long Thread |         |         |
|                                     |                                                                 |       | Optimum         | Minimum | Maximum | Optimum     | Minimum | Maximum |
|                                     | 36.00                                                           | K-55  | 4230            | 3170    | 5290    | 4890        | 3670    | 6110    |
|                                     | 40.00                                                           | K-55  | 4860            | 3650    | 6080    | 5610        | 4210    | 7010    |
|                                     | 40.00                                                           | C-75  | —               | —       | —       | 6940        | 5210    | 8680    |
|                                     | 43.50                                                           | C-75  | —               | —       | —       | 7760        | 5820    | 9700    |
|                                     | 47.00                                                           | C-75  | —               | —       | —       | 8520        | 6390    | 10650   |
|                                     | 53.50                                                           | C-75  | —               | —       | —       | 9990        | 7490    | 12490   |
|                                     | 40.00                                                           | L-80  | —               | —       | —       | 7270        | 5450    | 9090    |
|                                     | 43.50                                                           | L-80  | —               | —       | —       | 8130        | 6100    | 10160   |
|                                     | 47.00                                                           | L-80  | —               | —       | —       | 8930        | 6700    | 11160   |
|                                     | 53.50                                                           | L-80  | —               | —       | —       | 10470       | 7850    | 13090   |
|                                     | 40.00                                                           | N-80  | —               | —       | —       | 7370        | 5530    | 9210    |
|                                     | 43.50                                                           | N-80  | —               | —       | —       | 8250        | 6190    | 10310   |
|                                     | 47.00                                                           | N-80  | —               | —       | —       | 9050        | 6790    | 11310   |
|                                     | 53.50                                                           | N-80  | —               | —       | —       | 10620       | 7970    | 13280   |
|                                     | 40.00                                                           | C-90  | —               | —       | —       | 8040        | 6030    | 10050   |
|                                     | 43.50                                                           | C-90  | —               | —       | —       | 8990        | 6740    | 11240   |
|                                     | 47.00                                                           | C-90  | —               | —       | —       | 9870        | 7400    | 12340   |
|                                     | 53.50                                                           | C-90  | —               | —       | —       | 11570       | 8680    | 14460   |
|                                     | 59.40                                                           | C-90  | **              | **      | **      | **          | **      | **      |
|                                     | 64.90                                                           | C-90  | **              | **      | **      | **          | **      | **      |
|                                     | 70.30                                                           | C-90  | **              | **      | **      | **          | **      | **      |
|                                     | 75.60                                                           | C-90  | **              | **      | **      | **          | **      | **      |
|                                     | 40.00                                                           | C-95  | —               | —       | —       | 8470        | 6350    | 10590   |
|                                     | 43.50                                                           | C-95  | —               | —       | —       | 9480        | 7110    | 11850   |
|                                     | 47.00                                                           | C-95  | —               | —       | —       | 10400       | 7800    | 13000   |
|                                     | 53.50                                                           | C-95  | —               | —       | —       | 12200       | 9150    | 15250   |
|                                     | 43.50                                                           | P-110 | —               | —       | —       | 11060       | 8300    | 13830   |
|                                     | 47.00                                                           | P-110 | —               | —       | —       | 12130       | 9100    | 15160   |
|                                     | 53.50                                                           | P-110 | —               | —       | —       | 14220       | 10670   | 17780   |
|                                     | 47.00                                                           | Q125  | —               | —       | —       | 13600       | 10200   | 17000   |
|                                     | 53.50                                                           | Q125  | —               | —       | —       | 15950       | 11960   | 19940   |
| 10%                                 | 32.75                                                           | H-40  | 2050            | 1540    | 2560    | —           | —       | —       |
|                                     | 40.50                                                           | H-40  | 3140            | 2360    | 3930    | —           | —       | —       |
|                                     | 40.50                                                           | J-55  | 4200            | 3150    | 5250    | —           | —       | —       |
|                                     | 45.50                                                           | J-55  | 4930            | 3700    | 6160    | —           | —       | —       |
|                                     | 51.00                                                           | J-55  | 5650            | 4240    | 7060    | —           | —       | —       |
|                                     | 40.50                                                           | K-55  | 4500            | 3380    | 5630    | —           | —       | —       |
|                                     | 45.50                                                           | K-55  | 5280            | 3960    | 6600    | —           | —       | —       |
|                                     | 51.00                                                           | K-55  | 6060            | 4550    | 7580    | —           | —       | —       |
|                                     | 51.00                                                           | C-75  | 7560            | 5670    | 9450    | —           | —       | —       |
|                                     | 55.50                                                           | C-75  | 8430            | 6320    | 10540   | —           | —       | —       |
|                                     | 51.00                                                           | L-80  | 7940            | 5960    | 9930    | —           | —       | —       |
|                                     | 55.50                                                           | L-80  | 8840            | 6630    | 11050   | —           | —       | —       |
|                                     | 51.00                                                           | N-80  | 8040            | 6030    | 10050   | —           | —       | —       |
|                                     | 55.50                                                           | N-80  | 8950            | 6710    | 11190   | —           | —       | —       |
|                                     | 51.00                                                           | C-90  | 6920            | 5190    | 8650    | —           | —       | —       |
|                                     | 55.50                                                           | C-90  | 7710            | 5780    | 9640    | —           | —       | —       |
|                                     | 59.40                                                           | C-90  | **              | **      | **      | **          | **      | **      |
|                                     | 64.50                                                           | C-90  | **              | **      | **      | **          | **      | **      |
|                                     | 73.20                                                           | C-90  | **              | **      | **      | **          | **      | **      |
|                                     | 79.20                                                           | C-90  | **              | **      | **      | **          | **      | **      |
|                                     | 85.30                                                           | C-90  | **              | **      | **      | **          | **      | **      |



**TABLE 1.1 (cont.)**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                                   | 2                                                               | 3     | 4             | 5       | 6       | 7           | 8       | 9       |
|-------------------------------------|-----------------------------------------------------------------|-------|---------------|---------|---------|-------------|---------|---------|
| Size:<br>Outside<br>Diameter<br>in. | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lb. per ft. | Grade | Torque, ft-lb |         |         |             |         |         |
|                                     |                                                                 |       | Short Thread  |         |         | Long Thread |         |         |
|                                     |                                                                 |       | Optimum       | Minimum | Maximum | Optimum     | Minimum | Maximum |
|                                     | 51.00                                                           | C-95  | 9270          | 6950    | 11590   | —           | —       | —       |
|                                     | 55.50                                                           | C-95  | 10320         | 7740    | 12900   | —           | —       | —       |
|                                     | 51.00                                                           | P-110 | 10800         | 8100    | 13500   | —           | —       | —       |
|                                     | 55.50                                                           | P-110 | 12030         | 9020    | 15040   | —           | —       | —       |
|                                     | 60.70                                                           | P-110 | 13380         | 10040   | 16730   | —           | —       | —       |
|                                     | 65.70                                                           | P-110 | 14720         | 11040   | 18400   | —           | —       | —       |
|                                     | 60.70                                                           | Q125  | 15020         | 11270   | 18780   | —           | —       | —       |
|                                     | 65.70                                                           | Q125  | 16520         | 12390   | 20650   | —           | —       | —       |
| 11%                                 | 42.00                                                           | H-40  | 3070          | 2300    | 3840    | —           | —       | —       |
|                                     | 47.00                                                           | J-55  | 4770          | 3580    | 5960    | —           | —       | —       |
|                                     | 54.00                                                           | J-55  | 5680          | 4260    | 7100    | —           | —       | —       |
|                                     | 60.00                                                           | J-55  | 6490          | 4870    | 8110    | —           | —       | —       |
|                                     | 47.00                                                           | K-55  | 5090          | 3820    | 6360    | —           | —       | —       |
|                                     | 54.00                                                           | K-55  | 6060          | 4550    | 7580    | —           | —       | —       |
|                                     | 60.00                                                           | K-55  | 6930          | 5200    | 8660    | —           | —       | —       |
|                                     | 60.00                                                           | C-75  | 8690          | 6520    | 10860   | —           | —       | —       |
|                                     | 60.00                                                           | L-80  | 9130          | 6850    | 11410   | —           | —       | —       |
|                                     | 60.00                                                           | N-80  | 9240          | 6930    | 11550   | —           | —       | —       |
|                                     | 60.00                                                           | C-90  | 10110         | 7580    | 12640   | —           | —       | —       |
|                                     | 60.00                                                           | C-95  | 10660         | 8000    | 13330   | —           | —       | —       |
|                                     | 60.00                                                           | P-110 | 12420         | 9320    | 15530   | —           | —       | —       |
|                                     | 60.00                                                           | Q125  | 13950         | 10460   | 17440   | —           | —       | —       |
| 13%                                 | 48.00                                                           | H-40  | 3220          | 2420    | 4030    | —           | —       | —       |
|                                     | 54.50                                                           | J-55  | 5140          | 3860    | 6430    | —           | —       | —       |
|                                     | 61.00                                                           | J-55  | 5950          | 4460    | 7440    | —           | —       | —       |
|                                     | 68.00                                                           | J-55  | 6750          | 5060    | 8440    | —           | —       | —       |
|                                     | 54.50                                                           | K-55  | 5470          | 4100    | 6840    | —           | —       | —       |
|                                     | 61.00                                                           | K-55  | 6330          | 4750    | 7910    | —           | —       | —       |
|                                     | 68.00                                                           | K-55  | 7180          | 5390    | 8980    | —           | —       | —       |
|                                     | 68.00                                                           | C-75  | 9060          | 6800    | 11330   | —           | —       | —       |
|                                     | 72.00                                                           | C-75  | 9780          | 7340    | 12230   | —           | —       | —       |
|                                     | 68.00                                                           | L-80  | 9520          | 7140    | 11900   | —           | —       | —       |
|                                     | 72.00                                                           | L-80  | 10290         | 7720    | 12860   | —           | —       | —       |
|                                     | 68.00                                                           | N-80  | 9630          | 7220    | 12040   | —           | —       | —       |
|                                     | 72.00                                                           | N-80  | 10400         | 7800    | 13000   | —           | —       | —       |
|                                     | 68.00                                                           | C-90  | 10570         | 7930    | 13210   | —           | —       | —       |
|                                     | 72.00                                                           | C-90  | 11420         | 8570    | 14280   | —           | —       | —       |
|                                     | 68.00                                                           | C-95  | 11140         | 8360    | 13930   | —           | —       | —       |
|                                     | 72.00                                                           | C-95  | 12040         | 9030    | 15050   | —           | —       | —       |
|                                     | 68.00                                                           | P-110 | 12970         | 9730    | 16210   | —           | —       | —       |
|                                     | 72.00                                                           | P-110 | 14020         | 10520   | 17530   | —           | —       | —       |
|                                     | 72.00                                                           | Q125  | 15760         | 11820   | 19700   | —           | —       | —       |

**TABLE 1.1 (cont.)**  
**RECOMMENDED CASING MAKE-UP TORQUE**  
**8-ROUND-THREAD CASING**

| 1                                   | 2                                                               | 3     | 4             | 5       | 6       | 7           | 8       | 9       |
|-------------------------------------|-----------------------------------------------------------------|-------|---------------|---------|---------|-------------|---------|---------|
| Size:<br>Outside<br>Diameter<br>in. | Nominal<br>Weight,<br>Threads<br>and<br>Coupling<br>lb. per ft. | Grade | Torque, ft-lb |         |         |             |         |         |
|                                     |                                                                 |       | Short Thread  |         |         | Long Thread |         |         |
|                                     |                                                                 |       | Optimum       | Minimum | Maximum | Optimum     | Minimum | Maximum |
| *16                                 | 65.00                                                           | H-40  | —             | 4390    | —       | —           | —       | —       |
|                                     | 75.00                                                           | J-55  | —             | 7100    | —       | —           | —       | —       |
|                                     | 84.00                                                           | J-55  | —             | 8170    | —       | —           | —       | —       |
|                                     | 75.00                                                           | K-55  | —             | 7520    | —       | —           | —       | —       |
|                                     | 84.00                                                           | K-55  | —             | 8650    | —       | —           | —       | —       |
| *18%                                | 87.50                                                           | H-40  | —             | 5590    | —       | —           | —       | —       |
|                                     | 87.50                                                           | J-55  | —             | 7540    | —       | —           | —       | —       |
|                                     | 87.50                                                           | K-55  | —             | 7940    | —       | —           | —       | —       |
| *20                                 | 94.00                                                           | H-40  | —             | 5810    | —       | —           | —       | —       |
|                                     | 94.00                                                           | J-55  | —             | 7840    | —       | —           | 9070    | —       |
|                                     | 106.50                                                          | J-55  | —             | 9130    | —       | —           | 10570   | —       |
|                                     | 133.00                                                          | J-55  | —             | 11920   | —       | —           | 13800   | —       |
|                                     | 94.00                                                           | K-55  | —             | 8240    | —       | —           | 9550    | —       |
|                                     | 106.50                                                          | K-55  | —             | 9600    | —       | —           | 11130   | —       |
|                                     | 133.00                                                          | K-55  | —             | 12530   | —       | —           | 14530   | —       |

\*See Par. 1.14h for make-up instructions

\*\*End finish not yet specified

**TABLE 1.1**  
**TORQUE VALUES FOR EXTREMLINE CASING**

The torque values listed below are recommended for use in conjunction with close visual examination to be sure the shoulder closes and to avoid excessive box swelling.

TORQUE, FT.-LBS.

| Size<br>Outside<br>Diameter<br>Inches | J-55 &<br>K-55 |      |      | C-75, L-80,<br>N-80, C-90 |      |      | C-95,<br>P-110 |      |      | Q-125 |      |      |
|---------------------------------------|----------------|------|------|---------------------------|------|------|----------------|------|------|-------|------|------|
|                                       | Min.           | Aim. | Max. | Min.                      | Aim. | Max. | Min.           | Aim. | Max. | Min.  | Aim. | Max. |
| 5                                     | 2500           | 2700 | 3000 | 3000                      | 3200 | 3500 | 3500           | 3700 | 4000 | 4000  | 4200 | 4500 |
| 5 1/2                                 | 2500           | 2700 | 3000 | 3000                      | 3200 | 3500 | 3500           | 3700 | 4000 | 4000  | 4200 | 4500 |
| 6 5/8                                 | 3000           | 3200 | 3500 | 3500                      | 3700 | 4000 | 4000           | 4200 | 4500 | 4500  | 4700 | 5000 |
| 7                                     | 3000           | 3200 | 3500 | 3500                      | 3700 | 4000 | 4000           | 4200 | 4500 | 4500  | 4700 | 5000 |
| 7 7/8                                 | 3500           | 3700 | 4000 | 4000                      | 4200 | 4500 | 4500           | 4700 | 5000 | 5000  | 5200 | 5500 |
| 8 5/8                                 | 4000           | 4200 | 4500 | 4500                      | 4700 | 5000 | 5000           | 5200 | 5500 | 5500  | 5700 | 6000 |
| 9 5/8                                 | 4500           | 4700 | 5000 | 5000                      | 5200 | 5500 | 6000           | 6200 | 6500 | 6500  | 6700 | 7000 |

**NOTES:**

- (1) The outside shoulder is not a sealing surface; serves as a stop only.
- (2) Torque values higher than those listed above may be considered under certain conditions, providing box swelling does not occur.
- (3) Increased axial tension stress due to higher torque values could be excessive for sulfide service.
- (4) If the connection does not shoulder when maximum torque is applied, it should be treated as a questionable joint as provided under Par. 1.16.
- (5) Recommended make-up torque values for 10 1/4" are not available due to lack of data.

## SECTION 2

### RUNNING AND PULLING TUBING

#### Preparation and Inspection before Running

2.1 New tubing is delivered free of injurious defects as defined in the latest edition of API Spec 5CT and within the practical limits of the inspection procedures therein prescribed. Some Users have found that, for a limited number of critical well applications, these procedures do not result in tubing sufficiently free of defects to meet their needs for such critical applications. Various nondestructive inspection services have been employed by users to assure that the desired quality of tubing is being run. In view of this practice, it is suggested that the individual User:

- a. Familiarize himself with inspection practices specified in the standards and employed by the respective Manufacturers, and with the definition of "injurious defect" contained in the standards.
- b. Thoroughly evaluate any nondestructive inspection to be used by him on API tubular goods to assure himself that the inspection does in fact correctly locate and differentiate injurious defects from other variables which can be and frequently are sources of misleading "defect" signals with such inspection methods.

**CAUTION:** Due to the permissible tolerance on the outside diameter immediately behind the tubing upset, the user is cautioned that difficulties may occur when wrap-around seal-type hangers are installed on tubing manufactured on the high side of the tolerance; therefore, it is recommended that the user select the joint of tubing to be installed at the top of the string.

2.2 All tubing, whether new, used, or reconditioned, should always be handled with thread protectors in place. Tubing should be handled at all times on racks or on wooden or metal surfaces free of rocks, sand, or dirt other than normal drilling mud. When lengths of tubing are inadvertently dragged in the dirt, the threads should be recleaned and serviced again as outlined in Par. 2.9.

2.3 Before running in the hole for the first time, tubing should be drifted with an API drift mandrel to insure passage of pumps, swabs and packers.

2.4 Elevators should be in good repair and should have links of equal length.

2.5 Slip type elevators are recommended when running special clearance couplings, especially those beveled on the lower end.

2.6 Elevators should be examined to note if latch fitting is complete.

2.7 Spider slips which will not crush the tubing should be used. Slips should be examined before using to see that they are working together.

**NOTE:** Slip and tong marks are injurious. Every possible effort should be made to keep such damage at a minimum by using proper up-to-date equipment.

2.8 Tubing tongs which will not crush the tubing should be used on the body of the tubing and should fit properly to avoid unnecessary cutting of the pipe wall. Tong dies should fit properly and conform to the curvature of the tubing. The use of pipe wrenches is not recommended.

2.9 The following precautions should be taken in the preparation of tubing threads:

- a. Immediately before running, remove protectors from both field end and coupling end and clean

threads thoroughly, repeating as additional rows become uncovered.

- b. Carefully inspect the threads. Those found damaged, even slightly, should be laid aside unless satisfactory means are available for correcting thread damage.
- c. The length of each piece of tubing shall be measured prior to running. A steel tape calibrated in decimal feet to the nearest 0.01 ft should be used. The measurement should be made from the outermost face of the coupling or box to the position on the externally threaded end where the coupling or the box stops when the joint is made up power-tight. The total of the individual lengths so measured will represent the unloaded length of the tubing string. The actual length under tension in the hole can be obtained by consulting graphs which are prepared for this purpose and which are available in most pipe handbooks.
- d. Place clean protectors on field end of the pipe so that thread will not be damaged while rolling pipe onto the rack and pulling into the derrick. Several thread protectors may be cleaned and used repeatedly for this operation.
- e. Check each coupling for make-up. If the stand-off is abnormally great check the coupling for tightness. Loose couplings should be removed, the thread thoroughly cleaned, fresh compound applied over the entire thread surfaces, then the coupling replaced and tightened before pulling the tubing into the derrick.
- f. Before stabbing, liberally apply thread compound to the entire internally and externally threaded areas. It is recommended that high pressure modified thread compound as specified in the latest edition of API Bul 5A2: *Bulletin on Thread Compounds* be used, except in special cases where severe conditions are encountered, it is recommended that high pressure silicone thread compound as specified in the latest edition of Bul 5A2 be used.
- g. Connectors used as tensile and lifting members should have their thread capacity carefully checked to assure that the connector can safely support the load.
- h. Care should be taken when making up pup joints and connectors to assure that the mating threads are of the same size and type.

2.10 For high-pressure or condensate wells, additional precautions should be taken to insure tight joints as follows:

- a. Couplings should be removed, and both the mill-end pipe thread and coupling thread thoroughly cleaned and inspected. To facilitate this operation, tubing may be ordered with couplings handling tight, which is approximately one turn beyond hand-tight, or may be ordered with the couplings shipped separately.
- b. Thread compound should be applied to both the external and internal threads and the coupling should be reapplied handling tight. Field-end threads and the mating coupling threads should have thread compound applied just before stabbing.

2.11 When tubing is pulled into the derrick, care should be taken that the tubing is not bent, or couplings or protectors bumped.

**Stabbing, Making Up, and Lowering**

**2.12** Do not remove thread protector from field end of tubing until ready to stab.

**2.13** If necessary, apply thread compound over entire surface of threads just before stabbing. The brush or utensil used in applying thread compound should be kept free of foreign matter and the compound should never be thinned.

**2.14** In stabbing, lower tubing carefully to avoid injuring threads. Stab vertically, preferably with assistance of man on stabbing board. If the tubing tilts to one side after stabbing, lift up, clean, and correct any damaged thread with three-cornered file, then carefully remove any filings and reapply compound over thread surface. Care should be exercised, especially when running doubles or triples, to prevent bowing and resulting errors in alignment when the tubing is allowed to rest too heavily on the coupling threads. Intermediate supports may be placed in the derrick to limit bowing of the tubing.

**2.15** After stabbing, start screwing by hand or apply regular or power tubing tongs slowly. To prevent galling when making up connections in the field, the connections should be made up at a speed not to exceed 25 rpm. Power tubing tongs are recommended for high-pressure or condensate wells to insure uniform make-up and tight joints. Joints should be made up tight, approximately two turns beyond the hand-tight position, with care being taken not to gall the threads. When the additional preparation and inspection precautions for high-pressure or condensate wells are taken, the coupling will "float" or make up simultaneously at both ends until the proper number of turns beyond the hand-tight position have been obtained. The hand-tight position may be determined by checking several joints on the rack and noting the number of threads exposed when a coupling is made up with a torque of 50 ft-lb.

**Field Make-Up**

**2.16** Joint life of tubing under repeated field make-up is inversely proportional to the field make-up torque applied. Therefore, in wells where leak resistance is not a great factor, minimum field make-up torque values should be used to prolong joint life. The use of power tongs for making up tubing made desirable the establishment of recommended torque values for each size, weight, and grade of tubing. Table 2.1 contains recommended optimum make-up torque values for non-upset, external upset, and integral joint tubing, based on 1% of the calculated joint pullout strength determined from the joint pullout strength formula for 8-round-thread casing in the latest edition of *Bul 5C3: Bulletin on Formulas and Calculations for Casing, Tubing, Drill Pipe and Line Pipe Properties*. Minimum torque values listed are 75% of optimum values and maximum torque values listed are 125% of optimum values. All values are rounded to the nearest 10 foot pounds. The torque values listed in Table 2.1 apply to tubing with zinc plated or phosphate coated couplings. When making up connections with tin plated couplings, 80% of the listed value can be used as a guide. When making up round thread connections with PTFE (Polytetrafluoroethylene)\* rings, 70% of the listed values are recommended. As with standard couplings, make-up position shall govern. Buttress connections with PTFE (Polytetrafluoroethylene)\* seal rings may make up at torque values different from those normally observed on standard buttress threads.

NOTE: Thread galling of gall-prone materials (martensitic chromium steels—9Cr and 13Cr) occurs during

\*Teflon™ or equivalent

movement — stabbing or pulling and make-up or break-out. Galling resistance of threads is primarily controlled in two areas — surface preparation and finishing during manufacture and careful handling practices during running and pulling. Threads and lubricant must be clean. Assembly in the horizontal position should be avoided. Connections should be turned by hand to the hand-tight position before slowly power tightening. The procedure should be reversed for disassembly.

**2.17** Spider slips and elevators should be cleaned frequently and slips should be kept sharp.

**2.18** Finding bottom should be accomplished with extreme caution. Do not set tubing down heavily.

**Pulling Tubing**

**2.19** A caliper survey prior to pulling a worn string of tubing will provide a quick means of segregating badly worn lengths for removal.

**2.20** Break-out tongs should be positioned close to the coupling. Hammering the coupling to break the joint is an injurious practice. When tapping is required, use the flat face, never the peen face, of the hammer, and tap lightly at the middle and completely around the coupling, never near the end or on opposite sides only.

**2.21** Great care should be exercised to disengage all of the thread before lifting the tubing out of the coupling. Do not jump tubing out of the coupling.

**2.22** Tubing stacked in the derrick should be set on a firm wooden platform and without the bottom thread protector since the design of most protectors is not such as to support the joint or stand without damage to the field thread.

**2.23** Protect threads from dirt or injury when the tubing is out of the hole.

**2.24** Tubing set back in the derrick should be properly supported to prevent undue bending. Tubing 2½-in. OD and larger, preferably should be pulled in stands approximately 60 ft long or in doubles of range 2. Stands of tubing 1.900-in. OD or smaller, and stands longer than 60 ft, should have intermediate support.

**2.25** Before leaving location, always firmly tie a set-back of tubing in place.

**2.26** Make sure threads are undamaged, clean and well coated with compound before re-running.

**2.27** Distribute joint and tubing wear by moving a length from the top of the string to the bottom each time the tubing is pulled.

**2.28** In order to avoid leaks, all joints should be retightened occasionally.

**2.29** When tubing is stuck, the best practice is to use a calibrated weight indicator. Do not be misled, by stretching of the tubing string, into the assumption that the tubing is free.

**2.30** After a hard pull to loosen a string of tubing, all joints pulled on should be retightened.

**2.31** All threads should be cleaned and lubricated or should be coated with a material that will minimize corrosion. Clean protectors should be placed on the tubing before it is laid down.

**2.32** Before tubing is stored or re-used, pipe and threads should be inspected and defective joints marked for shopping and regaging.