

INTERNATIONAL STANDARD

ISO
105-E04

Third edition
1989-12-15

Textiles — Tests for colour fastness —

Part E04 :

Colour fastness to perspiration

Textiles — Essais de solidité des teintures —

Partie E04 : Solidité des teintures à la sueur



Reference number
ISO 105-E04:1989(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 105-E04 was prepared by Technical Committee ISO/TC 38, *Textiles*.

This third edition cancels and replaces the second edition (ISO 105-E04:1987), of which it constitutes a technical revision.

ISO 105 was previously published in 13 "parts", each designated by a letter (e.g. "Part A"), with publication dates between 1978 and 1985. Each part contained a series of "sections", each designated by the respective part letter and by a two-digit serial number (e.g. "Section A01"). These sections are now being republished as separate documents, themselves designated "parts" but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

© ISO 1989

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Textiles — Tests for colour fastness —

Part E04 :

Colour fastness to perspiration

1 Scope

This part of ISO 105 specifies a method for determining the resistance of the colour of textiles of all kinds and in all forms to the action of human perspiration.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 105. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 105 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 105-A01:1989, *Textiles — Tests for colour fastness — Part A01: General principles of testing*.

ISO 105-A02:1987, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*.

ISO 105-A03:1987, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*.

ISO 105-F:1985, *Textiles — Tests for colour fastness — Part F: Standard adjacent fabrics*.

ISO 105-F10:1989, *Textiles — Tests for colour fastness — Part F10: Specification for adjacent fabric: Multifibre*.

3 Principle

Specimens of the textile in contact with adjacent fabrics are treated in two different solutions containing histidine, drained and placed between two plates under a specified pressure in a test device. The specimens and the adjacent fabrics are dried separately. The change in colour of each specimen and the staining of the adjacent fabrics are assessed with the grey scales.

4 Apparatus and reagents

4.1 Test devices, each consisting of a frame of stainless steel into which a weight-piece of mass 5 kg and base of 60 mm × 115 mm is closely fitted, so that a pressure of 12,5 kPa can be applied on test specimens measuring 40 mm × 100 mm placed between glass or acrylic-resin plates measuring about 60 mm × 115 mm × 1,5 mm. The test device shall be constructed so that, if the weight-piece is removed during the test, the pressure of 12,5 kPa remains unchanged (see 8.1 and 8.2).

4.2 Oven, maintained at $37\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$.

4.3 Alkaline solution, freshly prepared, containing, per litre,

0,5 g of *L*-histidine monohydrochloride monohydrate ($\text{C}_6\text{H}_9\text{O}_2\text{N}_3\cdot\text{HCl}\cdot\text{H}_2\text{O}$);

5 g of sodium chloride (NaCl);

either

5 g of disodium hydrogen orthophosphate dodecahydrate ($\text{Na}_2\text{HPO}_4\cdot 12\text{H}_2\text{O}$);

or

2,5 g of disodium hydrogen orthophosphate dihydrate ($\text{Na}_2\text{HPO}_4 \cdot 2\text{H}_2\text{O}$).

The solution is brought to pH 8 with 0,1 mol/l sodium hydroxide solution.

4.4 Acid solution, freshly prepared, containing, per litre,

0,5 g of *L*-histidine monohydrochloride monohydrate ($\text{C}_6\text{H}_9\text{O}_2\text{N}_3 \cdot \text{HCl} \cdot \text{H}_2\text{O}$);

5 g of sodium chloride (NaCl);

2,2 g of sodium dihydrogen orthophosphate dihydrate ($\text{NaH}_2\text{PO}_4 \cdot 2\text{H}_2\text{O}$).

The solution is brought to pH 5,5 with 0,1 mol/l sodium hydroxide solution.

4.5 Adjacent fabrics (see ISO 105-A01:1989, sub-clause 8.3).

Either:

4.5.1 A multifibre adjacent fabric complying with ISO 105-F10.

Or:

4.5.2 Two single-fibre adjacent fabrics, complying with the relevant sections of F01 to F08 of ISO 105-F:1985.

One piece made of the same kind of fibre as that of the textile to be tested, or that predominating in the case of blends, the second piece made of the fibre as indicated in table 1 or, in the case of blends, of the kind of fibre second in order of predominance or as otherwise specified.

Table 1 — Single-fibre adjacent fabrics

If first piece is:	Second piece to be:
cotton	wool
wool	cotton
silk	cotton
linen	wool
viscose	wool
acetate	viscose
polyamide	wool or viscose
polyester	wool or cotton
acrylic	wool or cotton

4.5.3 If required, a non-dyeable fabric (for example, polypropylene).

4.6 Grey scale for assessing change in colour, complying with ISO 105-A02, and **grey scale for assessing staining**, complying with ISO 105-A03.

5 Test specimen

5.1 If the textile to be tested is fabric, either

a) attach a specimen measuring 40 mm × 100 mm to a piece of the multifibre adjacent fabric, also measuring 40 mm × 100 mm, by sewing along one of the shorter sides, with the multifibre fabric next to the face of the specimen; or

b) attach a specimen measuring 40 mm × 100 mm between the two single fibre adjacent fabrics, also measuring 40 mm × 100 mm, by sewing along one of the shorter sides.

5.2 Where yarns or loose fibre is to be tested, take a mass of the yarn or loose fibre approximately equal to one half of the combined mass of the adjacent fabrics, and either

a) place it between a 40 mm × 100 mm piece of the multifibre fabric and a 40 mm × 100 mm piece of the non-dyeable fabric and sew them along all four sides (see ISO 105-A01:1989, sub-clause 9.6); or

b) place it between a 40 mm × 100 mm piece of each of the two specified single-fibre fabrics and sew along all four sides.

6 Procedure

6.1 Lay out the composite specimen smooth in a flat-bottomed dish and cover with the solution. Thoroughly wet one composite specimen in the alkaline solution at pH 8 (4.3) at a liquor ratio of 50 : 1, and allow it to remain in the solution at room temperature for 30 min. Press and move it from time to time to ensure good and uniform penetration of the liquor. Pour off the solution and wipe the excess liquor off the specimen between two glass rods. Then place the composite specimen between two glass or acrylic resin plates, under a pressure of 12,5 kPa. Use separate apparatus for the acid test (4.4).

6.2 Place the test devices (4.1) each containing a composite specimen in the oven (4.2) for 4 h at $37^\circ\text{C} \pm 2^\circ\text{C}$.

6.3 Open out each composite specimen (by breaking the stitching except on one of the shorter sides, if necessary) and dry it by hanging it in air at a temperature not exceeding 60°C , with the two or three parts in contact only at the line of stitching.

6.4 Assess the change in colour of each specimen and the staining of the adjacent fabric(s) with the grey scales (4.5).

7 Test report

The test report shall include the following particulars:

- a) the number and date of this part of ISO 105, i.e. ISO 105-E04:1989;
- b) all details necessary for the identification of the sample tested;
- c) the numerical ratings for change in colour of the specimen in each solution;
- d) if single-fibre adjacent fabrics were used, the numerical rating for staining of each kind of adjacent fabric used;
- e) if a multifibre adjacent fabric was used, the staining of each type of fibre in the multifibre adjacent fabric, and the type of multifibre adjacent fabric used.

8 Notes

8.1 If the dimensions of the composite specimen differ from the size of 40 mm × 100 mm, a weight-piece shall be used such that a pressure of 12,5 kPa is applied to the specimen.

8.2 Other devices may be used provided that the same results are obtained as with the apparatus described above.

8.3 In many cases of cellulosic fibres dyed with direct dyes containing copper, or after treatment with copper salts, the prescribed tests and natural perspiration bring about a removal of copper from the dyeings. This may cause a significant alteration in fastness to light and washing, and it is therefore recommended that this possibility be taken into consideration.

STANDARDSISO.COM : Click to view the full PDF of ISO 105-E04:1989