



Textiles — Tests for colour fastness —

Part G01:

Colour fastness to nitrogen oxides

TECHNICAL CORRIGENDUM 1

Textiles — Essais de solidité des teintures —

Partie G01: Solidité des teintures aux oxydes d'azote

RECTIFICATIF TECHNIQUE 1

Technical corrigendum 1 to International Standard ISO 105-G01:1993 was prepared by Technical Committee ISO/TC 38, Textiles, Subcommittee SC 1, Tests for coloured textiles and colorants.

Page 1

Subclause 4.6

Replace the existing text with the following:

4.6 Urea, solution containing, per litre, 10 g of urea (NH_2CONH_2), buffered to pH 7 by the addition of 0,4 g of sodium dihydrogen orthophosphate dihydrate ($\text{NaH}_2\text{PO}_4 \cdot 2\text{H}_2\text{O}$) and 2,5 g of disodium hydrogen orthophosphate dodecahydrate ($\text{Na}_2\text{HPO}_4 \cdot 12\text{H}_2\text{O}$), and containing 0,1 g or less of a rapid-wetting surface-active agent, for example sodium dioctyl sulfosuccinate

Page 6

Clause B.2

In the sixth line, replace "Close cock 2, open cock 1 ..." with "Close cock 2, open cock 5 ...".