



Textiles — Tests for colour fastness —

Part G02:

Colour fastness to burnt-gas fumes

TECHNICAL CORRIGENDUM 1

Textiles — Essais de solidité des teintures —

Partie G02: Solidité des teintures aux fumées de gaz brûlés

RECTIFICATIF TECHNIQUE 1

Technical corrigendum 1 to International Standard ISO 105-G02:1993 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

Page 2

Subclause 4.6

Replace the existing text with the following:

4.6 Urea, solution containing, per litre, 10 g of urea (NH_2CONH_2), buffered to pH 7 by the addition of 0,4 g of sodium dihydrogen orthophosphate dihydrate ($\text{NaH}_2\text{PO}_4 \cdot 2\text{H}_2\text{O}$) and 2,5 g of disodium hydrogen orthophosphate dodecahydrate ($\text{Na}_2\text{HPO}_4 \cdot 12\text{H}_2\text{O}$), and containing 0,1 g or less of a rapid-wetting surface-active agent, for example sodium dioctyl sulfosuccinate.