
**Preparation of steel substrates before
application of paints and related
products — Specifications for non-
metallic blast-cleaning abrasives —**

**Part 4:
Coal furnace slag**

*Préparation des subjectiles d'acier avant application de peintures et
de produits assimilés — Spécifications pour abrasifs non métalliques
destinés à la préparation par projection —*

Partie 4: Cendres fondues



STANDARDSISO.COM : Click to view the full PDF of ISO 11126-4:2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Designation of abrasives	2
5 Sampling	2
6 Requirements	3
6.1 General requirements	3
6.2 Particular requirements	3
7 Identification and marking	3
8 Information to be supplied by the manufacturer or supplier	3
Bibliography	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*.

This second edition cancels and replaces the first edition (ISO 11126-4:1993), which has been technically revised.

The main changes compared to the previous edition are as follows:

— [Tables 1](#) and [2](#) have been technically revised.

A list of all parts in the ISO 11126 series can be found on the ISO website.

Preparation of steel substrates before application of paints and related products — Specifications for non-metallic blast-cleaning abrasives —

Part 4: Coal furnace slag

WARNING — Equipment, materials and abrasives used for surface preparation can be hazardous. It is important to ensure that adequate instructions are given and that all required precautions are exercised.

1 Scope

This document specifies requirements for coal furnace slag abrasives, as supplied for blast-cleaning processes. It specifies ranges of particle sizes and values for apparent density, Mohs hardness, moisture content, conductivity of aqueous extract and water-soluble chlorides.

The requirements specified in this document apply to abrasives supplied in the "new" condition only. They do not apply to abrasives either during or after use.

Test methods for non-metallic blast-cleaning abrasives are given in the various parts of ISO 11127.

NOTE Although this document has been developed specifically to meet requirements for preparation of steelwork, the properties specified will generally be appropriate for use when preparing other material surfaces, or components, using blast-cleaning techniques. These techniques are described in ISO 8504-2.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11127-1, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 1: Sampling*

ISO 11127-2, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 2: Determination of particle size distribution*

ISO 11127-3, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 3: Determination of apparent density*

ISO 11127-4, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 4: Assessment of hardness by a glass slide test*

ISO 11127-5, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 5: Determination of moisture*

ISO 11127-6, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 6: Determination of water-soluble contaminants by conductivity measurement*

ISO 11127-7, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 7: Determination of water-soluble chlorides*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 coal furnace slag

synthetic mineral blast-cleaning abrasive manufactured, by granulation in water, drying and sieving, with or without mechanical crushing processes, from slag originating when coal is burned in coal-fired power stations

Note 1 to entry: It is basically aluminium silicate.

Note 2 to entry: Slags manufactured by air cooling instead of granulation in water are generally of a different mineral structure and are therefore not covered by this document.

4 Designation of abrasives

Coal furnace slag abrasives shall be identified by "Abrasive ISO 11126" and the abbreviation N/CS indicating non-metallic, coal furnace slag abrasive. This shall be followed, without spaces, by an oblique stroke and then by the symbol G to indicate the required particle shape of the abrasive, when purchased, as grit. The designation shall be completed by numbers denoting the particle size range, in millimetres, required (see Table 1).

EXAMPLE

Abrasive ISO 11126 N/CS/G 0,2-1,4

denotes an abrasive of the non-metallic coal furnace slag type, complying with the requirements of this part of ISO 11126, of initial particle shape grit and particle size range 0,2 mm to 1,4 mm.

This full product designation shall be quoted on all orders.

Table 1 — Particle size distribution

Particle size range ^a		mm	0,2 to 0,5	0,2 to 1	0,2 to 1,4	0,2 to 2	0,2 to 2,8	0,5 to 1	0,5 to 1,4	1,0 to 2	1,4 to 2,8
oversize	Sieve size	mm	0,5	1	1,4	2	2,8	1	1,4	2	2,8
	Residue % (mass fraction)	max.	10	10	10	10	10	10	10	10	10
Nominal size	Sieve size	mm	0,2	0,2	0,2	0,2	0,2	0,5	0,5	1	1,4
	Residue % (mass fraction)	min.	85	85	85	85	85	85	85	85	85
undersize	Sieve size	mm	0,2	0,2	0,2	0,2	0,2	0,5	0,5	1	1,4
	Through-flow % (mass fraction)	max.	5	5	5	5	5	10	10	10	10

^a By agreement between the interested parties, abrasives of different particle size ranges may be mixed together. Details of proportions of nominal size, oversize and undersize shall be specified. The maximum particle size shall not exceed 3,15 mm and the proportion of particles less than 0,2 mm shall not exceed a mass fraction of 5 %.

5 Sampling

Sampling procedures shall be as specified in ISO 11127-1.

6 Requirements

6.1 General requirements

Coal furnace slag abrasives shall be vitreous amorphous materials that absorb no water but may be wetted on the surface only.

Silica in coal furnace slag abrasives shall be present as bonded silicate. The content of free crystalline silica (such as quartz, tridimite or cristobalite) shall not exceed 1 % (mass fraction), as determined by X-ray diffraction.

The material shall be free from corrosive constituents and adhesion-impairing contaminants.

6.2 Particular requirements

Particular requirements for coal furnace slag abrasives shall be as specified in [Table 2](#).

Table 2 — Particular requirements for coal furnace slag abrasives

Property		Requirement	Test method
Particle size range and distribution		See Table 1	ISO 11127-2
Apparent density	kg/m ³ (kg/dm ³)	(2,4 to 2,6) × 10 ³ (2,4 to 2,6)	ISO 11127-3
Mohs hardness ^a		min. 6	ISO 11127-4
Moisture	% (mass fraction)	max. 0,2	ISO 11127-5
Conductivity of aqueous extract	μS/cm	max. 250	ISO 11127-6
Water-soluble chlorides	% (mass fraction)	max. 0,002 5	ISO 11127-7
^a Another method for assessing hardness may be used, together with an appropriate minimum requirement, by agreement between the interested parties.			

7 Identification and marking

All supplies shall be clearly marked or identified using the appropriate designation as specified in [Clause 4](#), either directly or by the accompanying delivery note.

8 Information to be supplied by the manufacturer or supplier

The manufacturer or supplier shall supply, if requested, a test report detailing results for any relevant property as determined by the appropriate method specified in [Table 2](#).

Bibliography

- [1] ISO 8504-2, *Preparation of steel substrates before application of paints and related products — Surface preparation methods — Part 2: Abrasive blast-cleaning*

STANDARDSISO.COM : Click to view the full PDF of ISO 11126-4:2018