
Coal and coke — Calculation of analyses to different bases

*Charbon et coke — Calculs pour les analyses par rapport à différentes
bases*

STANDARDSISO.COM : Click to view the full PDF of ISO 1170:2008



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 1170:2008



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Symbols	1
5 Calculations for coal analyses	2
5.1 Introduction	2
5.2 Procedure	2
5.3 Carbon	2
5.4 Hydrogen	3
5.5 Nitrogen	3
5.6 Sulfur	3
5.7 Oxygen	3
5.8 Chlorine	4
5.9 Volatile matter	4
5.10 Net calorific value	4
6 Calculations for coke analyses	4
7 Table for calculation to different bases	5
Annex A (normative) Mineral matter	6
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1170 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This second edition cancels and replaces the first edition (ISO 1170:1977), which has been technically revised.

STANDARDSISO.COM : Click to view the full PDF of ISO 1170:2008

Coal and coke — Calculation of analyses to different bases

1 Scope

This International Standard gives equations that allow analytical data relating to coal and coke to be expressed on the various different bases in common use. Consideration is given to corrections that can be applied to certain determined values for coal prior to their calculation to other bases.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 602, *Coal — Determination of mineral matter*

ISO 17247, *Coal — Ultimate analysis*

3 Principle

In order to convert an analytical result expressed on one basis to another basis, it is multiplied by a factor calculated from the appropriate formulae (see Table 1) after insertion of the requisite numerical values.

4 Symbols

The symbols employed in the subsequent clauses are as follows, with suffixes (separated by a dot) “ad” (air-dried), “ar” (as-received), “d” (dry), “daf” (dry, ash-free) or “dmmf” (dry, mineral-matter-free) where appropriate.

w_A	ash, expressed as percent mass fraction
w_C	carbon content, expressed as percent mass fraction
w_{Cl}	chlorine content, expressed as percent mass fraction
$w_{Cl.inorg}$	inorganic chlorine content, expressed as percent mass fraction
w_{CO_2}	carbon dioxide content, expressed as percent mass fraction
w_H	hydrogen content, excluding hydrogen in the moisture, but including the hydrogen from water of hydration in minerals, expressed as percent mass fraction
w_{H_2O}	moisture content, expressed as percent mass fraction
w_h	water of hydration in the mineral matter, expressed as percent mass fraction
w_{MM}	mineral matter content, expressed as percent mass fraction (see Annex A)

w_N	nitrogen content, expressed as percent mass fraction
w_O	oxygen content, excluding oxygen in the moisture but including the oxygen from water of hydration in minerals, expressed as percent mass fraction
$w_{S,o}$	organic sulfur content, expressed as percent mass fraction
$w_{S,p}$	pyritic sulfur content, expressed as percent mass fraction
$w_{S,s}$	sulfate sulfur content, expressed as percent mass fraction
$w_{S,T}$	total sulfur content, expressed as percent mass fraction
w_V	volatile matter content, expressed as percent mass fraction
F_{Cl}	national correction factor for the estimation of the inorganic chlorine content
F_h	national correction factor for the estimation of water of hydration
F_{MM}	national correction factor for the estimation of the mineral matter (see Annex A)

5 Calculations for coal analyses

5.1 Introduction

In International Standards covering the analysis of coal, it is generally specified that the determination shall be carried out on an air-dried test sample. However, in making use of these analyses, it is sometimes necessary to express or report the results on some other basis. The bases in common use are “air-dried”, “as-received”, “dry”, “dry, ash-free”, and “dry, mineral-matter-free”.

5.2 Procedure

Any analytical value (except net calorific value) on a particular basis may be converted to any other basis by multiplying it by the appropriate factor calculated from the formulae given in Table 1, after insertion of the requisite numerical values for the symbols (for determination of moisture, see ISO 589 and ISO 11722; for ash, see ISO 1171). However, in some determinations, there is a direct involvement of the mineral matter and, in these cases, it is essential to apply a correction to the air-dried result prior to its calculation to the dry, mineral-matter-free basis. This correction is dependent on the nature, as well as the quantity, of the mineral matter present and, for any given sample, the formula recommended by the national standards organization of the country of origin of the sample should be used and should be quoted in full, together with the analysis. All the determinations that may be expressed on the dry, mineral-matter-free basis are considered individually below.

If it is necessary to calculate an analytical result expressed on the dry, mineral-matter-free basis back to any other basis, then it is essential that any correction deducted during the application of any Equations (1) to (10) inclusive be added back to the dry, mineral-matter-free value before applying the appropriate formula from Table 1.

5.3 Carbon

Total carbon, as determined in coal, is comprised of both organic carbon and carbonate carbon in the mineral matter. It is reported on the air-dried basis (see ISO 609, ISO 625, or ISO/TS 12902). In order to convert the total carbon content as analyzed to a dry, mineral-matter-free basis, subtract the carbonate carbon before the conversion as given in Equation (1):

$$w_{C,dmmf} = (w_{C,ad} - 0,273 w_{CO_2,ad}) \times \frac{100}{100 - (w_{H_2O,ad} + w_{MM,ad})} \quad (1)$$

5.4 Hydrogen

The hydrogen content reported on the air-dried basis includes the hydrogen of the coal substance and the hydrogen present (as water) in the mineral matter (see ISO 609, ISO 625 and ISO/TS 12902). The hydrogen present as moisture in the air-dried sample shall be deducted before reporting $w_{H.ad}$. Before calculating the hydrogen of the coal substance to a dry, mineral-matter-free basis, it is also necessary to deduct the hydrogen of the mineral matter as given in Equation (2):

$$w_{H.dmmf} = (w_{H.ad} - \frac{w_{h.ad}}{9}) \times \frac{100}{100 - (w_{H_2O.ad} + w_{MM.ad})} \quad (2)$$

Since the water of hydration in the mineral matter cannot readily be determined, it is generally estimated from a knowledge of the minerals likely to be present and the total mineral matter content as given in Equation (3):

$$w_{h.ad} = F_h \times w_{A.ad} \quad (3)$$

where F_h is a national factor, depending of the actual type of coal. If no national factor is available, a value of F_h equal to 0,1 may be used to achieve an approximate result.

5.5 Nitrogen

The nitrogen content is reported on the air-dried basis (see ISO 333). There is no nitrogen in the mineral state normally associated with coal, and the calculation to a dry, mineral-matter-free-basis is as given in Equation (4):

$$w_{N.dmmf} = w_{N.ad} \times \frac{100}{100 - (w_{H_2O.ad} + w_{MM.ad})} \quad (4)$$

5.6 Sulfur

The total sulfur content, $w_{S,T}$, as reported on the air-dried basis (see ISO 334, ISO 351 or ISO 19579), includes organic sulfur, $w_{S,o}$, pyritic sulfur, $w_{S,p}$, and sulfate sulfur, $w_{S,s}$. The pyritic sulfur and the sulfate sulfur are determined and the organic sulfur is obtained by difference (see ISO 157). In order to convert the total sulfur content to a dry, mineral-matter-free basis, subtract the content of pyritic and sulfate sulfur as given in Equation (5):

$$w_{S,o.dmmf} = (w_{S,T.ad} - w_{S,p.ad} - w_{S,s.ad}) \times \frac{100}{100 - (w_{H_2O.ad} + w_{MM.ad})} \quad (5)$$

5.7 Oxygen

Although oxygen is a significant component of coal and coke, there has been insufficient demand for its direct determination to justify continuation of an ISO standard.

The oxygen content is calculated by difference on an air-dried basis as given in Equation (6), which is taken from ISO 17247:

$$w_{Oa.d} = 100 - (w_{C.ad} - w_{H.ad} + w_{N.ad} + w_{S,T.ad} + w_{A.ad} + w_{H_2O.ad}) \quad (6)$$

The calculated "oxygen by difference" includes the oxygen in the coal substance, in the carbonate minerals (as carbon dioxide) and in the water of hydration of the mineral matter.

The oxygen content on a dry, mineral-matter-free basis can be calculated as given in Equation (7):

$$w_{O.dmmf} = 100 - (w_{C.dmmf} + w_{H.dmmf} + w_{N.dmmf} + w_{S.T.dmmf}) \quad (7)$$

It is necessary to exercise caution with the estimated result derived for "oxygen by difference" as it incorporates the summation of errors in the results of the other elements.

5.8 Chlorine

The chlorine content is reported on the air-dried basis (see ISO 587) and includes chlorine from the mineral matter and chlorine combined with the coal substance. It is, therefore, necessary to subtract the inorganic chlorine before calculating to the dry, mineral-matter-free basis as given in Equation (8):

$$w_{\text{Cl.dmmf}} = (w_{\text{Cl.ad}} - w_{\text{Cl.inorg.ad}}) \times \frac{100}{100 - (w_{\text{H}_2\text{O.ad}} + w_{\text{MM.ad}})} \quad (8)$$

The content of inorganic chlorine may be calculated using a national factor, F_{Cl} , as given in Equation (9):

$$w_{\text{Cl.inorg.ad}} = F_{\text{Cl}} \times w_{\text{Cl.ad}} \quad (9)$$

For higher rank coal, no chlorine combined with the coal matter has been found^[1]. Therefore, a value $F_{\text{Cl}} = 1$ may be used for these coals.

5.9 Volatile matter

The mineral matter associated with a sample also loses mass under the conditions of the volatile matter determination (see ISO 562), the magnitude of the loss being dependent on both the nature and the quantity of the minerals present.

Correction is, therefore, necessary prior to the calculation of the volatile matter to a dry, mineral-matter-free basis to take account of losses of sulfur, water of hydration, carbon dioxide and chlorine as given in Equation (10):

$$w_{\text{V.dmmf}} = (w_{\text{V.ad}} - w_{\text{CO}_2.\text{ad}} - 0.5 \times w_{\text{S.p.ad}} - w_{\text{h.ad}} - w_{\text{Cl.ad}}) \times \frac{100}{100 - (w_{\text{H}_2\text{O.ad}} + w_{\text{MM.ad}})} \quad (10)$$

The loss of mass from pyritic sulfur during devolatilization is approximately half of the sulfur bound in pyrite.

5.10 Net calorific value

The calculation of the net calorific value is dealt with in detail in ISO 1928, which, however, does not include calculation to a dry, mineral-matter-free basis as this basis is not of importance for net calorific values.

NOTE Net calorific values cannot be converted to any other basis by direct multiplying with the appropriate formulas in Table 1 as net calorific values includes a correction for the heat of vaporization related to the actual moisture content.

6 Calculations for coke analyses

Coke analyses may be expressed on the "air-dried", "as-received", "dry" and "dry, ash-free" bases, and these values (except for net calorific value) are calculated by the use of the appropriate formulae given in Table 1, after insertion of requisite numerical values for the symbols (for determination of moisture, see ISO 579 and ISO 687; for ash, see ISO 1171).

It is not proposed at present to recommend the calculation for the conversion of analytical results for coke to a dry, mineral-matter-free basis.

7 Table for calculation to different bases

Table 1 — Formulae for calculation of results to different bases

Basis of value given	Basis of value wanted				
	As analysed (air-dried) (ad)	As received ^a (ar)	Dry (d)	Dry, ash free (daf)	Dry, mineral matter free (dmmf)
As analysed (air-dried) (ad)	—	$\frac{100 - w_{\text{H}_2\text{O}.ar}}{100 - w_{\text{H}_2\text{O}.ad}}$	$\frac{100}{100 - w_{\text{H}_2\text{O}.ad}}$	$\frac{100}{100 - (w_{\text{H}_2\text{O}.ad} + w_{\text{A}.ad})}$	$\frac{100}{100 - (w_{\text{H}_2\text{O}.ad} + w_{\text{MM}.ad})}$
As received (ar)	$\frac{100 - w_{\text{H}_2\text{O}.ad}}{100 - w_{\text{H}_2\text{O}.ar}}$	—	$\frac{100}{100 - w_{\text{H}_2\text{O}.ar}}$	$\frac{100}{100 - (w_{\text{H}_2\text{O}.ar} + w_{\text{A}.ar})}$	$\frac{100}{100 - (w_{\text{H}_2\text{O}.ar} + w_{\text{MM}.ar})}$
Dry (d)	$\frac{100 - w_{\text{H}_2\text{O}.ad}}{100}$	$\frac{100}{100 - (M_{ad} + A_{ad})}$	—	$\frac{100}{100 - w_{\text{A}.d}}$	$\frac{100}{100 - w_{\text{MM}.d}}$
Dry, ash-free (daf)	$\frac{100 - (w_{\text{H}_2\text{O}.ad} + w_{\text{A}.ad})}{100}$	$\frac{100 - (w_{\text{H}_2\text{O}.ar} + w_{\text{A}.ar})}{100}$	$\frac{100 - w_{\text{A}.d}}{100}$	—	$\frac{100 - w_{\text{A}.d}}{100 - w_{\text{MM}.d}}$
Dry, mineral-matter-free (dmmf)	$\frac{100 - (w_{\text{H}_2\text{O}.ad} + w_{\text{A}.ad})}{100}$	$\frac{100 - (w_{\text{H}_2\text{O}.ar} + w_{\text{MM}.ar})}{100}$	$\frac{100 - w_{\text{MM}.d}}{100}$	$\frac{100 - w_{\text{MM}.d}}{100 - w_{\text{A}.d}}$	—
^a Note that the formulae given for calculating results for the “as received” basis may be used to calculate them for any other moisture basis, for example moisture-holding capacity or bed moisture.					