

---

---

**Solid mineral fuels — Hard coal —  
Determination of moisture in the  
general analysis test sample by  
drying in nitrogen**

*Combustibles minéraux solides — Houille — Détermination  
de l'humidité de l'échantillon pour analyse par dessiccation en  
atmosphère d'azote*



STANDARDSISO.COM : Click to view the full PDF of ISO 11722:2013



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

|                                                               |           |
|---------------------------------------------------------------|-----------|
| <b>Foreword</b> .....                                         | <b>iv</b> |
| <b>Introduction</b> .....                                     | <b>v</b>  |
| <b>1 Scope</b> .....                                          | <b>1</b>  |
| <b>2 Normatives references</b> .....                          | <b>1</b>  |
| <b>3 Terms and definitions</b> .....                          | <b>1</b>  |
| <b>4 Principle</b> .....                                      | <b>1</b>  |
| <b>5 Reagent</b> .....                                        | <b>1</b>  |
| <b>6 Apparatus</b> .....                                      | <b>1</b>  |
| <b>7 Preparation of the test sample</b> .....                 | <b>2</b>  |
| <b>8 Procedure</b> .....                                      | <b>2</b>  |
| <b>9 Expression of results</b> .....                          | <b>2</b>  |
| <b>10 Precision</b> .....                                     | <b>2</b>  |
| 10.1 Repeatability limit.....                                 | 2         |
| 10.2 Reproducibility limit.....                               | 2         |
| <b>11 Test report</b> .....                                   | <b>3</b>  |
| <b>Annex A (informative) Example of a suitable oven</b> ..... | <b>4</b>  |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. [www.iso.org/directives](http://www.iso.org/directives)

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. [www.iso.org/patents](http://www.iso.org/patents)

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

The committee responsible for this document is ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This second edition cancels and replaces the first edition (ISO 11722:1999), of which it constitutes a minor revision.

## Introduction

The determination of the moisture in the general analysis test sample is required to correct the results of certain analytical determinations, e.g. volatile matter and hydrogen, for the effect of water in the determination and to allow all determinations to be corrected to dry basis.

Since hard coal is hygroscopic, its moisture will vary with change of humidity of the atmosphere and the moisture in the general analysis test sample should therefore be determined whenever portions are weighed out for other analytical determinations. If test portions for several analytical determinations are weighed out at the same time, a single simultaneous moisture determination will suffice to correct those analyses.

STANDARDSISO.COM : Click to view the full PDF of ISO 11722:2013

STANDARDSISO.COM : Click to view the full PDF of ISO 11722:2013

# Solid mineral fuels — Hard coal — Determination of moisture in the general analysis test sample by drying in nitrogen

## 1 Scope

This International Standard specifies a method for determining the moisture in the general analysis test sample of hard coal by drying in nitrogen.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1213-2, *Solid mineral fuels — Vocabulary — Part 2: Terms relating to sampling, testing and analysis*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1213-2 apply.

## 4 Principle

A known mass of the coal is heated in a stream of nitrogen at a temperature between 105 °C and 110 °C and maintained at this temperature until it is constant in mass. The moisture content is calculated from the loss in mass of the coal.

## 5 Reagent

Nitrogen, moisture-free, having a volume fraction of oxygen of less than 30 µl/l.

Commercially available nitrogen with a water content of less than 5 µl/l does not require further drying.

## 6 Apparatus

**6.1** Analytical balance, capable of weighing to the nearest 0,1 mg.

**6.2** Oven, capable of being controlled at a temperature of 105 °C to 110 °C and with provision for the nitrogen to pass through it at a flow-rate of approximately 15 times the oven volume per hour and of lowest practical volume, i.e. minimum free space.

NOTE An example of a suitable oven is given in [Annex A](#).

**6.3** Weighing dish, shallow, of glass or of corrosion-resistant metal, with well-fitting covers, of such a size that the coal layer does not exceed 0,20 g/cm<sup>2</sup>.

**6.4** Cooling vessel, e.g. desiccator, without desiccant, containing a metal plate, preferably of aluminium or copper. The vessel may be provided with a means to pass nitrogen through it during the cooling period.

## 7 Preparation of the test sample

The coal used for the determination of mass fraction moisture is the general analysis test sample. Ensure that the mass fraction moisture in the sample is in equilibrium with the laboratory atmosphere, exposing it, if necessary, in a thin layer for the minimum time required to achieve equilibrium.

Before commencing the determination, thoroughly mix the equilibrated test sample for at least 1 min, preferably by mechanical means.

## 8 Procedure

Weigh, on an analytical balance (6.1), a clean, dry, empty weighing dish (6.3) with its cover to the nearest 0,1 mg. Add  $1 \text{ g} \pm 0,1 \text{ g}$  of the coal sample in an even layer and reweigh. Heat the uncovered dish in the oven (6.2) at 105 °C to 110 °C for at least 60 min while passing nitrogen through at approximately 15 times the oven volume per hour. Do not open the oven door during the drying period.

When the drying period is complete, remove the dish with the dried sample from the oven and replace the cover immediately. If the size of the oven allows this, replace the cover while the dish is still in the oven. Allow the dish to cool on a thick metal plate for 10 min. At the end of the 10 min cooling period, transfer the dish to a cooling vessel (6.4) and allow to cool to room temperature. As soon as room temperature is reached, reweigh to the nearest 0,1 mg.

NOTE If a cooling vessel with nitrogen flow is used, the dish can be transferred directly without cooling on a metal plate.

If there is any doubt that drying is not complete, reheat at 105 °C to 110 °C for further 30 min period until any change in mass does not exceed 1 mg.

## 9 Expression of results

The mass fraction of moisture in the hard coal as analysed,  $w_M$ , in percent, is given by the following formula:

$$w_M = \frac{m_2 - m_3}{m_2 - m_1} \times 100$$

where

$m_1$  is the mass, in grams, of empty dish plus cover;

$m_2$  is the mass, in grams, of dish plus cover plus coal before heating;

$m_3$  is the mass, in grams, of dish plus cover plus coal after heating.

Report the result, as the mean of duplicate determinations, to the nearest 0,1 % mass fraction.

## 10 Precision

### 10.1 Repeatability limit

The results of duplicate determinations (carried out over a short period of time, but not simultaneously) in the same laboratory, by the same operator, with the same apparatus on two representative portions taken from the same analysis sample, should not differ by more than the values shown in [Table 1](#).

### 10.2 Reproducibility limit

Since the humidity conditions in different laboratories vary, it is not practical to quote a limiting value for reproducibility.



**Table 1 — Precision**

| <b>Mass fraction of moisture</b><br>% | <b>Maximum acceptable differences between results</b><br>Repeatability limit |
|---------------------------------------|------------------------------------------------------------------------------|
| Less than 5                           | 0,10                                                                         |
| Equal to or more than 5               | 0,15                                                                         |

## 11 Test report

The test report shall include the following information:

- a) reference to this International Standard, i.e. ISO 11722;
- b) the identification of the sample tested;
- c) the results of the determination.

STANDARDSISO.COM : Click to view the full PDF of ISO 11722:2013