
**Heat-resistant cast steels and alloys for
general applications**

Aciers et alliages moulés réfractaires destinés à des applications générales



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 11973:1999

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 11973 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 11, *Steel castings*.

Heat-resistant cast steels and alloys for general applications

1 Scope

This International Standard specifies chemical composition and mechanical properties of cast steels for heat resistant service.

2 Normative reference

The following normative document contains provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the normative document indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 4990:1986, *Steel castings — General technical delivery conditions*.

3 General conditions for delivery

Materials furnished in conformity with this International Standard shall conform to the applicable requirements of ISO 4990 including the supplementary requirements that are indicated on the inquiry and purchase order.

4 Heat treatment

GX40CrSi13, GX40CrSi17, GX30CrSi7, GX40CrSi24, GX40CrSi28 and GX130CrSi29 may be annealed at a temperature of 800 °C to 850 °C. If required, GX30CrSi7 may also be supplied in the as-cast condition. Other grades produced to this International Standard do not require heat treatment. If heat treatment is required, the treatment shall be established by mutual agreement between the manufacturer and the purchaser, and shall be specified in the purchase contract.

5 Chemical requirements

Alloys shall conform to the chemical requirements prescribed in Table 1.

6 Mechanical requirements

Mechanical testing at room temperature shall be performed when agreed upon between the manufacturer and purchaser in which case the material shall conform to the requirements listed in Table 2.

7 Maximum use temperature

Limited information on maximum use temperatures are included in Table 2. These values are intended to allow comparison of grades. The actual conditions of service must be considered when selecting a grade including the composition of the environment and service mechanical loading.

8 Supplementary requirements

A list of standardized supplementary requirements for use on the option of the purchaser is included in ISO 4990. Those which are ordinarily considered suitable for use with this specification are given below. The details of these are listed in ISO 4990. Others, whether or not in ISO 4990, may be used with this specification upon agreement between the manufacturer and the purchaser.

- 9.1.2 Reporting of the steel making process
- 9.1.3 Agreed manufacturing procedure
- 9.3 Chemical analysis for residual elements
- 9.8.1 Prior agreement relating to major repair welds
- 9.8.2 Weld maps (Sketches)
- 9.9.1 Liquid penetrant inspection
- 9.9.3 Radiographic inspection
- 9.9.4 Ultrasonic inspection (not for austenitic castings)

Table 1 — Chemical composition, % (m/m)

Grade	C	Si	Mn	P max.	S max.	Cr	Mo	Ni	Others
GX30CrSi7	0,20 0,35	1,0 2,5	0,5 1,0	0,04	0,04	6 8	0,5	0,5	
GX40CrSi13	0,3 0,5	1,0 2,5	0,5 1,0	0,04	0,03	12 14	0,5	1	
GX40CrSi17	0,3 0,5	1,0 2,5	0,5 1,0	0,04	0,03	16 19	0,5	1	
GX40CrSi24	0,3 0,5	1,0 2,5	0,5 1,0	0,04	0,03	23 26	0,5	1	
GX40CrSi28	0,3 0,5	1,0 2,5	0,5 1,0	0,04	0,03	27 30	0,5	1	
GX130CrSi29	1,2 1,4	1,0 2,5	0,5 1,0	0,04	0,03	27 30	0,5	1	
GX25CrNiSi18-9	0,15 0,35	1,0 2,5	2	0,04	0,03	17 19	0,5	8 10	
GX25 CrNiSi 20-14	0,15 0,35	1,0 2,5	2	0,04	0,03	19 21	0,5	13 15	
GX40CrNiSi22-10	0,3 0,5	1,0 2,5	2	0,04	0,03	21 23	0,5	9 11	
GX40CrNiSiNb24-24	0,25 0,50	1,0 2,5	2	0,04	0,03	23 25	0,5	23 25	Nb 1,2-1,8
GX40CrNiSi25-12	0,3 0,5	1,0 2,5	2	0,04	0,03	24 27	0,5	11 14	
GX40CrNiSi25-20	0,3 0,5	1,0 2,5	2	0,04	0,03	24 27	0,5	19 22	
GX40CrNiSi27-4	0,3 0,5	1,0 2,5	1,5	0,04	0,03	25 28	0,5	3 6	
GX40NiCrCo20-20-20	0,35 0,60	1,0	2	0,04	0,03	19 22	2,5 3,0	18 22	Co 18-22 W 2-3
GX10NiCrNb31-20	0,05 0,12	1,2	1,2	0,04	0,03	19 23	0,5	30 34	Nb 0,8-1,5
GX40NiCrSi35-17	0,3 0,5	1,0 2,5	2	0,04	0,03	16 18	0,5	34 36	
GX40NiCrSi35-26	0,3 0,5	1,0 2,5	2	0,04	0,03	24 27	0,5	33 36	

Table 1 (continued)

Grade	C	Si	Mn	P max.	S max.	Cr	Mo	Ni	Others
GX40NiCrSiNb35-26	0,3 0,5	1,0 2,5	2	0,04	0,03	24 27	0,5	33 36	Nb 0,8-1,8
GX40NiCrSi38-19	0,3 0,5	1,0 2,5	2	0,04	0,03	18 21	0,5	36	
GX40NiCrSiNb38-19	0,3 0,5	1,0 2,5	2	0,04	0,03	18 21	0,5	36 39	Nb 1,2-1,8
GX45NiCrWSi48-28-5	0,35 0,55	1,0 2,5	1,5	0,04	0,03	27 30		47 50	W 4-6
GX10NiCrNb50-50	0,1	0,5	0,5	0,02	0,02	47 52	0,5	^a	N 0,16 N+C 0,2 Nb 1,4-1,7
GX50NiCr52-19	0,4 0,6	0,5 2,0	1,5	0,04	0,03	16 21	0,5	50 55	
GX50NiCr65-15	0,35 0,65	2	1,3	0,04	0,03	13 19		64 69	
GX45NiCrCoW35-25-15-5	0,44 0,48	1 2	2	0,04	0,03	24 26		33 37	W 4-6 Co 14-16
GX30CoCr50-28	0,5	1	1	0,04	0,03	25 30	0,5	1	Co 48-52-0 Fe 20 max.
NOTE A single value is the maximum limit.									
^a Balance									