



INTERNATIONAL STANDARD ISO 11997-1:1998
TECHNICAL CORRIGENDUM 1

Published 1998-10-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Paints and varnishes — Determination of resistance to cyclic corrosion conditions —

Part 1:

Wet (salt fog)/dry/humidity

TECHNICAL CORRIGENDUM 1

Peintures et vernis — Détermination de la résistance aux conditions de corrosion cyclique —

Partie 1: Brouillard salin/sécheresse/humidité

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to International Standard ISO 11997-1:1998 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

Page 3

Subclause 6.4

After “Drying-air supply”, add “of (50 ± 20) % relative humidity”.

Page 9

Clause C.2

In steps 2 and 5, add in the “Notes” column “Air purge (see 6.4)”.