
**Plastics pipes and fittings — Equipment
for fusion jointing polyethylene
systems —**

**Part 1:
Butt fusion**

*Tubes et raccords en matières plastiques — Appareillage pour
l'assemblage par soudage des systèmes en polyéthylène —*

Partie 1: Soudage bout à bout



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 12176-1:2006

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Design configurations	3
5 Chassis and clamps	3
5.1 General.....	3
5.2 Guide elements	4
6 Interface force transmission.....	6
6.1 General.....	6
6.2 Manual systems	7
6.3 Hydraulic and pneumatic systems.....	7
6.4 Electric systems.....	7
6.5 Performance	7
7 Planing tool	8
7.1 General.....	8
7.2 Performance	8
8 Heating plate	8
8.1 General.....	8
8.2 Dimensions.....	9
8.3 Materials and surface finish	9
8.4 Heating system	10
8.5 Performance	10
9 Power supply.....	11
10 Test methods.....	11
10.1 Chassis and clamps	11
10.2 Planing tool and check of gap after planing	12
10.3 Heating plate	12
11 Auxiliary equipment	16
12 Maintenance	16
13 Marking on the butt fusion machine	16
14 Other information to be provided by the manufacturer	16
Annex A (normative) Additional performance requirements for butt fusion machines with automatic controllers	17
Annex B (informative) Type classification scheme	18
Bibliography	21

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12176-1 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastics pipes and fittings for the supply of gaseous fuels*.

This second edition cancels and replaces the first edition (ISO 12176-1:1998), which has been technically revised.

ISO 12176 consists of the following parts, under the general title *Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems*:

- *Part 1: Butt fusion*
- *Part 2: Electrofusion*
- *Part 3: Operator's badge*
- *Part 4: Traceability coding*

Plastics pipes and fittings — Equipment for fusion jointing polyethylene systems —

Part 1: Butt fusion

1 Scope

This part of ISO 12176 specifies the general characteristics of, and performance requirements for, equipment for butt fusion jointing of polyethylene (PE) piping systems using electrically powered heater plates.

It is applicable to mechanical and pressure-activated equipment for butt fusion jointing PE pipes and fittings either intended to be used for the supply of gaseous fuels, conforming to ISO 4437 and ISO 8085-2, or intended for the conveyance of water for human consumption (including raw water prior to treatment) and for the conveyance of water for general purposes, conforming to ISO 4427-2 and ISO 4427-3.

The normal ambient-temperature range in which the butt fusion machine is intended to operate is $-10\text{ }^{\circ}\text{C}$ to $+40\text{ }^{\circ}\text{C}$. Use outside this temperature range will need to be agreed between the user and the supplier of the machine.

Butt fusion machines with an automatic controller are subject to additional requirements as given in Annex A.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4287, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Terms, definitions and surface texture parameters*

ISO 4427-2¹⁾, *Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 2: Pipes*

ISO 4427-3¹⁾, *Plastics piping systems — Polyethylene (PE) pipes and fittings for water supply — Part 3: Fittings*

ISO 4437, *Buried polyethylene (PE) pipes for the supply of gaseous fuels — Metric series — Specifications*

1) To be published. (Revision, in parts, of ISO 4427:1996)

ISO 8085-2, *Polyethylene fittings for use with polyethylene pipes for the supply of gaseous fuels — Metric series — Specifications — Part 2: Spigot fittings for butt fusion, for socket fusion using heated tools and for use with electrofusion fittings*

ISO 11414, *Plastics pipes and fittings — Preparation of polyethylene (PE) pipe/pipe or pipe/fitting test piece assemblies by butt fusion*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

base framework

self-supporting entity composed of two or more guides and pipe clamps

NOTE It provides the mechanism for heating and fusing the pipes and/or fittings.

3.2

frictional resistance of the butt fusion machine

force necessary to overcome friction in the whole mechanism

NOTE See 6.1.

3.3

peak drag

friction at the point at which movement is initiated

3.4

dynamic drag

friction occurring during movement

3.5

nominal outside diameter

d_n
numerical designation of size which is common to all components in a thermoplastics piping system other than flanges and components designated by thread size

NOTE It is a convenient round number for reference purposes.

[ISO 161-1:1996, definition 3.1]

3.6

nominal wall thickness

e_n
numerical designation of the wall thickness of a component, which is a convenient round number approximately equal to the manufacturing dimension in millimetres

3.7

drag compensation

ability of the butt fusion machine to overcome mechanical and frictional forces, as well as forces caused by operating on site, in order to achieve and maintain the fusion parameters specified for the pipe

4 Design configurations

To conform to the requirements of this part of ISO 12176, butt fusion machines may have different design configurations, as follows:

- a mechanical linkage system for force generation;
- a hydraulic hand-pump system for force generation;
- a semi-automatic externally powered system for force generation (manual preset of pressure);
- a semi-automatic system incorporating a device for monitoring and recording the fusion parameters;
- an automatic system that controls and records the fusion parameters.

Machines are generally designed for well-defined ranges of diameters, SDR ratios and fusion cycles.

Each component of the machine shall conform to relevant national safety regulations.

Machines which record fusion data shall be capable of transferring the data for further use.

5 Chassis and clamps

5.1 General

The butt fusion machine shall be as maintenance-free as possible.

The base framework of the butt fusion machine shall provide rigidity and stability without unnecessary weight.

The butt fusion machine shall be sufficiently robust to withstand normal field use.

The chassis shall provide facilities for the alignment of and relative movement between pipes and/or fittings.

The butt fusion machine shall incorporate a facility for supporting the heating plate and planing tool when in use. This support shall not affect transmission of interface forces across the heating plate and shall not prevent proper alignment of the heating plate during the heating operation.

The butt fusion machine shall be capable of making satisfactory joints at ambient temperature and under normal worksite conditions with pipes and fittings at extremes of dimensional tolerances.

With butt fusion machines designed for use in narrow trenches, the design and construction of the clamps shall enable the butt fusion machine to be removed from the trench after fusion without damaging the PE pipe.

The base framework shall be fitted with a minimum of two clamps, one fixed and one moveable, to position the PE pipes during the fusion cycle. These clamps shall be designed to enable the pipes to be positioned or removed quickly.

The clamps shall grip the circumference of the pipes and fittings and shall be designed and dimensioned to avoid damage to the pipe or fitting surfaces.

For safety reasons, the clamp jaws should preferably be designed so that they cannot close to less than a certain minimum distance apart.

No adjustment of the centreline of either pipe shall be required after changing the relevant parts to accommodate different pipe sizes. The clamps, inserts and liners shall not damage the pipe or fitting.

Clamps and/or liners for each pipe size should preferably be interchangeable between similar machines made by the same manufacturer.

The maximum number of removable clamping layers shall be three for machines for pipe diameters up to and including $d_n = 400$ mm, and four for machines for pipe diameters above $d_n = 400$ mm.

Operating instructions shall be available.

5.2 Guide elements

5.2.1 General

The sliding surfaces of the guide elements shall be protected from corrosion, e.g. by hard chromium plate.

The design of the butt fusion machine shall allow the heating plate to be removed and the pipe ends to be closed after heating, without damaging the heated surfaces, within a maximum time as given in Table 1.

Table 1 — Maximum time for removing the heating plate

Nominal wall thickness e_n mm	Maximum time t_{max} s
$e_n \leq 4,5$	5
$4,5 < e_n \leq 7$	$5 \leq t_{max} \leq 6$
$7 < e_n \leq 12$	$6 \leq t_{max} \leq 8$
$12 < e_n \leq 19$	$8 \leq t_{max} \leq 10$
$19 < e_n \leq 26$	$10 \leq t_{max} \leq 12$
$26 < e_n \leq 37$	$12 \leq t_{max} \leq 16$
$37 < e_n \leq 50$	$16 \leq t_{max} \leq 20$
$50 < e_n \leq 70$	$20 \leq t_{max} \leq 25$

The clamp alignment system shall provide the frictional resistance necessary to resist the jointing forces at extreme temperatures.

5.2.2 Rigidity under pressure

The butt fusion machine shall provide rigidity and stability. This shall be evaluated by determining it after trimming the gap between the pipe ends, when they are in contact. When measured in accordance with 10.3.4, the gap between Sp1 and Sp2 (see Figure 5) shall conform to Table 2.

Table 2 — Maximum gap

Nominal outside diameter d_n mm	Maximum gap between pipe ends mm
$d_n \leq 250$	0,3
$250 < d_n \leq 400$	0,5
$400 < d_n \leq 630$	1
$630 < d_n$	0,2 % of d_n

5.2.3 Rigidity under bending

The clamp support and bearing system shall be sufficiently rigid to maintain axial alignment to within 0,2 mm over its entire length of travel when tested in accordance with 10.1.2.1.

Misalignment of supported pipes shall not exceed 0,5 mm when determined in accordance with 10.1.2.2.


When the pipe supports are removed (see Figure 1), the additional bending of the butt fusion machine chassis and clamps shall not result in a deflection greater than the values given in Table 3.

Table 3 — Maximum deflection (to be tested with SDR 17,6 or SDR 17 pipes)


Nominal outside diameter d_n mm	Maximum deflection mm
< 225	0,5
250	1
315	2
400	3
500	4
630	5
800	7
1 000	9
1 200	11
1 600	15

5.2.4 Re-rounding action

The clamp alignment system shall have a re-rounding action on the pipe such that any out-of-roundness at the pipe end does not exceed 5 % of the pipe wall thickness and any mismatch of the pipe ends does not exceed 10 % of the wall thickness, when the test for out-of-roundness is carried out in accordance with 10.1.1.



a) Support rollers present



b) Support rollers removed

Key

- 1 clamp
- 2 pipe
- 3 support roller

- a Gap at upper measurement position.
- b Gap at lower measurement position.

Figure 1 — Gap between pipes when bent

6 Interface force transmission

6.1 General

All types of operating system are acceptable (e.g. manual, hydraulic, pneumatic, electric), provided they meet the requirements of this part of ISO 12176.

Pipe-to-pipe interface forces generated during the jointing cycle shall either be measured directly or, alternatively, means shall be provided to determine the interface force indirectly from the measurement of

appropriate machine-operating parameters which take into account the force transfer efficiency and frictional resistance of the machine.

In the case of machines with fluid power rams, the force may be indicated in terms of the applied cylinder pressure.

For such machines, a specific calibration table shall be provided that gives the relationship between the real interface force and the pressure indicated by the manometer (pressure gauge). The pressure gauge shall be calibrated. The accuracy of the pressure gauge shall be 1 % of full scale.

6.2 Manual systems

Mechanically operated equipment shall have the following features:

- the moving clamp shall be capable of continuous and steady displacement;
- a system for verifying the forces applied during the fusion cycle;
- a locking system to maintain the fusion force (fusion machines for pipes of $d_n < 63$ mm are not required to have such a locking system).

6.3 Hydraulic and pneumatic systems

The butt fusion machine shall be capable of maintaining the required interface pressure throughout each stage of the jointing cycle. Where the fluid pressure is generated by a manually operated pump, the pump shall be capable of single-person operation to meet all force and time requirements of the jointing cycle for the range of pipe sizes for which the butt fusion machine is designed.

The hydraulic system shall be capable of exerting the required force on the pipe or fitting ends as long as necessary.

The pressure indication display shall be clear and easily readable from a normal working distance.

The hydraulic system shall be protected against overpressure.

National standards shall apply for the construction of pressure vessels.

6.4 Electric systems

The butt fusion machine shall be capable of maintaining the required interface force throughout each stage of the jointing cycle.

The electric system shall be capable of exerting the required force on the pipe or fitting ends as long as necessary.

The force indication display shall be clear and easily readable from a normal working distance.

National standards shall apply for the construction and safety of electric systems.

6.5 Performance

For peak drag compensation, the butt fusion machine shall have a minimum reserve of 30 % of the fusion force specified for the maximum pipe diameter and wall thickness and the fusion cycle for which the machine has been designed.

The maximum permitted variation in the frictional resistance of the butt fusion machine, with the moving clamp in any position, shall be less than 10 %.

The design of the chassis, clamps and planing tool shall ensure sufficient fusion force and displacement after planing the pipe and/or fitting ends to assure proper fusion, taking into account the simultaneous action of the various external forces, e.g. drag compensation, frictional resistance, clamp motion.

7 Planing tool

7.1 General

The planing tool shall be a double-sided surface planer, powered by hand or by electrical, hydraulic or pneumatic power, and shall establish clean, flat, parallel mating surfaces of the pipe and fitting ends, perpendicular to the centreline of the pipe, in preparation for heating.

The design of the planing tool shall ensure that cut material is deflected away from the cut face, the planing tool and the bore of the pipe or fitting. The swarf produced shall be visible to the operator, so that completion of planing can be recognized.

Planing tools shall be interchangeable between any butt fusion machines of the size and type for which they were designed. They shall be suitable for planing the complete range of pipe sizes and materials for which the butt fusion machine is designed.

The cutting blades shall be removable.

Provision shall be made to prevent the planing of the pipe/fitting end beyond the limit needed for a good fusion joint.

7.2 Performance

The planing tool shall operate on both sides and produce a smooth cut on each fusion face so that the maximum gap between fusion faces, when measured in accordance with 10.2, shall not exceed that permitted in Table 2.

8 Heating plate

8.1 General

The heating plate shall establish a satisfactory melt or molten condition of the pipe and/or fitting ends in preparation for fusion. The heating plate shall be equipped with a temperature control system.

Heating plates shall be interchangeable between any butt fusion machines of the size and type for which they were designed.

If the heating plate cannot be easily removed during operation by one person for reasons of its weight or other factors, then hydraulic, pneumatic or other mechanical assistance shall be provided as part of the butt fusion machine.

For manual butt fusion machines, the total heat capacity of the tool shall be such that, if the electrical power supply is accidentally disconnected from the heating plate at the operating temperature, it can still complete a satisfactory joint. If the heating plate is not capable of meeting this requirement, then a foolproof alarm indicating accidental disconnection shall be provided on the butt fusion machine.

The heating system shall be designed to ensure that, under normal ambient conditions, the pipe and/or fitting ends are heated up correctly to the operating temperature and stable fusion conditions are maintained.


8.2 Dimensions

The heating plate shall be of adequate size to ensure good heat transfer to the two fusion ends.

The width x of the inside and outside parts of the heating plate (see Figure 2) shall be at least 10 mm for pipe diameters up to and including $d_n = 250$ mm and at least 15 mm for pipe diameters above $d_n = 250$ mm.

The heating plate shall be flat on both sides to $\pm 0,1$ mm/100 mm.

The thickness shall not vary by more than 0,2 mm up to $d_n = 250$ mm or by more than 0,5 mm above this size, and the plate shall have no holes or screws within the area of pipe contact.



$x \geq 10$ mm for $d_n \leq 250$ mm and $x \geq 15$ mm for $d_n > 250$ mm

Figure 2 — Heating-plate dimensions

8.3 Materials and surface finish

Heating plates shall be made of materials having good thermal conductivity and capable of resisting normal site handling.

The surfaces which contact the pipe or fittings shall be such that molten material does not stick to them, and they will allow damage-free cleaning and resist normal site handling. This can be attained, for example, by coating the surface with coloured PTFE (polytetrafluoroethylene) or by other surface treatments. The colour of the PTFE coating shall be such that, after the tool has been used for jointing operations, the presence of any surplus PE on the plate will be readily visible, regardless of any degradation of the PE or of the PTFE coating.

No release spray of any type, such as PTFE, shall be used at any time during the jointing cycle. Such a spray coating can be transferred to the fusion interface during the jointing procedure.

Alternatively, the heating plate may be made of hard-chromed or stainless steel.

8.4 Heating system

The heating plate shall be electrically heated.

For heating systems with electrical-resistance heater elements, the heating plate shall be fitted with a temperature-indicating device which clearly and visibly indicates when the operating temperature has been reached. This temperature indicator shall be independent of any other temperature control or monitoring system. It shall be protected from mechanical, electrical or thermal damage and shall be replaceable.

Heating plates shall be capable of continuous operation in the vertical position at their operating temperature for a minimum period of 4 h. After this period, the temperature of the grip shall not exceed 50 °C, measured at ambient temperature and no sun exposure.

An indicator shall be fitted to show clearly that the plate is under electric power and that it is heating up. This device shall indicate an operating temperature within ± 5 °C of the plate temperature, measured at a predefined reference point.

Provision shall be made to avoid accidental changing of the pre-set temperature.

8.5 Performance

8.5.1 The surface roughness R_a , as defined in ISO 4287, of a hard-chromed or stainless-steel heating plate shall be less than 0,63 μm when measured in accordance with 10.3.1, and this type of plate shall be free of all non-stick surface coatings.

If the heating-plate surfaces have a coating made of PTFE or some other non-stick material, then the contact faces shall have a maximum roughness R_a of 2,5 μm when measured in accordance with 10.3.1.

8.5.2 The coating shall be capable of withstanding for at least 1 h a temperature of 270 °C. After cooling to ambient temperature and reheating to the fusion temperature, the coating material shall meet all requirements on it.

The temperature control system shall be such that the contact surface temperature is controlled to within ± 7 °C of the required temperature over the range 170 °C to 260 °C under ambient operating conditions in the temperature range -10 °C to $+40$ °C.

The temperature control system shall also conform to these criteria before and after 50 test cycles of heating and cooling between ambient temperature and the operating temperature in accordance with 10.3.2.

8.5.3 The thermal capacity and heat transfer efficiency shall be such that the interface temperature of a pipe of the maximum diameter and thickness can be raised from -5 °C to $+180$ °C in less than 20 s when the heating plate is at working temperature and the specified bead formation pressure is applied. This pipe interface temperature shall be measured at an ambient temperature of 23 °C ± 2 °C. Testing shall be carried out in accordance with 10.3.3.

9 Power supply

The butt fusion machine shall be capable of operating satisfactorily from a domestic mains supply or from a generator.

Machines designed for use with portable generators shall make allowance for the harmonic distortion, inductance and reactance levels of the generator, which might affect its maximum available power output.

The input-voltage range shall be at least $\pm 15\%$ of the nominal value.

The butt fusion machine manufacturer shall be consulted for generator frequency limits during operation.

10 Test methods


10.1 Chassis and clamps

10.1.1 Effectiveness of re-rounding (see Figure 3)

Cut two pieces of SDR 11 pipe of the maximum diameter for the machine being tested and of a length that is at least twice the diameter. Compress each piece in a vice or press to a diameter of 20 % less than its nominal outside diameter. If the piece is too long to compress the entire length, position the pipe such that there is no more than 25 mm of pipe extending out of the vice jaw or platen at the end to be checked. Hold for 15 min. Insert the pipe in the butt fusion machine at the jointing position so that the larger dimension is perpendicular to the jaw pivot and/or clamping position. Install and tighten the clamps with the pipe ends held in the pipe clamps at typical pipe jointing positions, in accordance with the manufacturer's instructions.

Using vernier callipers or another suitable instrument, measure the maximum and minimum diameters half-way between the end of the pipe and the face of the clamp.

Calculate the out-of-roundness as the difference between the maximum and minimum diameters.



^a Maximum pipe diameter.

Figure 3 — Positioning of clamps

10.1.2 Clamp alignment

10.1.2.1 Confirm the axial alignment of the pipe clamps by the use of two rigid metal cylinders. These shall be machined to the same external diameter as the nominal diameter of the pipe for which the butt fusion machine has been designed and shall have an ovality of less than 0,1 % of d_n . The end faces of each cylinder shall be flat and perpendicular to its axis. With the cylinders held in the clamps at typical pipe-jointing positions, any resultant step at the cylinder interface, due to misalignment, shall not exceed that specified in 5.2.3.

10.1.2.2 Determine the stability and alignment of the pipe-clamping arrangement with the butt fusion machine supported such that the lowest point of a maximum-diameter pipe, measured at the clamp, is at least 200 mm above ground level (see Figure 4). With no pipe fitted, close up the clamps, face to face, and adjust to a close fit. Then clamp two maximum-diameter pipes of length 6 m into the butt fusion machine. Measure the distance between the clamp leading faces at the top and bottom and on both sides of the pipe, with the pipe faces closed together and then with the clamps fully retracted. At each clamp position, misalignment or bending of the framework will be evident as differences between each of the distances measured from one clamp face to the other. Conduct the test with both the pipes supported horizontally by support rollers at 1 m and 4 m from the butt fusion machine, and repeat it with the supports removed. In both cases, the criterion for acceptability shall be as specified in 5.2.3.

10.2 Planing tool and check of gap after planing

Plane two maximum-diameter pipes for each range of the butt fusion machine. The applied force on the pipe ends shall be zero at the end of the planing operation.

After removing the planing tool, close the two pipe faces together with a force sufficient to overcome the frictional resistance. With the two pipe faces in contact, the maximum gap between the pipe ends shall not exceed the applicable value specified in Table 2.


10.3 Heating plate

10.3.1 Roughness check

Measure the roughness on each side of the heating plate as follows:

- Clamp a pipe of the maximum diameter for which the butt fusion machine has been designed into the butt fusion machine and place the heating plate in position between the pipe ends. Draw the outside circumference of the pipe on the heating plate.
- Repeat with all the other pipe diameters for which the butt fusion machine has been designed.
- Draw two diagonal lines at 45° to the horizontal axis.
- Measure the surface roughness at the points of intersection of each of the pipe circumferences with the diagonals.

The surface roughness R_a shall be within the limit given in 8.5.1.

**Key**

- 1 clamp
- 2 pipe

^a At least 200 mm at lowest point.

Figure 4 — Clamp alignment check

10.3.2 Temperature control system check

The temperature control system check shall be conducted with the heating plate in the vertical position in still air at $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$.

The temperature measurements shall be made with an accurate, calibrated thermocouple suitable for the measurement of surface temperatures, or any other appropriate device.

First check that the heating plate conforms to the requirements given in 8.5.2.

Then heat and cool the heating plate from ambient to operating temperature for 50 complete cycles.

Subsequently check the temperature on each side of the heating plate at the same points as for the surface roughness check.

The temperatures shall be within the limits given in 8.5.2.


10.3.3 Heat transfer efficiency

Carry out the test for heat transfer to the pipe surface at the same time as the pipe jointing demonstration, when low-temperature ambient conditions are available. A thermocouple will need to be mounted in the end surface of the pipe. This shall be done after the pipe end has been trimmed. Small self-adhesive-patch thermocouples are satisfactory for this purpose. Alternatively, a small bead thermocouple or equivalent can be fixed in the surface using a soldering iron to melt a region of the pipe surface. Thicker wire thermocouples or soldered assemblies are not satisfactory since heat conduction along wires has to be minimized. The use of a recording instrument facilitates measurement of the temperature rise time. The acceptance limit is specified in 8.5.3.

10.3.4 Guide elements and work-holding fixtures

Carry out the test with pipes clamped in the machine and planed. Align and plane the pipes carefully so that no gap remains between the pipe ends. Then open the machine and place two clamps on the pipe ends at 90° off-centre relative to the guide elements. Bring the pipe ends together again under a jointing pressure of $0,15\text{ N/mm}^2$. The gap at measurement points Sp1 and Sp2 (see Figure 5) shall not exceed the value given in Table 2.

For checking the gap as shown in Figure 5, a wedge gauge should preferably be used.

**Key**

1, 2 clamps (off-centred 90° relative to the guide elements, e.g. pipe disposed horizontally with guide elements arranged below)

Sp1 upper measurement point

Sp2 lower measurement point

b width of clamp

$$b = (d_n - e) \pi / 100 \quad (\text{minimum } 10 \text{ mm})$$

where

d_n is the nominal outside diameter of the pipe;

e is the wall thickness of the pipe.

Figure 5 — Check of guide elements and work-holding fixtures — Measurement of gap size

11 Auxiliary equipment

For each size of butt fusion machine, the manufacturer shall make available the following items:

- Heating-plate guard and support. This shall provide thermal insulation and protection, keep the surface clean and avoid the risk of burns to people or equipment. The guard shall ensure secure retention of the insulating material and stable stowage, and carry a clearly visible “HOT” warning.
- Planing-tool stands or other suitable devices, used to support the trimmers when they are out of the butt fusion machine.

Operating instructions, and relevant legal safety requirements and maintenance schedules, shall be supplied for each butt fusion machine.

12 Maintenance

In order to maintain the performance of the machine in accordance with this part of ISO 12176, it is recommended that the complete machine be inspected, serviced and adjusted at least once per year. This should be carried out by the machine manufacturer or the manufacturer's authorized representative. After maintenance, all components of the machine (chassis, heating plate, planning tool, etc.) should be marked with a service badge.

National regulations, manufacturer's instructions and/or customer requirements shall be taken into account.

13 Marking on the butt fusion machine

The butt fusion machine and accompanying components shall be indelibly marked on all appropriate parts with the following information:

- a) the manufacturer's identification mark;
- b) the model of machine as defined by the manufacturer;
- c) the power supply used (input voltage and power consumption);
- d) the serial number;
- e) the maximum diameter for which the machine is designed.

14 Other information to be provided by the manufacturer

The following data shall be provided with the machine, e.g. on a technical-data sheet or in the operating instructions:

- a) the effective ram area of the machine (if applicable);
- b) the pipe diameter range for which the machine is designed;
- c) the SDRs for each pipe diameter;
- d) the fusion-jointing procedure used;
- e) the type of machine.

The type classification scheme for butt fusion machines given in Annex B may be used.