
**Rubber compounding ingredients —
Carbon black — Determination of iodine
adsorption number**

*Ingrédients de mélange du caoutchouc — Noir de carbone —
Détermination de l'indice d'adsorption d'iode*

STANDARDSISO.COM : Click to view the full PDF of ISO 1304:2006



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 1304:2006

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	2
5 Reagents	3
6 Preparation of solutions	3
7 Standardization of the solutions	5
7.1 General	5
7.2 Sodium thiosulfate solution	5
7.3 Iodine solution	6
8 Procedure	7
8.1 Conditions of test	7
8.2 Sample preparation	7
8.3 Iodine number determination	7
9 Expression of results	8
10 Verification using standard reference blacks	9
11 Precision and bias	9
11.1 Precision	9
11.2 Bias	11
12 Test report	11
Annex A (informative) CAS numbers of reagents	12
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1304 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This fourth edition cancels and replaces the third edition (ISO 1304:1999), the method in which has been entirely revised. In particular, a potentiometric titration has been included as an option and the concentration of the sodium thiosulfate solution has been changed.

STANDARDSISO.COM : Click to view the full PDF of ISO 1304:2006

Rubber compounding ingredients — Carbon black — Determination of iodine adsorption number

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies methods for the determination of iodine adsorption number of carbon blacks for use in the rubber industry. Two titration methods are described:

- method A: titration using a burette and starch as indicator;
- method B: potentiometric titration with an automatic titrator.

The iodine adsorption number is related to the surface area of a carbon black, and is generally in agreement with the nitrogen surface area. However, it is significantly depressed in the presence of a high content of volatile or solvent-extractable materials; the iodine adsorption number therefore does not always provide a measure of the specific surface area of a carbon black. Ageing of carbon black can also influence the iodine number.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385:2005, *Laboratory glassware — Burettes*

ISO 648:1977, *Laboratory glassware — One-mark pipettes*

ISO 1042:1998, *Laboratory glassware — One-mark volumetric flasks*

ISO 1126, *Rubber compounding ingredients — Carbon black — Determination of loss on heating*

ISO/TR 9272:2005, *Rubber and rubber products — Determination of precision for test method standards*

3 Principle

A test portion of carbon black is dried, weighed and mixed vigorously with a measured volume of standard iodine solution. The mixture is then centrifuged. A measured volume of the clear iodine solution is titrated with a standard solution of sodium thiosulfate. From this titration value and the mass of the test portion, the iodine adsorption number of the carbon black is calculated.

4 Apparatus

Ordinary laboratory equipment (beakers, funnels, porcelain spoon, weighing bottles, etc.), plus the following:

4.1 Analytical balance, with 0,1 mg sensitivity.

4.2 Oven, preferably of the gravity-convection type, capable of temperature regulation to within ± 1 °C at 125 °C and temperature uniformity to within ± 5 °C.

4.3 Stoppered one-mark volumetric flasks, preferably class A in accordance with ISO 1042:1998, of capacities:

a) 2 000 cm³, with a tolerance of $\pm 0,60$ cm³;

b) 1 000 cm³, with a tolerance of $\pm 0,40$ cm³.

4.4 Repetitive dispenser, 25 cm³ capacity, calibrated to within $\pm 0,03$ cm³ accuracy, or **one-mark pipettes**, high precision, of capacities:

a) 20 cm³, with a tolerance of $\pm 0,03$ cm³;

b) 25 cm³, with a tolerance of $\pm 0,03$ cm³.

If class A pipettes in accordance with ISO 648:1977 are used, no calibration is necessary. In other cases, pipettes shall be calibrated to the nearest 0,01 cm³ with distilled water, a temperature correction being made if necessary to show the true delivery at any volume used to within 0,01 cm³. The true delivered volume is the read volume plus (or minus) the calibration correction at that volume. For high-precision volume determination (see 7.2.2, 7.3.2, 8.3.3, 8.3.6 and 8.3.8), it is recommended that the 20 cm³ and 25 cm³ pipettes have calibration corrections of the same magnitude and in the same sense.

4.5 Digital burettes, with 0,01 cm³ increment counter and zero-reset control, calibrated to within $\pm 0,05$ cm³ accuracy, or **burettes** (for method A only), high precision, side-arm filling, graduated in 0,05 cm³ and with automatic zero, of capacities:

a) 25 cm³, with a tolerance of $\pm 0,05$ cm³;

b) 50 cm³, with a tolerance of $\pm 0,05$ cm³.

If class A burettes in accordance with ISO 385:2005 are used, no calibration is necessary. In other cases, burettes shall be calibrated to the nearest 0,01 cm³ with distilled water, a temperature correction being made if necessary to show the true delivery at any volume used to within 0,01 cm³. The true delivered volume is the read volume plus (or minus) the calibration correction at that volume.

4.6 Stoppered bottles, with ground-glass stoppers, of capacities 250 cm³ and 500 cm³.

4.7 Glass bottle, with ground-glass stopper, of capacity 2 000 cm³.

4.8 Amber-glass bottles, with ground-glass stoppers, of capacities 1 000 cm³ and 2 000 cm³.

4.9 Centrifuge tubes, of capacity 50 cm³, with screw cap and polyethylene liner.

Cork, rubber or metal stoppers shall not be used.

4.10 Mechanical shaker, capable of 240 strokes/min, with 25 mm stroke length.

4.11 Centrifuge, minimum speed 105 rad/s (1 000 r/min).

4.12 Desiccator.

4.13 Magnetic stirrers and spin bars.

4.14 Automatic titrator (for method B only), equipped with a combined electrode for potentiometric titration.

5 Reagents

Unless otherwise stated, all chemicals shall be of reagent grade.

5.1 Water, deionized or distilled.

5.2 Iodine (I_2).

5.3 Potassium iodide (KI).

5.4 Potassium iodate (KIO_3).

5.5 Sodium thiosulfate pentahydrate ($Na_2S_2O_3 \cdot 5H_2O$).

5.6 *n*-Amyl alcohol ($C_5H_{11}OH$).

5.7 Sulfuric acid (H_2SO_4), mass fraction 98 %, $\rho = 1,84 \text{ Mg/m}^3$.

5.8 Soluble starch (for method A only).

5.9 Salicylic acid ($C_7H_6O_3$) (for method A only).

6 Preparation of solutions

6.1 Iodine solution, $0,023\ 64 \text{ mol/dm}^3$ ($0,047\ 28 \text{ N}$), containing 9,5 parts of potassium iodide to 1 part of iodine.

NOTE Since the test result depends on the concentration of both iodine and potassium iodide in the solution, the instructions for the preparation and the standardization of the solution (see 7.3) have to be followed precisely.

6.1.1 Weigh, to the nearest 0,01 g, 114,00 g of potassium iodide (5.3) into a 100 cm^3 beaker.

6.1.2 Place about three-quarters of the KI in a clean $2\ 000 \text{ cm}^3$ volumetric flask (4.3) through a large-diameter funnel.

6.1.3 Add enough water (5.1) to cover the KI. Swirl to dissolve, and allow to stand until the solution attains ambient temperature.

6.1.4 Place the remainder of the KI in a 250 cm^3 beaker with enough water (5.1) to dissolve it.

6.1.5 Weigh, to the nearest 0,005 g, 12,000 g of iodine on the balance (4.1) in a weighing bottle fitted with a ground-glass stopper. Use only a porcelain spoon to transfer the iodine crystals, and close the weighing bottle when making weighings.

6.1.6 Transfer the iodine through a funnel to the potassium iodide solution prepared in 6.1.3.

6.1.7 Wash thoroughly the weighing bottle with portions of the KI solution prepared in 6.1.4 until no colour remains, and transfer the washings through the funnel to the $2\ 000 \text{ cm}^3$ volumetric flask.

6.1.8 Wash the funnel with the rest of the KI solution prepared in 6.1.4.

6.1.9 Add water (5.1) to almost fill the volumetric flask, cap it with the ground-glass stopper, invert it 2 or 3 times to homogenize and let it stand for about one hour.

6.1.10 Open the flask, make up to the mark with water (5.1), insert a spin bar in the flask, place it on the magnetic stirrer (4.13) and stir for 2 h at least at medium speed.

NOTE At medium speed, the depth of the vortex should be about 5 mm.

6.1.11 Transfer the solution to an amber-glass bottle (4.8) and let it stand overnight prior to any use.

6.2 Sodium thiosulfate solution, $0,05 \text{ mol/dm}^3$ (0,05 N).

NOTE Previous editions of this International Standard required a thiosulfate concentration of $0,039 4 \text{ mol/dm}^3$ (0,039 4 N). Since the concentration of the thiosulfate solution does not have any impact on the iodine adsorption number, this International Standard now includes a more commonly used solution of $0,05 \text{ mol/dm}^3$ (0,05 N). The advantage is that such a solution is readily available commercially. If preferred, it can be prepared from solid sodium thiosulfate as described below.

Use of sodium thiosulfate solution of $0,039 4 \text{ mol/dm}^3$ (0,039 4 N) is still permitted. In this case, the instructions for the preparation of the solution, the equations used in its standardization and the equations used in the calculation of the iodine adsorption number will have to be modified accordingly.

6.2.1 Weigh, to the nearest 0,005 g, 24,817 g of sodium thiosulfate pentahydrate (5.5) into a suitable container.

6.2.2 With the help of a funnel, transfer the weighed sodium thiosulfate to a $2\,000 \text{ cm}^3$ volumetric flask (see 4.3).

6.2.3 Add through the funnel about 1 litre of water (5.1). Wash carefully.

6.2.4 Add 10 cm^3 of *n*-amyl alcohol (5.6) to the flask, and shake the solution in the flask vigorously until all crystals are dissolved.

6.2.5 Make up to the mark with water (5.1), insert a spin bar in the flask, place it on the magnetic stirrer and stir for about 2 h at medium speed (see Note to 6.1.10).

6.2.6 Transfer the solution to a glass bottle (4.7).

6.3 Potassium iodate/iodide solution, $c(\text{KIO}_3) = 0,008\,33 \text{ mol/dm}^3$ (0,05 N).

6.3.1 Dry an adequate quantity of potassium iodate (5.4) in the oven (4.2) at $125\,^\circ\text{C}$ for 1 h. Allow to cool to ambient temperature in the desiccator (4.12).

6.3.2 In a $1\,000 \text{ cm}^3$ volumetric flask (see 4.3), dissolve 57,0 g (weighed to the nearest 0,1 g) of potassium iodide (5.3) in about 200 cm^3 of water (5.1). Allow to stand until the solution attains ambient temperature.

6.3.3 Weigh out, to the nearest 0,1 mg, 1,783 3 g of the freshly dried potassium iodate (5.4) and transfer to the iodide solution in the volumetric flask.

6.3.4 Make up to the mark with water (5.1). Cap the flask and homogenize the solution by inverting the flask 4 to 5 times.

6.3.5 Transfer the solution to an amber-glass bottle (4.8).

NOTE The potassium iodate/iodide solution is a primary standard in this test method, and it is essential that all precautions be taken to ensure its accuracy.

6.4 Sulfuric acid, mass fraction approximately 20 %.

6.4.1 Measure out 175 cm³ of water (5.1) in a graduated cylinder and transfer to a 250 cm³ conical flask.

6.4.2 Measure out 25 cm³ of concentrated sulfuric acid (5.7) in a small graduated cylinder.

6.4.3 Very carefully pour the acid into the flask of water (6.4.1), and swirl gently to mix. Rinse the graduated cylinder with diluted acid from the flask and pour the rinsings back into the flask. Do not use water for rinsing.

6.4.4 Transfer the solution to a 250 cm³ bottle (4.6), stopper the bottle and allow the solution to cool to ambient temperature before use.

6.5 Starch indicator solution, mass fraction 0,25 % (for method A only).

6.5.1 Place in a 50 cm³ beaker 2,5 g of powdered soluble starch (5.8), 2 mg of salicylic acid (5.9) and 25 cm³ of water (5.1). Stir with a glass rod.

6.5.2 Bring 1 000 cm³ of water (5.1) in a 2 000 cm³ beaker to the boil on a hotplate.

6.5.3 Pour the starch suspension prepared in 6.5.1 into the boiling water while stirring, and continue to boil for about 10 min.

6.5.4 Allow the solution to cool to ambient temperature and to settle, decant the clear portion into 500 cm³ glass bottles (4.6) and stopper the bottles.

7 Standardization of the solutions

7.1 General

The potassium iodate/iodide solution is used as a primary standard to standardize the sodium thiosulfate solution. This sodium thiosulfate solution is then used as a secondary standard to standardize the iodine solution.

7.2 Sodium thiosulfate solution

7.2.1 After a resting period of 24 h after preparation, fill a glass (or digital) burette (see 4.5) with the unstandardized sodium thiosulfate solution. Flush 2 cm³ to 3 cm³ through the tip and adjust the mark (with a digital burette, flush the inlet and delivery tubes and zero the counter).

7.2.2 With a pipette (see 4.4), transfer exactly 20 cm³ of potassium iodate/iodide solution (6.3) to a 250 cm³ conical flask or to a digital-burette titration beaker, respectively.

7.2.3 Add about 3 cm³ of 20 % sulfuric acid (6.4) to liberate the iodine. Mix thoroughly.

7.2.4 Titration with starch indicator (method A)

7.2.4.1 Add sodium thiosulfate from the burette until a pale-straw colour is observed. Wash the burette tip and the walls of the flask with water (5.1).

7.2.4.2 Add approximately 5 cm³ of starch indicator (6.5) to the flask.

7.2.4.3 Continue to add sodium thiosulfate solution dropwise until the blue or blue-violet colour almost disappears. Wash the burette tip and the walls of the flask with water (5.1).

7.2.4.4 Slowly continue to add thiosulfate dropwise (or advance the counter of the digital burette by 0,01 cm³ increments) until the blue colour is totally changed to colourless.

7.2.4.5 Record the titration volume as V_1 to the nearest 0,025 cm³ (or 0,01 cm³).

NOTE To achieve maximum performance with a glass burette, it is recommended that a small magnifier be used to read the burette to the nearest 0,025 cm³.

7.2.4.6 Repeat the sequence 7.2.2 to 7.2.4.5 to give a duplicate determination.

7.2.4.7 Proceed to 7.2.6.

7.2.5 Potentiometric titration (method B)

7.2.5.1 Place the titration beaker in the automatic titrator, immerse the electrode in the solution and start the titration with thiosulfate solution in accordance with the manufacturer's instructions.

7.2.5.2 When the titration has finished, read the titration volume V_1 as displayed by the titrator to the nearest 0,01 cm³.

7.2.5.3 Repeat the sequence 7.2.2, 7.2.3, 7.2.5.1 and 7.2.5.2 to give a duplicate determination.

7.2.6 Calculate the concentration, in mol/dm³, of the sodium thiosulfate solution c_1 as follows:

$$c_1 = \frac{20 \times 6 \times 0,008\,333}{V_1} \quad (1)$$

where

20 is the volume of iodate/iodide solution (6.3) titrated, expressed in cm³;

6 is a stoichiometric factor;

0,008 333 is the concentration of the iodate/iodide solution (6.3), expressed in mol/dm³;

V_1 is the average titration volume, in cm³, of the duplicate determinations.

7.3 Iodine solution

7.3.1 Fill a glass (or digital) burette with the standardized sodium thiosulfate solution as indicated in 7.2.1.

7.3.2 With a pipette (see 4.4), transfer exactly 20 cm³ of the unstandardized iodine solution into a 250 cm³ conical flask or a digital-burette titration beaker, respectively.

7.3.3 Titrate the contents of the flask with the standardized sodium thiosulfate solution, following the procedure described in 7.2.4 or 7.2.5.

7.3.4 Calculate the concentration, in mol/dm³, of the iodine solution c_2 as follows:

$$c_2 = \frac{V_2 \times c_1}{2 \times 20} \quad (2)$$

where

V_2 is the average titration volume, in cm³, of the duplicate determinations;

c_1 is the concentration of the standardized sodium thiosulfate solution, expressed in mol/dm³, as calculated in 7.2.6;

2 is a stoichiometric factor;

20 is the volume of the standardized sodium thiosulfate solution titrated, expressed in cm³.

7.3.5 To be acceptable, the concentration c_2 of the iodine solution shall be:

$$0,023\ 64\ \text{mol/dm}^3 \pm 0,000\ 05\ \text{mol/dm}^3$$

If the concentration is outside this range, the solution can be adjusted as follows:

- if the solution is too strong, add water (5.1) (4,2 cm³ of water per 1 000 cm³ of solution for each 0,000 1 mol/dm³ over 0,023 64 mol/dm³);
- if the solution is too weak, add iodine (0,025 4 g of iodine per 1 000 cm³ of solution for each 0,000 1 mol/dm³ under 0,023 64 mol/dm³).

NOTE The iodine may be more conveniently dispensed from a concentrated solution.

In either case, it is essential to homogenize the adjusted solution thoroughly and to restart the entire standardization procedure (7.3).

8 Procedure

8.1 Conditions of test

It is preferred that the test be carried out in a room having ambient conditions of either 23 °C ± 2 °C at (50 ± 5) % relative humidity or 27 °C ± 2 °C at (65 ± 5) % relative humidity.

It is recommended that the reagents and the apparatus be maintained at temperature equilibrium in the same room at least for a few hours before being used.

The test room shall be free from fumes or vapours which could contaminate the reagents and apparatus used, and therefore alter the results.

8.2 Sample preparation

Dry an adequate amount of the carbon black for 1 h at a temperature of 125 °C as specified in ISO 1126. Allow to cool to ambient temperature in a desiccator. Keep the dried carbon black in the desiccator until ready for testing. Standard reference blacks shall be dried to constant mass.

NOTE Pellets of carbon black need not be crushed. Unagitated, unpelletized carbon black may be densified, if desired, before drying.

8.3 Iodine number determination

8.3.1 Weigh, to the nearest 0,1 mg, a test portion of the dried carbon black into a centrifuge tube (4.9), taking the amount specified in Table 1.

Use the test portion mass corresponding to the expected iodine number. If the result falls either above or below the range shown for that mass, retest using the mass corresponding to the range in which the result fell.

8.3.2 The test portion masses given in Table 1 are valid only when 25 cm³ of iodine solution is used as specified in 8.3.3. Different volumes of iodine solution and different test portion masses are permissible only if the iodine solution to test portion ratio is the same as that given in Table 1.

The test portion mass shall be limited to 1,000 g maximum when using a 50 cm³ centrifuge tube. Should the test portion mass and corresponding volume of iodine solution be increased, then a tube of suitable capacity shall be used in order to ensure efficient shaking.

Table 1

Expected or nominal iodine adsorption number (IAN) g/kg	Mass of test portion <i>m</i> mg	Ratio of volume of iodine solution to mass of test portion cm ³ /g
0 to 130,9	500	50:1
131,0 to 280,9	250	100:1
281,0 to 520,9	125	200:1
521,0 and above	62,5	400:1

8.3.3 With a pipette (or repetitive dispenser) (see 4.4), introduce 25 cm³ of the 0,023 64 mol/dm³ iodine solution into the centrifuge tube containing the test portion and cap immediately.

8.3.4 Place the tube in the mechanical shaker (4.10), with the longitudinal axis of the tube parallel to the direction of shaking, and shake for 1 min at 240 strokes/min.

8.3.5 Immediately after shaking, centrifuge at a speed above 105 rad/s (1 000 r/min) for 1 min for pelletized blacks or 3 min for unpelletized blacks, measured from the moment the centrifuge speed reaches 105 rad/s.

8.3.6 Immediately after centrifuging, decant the iodine solution completely, in one smooth motion, into a 50 cm³ beaker, leaving the carbon black test portion at the bottom of the centrifuge tube. Immediately after decanting, use a pipette (see 4.4) to transfer exactly 20 cm³ of the solution into a 250 cm³ conical flask.

Alternatively, 20 cm³ of the iodine solution may be pipetted directly from the centrifuge tube without disturbing the carbon black.

If the titration is not carried out immediately, decant the solution into a small vial and cap it immediately.

8.3.7 Titrate the 20 cm³ of decanted iodine solution with the standardized 0,05 mol/dm³ sodium thiosulfate solution following the procedure described in 7.2.4 (titration with starch indicator) or 7.2.5 (automatic titrator).

8.3.8 Repeating the sequence 8.3.3 to 8.3.7, carry out a blank determination on the iodine solution and record the titration volume V_B to the nearest 0,025 cm³ (or 0,01 cm³) (see Note to 7.2.4.5).

8.3.9 Carry out a duplicate blank determination, and use the average of the two results in the calculations.

NOTE The duplicate blank determination needs to be run only once each day, unless new solutions are introduced during the day. For shift laboratories, it is recommended that duplicate blank determinations be made at the beginning of each shift.

8.3.10 If both the sodium thiosulfate and the iodine solutions are within acceptable limits, the blank average will be 18,91 cm³ ± 0,05 cm³. If not, the concentrations of one or both solutions shall be rechecked.

9 Expression of results

Calculate the iodine adsorption number (IAN), expressed in grams of iodine per kilogram of carbon black, to the nearest 0,1 g/kg, using Equation (3):

$$IAN = (V_B - V_S) \times \frac{25}{V_B} \times c_2 \times 253,82 \times \frac{1}{m} \quad (3)$$

where

- V_B is the volume, in cm^3 , of sodium thiosulfate solution required for the blank;
- V_S is the volume, in cm^3 , of sodium thiosulfate solution required for the test portion;
- c_2 is the concentration of the iodine solution, expressed in mol/dm^3 ;
- m is the mass, in g, of the test portion;
- 25 is the volume, in cm^3 , of iodine solution in contact with the carbon black (from calibrated pipette or dispenser);
- 253,82 is the molecular mass of iodine (I_2).

10 Verification using standard reference blacks

It is recommended that the proper execution of the procedure be checked by using standard reference blacks (see ASTM D 4821 for standard values and the range for each of them).

If the values for the SRBs do not fall within the accepted ranges, then new solutions shall be prepared and tested, including the primary standard solution prepared in 6.3.

11 Precision and bias

11.1 Precision

11.1.1 The precision of this test method was determined in accordance with the ISO/TR 9272:2005, level 2, method. Refer to this document for terminology and other statistical details.

11.1.2 The precision results give an estimate of the precision to be expected. The precision parameters shall not be used for acceptance/rejection testing of any group of materials without documentation that they are applicable to those particular materials and the specific testing protocols that include this test method.

11.1.3 A type 1 precision interlaboratory-trials programme was conducted. Both the repeatability and the reproducibility determined represent short-term testing conditions. For method A (titration with starch indicator), seven laboratories tested three carbon blacks twice on each of two different days; therefore, $p = 7$, $q = 3$ and $n = 4$. For method B (potentiometric titration), twenty-three laboratories tested three carbon black samples twice on each of two different days; therefore, $p = 23$, $q = 3$ and $n = 4$. A test result is the value obtained from a single determination. Acceptable difference values were not measured.

11.1.4 The results of the precision calculations are given in Table 2 (method A) and Table 3 (method B), with the materials arranged in descending order of mean iodine adsorption number. Outliers have been removed. The number of laboratories remaining after outlier deletion is marked in the tables.

Table 2 — Precision data — Method A (titration with starch indicator)

Material	Number of labs	Mean IAN g/kg	Within laboratory			Between laboratories		
			s_r	r	(r)	s_R	R	(R)
A (N115)	4	158,21	0,268	0,758	0,479	1,302	3,760	2,376
B (N772)	5	32,67	0,170	0,482	1,475	0,607	1,784	5,460
C (N330)	5	80,77	0,432	1,221	1,512	0,678	2,274	2,816
Average	5	90,55	—	—	—	—	—	—
Pooled values	—	—	0,309	0,875	1,250	0,917	2,738	3,803
The symbols used are defined as follows: s_r is the within-laboratory standard deviation r is the repeatability (in measurement units) (r) is the repeatability (in percent) s_R is the between-laboratory standard deviation R is the reproducibility (in measurement units) (R) is the reproducibility (in percent)								

Table 3 — Precision data — Method B (potentiometric titration)

Material	Number of labs	Mean IAN g/kg	Within laboratory			Between laboratories		
			s_r	r	(r)	s_R	R	(R)
A (N115)	19	160,55	0,570	1,612	1,005	2,519	7,306	4,551
B (N772)	20	33,38	0,400	1,131	3,387	0,911	2,814	8,430
C (N330)	19	82,47	0,344	0,972	1,178	1,360	3,969	4,812
Average	19	92,13	—	—	—	—	—	—
Pooled values	—	—	0,448	1,268	2,150	1,734	5,068	6,190
NOTE For explanation of symbols, see Table 2.								

NOTE Statistical analysis has shown that there is a significant difference between the mean level obtained with method A and method B. Method A (starch indicator) gives roughly 1 % lower values than method B (potentiometric titration). The reason for this phenomenon is not yet clear. When comparing the precision data for the two methods, it should be borne in mind that the number of participating laboratories, i.e. the statistical basis, was different: 7 laboratories used method A, whereas 23 laboratories used method B.

11.1.5 The precision for the pooled values of the iodine adsorption number may be expressed as follows:

11.1.5.1 Repeatability

The repeatability in percent (r) for the iodine adsorption number has been established as 1,25 % for method A and 2,15 % for method B. Two single test results (or determinations) that differ by more than 1,25 % (method A) or 2,15 % (method B) shall be considered suspect and dictate that some appropriate investigative action be taken.