
**Rubber and plastics hoses — Hose sizes,
minimum and maximum inside diameters,
and tolerances on cut-to-length hoses**

*Tuyaux en caoutchouc et en plastique — Diamètres nominaux,
diamètres intérieurs minimaux et maximaux, et tolérances sur la
longueur de coupe*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 1307:2006

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1307 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

This fourth edition cancels and replaces the third edition (ISO 1307:1992), which has been technically revised. The revision includes classifying the hoses by type according to the manufacturing process, adding additional sizes, and changing the inside-diameter tolerances to minimum and maximum dimensions to be consistent with the latest hose standards.

Rubber and plastics hoses — Hose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses

1 Scope

This International Standard specifies the sizes of rubber and plastics hoses and the minimum and maximum inside diameters permitted for each hose size. For this purpose, hoses are divided into four types according to the process by which they are manufactured. The standard also specifies tolerances on cut-to-length rubber and plastics hoses for industrial and automotive applications. This standard is intended to be used with the relevant hoses product standard unless there is justification for using a different hose size or unless a hose size needs a different inside-diameter range for a particular application.

2 Hose sizes and ID tolerances by manufacturing type

The sizes of rubber and plastic hoses and their respective inside-diameter ranges shall be in accordance with Table 1. Four types are specified, according to the process used to manufacture them:

- type A: hoses built using a rigid mandrel for inside-diameter control;
- type B: hoses built using a flexible mandrel for inside-diameter control (plus plastic hydraulic hoses made with or without a mandrel);
- type C: hoses built without using a mandrel (non-mandrel-built);
- type D: flexible extruded plastics hoses (type D does not include spiral-reinforced plastics suction and discharge hoses, which are classified as type C).

Table 1 — Hose sizes and inside-diameter tolerances

Nominal size	Minimum and maximum inside-diameters							
	mm							
	Type A Built on rigid mandrel		Type B Built on flexible mandrel		Type C Non-mandrel-built (standard tolerance)		Type D Extruded plastic Non-mandrel-built (tight tolerance)	
	min.	max.	min.	max.	min.	max.	min.	max.
3,2	3,2	3,8	N/A	N/A	N/A	N/A	3,0	3,4
4	4,0	4,8	4,0	4,8	3,4	4,6	3,7	4,3
5	4,6	5,4	4,6	5,4	4,2	5,4	4,7	5,3
6,3	6,2	7,0	6,2	7,0	5,6	7,2	6,0	6,6
8	7,7	8,5	7,7	8,5	7,2	8,8	7,7	8,3
10	9,3	10,1	9,3	10,1	8,7	10,3	9,7	10,3
12,5	12,3	13,5	12,3	13,5	11,9	13,5	12,2	12,8
16	15,5	16,7	15,5	16,7	15,1	16,7	15,7	16,3
19	18,6	19,8	18,6	19,8	18,3	19,9	18,4	19,6
20	19,6	20,8	19,6	20,8	19,3	20,9	N/A	N/A
25	25,0	26,4	25,0	26,4	24,2	26,6	24,4	25,6
31,5	31,4	33,0	31,4	33,0	30,2	33,4	30,9	32,1
38	37,7	39,3	37,7	39,3	36,5	39,7	37,4	38,6
40	39,7	41,3	39,7	41,3	38,5	41,7	N/A	N/A
50	49,4	51,0	N/A	N/A	48,1	51,6	N/A	N/A
51	50,4	52,0	N/A	N/A	49,1	52,6	50,2	51,8
63	63,1	65,1	N/A	N/A	61,5	65,5	62,2	63,8
76	74,6	77,8	N/A	N/A	74,2	78,2	75,0	77,0
80	78,6	81,8	N/A	N/A	78,2	82,2	N/A	N/A
90	87,3	90,5	N/A	N/A	N/A	N/A	N/A	N/A
100	100,0	103,2	N/A	N/A	99,4	103,9	N/A	N/A
125	125,4	128,6	N/A	N/A	124,8	129,3	N/A	N/A
150	150,4	154,4	N/A	N/A	150,2	154,7	N/A	N/A
160	N/A	N/A	N/A	N/A	162,9	167,4	N/A	N/A
200	200,7	205,7	N/A	N/A	200,2	206,2	N/A	N/A
250	251,0	257,0	N/A	N/A	251,0	257,0	N/A	N/A
305	301,8	307,8	N/A	N/A	301,8	307,8	N/A	N/A
315	314,5	320,5	N/A	N/A	N/A	N/A	N/A	N/A
350	N/A	N/A	N/A	N/A	351,6	359,6	N/A	N/A
400	N/A	N/A	N/A	N/A	402,4	410,4	N/A	N/A

N/A = Not available.