



INTERNATIONAL STANDARD ISO 13807:1999  
TECHNICAL CORRIGENDUM 1

Published 2000-10-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

**Vitreous and porcelain enamels — Determination of crack formation temperature in the thermal shock testing of enamels for the chemical industry**

TECHNICAL CORRIGENDUM 1

*Émaux vitrifiés — Détermination de la température de fissuration par choc thermique d'émaux pour l'industrie chimique*

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to International Standard ISO 13807:1999 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

Page 3

7.1 paragraph below Figure 1

Replace the last sentence with the following text:

Heat the specimens up to 600 °C in an oven, maintain this temperature for at least 20 min, then cool to  $\leq 250$  °C at a cooling rate of  $\leq 1$  °C/min (see annex A).