
INTERNATIONAL STANDARD



1403

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

General purpose rubber water hose

Tuyaux à eau en caoutchouc pour usages généraux

First edition — 1976-10-15

STANDARDSISO.COM : Click to view the full PDF of ISO 1403:1976

UDC 621.643.33

Ref. No. ISO 1403-1976 (E)

Descriptors : rubber products, hoses, specifications, dimensions, tests, marking, water pipes.

Price based on 2 pages

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

Prior to 1972, the results of the work of the technical committees were published as ISO Recommendations; these documents are in the process of being transformed into International Standards. As part of this process, Technical Committee ISO/TC 45, *Rubber and rubber products*, has reviewed ISO Recommendation R 1403-1970 and found it technically suitable for transformation. International Standard ISO 1403 therefore replaces ISO Recommendation R 1403-1970, to which it is technically identical.

ISO Recommendation R 1403 had been approved by the member bodies of the following countries :

Austria	India	Spain
Brazil	Iran	Sweden
Czechoslovakia	Israel	Switzerland
Egypt, Arab Rep. of	Italy	United Kingdom
France	Japan	U.S.S.R.
Germany	Netherlands	Yugoslavia
Greece	New Zealand	
Hungary	Poland	

The member bodies of the following countries had expressed disapproval of the Recommendation on technical grounds :

Ireland
U.S.A.

The member body of the U.S.A. also disapproved the transformation of the Recommendation into an International Standard.

General purpose rubber water hose

1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies the minimum acceptable requirements for the satisfactory performance of three types of general purpose rubber water hose as follows :

Type 1 — Low pressure : designed for a maximum working pressure of 0,6 MPa* and a test pressure of 0,75 MPa (all sizes).

Type 2 — Medium pressure : designed for a maximum working pressure of 1,0 MPa and a test pressure of 1,6 MPa (sizes up to 50 mm nominal bore).

Type 3 — High pressure : designed for a maximum working pressure of 2,5 MPa and a test pressure of 5,0 MPa (sizes up to 25 mm nominal bore).

The list of nominal bores given in table 1 [based on the R 10 series of preferred numbers (see ISO 3)] is not intended to be restrictive and will not preclude the manufacture of sizes outside this list which may be the subject of individual national standards.

2 REFERENCES

ISO 3, *Preferred numbers — Series of preferred numbers*.

ISO/R 36, *Determination of the adhesion strength of vulcanized rubbers to textile fabrics*.

ISO 37, *Rubber, vulcanized — Determination of tensile stress-strain properties*.

ISO 188, *Rubber, vulcanized — Accelerated ageing or heat-resistance tests*.

ISO 1307, *Rubber hose — Bore sizes, tolerances on length, and test pressures*.

ISO 1402, *Rubber hose — Hydrostatic testing*.

3 MATERIALS

The hose shall be made with a rubber lining and shall have a reinforcement of natural or synthetic fibres and a rubber cover.

4 CONSTRUCTION

4.1 The lining and cover shall be of uniform thickness, reasonably concentric, and free from air holes, porosity and other defects.

4.2 The lining shall be as smooth in the bore as is consistent with good manufacturing practice.

4.3 The cover of the moulded-type hose shall be smooth or fluted as required. The cover of mandrel-built hose shall have a smooth, fluted or cloth-wrapped finish.

4.4 The hose shall be uniformly vulcanized.

5 DIMENSIONS AND TOLERANCES

5.1 Bore

The bore of the hose shall be in accordance with the nominal dimensions and tolerances given in table 1.

TABLE 1 — Nominal bores

Values in millimetres

Nominal bore	Tolerance	Nominal bore	Tolerance
10	± 0,75	40	± 1,50
12,5	± 0,75	50	± 1,50
16	± 0,75	63	± 1,50
20	± 0,75	80	± 2,00
25	± 1,25	100	± 2,00
31,5	± 1,25		

NOTE — If special cases call for extra sizes :

a) for smaller or larger dimensions, further numbers shall be chosen from the R 10 series of preferred numbers (see ISO 3), with tolerances as specified in ISO 1307;

b) for intermediate dimensions, numbers shall be chosen from the R 20 series of preferred numbers (see ISO 3), with the tolerances as for the next larger bore size from the R 20 series.

* 1 MPa = 1 MN/m²