
**Thermal spraying — Powders —
Composition and technical supply
conditions**

*Projection thermique — Poudres — Composition et conditions techniques
de livraison*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 14232:2000

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Properties of powders for thermal spraying — Property determination	1
4 Classification of powders	4
5 Designation	13
6 Conditions of supply	13
7 Powder identification	13
8 Certification	13
Annex A (informative) Illustrations of the relationship between particle configuration and the manufacturing process	14

STANDARDSISO.COM : Click to view the full PDF of ISO 14232:2000

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 14232 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

Annex A of this International Standard is for information only.

STANDARDSISO.COM : Click to view the full PDF of ISO 14232:2000

Introduction

The majority of commercially available thermal spray powders are classified on the basis of their composition and degree of purity. They may be specified and characterized according to the information contained in this International Standard which will hopefully lead to a greater understanding of the variety and the wide choice of thermal spray powders now available to the manufacturer and the user.

Due to the great number of thermal spray powders classified in this International Standard, well-known abbreviations are used. The properties of sprayed coatings are not discussed and may differ greatly from the properties of the original material due to specific thermal spraying conditions, such as gas composition, deposition efficiency, material flow rate and stand-off distance. The many applications of thermally sprayed coatings are not reviewed here because they have been described elsewhere in the technical literature.

STANDARDSISO.COM : Click to view the full PDF of ISO 14232:2000

STANDARDSISO.COM : Click to view the full PDF of ISO 14232:2000

Thermal spraying — Powders — Composition and technical supply conditions

1 Scope

This International Standard designates the chemical and physical properties of the powders that are commonly used in the production of thermally sprayed coatings.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 3310-1:—¹⁾, *Test sieves — Requirements and tests — Part 1: Metal wire cloth sieves*.

ISO 3923-2:1981, *Metallic powders — Determination of apparent density — Part 2: Scott volumeter method*.

ISO 3954:1977, *Powders for powder metallurgical purposes — Sampling*.

ISO 4490:1978, *Metallic powders — Determination of flowability by means of a calibrated funnel (Hall flowmeter)*.

3 Properties of powders for thermal spraying — Property determination

3.1 Sampling and sample splitting

Sampling and sample splitting shall be done from a homogeneous mixture that is uniform in grain size. Directions for suitable methods and equipment for accomplishing this shall be in accordance with ISO 3954.

3.2 Chemical composition

The chemical composition shall be determined by any suitable testing method, for example, atomic absorption spectrometry, flame emission spectroscopy, X-ray fluorescent analysis, etc.

3.3 Particle size range

Typical particle size ranges apply to thermal spraying powder units.

When particle size distribution is determined by particle size measurement in accordance with ISO 3310-1, the upper limits may be exceeded by 2 % by mass maximum and the lower limits may be exceeded by 5 % by mass

1) To be published. (Revision of ISO 3310-1:1990)

maximum. The apparent particle size depends on the measurement technique and hence the maximum permissible tolerances of the upper and lower particle size range also depend on the measuring method.

Measuring method, particle size range and maximum permissible tolerances for upper and lower particle size range shall be agreed upon between the powder manufacturer and the producer of the thermally sprayed coating to ensure reproducibility of the thermal spraying process.

Powder shall be supplied to suit the application and the thermal spray process. Examples of typical particle size ranges applicable to thermal spray processes are given below.

Typical particle size ranges, in micrometres, are:

- 22/5
- 45/22
- 90/45
- 45/5
- 63/16
- 106/32

3.4 Particle size distribution

For a precise indication of particle size ranges, it is necessary to measure the particle size and its distribution. X-ray absorption and laser-beam scattering methods are preferred because of their higher reproducibility, rapidity and resolution compared with conventional screening methods.

The results of particle size and particle size distribution measurements are dependent on the methods used and in the case of agglomerated powders are affected by the solubility of the binder. It is, therefore, necessary to verify that the powder is suitable for the chosen test method. The powder test certificate shall state the test applied, in addition to the result of the particle size distribution measurement.

3.5 Process of manufacture — Particle shape

The process by which a powder is manufactured shall be indicated; e.g., fused, bonded, agglomerated, atomized, etc.

Particle shape and surfaces can be illustrated by means of scanning electron or stereo microscopy, and the images may be compared to those of referenced samples provided by the manufacturer to determine their similarity. Examples of the relationship between the manufacturing process and particle shape are given in annex A.

3.6 Apparent density

Apparent powder density shall be determined as specified in ISO 3923-2, and expressed in grams per cubic centimetre.

3.7 Flow properties – Flowability

Powder flowability shall be determined as specified in ISO 4490, and expressed in seconds per 50 g.

3.8 Microstructure

The microstructure of a powder particle can be determined by means of a metallographically-prepared cross-section of the particle. The preparation method is critical and shall be agreed upon between the manufacturer and the user.

3.9 Determination of phases

Determination of the type, quantity, shape, configuration, composition and size of phases in polyphase powders can be made by X-ray microstructure analysis, by microprobe or by metallographic and quantitative image analyses.

3.10 Summary

The relative importance of thermal spray powder properties as related to various materials and to different spraying processes is indicated in Table 1.

Table 1 — The relative importance of thermal spray powder properties for various categories of powder and for different processes

	Chemical composition	Particle size	Particle shape	Apparent density	Flow	Micro-structure	Phase composition	Melting range
Powder categories								
Pure metals	+++	+++	++	+	+	—	—	—
Metallic alloys	+++	+++	++	+	+	—	+	++ ^a
Carbides, carbides with metals, carbides with metallic alloys	+++	+++	++	+	+	++	++	—
Oxides, phosphate and other non-carbide ceramics	+++	+++	++	+	+	+	+	—
Organic materials	+++	+++	+	+	++	—	—	+++ ^b
Different thermal spray processes								
Plasma spraying	++	+++	++	—	+	—	++ ^c	—
Flame spraying	++	+++	+	—	+++	—	—	+++ ^a
High velocity flame spraying	++	+++	+++	++	+	—	++ ^c	+
+++ Specification of this property is imperative/a critical property. ++ Specification of this property is recommended/an important property. + Supplementary detail. — Without significance. ^a For self-fluxing (SF) alloys. ^b In organic material spraying, decomposition temperature and oxidation resistance of the molten material, as well as toxicological characteristics, are important. ^c Necessary detail for the spraying of carbides and oxides, e.g., $\text{ZrO}_2\text{-Y}_2\text{O}_3$.								

4 Classification of powders

4.1 General

Powders for thermal spraying are classified on the basis of chemical composition and may be put into the following categories:

- a) pure metals (4.2 and Table 2);
- b) metallic alloys and composites (4.3 and Tables 3-11);
- c) carbides, carbides with metals, carbides with metallic alloys and composites (4.4 and Table 12);
- d) oxides, phosphates and other non-carbide ceramics (4.5 and Table 13);
- e) organic materials (4.6).

Blended powders of several varying components are not included.

4.2 Pure metals

Table 2 — Pure metal powders

Code number	Chemical composition, %						
	Main constituent	O max.	C max.	N max.	H max.	Al max.	Co max.
1.1	Ti 99	0,3	0,3	0,3	0,1	—	—
1.2	Nb 99	0,3	0,3	0,3	0,1	—	—
1.3	Ta 99	0,3	0,3	0,3	0,1	—	—
1.4	Cr 98,5	0,8	0,1	0,1	—	0,5	—
1.5	Mo 99	0,3	0,15	0,1	—	—	—
1.6	W 99	0,3	0,15	0,1	—	—	0,3
1.7	Ni 99,3	0,5	0,1	0,1	—	—	—
1.8	Cu 99	—	—	—	—	—	—
1.9	Al 99	0,5	—	—	—	—	—
1.10	Si 99	—	—	—	—	—	—

4.3 Metallic alloys and composites

Table 3 — Self-fluxing metallic alloys and composite powders

Code number	Abbreviated designation	Chemical composition, %										
		C	Ni	Co	Cr	Cu	W	Mo	Fe	B	Si	Others max.
2.1	NiCuBSi 76 20	0,05 max.	balance	—	—	19 to 20	—	—	0,5 max	0,9 to 1,3	1,8 to 2,0	0,5
2.2	NiBSi 96	0.05 max.	balance	—	—	—	—	—	0,5 max	1,0 to 1,5	2,0 to 2,5	0,5
2.3	NiBSi 94	0,1 max.	balance	—	—	—	—	—	0,5 max	1,5 to 2,0	2,8 to 3,7	0,5
2.4	NiBSi 95	0,1 to 0,2	balance	—	—	—	—	—	2,0 max	1,2 to 1,7	2,2 to 2,8	0,5
2.5	NiCrBSi 90 4	0,1 to 0,2	balance	—	3 to 5	—	—	—	1,0 max	1,4 to 1,8	2,8 to 3,5	0,5
2.6	NiCrBSi 86 5	0,15 to 0,25	balance	—	4 to 6	—	—	—	3,0 to 3,5	0,8 to 1,2	2,8 to 3,2	0,5
2.7	NiCrBSi 88 5	0,15 to 0,25	balance	—	4 to 6	—	—	—	1,0 to 2,0	1,0 to 1,5	3,5 to 4,0	0,5
2.8	NiCrBSi 83 10	0,15 to 0,25	balance	—	8 to 12	—	—	—	1,5 to 3,5	2,0 to 2,5	2,3 to 2,8	0,5
2.9	NiCrBSi 85 8	0,15 to 0,25	balance	—	6 to 10	—	—	—	1,5 to 2,0	1,5 to 2,0	2,6 to 3,4	0,5
2.10	NiCrBSi 84 8	0,25 to 0,4	balance	—	7 to 10	—	—	—	1,7 to 2,5	1,5 to 2,2	3,2 to 4,0	0,5
2.11	NiCrBSi 88 4	0,3 to 0,4	balance	—	3,5 to 4,5	—	—	—	2 max	1,6 to 2,0	3,0 to 3,5	0,5
2.12	NiCrBSi 80 11	0,35 to 0,6	balance	—	10 to 12	—	—	—	2,5 to 3,5	2,0 to 2,5	3,5 to 4,0	0,5
2.13	NiCrWBSi 64 11 16	0,5 to 0,6	balance	—	10 to 12	—	15,5 to 16,5	—	3,5 to 4,0	2,3 to 2,7	3,0 to 3,5	0,5
2.14	NiCrCuMoBSi 67 17 3 3	0,5 to 0,7	balance	—	16 to 17	2,0 to 3,5	—	2,0 to 3,0	2,5 to 3,5	3,4 to 4,0	4,0 to 4,5	0,5
2.15	NiCrCuMoWBSi 64 17 3 3 3	0,4 to 0,6	balance	—	16 to 17	2,0 to 3,5	2,0 to 3,0	2,0 to 3,0	3,0 to 5,0	3,5 to 4,0	4,0 to 4,5	0,5
2.16	NiCrBSi 74 15	0,75 to 1,0	balance	—	16 to 17	—	—	—	3,5 to 5,0	2,8 to 3,5	3,6 to 4,5	0,5

Table 3 (continued)

Code number	Abbreviated designation	Chemical composition, %										
		C	Ni	Co	Cr	Cu	W	Mo	Fe	B	Si	Others max.
2.17	NiCrBSi 65 25	0,8 to 1,0	balance	—	24 to 26	—	—	—	0,2 to 1,0	3,2 to 3,6	4,0 to 4,5	0,5
2.18	NiCrBSi 74 14	0,05 max.	balance	—	13 to 15	—	—	—	4,0 to 5,0	2,75 to 3,5	4,0 to 5,0	0,5
2.19	NiCrBSi 82 7	0,06 max.	balance	—	6,5 to 8,5	—	—	—	2,5 to 3,5	2,5 to 3,5	4,1 to 4,6	0,5
2.20	NiBSi 92	0,06 max.	balance	—	—	—	—	—	0,5 max.	2,75 to 3,5	4,3 to 4,7	0,5
2.21	NiCoBSi 71 20	0,05 max.	balance	20	—	—	—	—	0,5 max.	2,7 to 3,2	4,0 to 5,0	0,5
2.22	CoCrNiMoBSi 40 18 27 5	0,1 max.	26 to 28	balance	18 to 19	—	—	4,0 to 6,0	2,0 max.	3,0 to 3,4	3,0 to 3,5	0,5
2.23	CoCrNiMoBSi 50 18 17 6	0,1 to 0,3	17 to 19	balance	18 to 20	—	—	6,0 to 8,0	2,5 max.	3,0	3,5	0,5
2.24	CoCrNiWBSi 53 20 13 7	0,75 to 1,0	13 to 16	balance	19 to 20	—	6 to 8	—	3,0 max.	1,5 to 1,8	2,4 to 2,5	0,5
2.25	CoCrNiWBSi 52 19 15 9	0,8 to 1,1	13 to 16	balance	19 to 20	—	8 to 10	—	3,0 max.	1,5 to 1,8	2,4 to 2,5	0,5
2.26	CoCrNiWBSi 47 19 15 13	1,0 to 1,3	13 to 16	balance	19 to 20	—	12,5 to 13,5	—	3,0 max.	1,5 to 2,0	2,0 to 2,5	0,5
2.27	CoCrNiWBSi 45 19 15 15	1,3 to 1,6	13 to 16	balance	19 to 20	—	14,5 to 15,5	—	3,0 max.	2,8 to 3,0	2,7 to 3,5	0,5

Table 4 — Nickel–chromium–iron metallic alloys and composite powder

Code number	Abbreviated designation	Chemical composition, %											
		Ni	Cr	Al	W	Co	Mo	Fe	Si	Mn	Ti	C max.	Others
3.1	NiCr 80 20	balance	18 to 21	—	—	—	—	≤ 1	≤ 1,5	≤ 2,5	—	0,25	—
3.2	NiCrFe 75 15 8	balance	14 to 17	—	—	—	—	6 to 10	—	—	—	0,30	—
3.3	NiCrAl 74 19 5	balance	17 to 20	3 to 6	—	—	—	≤ 1	≤ 1,5	≤ 2,5	—	0,25	—
3.4	NiCrNb 70 21 4	balance	20 to 22	0,3 to 0,5	—	—	—	2 to 3	0,4 to 0,6	0,4 to 0,6	0,3 to 0,5	0,1	3 to 4 Nb
3.5	NiCrMoW 54 16 17 5	balance	14 to 18	—	4 to 6	—	16 to 18	≤ 6	≤ 1,0	≤ 0,5	—	0,5	—
3.6	NiCrAlMoFe 73 9 7 6 5	balance	8 to 10	6 to 8,8	—	—	4 to 6	4 to 6	—	—	—	—	—
3.7	NiCrTiAl 75 20 3 2	balance	18 to 22	1,5 to 2,5	—	—	—	—	—	—	2 to 3	—	—
3.8	NiCrCoAlTi 67 16 9 4 4	balance	15 to 17	3 to 4	2 to 3	8 to 9	1 to 3	0,4 to 0,6	≤ 0,3	≤ 0,2	3 to 4	0,2	—
3.9	NiCoCrAlMoTi 63 15 10 5 3 4	balance	8 to 12	4 to 6	—	14 to 16	2 to 4	—	—	—	4 to 5	0,2	—
3.10	NiCoCrAlMoTi 57 17 11 5 6 4	balance	10 to 12	4 to 5	—	15 to 18	5 to 7	≤ 0,5	≤ 0,2	—	3 to 5	0,03	—
3.11	NiCr 50 50	balance	50 to 53	—	—	—	—	—	≤ 2	≤ 1	—	0,5	—
3.12	NiCrMoNb 64 22 9 3,5	balance	20 to 23	—	—	—	8 to 10	1	≤ 0,25	—	—	0,01	3 to 4 Nb
3.13	NiCrCoMoTiAlW 57 18 12 6 3 2 1	balance	17 to 19	1,5 to 2,5	1	—	5 to 7	—	—	—	2,5 to 3,5	—	—
3.14	NiCrNbFeAl 66 14 7 8 5,5	balance	11,5 to 16	2,5 to 4,5	—	11 to 13	—	6 to 9,5	—	0,4 to 0,6	0,3 to 0,5	0,1	6,5 to 7,5 Nb
3.15	NiCrFeAlMo 68 14 7 5 5	balance	12 to 16	4 to 6	—	—	4 to 6	5 to 9	—	—	—	—	—
3.16	NiCrAlMoTiO ₂ 68 8 7 5 2,5	balance	7 to 10	5 to 9	—	—	3 to 7	1 to 3	—	—	—	—	2,5 TiO ₂ 2 B
3.17	FeCrMoAl 65 23 5 5	≤ 0,5	20 to 25	4 to 6	—	—	3 to 7	balance	—	—	—	0,1 to 0,5	—

Table 5 — MCrAlY metallic alloys and composite powders

Code number	Abbreviated designation	Chemical composition, %								
		Ni	Cr	Al	Co	Fe	Si	Y	C max.	Others
4.1	NiCrAlY 66 22 10 1	balance	21 to 23	9 to 11	—	—	—	0,8 to 1,2	—	—
4.2	NiCrAlY 70 23 6	balance	22 to 24	5 to 7	—	—	—	0,3 to 0,5	—	—
4.3	NiCoCrAlY 46 23 17 13	balance	15 to 19	11,5 to 13,5	20 to 26	—	—	0,2 to 0,7	—	—
4.4	NiCoCrAlY 47 22 17 13	balance	15 to 19	11,5 to 13,5	20 to 24	—	—	0,4 to 0,8	—	—
4.5	NiCoCrAlYSiHf 47 22 17 13	balance	15 to 19	11,8 to 13,2	20 to 24	—	0,2 to 0,6	0,4 to 0,8	—	0,1 to 0,4 Hf
4.6	CoCrAlY 63 23 13	—	22 to 24	12 to 14	balance	—	—	0,55 to 0,75	—	—
4.7	CoNiCrAlY 38 32 21 8	31 to 33	20 to 22	7 to 9	balance	—	—	0,35 to 0,65	—	—
4.8	CoCrNiAlYT 52 25 10 7,5	8 to 12	23 to 27	5 to 9	balance	—	—	0,4 to 0,8	—	4 to 6 Ta
4.9	FeCrAlY 74 20 5	—	18 to 22	18 to 22	—	balance	—	0,3 to 0,7	0,02	—

Table 6 — Nickel–aluminium–iron metallic alloys and composite powders

Code number	Abbreviated designation	Chemical composition, %						
		Ni	Al	Mo	Fe max.	Si max.	Mn max.	C max.
5.1	NiAl 95 5	balance	3 to 6	—	1	0,5	—	—
5.2	NiAl 70 30	balance	28 to 32	—	1	0,5	1	0,25
5.3	NiAl 80 20	balance	18 to 22	—	1	0,5	1	0,25
5.4	NiAlMo 90 5 5	balance	3 to 6	4 to 6	1	0,5	—	—
5.5	NiAlMo 89 10 1	balance	8 to 12	0,5 to 1,5	1	0,5	—	—
5.6	FeNiAl 51 38 10	36 to 40	8 to 12	—	balance	—	—	—
5.7	FeNiAlMo 54 35 5 5	33 to 37	3 to 6	3 to 7	balance	—	—	—

Table 7 — High alloy steels

Code number	Abbreviated designation	Chemical composition, %									
		Ni	Cr	Mo	Fe	Si	Mn	P max.	S max.	C	Others
6.1	X42Cr 13	—	11,5 to 13,5	—	balance	0,3 to 0,5	0,2 to 0,4	0,03	0,03	0,38 to 0,45	
6.2	X105CrMo 17	—	16 to 18	0,4 to 0,8	balance	≤ 1	≤ 1	0,045	0,03	0,95 to 1,20	
6.3	X2CrNi 18 9	10 to 12,5	17 to 20	—	balance	≤ 1	≤ 2	0,045	0,03	≤ 0,03	
6.4	X5CrNi 18 9	8,5 to 10	17 to 20	—	balance	≤ 1	≤ 2	0,045	0,03	≤ 0,07	
6.5	X2CrNiMo 18 10	11 to 14	16,5 to 18,5	2 to 2,5	balance	≤ 1	≤ 2	0,045	0,03	≤ 0,03	
6.6	X2CrNiMo 18 12	12,5 to 15	16,5 to 18,5	2,5 to 3	balance	≤ 1	≤ 2	0,045	0,03	≤ 0,03	
6.7	X5CrNiMo 18 10	9,5 to 13,5	16,5 to 20,0	2 to 2,5	balance	≤ 1	≤ 2	0,045	0,03	≤ 0,07	
6.8	X5CrNiMo 18 12	11,5 to	16,5 to 18,5	2,5 to 3,0	balance	≤ 1	≤ 2	0,045	0,03	≤ 0,07	
6.9	X10CrNiMo 17 13	12 to 14	16 to 18	2 to 2,5	balance	≤ 0,75	≤ 2	0,045	0,03	0,08 to 0,11	
6.10	X2NiCrMoCu 25 20 5	24 to 26	19 to 21	4 to 5	balance	≤ 1	≤ 2	0,03	0,02	≤ 0,02	
6.11	X130CrMoWV 5 5 5 4	—	4 to 5	4 to 5	balance	—	—	—	—	1,0 to 1,5	V 3,5 to 4,5 W 5 to 6

Table 8 — Cobalt–chromium metallic alloys and composites

Code number	Abbreviated designation	Chemical composition, %										
		Ni	Cr	W	Co	Mo	Cu	Fe max.	Si	Mn max.	C	Others
7.1	CoCrW 50 30 12	≤ 3	29 to 31	11,5 to 13,5	balance	—	—	3	0,8 to 1,1	—	2,3 to 2,5	—
7.2	CoCrW 60 28 4	≤ 3	27 to 30	3,5 to 5	balance	—	—	3	0,8 to 1,1	—	0,9 to 1,2	—
7.3	CoCrW 53 30 8	≤ 3	29 to 31	7,5 to 9	balance	—	—	3	1,0 to 1,6	—	1,3 to 1,6	—
7.4	CoCrNiW 50 26 10 7	9,5 to 11,5	24 to 27	6,5 to 8,5	balance	—	—	2	≤ 0,6	0,6	≤ 0,5	—
7.5	CoCrMo 60 27 5	≤ 3	25 to 29	—	balance	4,5 to 6,5	—	3	≤ 2,5	1	≤ 0,3	—
7.6	CoCrNiW 40 25 22 10	20 to 24	23 to 27	10 to 14	balance	—	—	—	—	1	1,5 to 2,0	—
7.7	CoMoCrSi 51 28 17 3	≤ 1,5	16 to 19	—	balance	27 to 30	—	1,5	3 to 4	—	—	—
7.8	CoCrNiNb 50 28 7 6	5,5 to 7,5	26 to 30	—	balance	2,5 to 4,5	1,4 to 1,8	2	≤ 0,6	0,6	1,8 to 2,2	Nb 4,5 to 6,5

Table 9 — Copper-aluminium alloys and composites; copper-tin and copper nickel alloys

Code number	Abbreviated designation	Chemical composition, %						
		Ni	Al	Cu	Fe max.	Sn	P max.	Others
8.1	CuAl10	—	9 to 11	balance	—	—	—	—
8.2	CuAl10Fe	—	9 to 11	balance	1	—	—	—
8.3	CuAl10Ni	2 to 5	9 to 11	balance	—	—	—	—
8.4	CuSn8	—	—	balance	—	7,5 to 9	0,4	—
8.5	CuNi38	35 to 40	—	balance	—	—	—	—
8.6	CuNi36In	35 to 38	—	balance	1	—	—	4 to 6 In

Table 10 —Aluminium alloys

Code number	Abbreviated designation	Chemical composition, %	
		Al	Si
9.1	AlSi 88 12	balance	11 to 13

Table 11 — Nickel-graphite composites

Code number	Abbreviated designation	Chemical composition, %		
		Ni	Co max.	Graphite
10.4	Ni-graphite 60/40	59 to 62	0,5	balance
10.5	Ni-graphite 75/25	74 to 76	0,5	balance
10.6	Ni-graphite 80/20	79 to 81	0,5	balance
10.7	Ni-graphite 85/15	84 to 86	0,5	balance

4.4 Carbides, carbides with metals, carbides with metallic alloys and composites

Table 12 — Carbides, carbides with metals, carbides with metallic alloys and composites

Code number	Abbreviated designation	Chemical composition, %							
		W	Cr	Ti min.	Co	Ni	C	Fe max.	Si max.
11.1	TiC ^a	—	—	79,5	—	—	19 to 20	—	—
11.2	WC ^a	balance	—	—	—	—	6,0 to 6,2	—	—
11.3	W ₂ C/MC ^a	balance	—	—	—	—	3,8 to 4,3	—	—
11.4	W ₂ C ^a	balance	—	—	—	—	3,1 to 3,3	—	—
11.5	Cr ₃ C ₂ ^a	—	≥ 86	—	—	—	≥ 12,5	0,7	0,1
11.10	WC/Co 94 6	balance	—	—	5 to 7	—	≥ 5,2	—	—
11.11	WC/Co 88 12	balance	—	—	11 to 13	—	3,6 to 4,2	—	—
11.12	WC/Co 88 12	balance	—	—	11 to 13	—	4,8 to 5,5	—	—
11.13	WC/Co 83 17	balance	—	—	16 to 18	—	≥ 4,8	—	—
11.14	WC/Co 80 20	balance	—	—	18 to 20	—	4,5 to 5,0	—	—
11.15	W ₂ C/Co	balance	—	—	18 to 21	—	2,4 to 2,6	—	—
11.16	WC/Ni 92 8	balance	—	—	—	6 to 8	3,5 to 4,0	—	—
11.17	WC/Ni 88 12	balance	—	—	—	11 to 13	5,0 to 5,5	—	—
11.18	WC/Ni 85 15	balance	—	—	—	14 to 16	3 to 4	—	—
11.19	WC/Ni 83 17	balance	—	—	—	16 to 19	4,5 to 5,5	—	—
11.20	WC/Co/Cr 86 10 4	balance	3,5 to 4,5	—	9 to 11	—	3,5 to 4,5	—	—
11.21	WCrC/Ni 93 7	balance	22 to 28	—	—	6 to 8	5 to 7	—	—
11.30	Cr ₃ C ₂ /NiCr 75 25	—	balance	—	—	16 to 19	10 to 11	—	—
11.31	Cr ₃ C ₂ /NiCr 75 25	—	balance	—	—	19 to 21	9 to 10	—	—
11.32	Cr ₃ C ₂ /NiCr 80 20	—	balance	—	—	14 to 18	9 to 11	—	—

^a These powders are blended with other powders.

4.5 Oxides, phosphates and non-carbide ceramics

Table 13 — Oxides, phosphates and non-carbide ceramic powders

Code number	Abbreviated designation	Chemical composition, %								
		Al ₂ O ₃	TiO ₂	Cr ₂ O ₃	ZrO ₂	MgO/CeO ₂ /H-A	Y ₂ O ₃	CaO	FeO max.	SiO ₂
12.1	Al ₂ O ₃	≥ 99,5	—	—	—	—	—	—	0,1	≤ 0,1
12.2	Al ₂ O ₃ -TiO ₂ 97 3	≥ 96	2,5 to 3,5	—	—	—	—	—	1	≤ 1
12.3	Al ₂ O ₃ -TiO ₂ 87 13	balance	12 to 14	—	—	—	—	—	0,5	≤ 1
12.4	Al ₂ O ₃ -TiO ₂ 60 40	balance	37 to 42	—	—	—	—	—	—	—
12.5	Al ₂ O ₃ -MgO 70 30	balance	—	—	—	MgO 28 to 31	—	—	0,5	≤ 1,5
12.6	Al ₂ O ₃ -SiO ₂ 70 30	balance	—	—	—	—	—	—	0,2	22 to 28
12.7	Al ₂ O ₃ -Cr ₂ O ₃ 98 2	≥ 97,5	—	1,5 to 2,1	—	—	—	—	0,1	≤ 0,3
12.8	Al ₂ O ₃ -Cr ₂ O ₃ 90 10	balance	—	8 to 12	—	—	—	—	0,1	≤ 0,2
12.9	Al ₂ O ₃ -Cr ₂ O ₃ 50 50	balance	—	48 to 52	—	—	—	—	0,1	≤ 0,2
12.20	Cr ₂ O ₃	—	—	≥ 99,5	—	—	—	—	0,1	≤ 0,25
12.21	Cr ₂ O ₃	≤ 1,0	—	≥ 96	—	—	—	—	1	≤ 1
12.22	Cr ₂ O ₃ -TiO ₂ 97 3	—	≤ 3	≥ 96,5	—	—	—	—	0,5	—
12.23	Cr ₂ O ₃ -TiO ₂ 45 55	—	53 to 56	balance	—	—	—	—	0,5	≤ 0,5
12.24	Cr ₂ O ₃ -TiO ₂ 60 40	—	38 to 42	balance	—	—	—	—	0,5	≤ 0,5
12.25	Cr ₂ O ₃ -SiO ₂ -TiO ₂ 92 5 3	—	2 to 4	balance	—	—	—	—	0,5	4 to 6
12.30	TiO ₂	—	≥ 99	—	—	—	—	—	0,5	≤ 0,5
12.40	ZrO ₂ -CaO 95 5	≤ 0,5	—	—	balance	—	—	5 to 7	—	≤ 0,4
12.41	ZrO ₂ -CaO 90 10	≤ 0,5	—	—	balance	—	—	8 to 10	—	≤ 0,4
12.42	ZrO ₂ -CaO 70 30	≤ 0,5	—	—	balance	—	—	28 to 31	—	—
12.43	ZrO ₂ -MgO 80 20	—	—	—	balance	MgO 18 to 24	—	1,5	—	≤ 1,5
12.44	ZrO ₂ -Y ₂ O ₃ 93 7	≤ 0,2	≤ 0,3	—	balance	—	6 to 8	—	0,2	≤ 0,5
12.45	ZrO ₂ -Y ₂ O ₃ 80 20	—	—	—	balance	—	18 to 21	—	0,2	≤ 0,5
12.46	ZrO ₂ -SiO ₂ 65 35	—	≤ 0,3	—	balance	—	—	—	0,3	32 to 35
12.47	ZrO ₂ -CeO ₂ -Y ₂ O ₃ 68-25-3	—	—	—	balance	CeO ₂ 24 to 26	2 to 4	—	0,2 to 0,5	0,5 to 1,5
12.60	Hydroxylapatite	—	—	—	—	≥ H-A 95 ^a	—	—	—	—

^a Other impurities: As 0,000 3 max.; Cd 0,000 5 max.; Hg 0,000 5 max.; Pb 0,003 max.; Total max. 0,1.

4.6 Organic materials

A number of organic spray materials (synthetics) are currently being evaluated. The most frequently used materials are an ethylene–hydroethylene copolymer and a polyester, both of which are used for powder flame spraying.

5 Designation

Spray powders conforming to this International Standard shall be designated in accordance with the following example.

EXAMPLE

A sintered tungsten-carbide-cobalt alloy powder containing 12 % Co and approximately 5 % C (Code Number 11.12) with a particle size range of 45/5 μm , is designated as follows:

Spray powder ISO 14232 - 11.12 - 45/5 - sintered

6 Conditions of supply

Powders shall be dry and free of impurities, and shall be delivered in airtight and damp-proof sheet metal containers. Special packaging, e.g., vacuum containers with flange connections, is to be agreed upon with the powder manufacturer or supplier.

The powder containers shall be labelled "Mix before using" and "For powder processing, safety regulations shall be observed, as defined in the safety regulation sheet".

7 Powder identification

The uniform identification of powders for thermal spraying should serve to designate a spray powder in a brief and well-defined (unmistakable) form.

8 Certification

The manufacturer/supplier shall certify that every batch of his products meet the requirements of this International Standard, documented by a test certificate accompanying the thermal spray powder.

This certificate, in addition to the results of chemical and physical analysis — as far as specified and /or agreed upon between customer and manufacturer — shall contain the product designation and batch number.