
**Welding consumables — Wire
electrodes, strip electrodes, wires and
rods for arc welding of stainless and
heat resisting steels — Classification**

Produits consommables pour le soudage — Fils-électrodes, électrodes en feuillard, fils d'apport et baguettes de soudage pour le soudage à l'arc des aciers inoxydables et des aciers résistant aux températures élevées — Classification



STANDARDSISO.COM : Click to view the full PDF of ISO 14343:2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	2
4.1 General	2
4.2 Symbols for products/processes	2
4.3 Symbols for chemical composition	2
5 Properties of all-weld metal	12
6 Chemical analysis	12
7 Rounding procedure	12
8 Retesting	12
9 Technical delivery conditions	12
10 Examples of designation	12
Annex A (informative) Expected minimum tensile properties of all-weld metal	14
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This third edition cancels and replaces the second edition (ISO 14343:2009), which has been technically revised and contains the following changes:

- a number of new alloy designations have been added to [Table 1](#) and [Table A.1](#);
- the chemistries of some alloy designations have been revised in [Table 1](#);
- the mechanical properties of some alloy designations have been revised in [Table A.1](#);
- [Clause 7](#) has been updated to new text for all new and revised standards;
- examples for Z designations have been added to [Clause 10](#).

Requests for official interpretations of any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Introduction

This document provides a classification system for wire electrodes, strip electrodes, wires and rods for arc welding of stainless and heat resisting steels. It recognizes that there are two somewhat different approaches in the global market to classifying a given welding consumable, and allows for either or both to be used, to suit a particular market need. Many, but not all, commercial products addressed by this document can be classified using both approaches, and suitable products can also be marked.

System A uses the *nominal composition* approach with designators to indicate the principal alloying elements at their nominal levels, in a particular sequence, and which is sometimes followed by chemical element symbols to indicate compositional modifications to the original grade. System B uses the *alloy type* approach with three- or four-digit designations for certain grades, sometimes followed by one or more chemical element symbols indicating compositional modifications of the grade. In both approaches, classification is based upon the chemical composition of the product. In many cases, a given product can be classified using both approaches, because the composition ranges, although slightly different, overlap to a considerable extent between the two.

For stainless steel welding consumables, there is no unique relationship between the product form (wire electrode, strip electrode, wire or rod) and the welding process used (gas-shielded metal arc welding, gas tungsten arc welding, plasma arc welding, submerged arc welding, electroslag welding and laser beam welding). For this reason, the wire electrodes, strip electrodes, wires or rods can be classified on the basis of any of the above product forms and can be used, as appropriate, for more than one of the above processes.

Classification according to system A, by nominal composition, is based mainly on EN 12072^[1], while that of system B, by alloy type, is mainly based upon standards used around the Pacific Rim.

STANDARDSISO.COM : Click to view the full PDF of ISO 14343:2017

Welding consumables — Wire electrodes, strip electrodes, wires and rods for arc welding of stainless and heat resisting steels — Classification

1 Scope

This document specifies requirements for classification of wire electrodes, strip electrodes, wires and rods for gas-shielded metal arc welding, gas tungsten arc welding, plasma arc welding, submerged arc welding, electroslag welding and laser beam welding of stainless and heat-resisting steels. The classification of the wire electrodes, strip electrodes, wires and rods is based upon their chemical composition.

This document is a combined specification providing for classification utilizing a system based upon nominal composition (system A), or utilizing a system based upon alloy type (system B).

- a) Paragraphs which carry the label “classification according to nominal composition” and the suffix letter “A”, or “ISO 14343-A”, are applicable only to products classified according to system A;
- b) Paragraphs which carry the label “classification according to alloy type” and the suffix letter “B”, or “ISO 14343-B”, are applicable only to products classified according to system B.
- c) Paragraphs which carry neither label nor suffix letter are applicable to products that can be classified according to either system A or B or both.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 80000-1:2009, *Quantities and units — Part 1: General*. Corrected by ISO 80000-1:2009/Cor 1:2011

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 rod

form of welding filler metal, normally packaged in straight lengths, that does not conduct the welding current, used in gas tungsten arc and plasma arc welding

3.2

strip electrode

form of welding filler metal, normally packaged as coils, having a rectangular cross-section of width much greater than thickness, that becomes part of the welding circuit through which current is conducted, and that terminates at the arc for submerged arc welding, or at the slag bath for electroslag welding

3.3

wire

form of welding filler metal, normally packaged as coils, spools or drums, that does not conduct the welding current, for gas tungsten arc, plasma arc welding and laser beam welding

3.4

wire electrode

form of welding filler metal, normally packaged as coils, spools or drums, that becomes part of the welding circuit through which electrical current is conducted, and that terminates at the arc, used in gas-shielded metal arc and submerged arc welding

4 Classification

4.1 General

A wire electrode, strip electrode, wire or rod shall be classified according to its chemical composition as given in [Table 1](#).

The classification is divided into two parts:

- a) the first gives a symbol indicating the product/process to be identified;
- b) the second gives a symbol indicating the chemical composition of the wire electrode, strip electrode, wire or rod.

4.2 Symbols for products/processes

4.2A Classification according to nominal composition

The symbol for the wire electrode, strip electrode, wire or rod used in the arc welding process shall be the letter

- “G” for gas metal arc welding,
- “W” for gas tungsten arc welding,
- “P” for plasma arc welding,
- “S” for submerged arc welding,
- “B” for submerged arc welding or electroslag welding with strip electrode, or
- “L” for laser beam welding, placed at the beginning of the designation.

See [Clause 10](#) for designation examples.

4.2B Classification according to alloy type

No symbol is used to indicate the welding process.

The symbol for solid stainless and heat-resisting steel wire electrodes, wires and rods for use in all welding processes shall be the letters “SS”. The initial “S” indicates solid wire as distinguished from covered electrodes or from tubular cored wires or tubular cored rods.

The symbol for strip electrodes for use in submerged arc welding or electroslag welding shall be the letters “BS”. The “B” indicates a strip electrode, while the second “S” in “SS” and the “S” in “BS” indicates that the alloy system is stainless or heat-resisting steel.

See [Clause 10](#) for designation examples.

4.3 Symbols for chemical composition

The symbols presented in [Table 1](#) indicate the chemical composition of the wire electrode, strip electrode, wire or rod determined using the analysis specified in [Clause 6](#).

Table 1 — Chemical composition requirements

Alloy designation ^a according to		Chemical composition, % by mass ^b											
Nominal composition ^c ISO 14343-A	Alloy type ISO 14343-B ^c	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^d	Other
Martensitic/ferritic types													
—	409	0,08	0,8	0,8	0,03	0,03	10,5 to 13,5	0,6	0,50	—	0,75	—	Ti 10 × C to 1,5
—	409Nb	0,08	1,0	0,8	0,04	0,03	10,5 to 13,5	0,6	0,50	—	0,75	10 × C to 0,75	—
13	(410)	0,15	1,0	1,0	0,03	0,02	12,0 to 15,0	0,5	0,5	—	0,5	—	—
(13)	410	0,12	0,5	0,6	0,03	0,03	11,5 to 13,5	0,6	0,75	—	0,75	—	—
13 L	—	0,05	1,0	1,0	0,03	0,02	12,0 to 15,0	0,5	0,5	—	0,5	—	—
13 4	(410NiMo)	0,05	1,0	1,0	0,03	0,02	11,0 to 14,0	3,0 to 5,0	0,4 to 1,0	—	0,5	—	—
(13 4)	410NiMo	0,06	0,5	0,6	0,03	0,03	11,0 to 12,5	4,0 to 5,0	0,4 to 0,7	—	0,75	—	—
—	420	0,25 to 0,40	0,5	0,6	0,03	0,03	12,0 to 14,0	0,6	0,75	—	0,75	—	—
16 5 1	—	0,04	0,2 to 0,7	1,2 to 3,5	0,02	0,01	15,0 to 17,0	4,5 to 6,5	0,9 to 1,5	—	0,5	—	—
17	(430)	0,12	1,0	1,0	0,03	0,02	16,0 to 19,0	0,5	0,5	—	0,5	—	—
(17)	430	0,10	0,5	0,6	0,03	0,03	15,5 to 17,0	0,6	0,75	—	0,75	—	—
—	430Nb	0,10	0,5	0,6	0,03	0,03	15,5 to 17,0	0,6	0,75	—	0,75	8 × C to 1,2	—
(18 L Nb)	430LNb	0,03	0,5	0,6	0,03	0,03	15,5 to 17,0	0,6	0,75	—	0,75	8 × C to 1,2	—
18 L Nb	(430LNb)	0,03	0,5	0,8	0,03	0,02	17,8 to 18,8	0,5	0,5	0,02	0,5	0,05 + 7(C+N) to 0,6	—
18 L Nb Si	—	0,03	0,5 to 1,5	1,0	0,03	0,03	17,5 to 19,5	0,5	0,5	0,02	0,5	0,05 + 7(C+N) to 0,6	—
18 L Nb Ti	—	0,03	1,5	1,0	0,03	0,03	17,5 to 19,5	0,5	0,5	0,02	0,5	8 × C to 0,8	Ti 10 × C to 0,5

Table 1 (continued)

Alloy designation ^a according to		Chemical composition, % by mass ^b											
Nominal composition ^c ISO 14343-A	Alloy type ISO 14343-B ^c	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^d	Other
—	439	0,04	0,8	0,8	0,03	0,03	17,0 to 19,0	0,6	0,5	—	0,75	—	Ti 10 × C to 1,1
—	446LMo	0,015	0,4	0,4	0,02	0,02	25,0 to 27,5	g	0,75 to 1,00	0,015	g	—	—
Austenitic types													
—	209	0,05	0,90	4,0 to 7,0	0,03	0,03	20,5 to 24,0	9,5 to 12,0	1,5 to 3,0	0,10 to 0,30	0,75	—	V 0,10 to 0,30
—	218	0,10	3,5 to 4,5	7,0 to 9,0	0,03	0,03	16,0 to 18,0	8,0 to 9,0	0,75	0,08 to 0,18	0,75	—	—
—	219	0,05	1,00	8,0 to 10,0	0,03	0,03	19,0 to 21,5	5,5 to 7,0	0,75	0,10 to 0,30	0,75	—	—
—	240	0,05	1,00	10,5 to 13,5	0,03	0,03	17,0 to 19,0	4,0 to 6,0	0,75	0,10 to 0,30	0,75	—	—
—	308	0,08	0,30 to 0,65	1,0 to 2,5	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
—	308Si	0,08	0,65 to 1,00	1,0 to 2,5	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
19 9 L	(308L)	0,03	0,65	1,0 to 2,5	0,03	0,02	19,0 to 21,0	9,0 to 11,0	0,5	—	0,5	—	—
(19 9 L)	308L	0,03	0,30 to 0,65	1,0 to 2,5	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
19 9 L Si	(308LSi)	0,03	0,65 to 1,2	1,0 to 2,5	0,03	0,02	19,0 to 21,0	9,0 to 11,0	0,5	—	0,5	—	—
(19 9 L Si)	308LSi	0,03	0,65 to 1,00	1,0 to 2,5	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
—	308N2	0,10	0,90	1,0 to 4,0	0,03	0,03	20,0 to 25,0	7,0 to 11,0	0,75	0,12 to 0,30	0,75	—	—
19 9 Nb	(347)	0,08	0,65	1,0 to 2,5	0,03	0,02	19,0 to 21,0	9,0 to 11,0	0,5	—	0,5	10 × C to 1,0	—

Table 1 (continued)

Alloy designation ^a according to		Chemical composition, % by mass ^b											
Nominal composition ^c ISO 14343-A	Alloy type ISO 14343-B ^c	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^d	Other
(19 9 Nb)	347	0,08	0,30 to 0,65	1,0 to 2,5	0,03	0,03	19,0 to 21,5	9,0 to 11,0	0,75	—	0,75	10 × C to 1,0	—
19 9 Nb Si	(347Si)	0,08	0,65 to 1,2	1,0 to 2,5	0,03	0,02	19,0 to 21,0	9,0 to 11,0	0,5	—	0,5	10 × C to 1,0	—
(19 9 Nb Si)	347Si	0,08	0,65 to 1,00	1,0 to 2,5	0,03	0,03	19,0 to 21,5	9,0 to 11,0	0,75	—	0,75	10 × C to 1,0	—
—	347L	0,03	0,65	1,0 to 2,5	0,03	0,03	19,0 to 21,5	9,0 to 11,0	0,75	—	0,75	10 × C to 1,0	—
—	347H	0,04 to 0,08	0,65	1,0 to 2,5	0,03	0,03	19,0 to 21,5	9,0 to 11,0	0,75	—	0,75	10 × C to 1,0	—
—	316	0,08	0,30 to 0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
—	316Si	0,08	0,65 to 1,00	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
19 12 3 L	(316L)	0,03	0,65	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,5 to 3,0	—	0,5	—	—
(19 12 3 L)	316L	0,03	0,30 to 0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
19 12 3 L Si	(316LSi)	0,03	0,65 to 1,2	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,5 to 3,0	—	0,5	—	—
(19 12 3 L Si)	316LSi	0,03	0,65 to 1,00	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
—	316LCu	0,03	0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	1,0 to 2,5	—	—
19 12 3 Nb	(318)	0,08	0,65	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,5 to 3,0	—	0,5	10 × C to 1,0	—
(19 12 3 Nb)	318	0,08	0,30 to 0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	8 × C to 1,0; 0,2 min.	—
—	318L	0,03	0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	8 × C to 1,0; 0,2 min.	—

Table 1 (continued)

Alloy designation ^a according to		Chemical composition, % by mass ^b											
Nominal composition ^c ISO 14343-A	Alloy type ISO 14343-B ^c	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^d	Other
19 12 3 Nb Si	—	0,08	0,65 to 1,2	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,5 to 3,0	—	0,5	10 × C to 1,0	—
—	317	0,08	0,30 to 0,65	1,0 to 2,5	0,03	0,03	18,5 to 20,5	13,0 to 15,0	3,0 to 4,0	—	0,75	—	—
(18 15 3 L)	317L	0,03	0,30 to 0,65	1,0 to 2,5	0,03	0,03	18,5 to 20,5	13,0 to 15,0	3,0 to 4,0	—	0,75	—	—
—	321	0,08	0,30 to 0,65	1,0 to 2,5	0,03	0,03	18,5 to 20,5	9,0 to 10,5	0,75	—	0,75	—	Ti 9 × C to 1,0; 0,2 min.
Ferritic-austenitic types (sometimes referred to as austenitic-ferritic types)													
22 9 3 N L	(2209)	0,03	1,0	2,5	0,03	0,02	21,0 to 24,0	7,0 to 10,0	2,5 to 4,0	0,10 to 0,20	0,5	—	—
(22 9 3 N L)	2209	0,03	0,90	0,5 to 2,0	0,03	0,03	21,5 to 23,5	7,5 to 9,5	2,5 to 3,5	0,08 to 0,20	0,75	—	—
23 7 N L	2307	0,03	1,0	2,5	0,03	0,02	22,5 to 25,5	6,5 to 9,5	0,8	0,10 to 0,20	0,5	—	—
25 7 2 L	—	0,03	1,0	2,5	0,03	0,02	24,0 to 27,0	6,0 to 8,0	1,5 to 2,5	—	0,5	—	—
25 9 3 Cu N L	—	0,03	1,0	2,5	0,03	0,02	24,0 to 27,0	8,0 to 11,0	2,5 to 4,0	0,10 to 0,20	1,5 to 2,5	—	—
25 9 4 N L	2594	0,03	1,0	2,5	0,03	0,02	24,0 to 27,0	8,0 to 10,5	2,5 to 4,5	0,20 to 0,30	1,5	—	W 1,0
—	329J4L	0,03	0,90	0,5 to 2,5	0,03	0,03	23,0 to 27,0	8,0 to 11,0	3,0 to 4,5	0,08 to 0,30	1,0	—	—
Fully austenitic types ^e													
18 15 3 L ^e	(317L) ^e	0,03	1,0	1,0 to 4,0	0,03	0,02	17,0 to 20,0	13,0 to 16,0	2,5 to 4,0	—	0,5	—	—
18 16 5 N L ^e	—	0,03	1,0	1,0 to 4,0	0,03	0,02	17,0 to 20,0	16,0 to 19,0	3,5 to 5,0	0,10 to 0,20	0,5	—	—

Table 1 (continued)

Alloy designation ^a according to		Chemical composition, % by mass ^b											
Nominal composition ^c ISO 14343-A	Alloy type ISO 14343-B ^c	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^d	Other
19 13 4 L ^e	(317L) ^e	0,03	1,0	1,0 to 5,0	0,03	0,02	17,0 to 20,0	12,0 to 15,0	3,0 to 4,5	—	0,5	—	—
19 13 4 N L ^e	—	0,03	1,0	1,0 to 5,0	0,03	0,02	17,0 to 20,0	12,0 to 15,0	3,0 to 4,5	0,10 to 0,20	0,5	—	—
20 25 5 Cu L ^e	(385) ^e	0,03	1,0	1,0 to 4,0	0,03	0,02	19,0 to 22,0	24,0 to 27,0	4,0 to 6,0	—	1,0 to 2,0	—	—
(20 25 5 Cu L) ^e	385 ^e	0,025	0,50	1,0 to 2,5	0,02	0,03	19,5 to 21,5	24,0 to 26,0	4,2 to 5,2	—	1,2 to 2,0	—	—
20 25 5 Cu N L ^e	—	0,03	1,0	1,0 to 4,0	0,03	0,02	19,0 to 22,0	24,0 to 27,0	4,0 to 6,0	0,10 to 0,20	1,0 to 2,0	—	—
20 16 3 Mn L ^e	—	0,03	1,0	5,0 to 9,0	0,03	0,02	19,0 to 22,0	15,0 to 18,0	2,5 to 4,5	—	0,5	—	—
20 16 3 Mn N L ^e	316LM ^e	0,03	0,30 to 0,65	5,0 to 9,0	0,03	0,03	19,0 to 22,0	15,0 to 18,0	2,5 to 3,5	0,10 to 0,20	0,5	—	—
25 22 2 N L ^e	—	0,03	1,0	3,5 to 6,5	0,03	0,02	24,0 to 27,0	21,0 to 24,0	1,5 to 3,0	0,10 to 0,20	0,5	—	—
26 23 5 Ne	—	0,02	1,0	1,5 to 5,5	0,02	0,01	25,0 to 27,0	21,0 to 25,0	4,0 to 6,0	0,30 to 0,40	0,5	—	—
27 31 4 Cu L ^e	(383) ^e	0,03	1,0	1,0 to 3,0	0,03	0,02	26,0 to 29,0	30,0 to 33,0	3,0 to 4,5	—	0,7 to 1,5	—	—
(27 31 4 Cu L) ^e	383 ^e	0,025	0,50	1,0 to 2,5	0,02	0,03	26,5 to 28,5	30,0 to 33,0	3,2 to 4,2	—	0,7 to 1,5	—	—
—	320 ^e	0,07	0,60	2,5	0,03	0,03	19,0 to 21,0	32,0 to 36,0	2,0 to 3,0	—	3,0 to 4,0	8 × C to 1,0	—
—	320LR ^e	0,025	0,15	1,5 to 2,0	0,015	0,02	19,0 to 21,0	32,0 to 36,0	2,0 to 3,0	—	3,0 to 4,0	8 × C to 0,40	—
—	33–31	0,015	0,50	2,00	0,02	0,01	31,0 to 35,0	30,0 to 33,0	0,5 to 2,0	0,35 to 0,60	0,3 to 1,2	—	—

Table 1 (continued)

Alloy designation ^a according to		Chemical composition, % by mass ^b											
Nominal composition ^c ISO 14343-A	Alloy type ISO 14343-B ^c	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^d	Other
Special types (often used for dissimilar metal joining)													
—	307 ^e	0,04 to 0,14	0,30 to 0,65	3,30 to 4,75	0,03	0,03	19,5 to 22,0	8,0 to 10,7	0,5 to 1,5	—	0,75	—	—
18 8 Mne	—	0,20	1,2	5,0 to 8,0	0,03	0,03	17,0 to 20,0	7,0 to 10,0	0,5	—	0,5	—	—
20 10 3	(308Mo)	0,12	1,0	1,0 to 2,5	0,03	0,02	18,0 to 21,0	8,0 to 12,0	1,5 to 3,5	—	0,5	—	—
(20 10 3)	308Mo	0,08	0,30 to 0,65	1,0 to 2,5	0,03	0,03	18,0 to 21,0	9,0 to 12,0	2,0 to 3,0	—	0,75	—	—
—	308LMo	0,04	0,30 to 0,65	1,0 to 2,5	0,03	0,03	18,0 to 21,0	9,0 to 12,0	2,0 to 3,0	—	0,75	—	—
23 12 L	(309L)	0,03	0,65	1,0 to 2,5	0,03	0,02	22,0 to 25,0	11,0 to 14,0	0,5	—	0,5	—	—
(23 12 L)	309L	0,03	0,30 to 0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
22 11 L ^f	309LD ^f	0,03	0,65	1,0 to 2,5	0,03	0,03	21,0 to 24,0	10,0 to 12,0	0,75	—	0,75	—	—
23 12 L Si	(309LSi)	0,03	0,65 to 1,2	1,0 to 2,5	0,03	0,02	22,0 to 25,0	11,0 to 14,0	0,5	—	0,5	—	—
(23 12 L Si)	309LSi	0,03	0,65 to 1,00	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
23 12 Nb	(309LNb)	0,08	1,0	1,0 to 2,5	0,03	0,02	22,0 to 25,0	11,0 to 14,0	0,5	—	0,5	10 × C to 1,0	—
(23 12 Nb)	309LNb	0,03	0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	10 × C to 1,0; 0,2 min.	—
22 12 L Nb ^f	309LNbD ^f	0,03	0,65	1,0 to 2,5	0,03	0,03	20,0 to 23,0	11,0 to 13,0	0,75	—	0,75	10 × C to 1,2; 0,2 min.	—
—	309Mo	0,12	0,30 to 0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	2,0 to 3,0	—	0,75	—	—

Table 1 (continued)

Alloy designation ^a according to		Chemical composition, % by mass ^b												
Nominal composition ^c ISO 14343-A	Alloy type ISO 14343-B ^c	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^d	Other	
23 12 2 L	(309LMo)	0,03	1,0 0,65	1,0 to 2,5	0,03	0,02	21,0 to 25,0	11,0 to 15,5	2,0 to 3,5	—	0,5	—	—	
(23 12 2 L)	309LMo	0,03	0,30 to 0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	2,0 to 3,0	—	0,75	—	—	
(21 13 3 L)	309LMoD ^f	0,03	0,65	1,0 to 2,5	0,03	0,03	19,0 to 22,0	12,0 to 14,0	2,3 to 3,3	—	0,75	—	—	
21 13 3 L ^f	(309LMoD)	0,03	0,65	1,0 to 2,5	0,03	0,03	19,0 to 22,0	12,0 to 14,0	2,8 to 3,3	—	0,75	—	—	
29 9	(312)	0,15	1,0	1,0 to 2,5	0,03	0,02	28,0 to 32,0	8,0 to 12,0	0,5	—	0,5	—	—	
(29 9)	312	0,15	0,30 to 0,65	1,0 to 2,5	0,03	0,03	28,0 to 32,0	8,0 to 10,5	0,75	—	0,75	—	—	
Heat resisting types														
16 8 2	(16-8-2)	0,10	1,0	1,0 to 2,5	0,03	0,02	14,5 to 16,5	7,5 to 9,5	1,0 to 2,5	—	0,5	—	—	
(16 8 2)	16-8-2	0,10	0,30 to 0,65	1,0 to 2,0	0,03	0,03	14,5 to 16,5	7,5 to 9,5	1,0 to 2,0	—	0,75	—	—	
19 9 H	(19-10H)	0,04 to 0,08	1,0	1,0 to 2,5	0,03	0,02	18,0 to 21,0	9,0 to 11,0	0,5	—	0,5	—	—	
(19 9 H)	19-10H	0,04 to 0,08	0,30 to 0,65	1,0 to 2,0	0,03	0,03	18,5 to 20,0	9,0 to 11,0	0,25	—	0,75	0,05	Ti 0,05	
—	33-31	0,015	0,50	2,00	0,02	0,01	31,0 to 35,0	30,0 to 33,0	0,5 to 2,0	0,35 to 0,60	0,3 to 1,2	—	—	
(19 9 H)	308H	0,04 to 0,08	0,30 to 0,65	1,0 to 2,5	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,50	—	0,75	—	—	
19 12 3 H	(316H)	0,04 to 0,08	1,0	1,0 to 2,5	0,03	0,02	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,5	—	—	
(19 12 3 H)	316H	0,04 to 0,08	0,30 to 0,65	1,0 to 2,5	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—	

Table 1 (continued)

Alloy designation ^a according to		Chemical composition, % by mass ^b											
Nominal composition ^c ISO 14343-A	Alloy type ISO 14343-B ^c	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^d	Other
21 10 Ne	—	0,06 to 0,09	1,0 to 2,0	0,3 to 1,0	0,02	0,01	20,5 to 22,5	9,5 to 11,0	0,5	0,10 to 0,20	0,5	—	Ce 0,03 to 0,08
22 12 H	(309)	0,04 to 0,15	2,0 to 2,5	1,0 to 2,5	0,03	0,02	21,0 to 24,0	11,0 to 14,0	0,5	—	0,5	—	—
(22 12 H)	309	0,12	0,30 to 0,65	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
—	309Si	0,12	0,65 to 1,00	1,0 to 2,5	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
25 4	—	0,15	2,0	1,0 to 2,5	0,03	0,02	24,0 to 27,0	4,0 to 6,0	0,5	—	0,5	—	—
25 20 ^e	(310) ^e	0,08 to 0,15	2,0	1,0 to 2,5	0,03	0,02	24,0 to 27,0	18,0 to 22,0	0,5	—	0,5	—	—
(25 20) ^e	310 ^e	0,08 to 0,15	0,30 to 0,65	1,0 to 2,5	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,75	—	0,75	—	—
—	310Se	0,08	0,65	1,0 to 2,5	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,75	—	0,75	—	—
—	310Le	0,03	0,65	1,0 to 2,5	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,75	—	0,75	—	—
25 20 He	—	0,35 to 0,45	2,0	1,0 to 2,5	0,03	0,02	24,0 to 27,0	18,0 to 22,0	0,5	—	0,5	—	—
25 20 Mn ^e	—	0,08 to 0,15	2,0	2,5 to 5,0	0,03	0,02	24,0 to 27,0	18,0 to 22,0	0,5	—	0,5	—	—
18 36 He	(330)	0,18 to 0,25	0,4 to 2,0	1,0 to 2,5	0,03	0,02	15,0 to 19,0	33,0 to 37,0	0,5	—	0,5	—	—
(18 36 H) ^e	330	0,18 to 0,25	0,30 to 0,65	1,0 to 2,5	0,03	0,03	15,0 to 17,0	34,0 to 37,0	0,75	—	0,75	—	—
28 35 Ne	—	0,03 to 0,09	0,5 to 1,0	1,0 to 2,0	0,02	0,02	26,5 to 29,0	33,0 to 36,0	0,5	—	0,5	—	—

Table 1 (continued)

Alloy designation ^a according to		Chemical composition, % by mass ^b											
Nominal composition ^c ISO 14343-A	Alloy type ISO 14343-B ^c	C	Si	Mn	P	S	Cr	Ni	Mo	N	Cu	Nb ^d	Other
—	3556	0,05 to 0,15	0,20 to 0,80	0,50 to 2,00	0,04	0,015	21,0 to 23,0	19,0 to 22,5	2,5 to 4,0	0,10 to 0,30	-	0,30	Co 16,0 to 21,0 W 2,0 to 3,5 Ta 0,30 to 1,25 Al 0,10 to 0,50 Zr 0,001 to 0,100 La 0,005 to 0,100 B 0,02
Precipitation hardening type													
—	630	0,05	0,75	0,25 to 0,75	0,03	0,03	16,00 to 16,75	4,5 to 5,0	0,75	—	3,25 to 4,00	0,15 to 0,30	—
Other compositions													
Z ^c		Any other agreed composition											
^a A designation in parentheses, e.g. (308L) or (19 9 L), indicates a near match in the other designation system, but not an exact match. The correct designation for a given composition range is the one not in parentheses. A given product may, by having a more restricted chemical composition which fulfills both sets of designation requirements, be assigned both designations independently. ^b Single values shown in the table are maximum values. Two values shown indicate minimum and maximum limits for a range. ^c Wire electrodes, strip electrodes, wires or rods not listed in the table shall be symbolised similarly and prefixed by the letter "Z". The chemical composition ranges are not specified and therefore, two electrodes with the same Z classification might not be interchangeable. ^d Up to 20 % of the amount of Nb can be replaced by Ta. ^e The all-weld metal is in most cases fully austenitic and therefore can be susceptible to microfissuring or hot cracking. The occurrence of fissuring/cracking is reduced by increasing the weld metal manganese level, and in recognition of this, the manganese range is extended for a number of grades. ^f These compositions are mainly used in low dilution overlay welding such as electroslag strip cladding. ^g Ni + Cu ≤ 0,5 %.													

5 Properties of all-weld metal

Properties of the all-weld metal are not part of the classification.

NOTE 1 The influence of the shielding gas or flux on the chemical composition of the all-weld metal is considered. Differences between the chemical composition of the all-weld metal and the wire electrode, wire or rod can occur.

NOTE 2 Proof strength and tensile strength of the weld metal made by a consumable listed in [Table 1](#) is expected to comply with the minimum requirements given in [Annex A](#). Elongation and impact properties of the weld metal can deviate from the minimum values specified for the corresponding parent metal as a result of variations in the microstructure.

NOTE 3 [Table A.1](#) lists expected minimum tensile properties of weld metal.

6 Chemical analysis

Chemical analysis shall be performed on specimens of the product or the stock from which it is made. Any analytical technique may be used, but in case of dispute, reference shall be made to established published methods.

7 Rounding procedure

Actual test values obtained shall be subject to ISO 80000-1:2009, B.3, Rule A. If the measured values are obtained by equipment calibrated in units other than those of this document, the measured values shall be converted to the units of this document before rounding. If an average value is to be compared to the requirements of this document, rounding shall be done only after calculating the average. The rounded results shall fulfil the requirements of the appropriate table for the classification under test.

8 Retesting

If any test fails to meet the requirement, that test shall be repeated twice. The results of both retests shall meet the requirement. Specimens for the retest may be taken from the original sample or from a new sample. For chemical analysis, retesting need only be for those specific elements that failed to meet their testing requirement. If the results of one or both retests fail to meet the requirement, the material under test shall be considered as not meeting the requirements of this specification for that classification.

In the event that, during preparation or after completion of any test, it is clearly determined that prescribed or proper procedures were not followed in preparing the weld test assembly or test specimen(s), or in conducting the tests, the test shall be considered invalid, without regard to whether the test was actually completed, or whether the test results met, or failed to meet, the requirements. That test shall be repeated, following proper prescribed procedures. In this case, the requirement for doubling the number of test specimens does not apply.

9 Technical delivery conditions

Technical delivery conditions shall be in accordance with ISO 544 and ISO 14344.

10 Examples of designation

The designation of the welding consumable shall follow the principle given in the examples below.

EXAMPLE 1 A wire electrode for gas-shielded metal arc welding, also applicable to submerged arc welding, having a chemical composition within the limits for the alloy symbol 20 10 3 and within the limits for the alloy symbol 308Mo of [Table 1](#):

Classification according to nominal composition

ISO 14343-A - G 20 10 3 and/or S 20 10 3

EXAMPLE 2 A rod for gas tungsten arc welding having a chemical composition within the limits for the alloy symbol 20 10 3 and within the limits for the alloy symbol 308Mo of [Table 1](#):

Classification according to alloy type

ISO 14343-B - SS308Mo

Classification according to nominal composition

ISO 14343-A - W 20 10 3

EXAMPLE 3 A wire electrode for gas-shielded metal arc welding having a chemical composition within the limits for the alloy symbol 19 12 3 L Si and within the limits for alloy symbol 316LSi of [Table 1](#):

Classification according to alloy type

ISO 14343-B - SS308Mo

Classification according to nominal composition

ISO 14343-A - G 19 12 3 L Si

EXAMPLE 4 A strip electrode for submerged arc welding or electroslag welding has a chemical composition within the limits for the alloy symbol 23 12 2 L and within the limits for alloy symbol 309LMo of [Table 1](#):

Classification according to alloy type

ISO 14343-B - SS316LSi

Classification according to nominal composition

ISO 14343-A - B 23 12 2 L

Classification according to alloy type

ISO 14343-B - BS 309LMo

where, in all four examples

ISO 14343-A = the number of this document, classification by nominal composition (system A);

G or S or W or B = product or process symbol (see [4.2](#));

20 10 3, 19 12 3 L Si or 23 12 2 L = the chemical composition of the product (see [Table 1](#)).

ISO 14343-B = the number of this document, classification by alloy type (system B);

SS or BS = product or process symbol (see [4.2](#));

308Mo, 316LSi or 309LMo = the chemical composition of the product (see [Table 1](#)).

EXAMPLE 5 A wire electrode gas tungsten arc welding has a chemical composition (17 % and Ti stabilized) not listed in [Table 1](#) and therefore designated with "Z":

Classification according to nominal composition

ISO 14343-A - G Z 17Ti

Classification according to alloy type

ISO 14343-B - G Z 17Ti

where,

ISO 14343-A = the number of this document, classification by nominal composition (system A);

G = product or process symbol (see [4.2](#));

Z = the chemical composition of the product is not specified (see [Table 1](#));

17Ti = the nominal chemical composition of the product as agreed between manufacturer and customer (see [Table 1](#)).

where,

ISO 14343-B = the number of this document, classification by nominal composition (system B);

G = product or process symbol (see [4.2](#));

Z = the chemical composition of the product is not specified (see [Table 1](#));

17Ti = the nominal chemical composition of the product as agreed between manufacturer and customer (see [Table 1](#)).