
**Continuous hot-dip zinc-5 % aluminium
alloy coated steel sheet**

*Tôles en acier revêtues à chaud en continu d'alliage
zinc-aluminium 5 %*

STANDARDSISO.COM : Click to view the full PDF of ISO 14788:2005



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 14788:2005

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14788 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 12, *Continuous mill flat rolled products*.

This second edition cancels and replaces the first edition (ISO 14788:1998), which has been technically revised.

Continuous hot-dip zinc-5 % aluminium alloy coated steel sheet

1 Scope

1.1 This International Standard specifies the minimum requirements for steel sheet, in coils and cut lengths, metallic-coated by the continuous hot-dip process, with zinc-5 % aluminium alloy coating.

1.2 The product is intended for applications requiring corrosion resistance, formability and paintability.

1.3 The steel sheet is produced in a number of qualities and grades, coating mass, surface treatments and coating conditions designed to be compatible with differing application requirements.

1.4 The product is produced in two types:

- T1: zinc-5 % aluminium-mischmetal alloy coating,
- T2: zinc-5 % aluminium-0,1 % magnesium alloy coating.

NOTE There may be differences in product characteristics between Type 1 and Type 2 coated steel sheet, depending on the intended application.

1.5 Zinc-5 % aluminium alloy coated steel sheet is produced in thicknesses up to 5 mm after coating, and in widths of 600 mm and over in coils and cut lengths. Zinc-5 % aluminium alloy coated steel sheet less than 600 mm wide may be slit from wide sheet and will be considered as sheet.

1.6 The thickness of zinc-5 % aluminium alloy coated sheet steel may be specified as a combination of the base metal and metallic coating, or as the base metal alone. The purchaser shall indicate on the order which method of specifying thickness is required. In the event that the purchaser does not indicate any preference, the thickness as a combination of the base metal and coating will be provided. Annex A describes the requirements for specifying the thickness of the base metal alone.

1.7 Zinc-5 % aluminium alloy coated steel sheet may be ordered in one of two conditions as described in 4.2.1:

- a) Condition A) Steel ordered to satisfy mechanical property requirements,
- b) Condition B) Steel when ordered to make an identified part.

1.8 Zinc-5 % aluminium alloy coated steel sheet is available in several fabrication qualities.

- Commercial: intended for general fabrication purposes, where sheet is used in the flat or for bending or moderate forming.
- Drawing: intended for fabricating parts where drawing or severe forming may be involved.
- Deep drawing-aluminium killed (non-aging): intended for fabricating parts where particularly severe drawing or forming may be involved or essential freedom from aging is required.
- Extra deep drawing (stabilized interstitial free): intended for applications requiring interstitial-free steel (IF) which is non-aging and has maximum formability.
- Structural: zinc-5 % aluminium alloy coated steel sheet is produced in six grades as defined by a minimum yield stress.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1460:1992, *Metallic coatings — Hot dip galvanized coatings on ferrous materials — Gravimetric determination of the mass per unit area*

ISO 2178:1982, *Non-magnetic coatings on magnetic substrates — Measurement of coating thickness — Magnetic method*

ISO 3497:2000, *Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods*

ISO 6892:1998, *Metallic materials — Tensile testing at ambient temperature*

ISO 7438:2005, *Metallic materials — Bend test*

ISO 16160:2000, *Continuously hot-rolled steel sheet products — Dimensional and shape tolerances*

ISO 16162:2000, *Continuously cold-rolled steel sheet products — Dimensional and shape tolerances*

ISO 16163:2000, *Continuously hot-dipped coated steel sheet products — Dimensional and shape tolerances*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

continuous hot-dip zinc-5 % aluminium-coated steel sheet

product obtained by hot-dip coating of steel sheet coils on a continuous coating line to produce either coated coils or cut lengths

3.2

normal spangle

coating formed as a result of the unrestricted growth of zinc-5 % aluminium alloy crystals during normal solidification

3.3

smooth finish

smooth coating produced by skin-passing the coated material in order to achieve an improved-surface condition as compared with the normal as-coated product

3.4

skin pass

light cold rolling of the coated steel sheet

NOTE The purpose of the skin pass is to produce a higher degree of surface smoothness and thereby improve the surface appearance. The skin pass also temporarily minimizes the occurrence of a surface condition known as stretcher strain (Luder's Lines) or fluting during fabrication of finished parts. The skin pass also controls and improves flatness.

3.5

ageing

susceptibility of zinc-5 % aluminium alloy coated steel sheet to changes in properties with the passage of time

NOTE Aging may result in a change in yield strength and corresponding decrease in ductility during storage. Aging always has a negative effect on formability. The redevelopment of an upper yield point as a result of aging can result in renewed susceptibility to surface imperfections, such as stretcher strain marks (Luder's Lines) and fluting, when the steel

is formed. To avoid these adverse outcomes, it is essential that the period between final processing at the producing mill and fabrication be kept to a minimum. Rotation of stock, by using the oldest material first, is important. Effective roller leveling immediately prior to fabrication can achieve reasonable freedom from stretcher strain marks.

3.6

differential coating

coating having a coating mass on one surface significantly different from the coating mass on the other surface

4 Requirements

4.1 Chemical composition

The chemical composition (heat analysis) shall not exceed the values given in Tables 1 and 2. On request, a report of the heat analysis shall be made to the purchaser.

A verification analysis may be made by the purchaser to verify the specified analysis of the semi-finished or finished steel and shall take into consideration any normal heterogeneity. Non-killed steels, such as rimmed or capped steels, are not technologically suited for verification analysis. The product analysis tolerances are shown in Table 3.

The processes used in making the steel and in manufacturing zinc-5 % aluminium alloy coated sheet are left to the discretion of the manufacturer. When requested, the purchaser shall be informed of the steelmaking process being used.

Table 1 — Chemical composition (heat analysis), %

Base-metal quality	C max.	Mn max.	P max.	S max.	Ti max.
Commercial	0,15	0,60	0,05	0,05	—
Drawing ^a	0,12	0,50	0,04	0,04	—
Drawing quality aluminum killed ^a	0,08	0,45	0,03	0,03	—
Extra-deep drawing quality ^a	0,02	0,25	0,02	0,02	0,15
Structural	0,40	0,20	0,04	0,05	—

^a For interstitial free steels only, the values of 0,15 % titanium, and 0,10 % maximum for niobium and vanadium, are acceptable to ensure that the carbon and nitrogen are fully stabilized.

Table 2 — Limits on additional chemical elements, %

Element	Cu ^a max.	Ni ^a max.	Cr ^{a, b} max.	Mo ^{a, b} max.	Nb ^c max.	V ^{c, d} max.	Ti ^d max.
Heat analysis	0,20	0,20	0,15	0,06	0,008	0,008	0,008
Product analysis	0,23	0,23	0,19	0,07	0,018	0,018	0,018
NOTE Each of the elements listed in this table shall be included in the report of the heat analysis. When the amount of copper, nickel, chromium or molybdenum present is less than 0,02 %, the analysis may be reported as < 0,02 %.							
^a The sum of copper, nickel, chromium and molybdenum shall not exceed 0,50 % on the heat analysis. When one or more of these elements are specified, the sum does not apply; in which case, only the individual limits on the remaining elements will apply.							
^b The sum of chromium and molybdenum shall not exceed 0,16 % on heat analysis. When one or more of these elements are specified, the sum does not apply; in which case, only the individual limits on the remaining elements will apply.							
^c For interstitial free steels only, the value of 0,15 % titanium, and 0,10 % maximum for niobium and vanadium are acceptable to ensure that the carbon and nitrogen are fully stabilized.							
^d Heat analysis greater than 0,008 % may be supplied after agreement between the producer and consumer.							

Table 3 — Product analysis tolerances, %

Element	Maximum of specified element	Tolerance over maximum specified
C	0,25	0,04
Mn	1,70	0,14
P	0,05	0,01
S	0,035	0,01
NOTE The above maximum tolerance is the allowable excess over the specified requirement and not the heat analysis.		

4.2 Mechanical properties

4.2.1 Commercial and drawing qualities

Zinc-5 % aluminium alloy coated steel sheet of designations 01, 02, 03, and 04 is supplied under the following two ordering conditions:

- Ordering condition A): steel when ordered to mechanical properties shall, at the time the steel is made available for shipment, satisfy the applicable requirements of Table 4.
- Ordering condition B): steel when ordered to make an identified part shall be supplied with a commitment to satisfactory manufacturing performance within a properly established breakage allowance, which shall be previously agreed upon between the interested parties. In these cases, the part name, the details of fabrication, and special requirements (such as freedom from stretcher strain or fluting) shall be specified.

Prolonged storage of the sheet can cause a change in mechanical properties (increase in hardness and decrease in elongation), leading to a decrease in drawability. To minimize this effect, quality 03 or 04 should be specified.

4.2.2 Structural quality

The mechanical properties, at the time the steel is made available for shipment, shall satisfy the requirements listed in Table 5.

Table 4 — Mechanical properties

Base-metal quality ^a		R_e ^b max N/mm ^{b, e}	R_m ^c max N/mm ^{b, e}	A min. ^d %		
Designation	Name			$L_o = 50$ mm	$L_o = 80$ mm	$L_o = 5,65\sqrt{S_o}$ ^f
01	Commercial	—	—	—	—	—
02	Drawing	300 ^g	430	24	23	22
03	Deep drawing aluminum killed	220	410	29	28	27
04	Extra-deep drawing (stabilized interstitial free)	200	350	37	36	35

R_e yield stress
 R_m tensile strength
 A percentage elongation after fracture
 L_o gauge length of test piece
 S_o original cross-sectional area of gauge length
 e thickness of steel sheet, in millimetres

NOTE 1 Time period from date of shipment for values stated in this table to be applicable.

Designation	Time period
0	—
02	8 days
03	6 months
04	6 months

NOTE 2 For products produced according to performance criteria, 4.2.1, the typical mechanical properties presented here are non-mandatory. For products ordered according to specific mechanical properties (ordering condition A), the purchaser may negotiate with the supplier if a specific range, or a more restrictive range, is required for the application. Therefore, by agreement, these values can be specified.

NOTE 3 These typical mechanical properties apply to the full range of steel sheet thicknesses. The yield tends to increase and some of the formability aspects tend to decrease as the sheet thickness decreases.

^a All qualities are available with a normal spangle or smooth finish zinc-5 % aluminium alloy coating.
^b The yield values apply to 0,2 % proof stress if the yield point is not pronounced, otherwise to the lower yield point (R_{eL}).
^c Minimum tensile strength, for qualities 02, 03 and 04, would normally be expected to be 270 N/mm². All tensile strength values are determined to the nearest 10 N/mm².
^d For material up to and including 0,6 mm in thickness, the elongation values in the table shall be reduced by 2.
^e 1 N/mm² = 1 MPa.
^f May be used for material over 3 mm in thickness.
^g This value applies to skin-passed products only.

4.3 Coating

4.3.1 Coating mass

The coating mass limits shall conform to the limits for the designations shown in Table 6. The coating mass is the total amount of coating on both sides of the sheet, expressed in grams per square metre.

4.3.2 Coating adherence

The coated sheet shall be capable of being bent in any direction, in accordance with the mandrel diameter requirements of Table 7, without flaking of the coating on the outside of the bend. Flaking of the coating within 7 mm from the edge of the test piece shall not be a cause for rejection.

Table 5 — Mechanical properties of structural-quality steels

Grade	R_e^a min N/mm ²	R_m min N/mm ²	A min ^b %	
			$L_0 = 50$ mm	$L_0 = 80$ mm
220	220	310	20	18
250	250	360	18	16
280	280	380	16	14
320	320	430	14	12
350	350	450	12	10
380	380	540	12	10
550 ^c	550	570	—	—

NOTE In determining the base-metal mechanical properties, base-metal thickness should be measured after stripping the coating from the end of the specimen contacting the grips of the tension-testing machine before testing.

^a The yield stress specified in this table shall be the lower yield stress (R_{eL}). The values can also be measured by 0,5 % total elongation proof stress (proof stress under load) or by 0,2 % offset when a definite yield phenomenon is not present. When the upper yield stress (R_{eH}) is specified, the values shall be 20 N/mm² above the R_{eL} values for each grade.

^b The elongation values in the table shall be reduced by 2 for material up to and including 0,6 mm in thickness.

^c Grade 550 is in the unannealed condition and therefore has limited ductility. If the hardness is HRB 85 or higher, no tension test is required. Bend testing for coating adherence is not applicable to Grade 550.

Table 6 — Coating mass test limits for zinc-5 % aluminium alloy coated steel sheet

Coating designation	Triple-spot test total both sides min. g/m ²	Single-spot test total both sides min. g/m ²
ZA001	no minimum	no minimum
ZA080	80	70
ZA090	90	75
ZA095	95	80
ZA100	100	85
ZA120	120	100
ZA130	130	110
ZA135	135	115
ZA140	140	120
ZA150	150	130
ZA160	160	135
ZA180	180	155

Table 6 — (continued)

Coating designation	Triple-spot test total both sides min. g/m ²	Single-spot test total both sides min. g/m ²
ZA185	185	155
ZA200	200	170
ZA225	225	190
ZA250	250	210
ZA255	255	215
ZA275	275	235
ZA300	300	255
ZA350	350	300
ZA450	450	385
ZA600	600	510
ZA700	700	595

NOTE 1 Not all coating designations may be available from all producers.

NOTE 2 The coating mass, in grams per square metre, refers to the total coating on both surfaces. Because of the many variables and changing conditions that are characteristics of continuous hot-dip coating, the coating mass is not always evenly divided between the two surfaces of a sheet, nor is the coating evenly distributed from edge to edge. However, it can normally be expected that no less than 40 % of the single-spot test limit will be found on either surface.

NOTE 3 The coating thickness may be estimated from the coating mass by using the following relationship:
 $100 \text{ g/m}^2 \text{ total both sides} \approx 0,015 \text{ mm total both sides.}$

Table 7 — Coating adherence — Bend test mandrel diameter

Base-metal quality		Coated metal-180° bend mandrel diameter, mm							
		Coating designation							
		$e < 3 \text{ mm}$				$e \geq 3 \text{ mm}$			
		up to ZA275	ZA300 ZA350	ZA450 ZA600	ZA700	up to ZA275	ZA300 ZA350	ZA450	ZA600 ZA700
Commercial		1a	1a	2a	3a	2a	2a	2a	3a 4a
Drawing		0	1a	2a	2a	0	1a	2a	2a 2a
Deep drawing		0	1a	2a	2a	0	1a	2a	2a 2a
Extra deep drawing		0	1a	2a	2a	0	1a	2a	2a 2a
Structural grade									
	220	1a	1a	2a	3a	2a	2a	2a	3a 4a
	250	1a	1a	2a	3a	2a	2a	2a	3a 4a
	280	2a	2a	2a	3a	3a	3a	3a	3a 4a
	320	3a	3a	3a	3a	3a	3a	3a	3a 4a
	350	3a	3a	3a	3a	3a	3a	3a	3a 4a
	380	3a	3a	3a	3a	3a	3a	3a	3a 4a

a = bend mandrel diameter = e
 e = thickness of steel sheet, in millimetres

4.4 Weldability

The product is normally suitable for welding such as spot welding, roller-seam welding and fusion welding if appropriate welding conditions are selected with special attention to the heavier coatings. When the carbon content increases above 0,15 %, spot welding becomes increasingly difficult. Because the heat of welding might have a significant effect on lowering the strength of grade 550, this grade is not recommended for welding.

4.5 Painting

Hot-dip zinc-5 % aluminium alloy coated steel sheet is a suitable base for paint, but the first treatment may be different from those used on uncoated steel. Pretreatment primers, chemical conversion coatings (chromate, phosphate or oxide type), and some paints specially formulated for direct application to zinc surfaces, are all appropriate first treatments for hot-dip zinc-5 % aluminium alloy coated sheet. In a painting schedule, it should be considered whether the product should be ordered with or without chemical passivation. Surfaces with certain passivation treatments (e.g. chromated) are not suitable for phosphating or the application of a pretreatment (etch) primer.

4.6 Surface treatment

4.6.1 Mill passivation

A chemical treatment may be applied to zinc-5 % aluminium alloy coated steel sheet, to minimize the hazard of wet-storage stain during shipment and storage. However, the inhibiting characteristics of the treatment are limited and if a shipment is received wet, the material shall be used immediately or dried.

4.6.2 Oiling

Oiling of the as-produced zinc-5 % aluminium alloy coated steel sheet prevents marring and scratching of the soft surface during handling or shipping, and helps to minimize the hazard of wet-storage stains (known as white rust on this type of product). For these reasons, the purchaser is advised to consider specifying the zinc-5 % aluminium alloy coated steel in the oiled condition, provided this is compatible with his processing system.

4.7 Coated coil joining

Continuous-coil coating lines use various methods to join coil ends. These methods include lap welding, butt welding, and stitching. The shipment of coils containing the joined coil ends may be permitted if agreed upon between the manufacturer and purchaser.

4.8 Dimensional and shape tolerances

4.8.1 Dimensional tolerances applicable to zinc-5 % aluminium alloy coated steel sheet shall be as given in ISO 16163. The tolerances for thickness apply to products whose thickness is a combination of base metal and coating.

4.8.2 When the base-metal thickness is specified, the thickness tolerances of Tables 6, 7 and 8 of ISO 16163:2000 shall apply to the average coated product thickness as calculated in accordance with Annex A. The tolerances for thickness of the base metal shall be as given in ISO 16160 for hot-rolled steel, and ISO 16162 for cold-rolled steel.

5 Sampling

5.1 Chemical composition

A heat analysis of each heat shall be made by the manufacturer to determine compliance with the requirements of Tables 1 and 2.

5.2 Tensile test

When required, one representative transverse test shall be taken from each lot for shipment to determine compliance with the requirements of Tables 4 and 5. Transverse test pieces shall be taken mid-way between the center and the edge of the sheet as-rolled. A lot consists of 50 tonnes or less of sheet of the same grade rolled to the same thickness and condition.

5.3 Coating tests

5.3.1 Coating mass

5.3.1.1 The producer shall develop a testing plan with a frequency sufficient to adequately characterize the lot of material and ensure conformance with specification requirements.

5.3.1.2 The purchaser may conduct verification tests by securing a sample piece approximately 300 mm in length by the as-coated width and cutting three test specimens, one from the mid-width position and one from each side, not closer than 25 mm from the side edge. The minimum specimen area shall be 2 000 mm².

5.3.2 Triple-spot test

The triple-spot test result shall be the average coating mass found on the three specimens taken according to 5.3.1.

5.3.3 Single-spot test

The single-spot test result shall be the minimum coating mass found on any one of the three specimens used for the triple-spot test. Material, which has been slit from wide coil, shall be subject to a single-spot test only.

5.4 Coating adherence

One representative sample for the coating-adherence bend test shall be taken from each lot of sheet for shipment. The specimens for the coated bend test shall be taken not closer than 25 mm from the side edge. The minimum width of the test specimen shall be 50 mm.

5.5 Retest

If a test does not satisfy the specified results, two more test pieces shall be taken at random from the same lot. Both retests shall conform to the requirements of this International Standard; otherwise the lot shall be rejected.

6 Test methods

6.1 Tensile tests

The tests shall be conducted in accordance with the methods specified in ISO 6892. Transverse test pieces shall be taken mid-way between the center and the edge of the sheet as-rolled. Base-metal thickness shall be used to calculate the cross-sectional area needed for the tensile test; however, for orders specifying thickness "as base metal only", there are two permissible methods for determining the base-metal thickness:

- a) Option A — Determine the actual base-metal thickness through direct measurement of the substrate of a specimen whose coating has been removed.
- b) Option B — Calculation of the base-metal thickness through subtraction of the average coating thickness for the appropriate coating designation included in Annex A from the actual coated thickness of the test specimen.

6.2 Coating properties

6.2.1 Coating mass

The manufacturer shall conduct tests using methods deemed necessary to ensure that the material complies with the requirements shown in Table 3. Commonly used methods include those specified in ISO 1460, ISO 3497 or ISO 2178. Coating mass is determined by converting coating thickness measurements made with magnetic gauges (ISO 2178) or by X-ray spectrometry (ISO 3497). Test methods ISO 2178 and ISO 3497 may be used as a basis for acceptance but not for rejection. In cases of dispute, ISO 1460 shall be used as the referee method.

6.2.2 Coating adherence

Bend tests shall be conducted in accordance with the methods specified in ISO 7438.

7 Designation system

The designation system includes the coating name, coating type, coating mass, coating condition, surface treatment, base-metal quality or grade of structural steel.

7.1 Coating name

The letters ZA are used to indicate the zinc-5 % aluminium alloy coating.

7.2 Coating type

The designators T1 and T2 are used to indicate the type of coating (see 1.4).

7.3 Coating mass

The coating mass designations are 001, 080, 090, 095, 100, 120, 130, 135, 140, 150, 160, 180, 185, 200, 225, 250, 255, 275, 300, 350, 450, 600, 700 as described in Table 5.

The coating is expressed as the total mass on both surfaces, in grams per square metre. The coating mass specified should be compatible with the desired service life, the thickness of the base metal, and with the forming requirements involved.

NOTE For differential coatings, the standard would be top surface before bottom surface. An example of a differential coating designation is: ZAT1 275S100C02.

7.4 Coating condition

The conditions of coating designations are:

- N: normal spangle coating (as-produced);
- S: smooth finish (skin passed).

NOTE 1 The normal spangle is the "as-coated" condition and the smooth finish is achieved with a skin pass.

NOTE 2 End-use applications may require negotiation between the supplier and consumer to establish specific surface requirements.

7.5 Surface treatment

The surface treatment designations are:

- O oiling;
- CO mill passivation plus oiling;
- C mill passivation.

7.6 Base-metal quality

The base-metal quality designations are:

- 01 Commercial;
- 02 Drawing;
- 03 Deep drawing aluminum killed (non-aging);
- 04 Extra deep drawing (stabilized interstitial free).

Three digits as described in Table 5 indicate structural grades.

7.7 Examples

7.7.1 An example of a complete designation is ZAT1 160NC02. This designation example includes the following components:

- ZA: Zinc-5 % aluminium alloy coating;
- T1: coating Type 1;
- 160: coating mass designation;
- N: normal spangle coating condition;
- C: mill passivation;
- 02: drawing quality.

7.7.2 An example of a complete designation for one of the structural-quality products is ZAT2 150SCO350. This designation example includes the following components:

- ZA: Zinc-5 % aluminium alloy coating;
- T2: coating type 2;
- 150: coating mass designation;
- S: smooth finish condition;
- CO: mill passivation plus oiling;
- 350: structural steel grade.

8 Resubmission

8.1 The manufacturer may resubmit, for acceptance, the products that have been rejected during earlier inspection because of unsatisfactory properties, after he has subjected them to a suitable treatment (selection, heat treatment) which, on request, will be indicated to the purchaser. In this case, the tests should be carried out as if they applied to a new lot.

8.2 The manufacturer has the right to present the rejected products to a new examination for compliance with the requirements for another quality or grade.

9 Workmanship

The zinc-5 % aluminium alloy coated steel sheet in cut lengths shall be free from amounts of laminations, surface flaws and other imperfections that are detrimental to subsequent appropriate processing. Processing for shipment in coils does not afford the manufacturer the opportunity to observe readily or to remove defective portions as can be carried out in the cut-length product.

10 Inspection and acceptance

10.1 While not usually required for products covered by this International Standard, the purchaser may specify that inspection and tests for acceptance be observed prior to shipment from the manufacturer's works. In these cases, the manufacturer shall afford the purchaser's inspector all reasonable facilities to determine that the steel is being furnished in accordance with this International Standard.

10.2 Steel that is reported to be defective after arrival at the user's works shall be set aside, properly and correctly identified, and adequately protected.

11 Marking

Unless otherwise stated, the following minimum requirements for identifying the steel shall be legibly stenciled on the top of each lift or shown on a tag attached to each coil or shipping unit.

- a) manufacturer's name or identifying brand;
- b) reference to this International Standard, i.e. ISO 14788;
- c) product designation (coating, type, coating mass, coating condition, surface treatment and quality or grade or the base metal);
- d) order number;
- e) product dimensions;
- f) lot number;
- g) mass.

12 Information to be supplied by the purchaser

To adequately specify requirements in accordance with this International Standard, enquiries and orders should include the following information:

- a) reference to this International Standard, i.e. ISO 14788;