

First edition
2003-04-15

AMENDMENT 1
2016-12-15

Plastics piping systems for industrial applications — Acrylonitrile-butadiene-styrene (ABS), unplasticized poly(vinyl chloride) (PVC-U) and chlorinated poly(vinyl chloride) (PVC-C) — Specifications for components and the system — Metric series

AMENDMENT 1

Systèmes de canalisations en matières plastiques pour les applications industrielles — Acrylonitrile-butadiène-styrène (ABS), poly(chlorure de vinyle) non plastifié (PVC-U) et poly(chlorure de vinyle) chloré (PVC-C) — Spécifications pour les composants et le système — Série métrique

AMENDEMENT 1



Reference number
ISO 15493:2003/Amd.1:2016(E)

© ISO 2016

STANDARDSISO.COM : Click to view the full PDF of ISO 15493:2003/Amd 1:2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

Amendment 1 to ISO 15493:2003 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 3, *Plastics pipes and fittings for industrial applications*.

STANDARDSISO.COM : Click to view the full PDF of ISO 15493:2003/Amd 1:2016

Plastics piping systems for industrial applications — Acrylonitrile-butadiene-styrene (ABS), unplasticized poly(vinyl chloride) (PVC-U) and chlorinated poly(vinyl chloride) (PVC-C) — Specifications for components and the system — Metric series

AMENDMENT 1

Page 2, Clause 2

Delete the following references.

ISO 12092, *Fittings, valves and other piping system components made of unplasticized poly(vinyl chloride) (PVC-U), chlorinated poly(vinyl chloride) (PVC-C), acrylonitrile-butadiene-styrene (ABS) and acrylonitrile-styrene-acrylester (ASA) for pipes under pressure — Resistance to internal pressure — Test method*

ISO 1167:1996, *Thermoplastics pipes for the conveyance of fluids — Resistance to internal pressure — Test method*

Add the following reference.

ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

Page 6, 3.4.1

Replace the footnote ³⁾ with the following equivalence.

³⁾ 1 bar = 0,1 MPa = 10⁵ Pa; 1 MPa = 1 N/mm².

Page 8, 5.1 General

Delete the first paragraph and insert the following text.

The material from which the components are made shall be ABS, PVC-U or PVC-C, as applicable, to which are added those additives that are needed to facilitate the manufacture of pipes, fittings, valves, appurtenances and assemblies conforming to this document.

Page 8, 5.2 Hydrostatic strength properties

Add the following note after the third paragraph.

NOTE In some cases, the component manufacturer may be regarded as the raw material producer.

Page 12, Clause 11 Adhesives

Delete the two paragraphs and insert the following text.

The adhesive(s) shall be as recommended by the manufacturer of the components.

The adhesive(s) shall not cause the test assembly to fail to conform to the requirements given in the applicable annex to this document.

Page 48, C.1.5.1 Density and chlorine content

Replace Table C.1 with the following table.

Table C.1 — Density and chlorine content of PVC-C

Characteristic	Requirement ^a	Test temperature	Test method
Density, ρ (kg/m ³)	$1\,450 \leq \rho \leq 1\,650$	23 °C	ISO 3514
Chlorine content	≥55 % by mass	23 °C	ISO 1158
a Conformity to these requirements shall be declared by the raw-material producer.			

Page 48, C.1.5.2 Thermal stability

Replace the two paragraphs with the following.

For pipes, the thermal stability of the material is regarded as proven if the pipe meets the requirements of the internal-pressure test in accordance with ISO 1167-1 at 95 °C, ≥8 760 h and 3,6 MPa (for test conditions, see Table C.9).

For fittings, the thermal stability of the material is regarded as proven if the fitting meets the requirements of the internal-pressure test in accordance with ISO 1167-1 at 90 °C, ≥8 760 h and 3,1 MPa (for test conditions, see Table C.12).

Page 50, C.3.2 Dimensions of sockets for solvent cementing

Delete the following sentence.

The dimensions of tapered sockets for solvent cementing (see Figure C.4) shall be as specified in Table C.5.

Page 53, C.3.3.2.4 Diameters and lengths of tapered sockets

Delete C.3.3.2.4, including Figure C.4 and Table C.5

Page 56, C.4.1.1 Resistance to internal pressure

Replace Table C.8 with the following table.

Table C.8 — Requirements for internal-pressure testing of pipes

Characteristic	Requirement	Test conditions			Test method
		Hydrostatic (hoop) stress MPa	Time h	Number of test pieces	
Resistance to internal pressure at 20 °C	No failure during test period	43,0	≥1	3	ISO 1167-1
Resistance to internal pressure at 95 °C		5,6	≥165	3	ISO 1167-1
Resistance to internal pressure at 95 °C		4,6	≥1 000	3	ISO 1167-1