

First edition
2003-12-01

AMENDMENT 2
2020-11

**Plastics piping systems for hot and
cold water installations — Crosslinked
polyethylene (PE-X) —**

**Part 2:
Pipes**

AMENDMENT 2

*Systèmes de canalisations en plastique pour les installations d'eau
chaude et froide — Polyéthylène réticulé (PE-X) —*

Partie 2: Tubes

AMENDEMENT 2



Reference number
ISO 15875-2:2003/Amd.2:2020(E)

© ISO 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 2, *Plastics pipes and fittings for water supplies*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 155, *Plastics piping systems and ducting systems*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 15875 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

STANDARDSISO.COM : Click to view the full PDF of ISO 15875-2:2003/Amd 2:2020

Plastics piping systems for hot and cold water installations — Crosslinked polyethylene (PE-X) —

Part 2: Pipes

AMENDMENT 2

Normative references

Replace the reference to "EN 578" with the following:

ISO 7686, *Plastics pipes and fittings — Determination of opacity*

Replace the reference to "EN 579" with the following:

ISO 10147, *Pipes and fittings made of crosslinked polyethylene (PE-X) — Estimation of the degree of crosslinking by determination of the gel content*

Replace the reference to "EN 743" with the following:

ISO 2505, *Thermoplastics pipes — Longitudinal reversion — Test method and parameters*

Replace the reference to "EN 921" with the following:

ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces*

4.2

Replace all references to "EN 921:1994" with "ISO 1167-1 and ISO 1167-2".

5.2

Replace the reference to "EN 578" with "ISO 7686".

6.2.2, Table 2

Replace Table 2 with the following table:

Table 2 — Pipe dimensions for dimension class A
(sizes conform to ISO 4065 and are applicable for all classes of service conditions)

Dimensions in millimetres

Nominal size DN/OD	Nominal outside diameter d_n	Mean outside diameter ^a		Pipe series			
		$d_{em,min}$	$d_{em,max}$	S 6,3	S 5	S 4	S 3,2
				Wall thicknesses e_{min} and e_n			
12	12	12,0	12,3	—	1,3 ^a	1,4	1,7
16	16	16,0	16,3	1,3	1,5	1,8	2,2
20	20	20,0	20,3	1,5	1,9	2,3	2,8
25	25	25,0	25,3	1,9	2,3	2,8	3,5
32	32	32,0	32,3	2,4	2,9	3,6	4,4
40	40	40,0	40,4	3,0	3,7	4,5	5,5
50	50	50,0	50,5	3,7	4,6	5,6	6,9
63	63	63,0	63,6	4,7	5,8	7,1	8,6
75	75	75,0	75,7	5,6	6,8	8,4	10,3
90	90	90,0	90,9	6,7	8,2	10,1	12,3
110	110	110,0	111,0	8,1	10,0	12,3	15,1
125	125	125,0	126,2	9,2	11,4	14,0	17,1
140	140	140,0	141,3	10,3	12,7	15,7	19,2
160	160	160,0	161,5	11,8	14,6	17,9	21,9
180	180	180,0	181,7	13,3	16,4	20,1	24,6
200	200	200,0	201,8	14,7	18,2	22,4	27,4
225	225	225,0	227,1	16,6	20,5	25,2	30,8
250	250	250,0	252,3	18,4	22,7	27,9	34,2

NOTE A non-preferred wall thickness of 1,1 mm is permitted for dimension $d_n = 12$.

^a The level of the tolerances conforms to Grade A in ISO 11922-1.

6.2.2, Table 6

Replace Table 6 with the following table:

Table 6 — Tolerance on wall thicknesses

Dimensions in millimetres

Minimum wall thickness		Tolerance ^a	Minimum wall thickness		Tolerance ^a
$e_{\min}$		x	$e_{\min}$		x
>	≤		>	≤	
1,0	2,0	0,3	19,0	20,0	2,1
2,0	3,0	0,4	20,0	21,0	2,2
3,0	4,0	0,5	21,0	22,0	2,3
4,0	5,0	0,6	22,0	23,0	2,4
5,0	6,0	0,7	23,0	24,0	2,5
6,0	7,0	0,8	24,0	25,0	2,6
7,0	8,0	0,9	25,0	26,0	2,7
8,0	9,0	1,0	26,0	27,0	2,8
9,0	10,0	1,1	27,0	28,0	2,9
10,0	11,0	1,2	28,0	29,0	3,0
11,0	12,0	1,3	29,0	30,0	3,1
12,0	13,0	1,4	30,0	31,0	3,2
13,0	14,0	1,5	31,0	32,0	3,3
14,0	15,0	1,6	32,0	33,0	3,4
15,0	16,0	1,7	33,0	34,0	3,5
16,0	17,0	1,8	34,0	35,0	3,6
17,0	18,0	1,9			
18,0	19,0	2,0			

^a The tolerance is expressed in the form $^{+x}_0$ mm, where "x" is the value of the tolerance given. The level of the tolerances conforms to Grade V in ISO 11922-1.

Clause 7, Table 7

Replace the reference to "EN 921 of 1994" with "ISO 1167-1 and ISO 1167-2".

Clause 8, Table 8

Replace Table 8 with the following table:

Table 8 — Physical and chemical characteristics of pipes

Characteristic	Requirement	Test parameters		Test method
		Parameter	Value	
Longitudinal reversion	≤ 3 %	Temperature Duration of exposure for: $e_n \leq 8$ mm $8 \text{ mm} < e_n \leq 16$ mm $e_n > 16$ mm Number of test pieces	120 °C 1 h 2 h 4 h 3	Method B of ISO 2505 (oven test)
Thermal stability by hydrostatic pressure testing	No bursting during the test period	Sampling procedure End cap Orientation Type of test Hydrostatic (hoop) stress Test temperature Test period Number of test pieces	a Type a) Not specified Water-in-air 2,5 MPa 110 °C 8760 h 1	ISO 1167-1/ ISO 1167-2
Crosslinking - peroxide PE-Xa - silan PE-Xb - electron beam PE-Xc - azo PE-Xd - UV-light initiated PE-Xe	≥ 70 % ≥ 65 % ≥ 60 % ≥ 60 % ≥ 70 %	Shall conform to ISO 10147		ISO 10147
a The sampling procedure is not specified. For guidance see ISO/TS 15875-7.				