
**Closed end blind rivets with break pull
mandrel and countersunk head — AIA/St**

Rivets aveugles à rupture de tige à corps fermé, à tête fraisée — AIA/St



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 15974:2000

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 15974 was prepared by Technical Committee ISO/TC 2, *Fasteners*.

Annex A of this International Standard is for information only.

Closed end blind rivets with break pull mandrel and countersunk head — AIA/St

1 Scope

This International Standard specifies dimensional and mechanical characteristics and application data for closed end blind rivets with break pull mandrel and protruding head, with an aluminium alloy body (Al) and a steel mandrel (St) and with nominal diameters from 3,2 mm up to and including 4,8 mm.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 3269:2000, *Fasteners — Acceptation inspection.*

ISO 14588:2000, *Blind rivets — Terminology and definitions.*

ISO 14589:2000, *Blind rivets — Mechanical testing.*

3 Dimensions

NOTE Symbols and designations of dimensions are specified in ISO 14588.

3.1 Rivet dimensions

See Figure 1 and Table 1.




Figure 1 — Rivet dimensions

Table 1 — Rivet dimensions

Dimensions in millimetres


Rivet	d	nom.	3,2	4	4,8
		max.	3,28	4,08	4,88
		min.	3,05	3,85	4,65
	d_k	max.	6,7	8,4	10,1
		min.	5,8	6,9	8,3
	k	max.	1,3	1,7	2
Mandrel	d_m	max.	1,85	2,35	2,77
	p	min.	25	25	27
l			Recommended grip ranges ^a		
nom. = min.		max.			
8		9	2,0 to 3,5	2,0 to 3,5	
8,5		9,5	—	—	2,5 to 3,5
9,5		10,5	3,5 to 5,0	3,5 to 5,0	3,5 to 5,0
11		12	5,0 to 6,5	5,0 to 6,5	5,0 to 6,5
12,5		13,5	6,5 to 8,0	6,5 to 8,0	—
13		14		—	6,5 to 8,0
14,5		15,5		8 to 10	8,0 to 9,5
15,5		16,5			—
16		17			9,5 to 11,0
18		19			11 to 13
21		22			13 to 16
NOTE The rivet body dimensions are generated from the design formulae specified in annex A (informative).					
^a The grip ranges of rivets with dimensions as given in Table 1 and with the material combination as given in clause 4 are specified by the minimum and maximum grip lengths. The minimum grip lengths are given as a recommendation only. It may be possible to apply lower minimum values in certain cases.					

3.2 Clearance hole diameters

The clearance hole (d_{h1}) to accommodate the rivet in the components to be fastened is shown in Figure 2 and its diameters are given in Table 2.

Nonconformance to the values in Table 2 may result in assembly difficulties and/or reduction in the shear and tensile loads specified in Table 3.

If necessary, to facilitate alignment, only the component on the access side may have a clearance hole larger than specified in Table 2, see Figure 2. This may also result in a reduction of the shear and tensile loads specified in Table 3.



a Enlarged clearance hole.

Figure 2 — Enlarged clearance hole to facilitate alignment

Table 2 — Clearance hole diameters

Dimensions in millimetres

d nom.	d_{h1}	
	min.	max.
3,2	3,3	3,4
4	4,1	4,2
4,8	4,9	5,0

4 Material and finish

Blind rivets to this International Standard shall have a rivet body made of aluminium alloy (AlA) and a mandrel made of steel (St) and shall have mechanical properties as specified in clause 5.

Material specification is at the discretion of the manufacturer.

The surface finish shall be natural with a protection for storage.

5 Mechanical properties

The minimum shear load, minimum tensile load and maximum mandrel break load shall be as specified in Table 3 if tested in accordance with ISO 14589.

Table 3 — Mechanical properties

d nom.	Shear load min.	Tensile load min.	Mandrel break load max.
mm	N	N	N
3,2	1 100	1 450	3 500
4	1 600	2 200	5 000
4,8	2 200	3 100	7 000

6 Workmanship

Rivets shall be free from burrs and harmful defects and shall have well formed heads and shanks.

After setting, rivets shall not show evidence of cracking when viewed at $\times 5$ magnification.

7 Acceptance testing

If there is no other agreement, acceptance inspection in accordance with ISO 3269 applies.

8 Designation

EXAMPLE A closed end blind rivet, with break pull mandrel and protruding head, with nominal diameter $d = 4$ mm and nominal length $l = 12,5$ mm with an aluminium alloy body (AlA) and a steel mandrel (St) is designated as follows:

Blind rivet ISO 15974 - 4 $\times$ 12,5 - AlA/St

STANDARDSISO.COM : Click to view the full PDF of ISO 15974:2000