
**Continuously hot-dipped coated steel
sheet products — Dimensional and shape
tolerances**

*Tôles en acier revêtues en continu par immersion à chaud —
Tolérances sur dimensions et forme*

STANDARDSISO.COM : Click to view the full PDF of ISO 16163:2010



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 16163:2010



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16163 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 12, *Continuous mill flat rolled products*.

This third edition cancels and replaces the second edition (ISO 16163:2005), which has been technically revised.

STANDARDSISO.COM : Click to view the full PDF of ISO 16163:2010

Continuously hot-dipped coated steel sheet products — Dimensional and shape tolerances

1 Scope

This International Standard applies to dimensional and shape tolerances for all continuously hot-dipped coated steel sheet products.

2 Dimensional tolerances

Dimensional tolerances are given in Tables 1 to 11.

Table 1 — Normal thickness tolerances for commercial, drawing, drawing aluminum-killed and extra-deep-drawing (stabilized interstitial-free) quality coils and cut lengths

Dimensions and tolerances in millimetres

Specified width	Thickness tolerances ^{ab} for specified thicknesses ^c										
	≤ 0,4	> 0,4 ≤ 0,6	> 0,6 ≤ 0,8	> 0,8 ≤ 1,0	> 1,0 ≤ 1,2	> 1,2 ≤ 1,6	> 1,6 ≤ 2,0	> 2,0 ≤ 2,5	> 2,5 ≤ 3,0	> 3,0 ≤ 4,0	> 4,0 ≤ 5,0
600 ≤ 1 200	±0,05	±0,06	±0,08	±0,09	±0,10	±0,12	±0,18	±0,19	±0,21	±0,23	±0,25
> 1 200 ≤ 1 500	±0,06	±0,07	±0,09	±0,10	±0,11	±0,13	±0,20	±0,22	±0,23	±0,25	±0,27
> 1 500 ≤ 1 800	—	±0,09	±0,10	±0,11	±0,13	±0,15	±0,22	±0,24	±0,25	±0,27	±0,29

NOTE 1 Thicknesses up to 1,6 mm are generally produced with a cold-rolled substrate.

NOTE 2 When International Standards that reference this standard permit slitting sheet to less than 600 mm in width to be considered as sheet, tolerances shall be subject to agreement.

^a Thickness tolerances for sheet in coil form are the same as for sheet supplied in cut lengths but, in cases where welds are present, the tolerances shall be double those given over a length of 15 m in the vicinity of the weld.

^b Given the difference in tolerances and physical properties of hot-rolled and cold-rolled sheet products, the user and the supplier may negotiate a specific type of substrate. The relationship between the coating mass, in grams per square metre, and the thickness, in micrometres, can be retrieved from the respective standards.

^c Thickness is measured at any point on the sheet not less than 25 mm from a side edge.

Table 2 — Normal thickness tolerances for structural-quality coils and cut lengths

Dimensions and tolerances in millimetres

Specified width	Thickness tolerances ^{abc} for specified thicknesses ^{de}										
	≤ 0,4	> 0,4 ≤ 0,6	> 0,6 ≤ 0,8	> 0,8 ≤ 1,0	> 1,0 ≤ 1,2	> 1,2 ≤ 1,6	> 1,6 ≤ 2,0	> 2,0 ≤ 2,5	> 2,5 ≤ 3,0	> 3,0 ≤ 4,0	> 4,0 ≤ 5,0
600 ≤ 1 200	±0,06	±0,07	±0,09	±0,10	±0,11	±0,13	±0,18	±0,19	±0,21	±0,23	±0,25
> 1 200 ≤ 1 500	±0,07	±0,08	±0,10	±0,11	±0,12	±0,14	±0,20	±0,22	±0,23	±0,25	±0,27
> 1 500 ≤ 1 800	—	±0,10	±0,11	±0,12	±0,14	±0,16	±0,22	±0,24	±0,25	±0,27	±0,29

NOTE 1 Thicknesses up to 1,6 mm are generally produced with a cold-rolled substrate.

NOTE 2 When International Standards that reference this standard permit slitting sheet to less than 600 mm in width to be considered as sheet, tolerances shall be subject to agreement.

a Thickness tolerances for sheet in coil form are the same as for sheets supplied in cut lengths but, in cases where welds are present, the tolerances shall be double those given over a length of 15 m in the vicinity of the weld.

b For specified strength levels of $R_e = 360$ MPa and greater, increase the thickness tolerances by 10 %, by applying normal rounding-off procedures.

c Tolerances for grade 550 shall be as agreed upon between the purchaser and the manufacturer.

d Given the difference in tolerances and physical properties of hot-rolled and cold-rolled sheet products, the user and the supplier may negotiate a specific type of substrate. The relationship between the coating mass, in grams per square metre, and the thickness, in micrometres, can be retrieved from the respective standards.

e Thickness is measured at any point on the sheet not less than 25 mm from a side edge.

Table 3 — Restricted thickness tolerances for commercial, drawing, drawing aluminum-killed, extra-deep-drawing (stabilized interstitial-free) and structural-quality coils and cut lengths — Hot-rolled substrate

Dimensions and tolerances in millimetres

Specified width	Thickness tolerances ^{abc} for specified thicknesses ^{de}				
	≤ 2,0	> 2,0 ≤ 2,5	> 2,5 ≤ 3,0	> 3,0 ≤ 4,0	> 4,0 ≤ 5,0
600 ≤ 1 200	±0,14	±0,15	±0,16	±0,18	±0,20
> 1 200 ≤ 1 500	±0,15	±0,16	±0,18	±0,19	±0,22
> 1 500 ≤ 1 800	±0,15	±0,18	±0,20	±0,22	±0,23

NOTE 1 Thicknesses up to 1,6 mm are generally produced with a cold-rolled substrate.

NOTE 2 When International Standards that reference this standard permit slitting sheet to less than 600 mm in width to be considered as sheet, tolerances shall be subject to agreement.

a Thickness tolerances for sheet in coil form are the same as for sheets supplied in cut lengths but, in cases where welds are present, the tolerances shall be double those given over a length of 15 m in the vicinity of the weld.

b For specified strength levels of $R_e = 360$ MPa and greater, tolerances are increased by 10 %, applying normal rounding-off procedures.

c Tolerances for grade 550 shall be as agreed upon between the purchaser and the manufacturer.

d Thickness is measured at any point on the sheet not less than 25 mm from a side edge

e The relationship between the coating mass, in grams per square metre, and the thickness, in micrometres, can be retrieved from the respective standards.

Table 4 — Restricted thickness tolerances for commercial, drawing, drawing aluminum-killed, extra-deep-drawing (stabilized interstitial-free) and structural-quality coils and cut lengths — Cold-rolled substrate

Dimensions and tolerances in millimetres

Specified width mm	Thickness tolerances ^{abc} for specified thicknesses ^{de}									
	≤ 0,4	> 0,4 ≤ 0,6	> 0,6 ≤ 0,8	> 0,8 ≤ 1,0	> 1,0 ≤ 1,2	> 1,2 ≤ 1,6	> 1,6 ≤ 2,0	> 2,0 ≤ 2,5	> 2,5 ≤ 3,0	> 3,0 ≤ 4,0
600 ≤ 1 200	±0,035	±0,045	±0,05	±0,055	±0,065	±0,08	±0,09	±0,11	±0,12	±0,13
> 1 200 ≤ 1 500	±0,045	±0,055	±0,06	±0,07	±0,08	±0,09	±0,10	±0,12	±0,13	±0,14
> 1 500 ≤ 1 800	—	±0,06	±0,07	±0,07	±0,08	±0,09	±0,10	±0,12	±0,13	±0,14

NOTE 1 Thicknesses up to 1,6 mm are generally produced with a cold-rolled substrate.

NOTE 2 When International Standards that reference this standard permit slitting sheet to less than 600 mm in width to be considered as sheet, tolerances shall be subject to agreement.

a Thickness tolerances for sheet in coil form are the same as for sheets supplied in cut lengths but, in cases where welds are present, the tolerances shall be double those given over a length of 15 m in the vicinity of the weld.

b For specified strength levels of $R_e = 360$ MPa and greater, tolerances are increased by 10 %, applying normal rounding-off procedures.

c Tolerances for grade 550 shall be as agreed upon between the purchaser and the manufacturer.

d Thickness is measured at any point on the sheet not less than 25 mm from a side edge.

e The relationship between the coating mass, in grams per square metre, and the thickness, in micrometres, can be retrieved from the respective standards.

Table 5 — Width tolerances for coils and cut lengths, not resquared

Dimensions and tolerances in millimetres

Specified width	Tolerance
≤ 1 500	+ 7 0
> 1 500 ≤ 1 800	+ 10 0

NOTE For resquared material, more restrictive tolerances are subject to negotiation.

Table 6 — Length tolerances for cut lengths, not resquared

Dimensions and tolerances in millimetres

Specified length	Tolerance
≤ 3 000	+ 20 0
> 3 000 ≤ 6 000	+ 30 0
> 6 000	+ 0,5 % × length 0

NOTE For resquared material, more restrictive tolerances are subject to negotiation.

Table 7 — Camber tolerances for coils and cut lengths, not resquared

Dimensions and tolerances in millimetres

Form	Camber tolerance
Coils	20 in any 5 000 length
Cut lengths	0,4 % × length

NOTE Camber is the greatest deviation of a side edge from a straight line, the measurement being taken on the concave side with a straight edge as shown in Figure 1. For resquared material, more restrictive tolerances are subject to negotiation.

Table 8 — Out-of-square tolerance for cut lengths, not resquared

Dimensions	Out-of-square tolerance
All thicknesses and all sizes	1 % × width

NOTE Out-of-square is the greatest deviation of an end edge from a straight line, at right angles to a side and touching one corner, the measurement being taken as shown in Figure 2. It can also be measured as one-half of the difference between the diagonals of a cut-length sheet.

Table 9 — Out-of-square tolerances for resquared material

Dimensions and tolerances in millimetres

Specified length	Specified width	Out-of-square tolerance
≤ 3 000	≤ 1 200	+ 2 0
	> 1 200	+ 3 0
> 3 000	All widths	+ 3 0

NOTE Out-of-square is the greatest deviation of an end edge from a straight line, at right angles to a side and touching one corner, the measurement being taken as shown in Figure 2. It can also be measured as one-half of the difference between the diagonals of the cut-length sheet. When measuring material ordered to resquared tolerances, consideration might have to be given to extreme variations in temperature.

Table 10 — Standard flatness tolerances for cut lengths

Dimensions and tolerances in millimetres

Specified thickness	Specified width	Flatness tolerance Specified strength level of R_e		
		< 220 MPa	$\geq 220 \leq 340$ MPa	> 340 MPa
$\leq 0,7$	$\leq 1\,200$	14	17	20
	$> 1\,200 \leq 1\,500$	17	20	23
	$> 1\,500$	21	24	29
$> 0,7 \leq 1,2$	$\leq 1\,200$	12	15	18
	$> 1\,200 \leq 1\,500$	14	17	21
	$> 1\,500$	19	22	27
$> 1,2 \leq 2,0$	$\leq 1\,200$	12	12	18
	$> 1\,200 \leq 1\,500$	14	15	21
	$> 1\,500$	19	21	27
$> 2,0 \leq 3,0$	$\leq 1\,200$	16	16	20
	$> 1\,200 \leq 1\,500$	20	20	30
	$> 1\,500$	25	25	40

NOTE 1 This table also applies to sheet cut to length from coils by the customer when agreed-upon flattening procedures are performed.

NOTE 2 Maximum deviation from a flat horizontal surface: with the sheet lying under its own weight on a flat surface, the maximum distance between the lower surface of the sheet and the flat horizontal surface is the maximum deviation from flatness as shown in Figure 3.

Table 11 — Restricted flatness tolerances for cut lengths

Dimensions and tolerances in millimetres

Specified thickness	Specified width	Flatness tolerance Specified strength level of R_e		
		< 220 MPa	$\geq 220 \leq 340$ MPa	> 340 MPa
$\leq 0,7$	$\leq 1\,200$	7	10	—
	$> 1\,200 \leq 1\,500$	8	11	—
	$> 1\,500$	10	14	—
$> 0,7 \leq 1,2$	$\leq 1\,200$	6	8	—
	$> 1\,200 \leq 1\,500$	7	10	—
	$> 1\,500$	9	12	—
$> 1,2 \leq 2,0$	$\leq 1\,200$	6	7	—
	$> 1\,200 \leq 1\,500$	7	8	—
	$> 1\,500$	8	11	—
$> 2,0 \leq 3,0$	$\leq 1\,200$	6	7	—
	$> 1\,200 \leq 1\,500$	7	8	—
	$> 1\,500$	8	11	—

NOTE 1 This table also applies to sheet cut to length from coils by the customer when agreed-upon flattening procedures are performed.

NOTE 2 Maximum deviation from a flat horizontal surface: with the sheet lying under its own weight on a flat surface, the maximum distance between the lower surface of the sheet and the flat horizontal surface is the maximum deviation from flatness as shown in Figure 3.

More restrictive tolerances may be negotiated.