
Cubic boron nitride inserts, tipped or solid — Dimensions, types

*Plaquettes en nitrure de bore cubique, brasées ou monobloc —
Dimensions, types*

STANDARDSISO.COM : Click to view the full PDF of ISO 16462:2014



STANDARDSISO.COM : Click to view the full PDF of ISO 16462:2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Insert shapes and design	1
3.1 Insert shapes	1
3.2 Normal clearance α_n	1
3.3 Cutting edge corner	1
3.4 Tolerance class	1
3.5 Design of cutting edges	2
3.6 Insert type	2
4 Designation	2
4.1 General	2
4.2 Designation of inserts for turning	2
4.3 Designation of a tipped insert for milling	2
5 Dimensions	3
5.1 Insert shape T with fixing hole (inserts for turning)	3
5.2 Insert shape S with fixing hole (inserts for turning)	4
5.3 Insert shape C with fixing hole (inserts for turning)	5
5.4 Insert shape D with fixing hole (inserts for turning)	6
5.5 Insert shape V with fixing hole (inserts for turning)	7
5.6 Insert shape S with fixing hole (inserts for milling)	8
5.7 Insert shape C with fixing hole (inserts for milling)	9
5.8 Insert shapes C, R, S, and T without fixing hole (inserts for turning)	9
5.9 Insert shapes S and T without fixing hole (inserts for milling)	11
5.10 Insert shapes S and T without fixing hole (inserts for milling)	12
5.11 Insert shape W with fixing hole (inserts for turning)	13
5.12 Insert shape W without fixing hole (inserts for turning)	14
6 Cutting edge length, l_1, of tipped inserts	15
6.1 General	15
6.2 Inserts with radius	15
6.3 Inserts with wiper edge	15
7 Base material, cutting material	16
8 Measurements	16
9 Marking	16
Annex A (informative) Relationship between designations in ISO 16462 and ISO/TS 13399-2	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 29, *Small Tools*, Subcommittee SC 9, *Tools with cutting edges made of hard cutting materials*.

This second edition cancels and replaces the first edition (ISO 16462:2004), of which it constitutes a minor revision.

Cubic boron nitride inserts, tipped or solid — Dimensions, types

1 Scope

This International Standard applies to inserts with insert shapes in accordance with ISO 883, ISO 3364, ISO 3365, and ISO 6987, tipped with cubic boron nitride (BL, BH, BC) or made of solid cubic boron nitride (BL, BH, BC).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 513, *Classification and application of hard cutting materials for metal removal with defined cutting edges — Designation of the main groups and groups of application*

ISO 883, *Indexable hardmetal (carbide) inserts with rounded corners, without fixing hole — Dimensions*

ISO 1832, *Indexable inserts for cutting tools — Designation*

ISO 3364, *Indexable hardmetal (carbide) inserts with rounded corners, with cylindrical fixing hole — Dimensions*

ISO 3365, *Indexable hardmetal (carbide) inserts with wiper edges, without fixing hole — Dimensions*

ISO 6987, *Indexable hard material inserts with rounded corners, with partly cylindrical fixing hole — Dimensions*

3 Insert shapes and design

3.1 Insert shapes

Triangular (T), square (S), rhombic 80° (C), 55° (D) and 35° (V), round (R), and trigon (W).

3.2 Normal clearance α_n

Normal clearance 0° (N), 5° (B), 7° (C), and 11° (P).

3.3 Cutting edge corner

Inserts for turning with corner radius r_ϵ 0,2 mm, 0,4 mm, 0,8 mm, 1,2 mm, and 1,6 mm.

Inserts for milling with wiper edge.

NOTE The design of non-tipped corners is optional.

3.4 Tolerance class

Tolerance class in accordance with ISO 1832 shall be applied. In [Tables 1 to 12](#), this position is shown with a dot (•).

3.5 Design of cutting edges

Any design shall be indicated in the designation (see ISO 1832).

3.6 Insert type

The styles of tipped or solid cutting edges in accordance with ISO 1832 shall be applied.

4 Designation

4.1 General

The designation of inserts tipped or solid with cubic boron nitride (BL, BH, BC) is based on ISO 1832. The letter symbol for the cutting edge condition and the letter symbol for the insert type shall be indicated in the designation in each case.

Designations contained in 4.2 and 4.3 are examples of the use of designations in accordance with ISO 1832.

4.2 Designation of inserts for turning

4.2.1 Solid insert (S)

Designation of a rhombic insert with included angle $\varepsilon_r = 80^\circ$ (C), normal clearance $\alpha_n = 0^\circ$ (N), with tolerance class M, without chip breakers and without fixing hole (N), with side length $l = 9,67$ mm (09), thickness $s = 3,18$ mm (03), corner radius $r_\varepsilon = 0,8$ mm (08), with chamfered and rounded cutting edges (S), insert type solid (S), cutting material in accordance with ISO 513 (e.g. BL05):

Insert CNMN 090308S — S — BL05 —

NOTE BL05 is optional in accordance with ISO 1832, designation symbol 13.

4.2.2 Insert, tipped — full thickness — one corner (T)

Designation of a rhombic insert with included angle $\varepsilon_r = 55^\circ$ (D), normal clearance $\alpha_n = 0^\circ$ (N), with tolerance class M, without chip breakers and with cylindrical fixing hole (A), with side length $l = 15,5$ mm (15), thickness $s = 4,76$ mm (04), corner radius $r_\varepsilon = 0,8$ mm (08), with chamfered and rounded cutting edges (S), tipped — full thickness — one corner (T), long (L), cutting material in accordance with ISO 513 (e.g. BL05):

Insert DNMA 150408S — TL — BL05 —

NOTE BL05 is optional in accordance with ISO 1832, designation symbol 13.

4.3 Designation of a tipped insert for milling

Designation of a square insert (S) with normal clearance $\alpha_n = 7^\circ$ (C), with tolerance class G, without chip breakers and with fixing hole (W), with side length $l = 12,7$ mm (12), thickness $s = 4,76$ mm (04), cutting edge angle $\kappa_r = 75^\circ$ (E), normal clearance at wiper edge $\alpha = 15^\circ$ (D), right-hand type (R), tipped — one side — one corner (A), long (L), cutting material in accordance with ISO 513 (e.g. BL05):

Insert SCGW 1204EDR — AL — BL05 —

NOTE BL05 is optional in accordance with ISO 1832, designation symbol 13.

5 Dimensions

5.1 Insert shape T with fixing hole (inserts for turning)

See [Figure 1](#) and [Table 1](#).

NOTE For the dimensions of l_1 , see [Table 13](#).




Figure 1

Table 1

Designation	d	d_1	$l_1 \approx$	m	s	α_n	r_ε
TC•W 09 02 02S	5,56	2,5	9,63	8,137	2,38	7°	0,2
TC•W 09 02 04S	5,56	2,5	9,63	7,943	2,38	7°	0,4
TC•W 09 02 08S	5,56	2,5	9,63	7,541	2,38	7°	0,8
TC•W 11 02 02S	6,35	2,8	11	9,322	2,38	7°	0,2
TC•W 11 02 04S	6,35	2,8	11	9,128	2,38	7°	0,4
TC•W 11 02 08S	6,35	2,8	11	8,731	2,38	7°	0,8
TC•W 16 T3 02S	9,525	4,4	16,5	14,084	3,97	7°	0,2
TC•W 16 T3 04S	9,525	4,4	16,5	13,891	3,97	7°	0,4
TC•W 16 T3 08S	9,525	4,4	16,5	13,494	3,97	7°	0,8
TC•W 16 T3 12S	9,525	4,4	16,5	13,097	3,97	7°	1,2
TC•W 16 T3 16S	9,525	4,4	16,5	12,700	3,97	7°	1,6
TN•A 11 03 02S	6,35	2,26	11	9,322	3,18	0°	0,2
TN•A 11 03 04S	6,35	2,26	11	9,128	3,18	0°	0,4
TN•A 11 03 08S	6,35	2,26	11	8,731	3,18	0°	0,8
TN•A 16 04 04S	9,525	3,81	16,5	13,891	4,76	0°	0,4
TN•A 16 04 08S	9,525	3,81	16,5	13,494	4,76	0°	0,8
TN•A 16 04 12S	9,525	3,81	16,5	13,097	4,76	0°	1,2
TN•A 16 04 16S	9,525	3,81	16,5	12,700	4,76	0°	1,6
TP•W 08 02 02S	4,763	2,3	8,2	6,945	2,38	11°	0,2
TP•W 08 02 04S	4,763	2,3	8,2	6,747	2,38	11°	0,4
TP•W 08 02 08S	4,763	2,3	8,2	6,350	2,38	11°	0,8
TP•W 09 02 02S	5,56	2,5	9,63	8,137	2,38	11°	0,2

Table 1 — (continued)

Designation	d	d_1	l $\approx$	m	s	α_n	r_ε
TP•W 09 02 04S	5,56	2,5	9,63	7,943	2,38	11°	0,4
TP•W 09 02 08S	5,56	2,5	9,63	7,541	2,38	11°	0,8
TP•W 11 02 02S	6,35	2,8	11	8,731	2,38	11°	0,2
TP•W 11 02 04S	6,35	2,8	11	8,137	2,38	11°	0,4
TP•W 11 02 08S	6,35	2,8	11	7,943	2,38	11°	0,8
TP•W 11 03 02S	6,35	3,3	11,0	9,327	3,18	11°	0,2
TP•W 11 03 04S	6,35	3,3	11,0	9,128	3,18	11°	0,4
TP•W 11 03 08S	6,35	3,3	11,0	8,731	3,18	11°	0,8
TP•W 16 03 04S	9,525	4,4	16,5	13,891	3,18	11°	0,4
TP•W 16 03 08S	9,525	4,4	16,5	13,494	3,18	11°	0,8
TP•W 16 T3 04S	9,525	4,4	16,5	13,891	3,97	11°	0,4
TP•W 16 T3 08S	9,525	4,4	16,5	13,494	3,97	11°	0,8
TP•W 16 T3 12S	9,525	4,4	16,5	13,097	3,97	11°	1,2
TP•W 16 T3 16S	9,525	4,4	16,5	12,700	3,97	11°	1,6
TP•W 16 04 04S	9,525	4,4	16,5	13,891	4,76	11°	0,4
TP•W 16 04 08S	9,525	4,4	16,5	13,494	4,76	11°	0,8

5.2 Insert shape S with fixing hole (inserts for turning)

See [Figure 2](#) and [Table 2](#).

NOTE For the dimensions of l_1 , see [Table 13](#).




Figure 2

Table 2

Designation	d	d_1	l $\approx$	m	s	α_n	r_ε
SC•W 09 T3 02S	9,525	4,4	9,525	1,889	3,97	7°	0,2
SC•W 09 T3 04S	9,525	4,4	9,525	1,808	3,97	7°	0,4
SC•W 09 T3 08S	9,525	4,4	9,525	1,644	3,97	7°	0,8
SC•W 09 T3 12S	9,525	4,4	9,525	1,479	3,97	7°	1,2
SC•W 12 04 04S	12,7	5,5	12,7	2,466	4,76	7°	0,4

Table 2 — (continued)

Designation	d	d_1	l $\approx$	m	s	α_n	r_ε
SC•W 12 04 08S	12,7	5,5	12,7	2,301	4,76	7°	0,8
SC•W 12 04 12S	12,7	5,5	12,7	2,137	4,76	7°	1,2
SN•A 09 03 04S	9,525	3,81	9,525	1,808	3,18	0°	0,4
SN•A 09 03 08S	9,525	3,81	9,525	1,644	3,18	0°	0,8
SN•A 09 03 12S	9,525	3,81	9,525	1,479	3,18	0°	1,2
SN•A 12 04 04S	12,7	5,16	12,7	2,466	4,76	0°	0,4
SN•A 12 04 08S	12,7	5,16	12,7	2,301	4,76	0°	0,8
SN•A 12 04 12S	12,7	5,16	12,7	2,137	4,76	0°	1,2
SN•A 12 04 16S	12,7	5,16	12,7	1,972	4,76	0°	1,6

5.3 Insert shape C with fixing hole (inserts for turning)

See [Figure 3](#) and [Table 3](#).

NOTE For the dimensions of l_1 , see [Table 13](#).




Figure 3

Table 3

Designation	d	d_1	l $\approx$	m_1	m_2	s	α_n	r_ε
CC•W 06 02 02S	6,35	2,8	6,45	1,652	0,908	2,38	7°	0,2
CC•W 06 02 04S	6,35	2,8	6,45	1,544	0,848	2,38	7°	0,4
CC•W 06 02 08S	6,35	2,8	6,45	1,323	0,727	2,38	7°	0,8
CC•W 09 T3 02S	9,525	4,4	9,67	2,535	1,392	3,97	7°	0,2
CC•W 09 T3 04S	9,525	4,4	9,67	2,426	1,333	3,97	7°	0,4
CC•W 09 T3 08S	9,525	4,4	9,67	2,206	1,212	3,97	7°	0,8
CC•W 09 T3 12S	9,525	4,4	9,67	1,985	1,091	3,97	7°	1,2
CC•W 12 04 04S	12,7	5,5	12,9	3,308	1,818	4,76	7°	0,4
CC•W 12 04 08S	12,7	5,5	12,9	3,088	1,697	4,76	7°	0,8
CC•W 12 04 12S	12,7	5,5	12,9	2,867	1,576	4,76	7°	1,2
CC•W 12 04 16S	12,7	5,5	12,9	2,646	1,454	4,76	7°	1,6

Table 3 — (continued)

Designation	d	d_1	l $\approx$	m_1	m_2	s	α_n	r_ε
CN•A 09 03 04S	9,525	3,81	9,67	2,426	1,333	3,18	0°	0,4
CN•A 09 03 08S	9,525	3,81	9,67	2,206	1,212	3,18	0°	0,8
CN•A 12 04 04S	12,7	5,16	12,9	3,308	1,818	4,76	0°	0,4
CN•A 12 04 08S	12,7	5,16	12,9	3,088	1,697	4,76	0°	0,8
CN•A 12 04 12S	12,7	5,16	12,9	2,867	1,576	4,76	0°	1,2
CN•A 12 04 16S	12,7	5,16	12,9	2,646	1,454	4,76	0°	1,6
CP•W 06 02 02S	6,35	2,8	6,45	1,652	0,908	2,38	11°	0,2
CP•W 06 02 04S	6,35	2,8	6,45	1,544	0,848	2,38	11°	0,4
CP•W 06 02 08S	6,35	2,8	6,45	1,323	0,727	2,38	11°	0,8
CP•W 09 03 02S	9,525	4,4	9,67	2,534	1,392	3,18	11°	0,2
CP•W 09 03 04S	9,525	4,4	9,67	2,426	1,333	3,18	11°	0,4
CP•W 09 03 08S	9,525	4,4	9,67	2,206	1,212	3,18	11°	0,8
CP•W 09 T3 02S	9,525	4,4	9,67	2,534	1,392	3,97	11°	0,2
CP•W 09 T3 04S	9,525	4,4	9,67	2,426	1,333	3,97	11°	0,4
CP•W 09 T3 08S	9,525	4,4	9,67	2,206	1,212	3,97	11°	0,8
CP•W 09 T3 12S	9,525	4,4	9,67	1,985	1,091	3,97	11°	1,2

5.4 Insert shape D with fixing hole (inserts for turning)

See [Figure 4](#) and [Table 4](#).

NOTE For the dimensions of l_1 , see [Table 13](#).




Figure 4

Table 4

Designation	d	d_1	l $\approx$	m	s	α_n	r_ϵ
DC•W 07 02 02S	6,35	2,8	7,75	3,464	2,38	7°	0,2
DC•W 07 02 04S	6,35	2,8	7,75	3,238	2,38	7°	0,4
DC•W 07 02 08S	6,35	2,8	7,75	2,776	2,38	7°	0,8
DC•W 11 T3 02S	9,525	4,4	11,6	5,315	3,97	7°	0,2
DC•W 11 T3 04S	9,525	4,4	11,6	5,089	3,97	7°	0,4
DC•W 11 T3 08S	9,525	4,4	11,6	4,626	3,97	7°	0,8
DC•W 11 T3 12S	9,525	4,4	11,6	4,164	3,97	7°	1,2
DN•A 11 04 04S	9,525	3,81	11,6	5,089	4,76	0°	0,4
DN•A 11 04 08S	9,525	3,81	11,6	4,626	4,76	0°	0,8
DN•A 15 04 04S	12,7	5,16	15,5	6,939	4,76	0°	0,4
DN•A 15 04 08S	12,7	5,16	15,5	6,477	4,76	0°	0,8
DN•A 15 04 12S	12,7	5,16	15,5	6,014	4,76	0°	1,2
DN•A 15 06 04S	12,7	5,16	15,5	6,939	6,35	0°	0,4
DN•A 15 06 08S	12,7	5,16	15,5	6,477	6,35	0°	0,8
DN•A 15 06 12S	12,7	5,16	15,5	6,014	6,35	0°	1,2
DN•A 15 06 16S	12,7	5,16	15,5	5,551	6,35	0°	1,6

5.5 Insert shape V with fixing hole (inserts for turning)

See [Figure 5](#) and [Table 5](#).

NOTE For the dimensions of l_1 , see [Table 13](#).




Figure 5

Table 5

Designation	d	d_1	l $\approx$	m	s	α_n	r_ϵ
VC•W 11 03 02S	6,35	2,8	11,1	6,911	3,18	7°	0,2
VC•W 11 03 04S	6,35	2,8	11,1	6,460	3,18	7°	0,4
VC•W 11 03 08S	6,35	2,8	11,1	5,537	3,18	7°	0,8
VC•W 16 04 02S	9,525	4,4	16,6	10,603	4,76	7°	0,2
VC•W 16 04 04S	9,525	4,4	16,6	10,154	4,76	7°	0,4
VC•W 16 04 08S	9,525	4,4	16,6	9,231	4,76	7°	0,8
VC•W 16 04 12S	9,525	4,4	16,6	8,306	4,76	7°	1,2


Table 5 — (continued)

Designation	d	d_1	l $\approx$	m	s	α_n	r_ε
VB•W 16 04 02S	9,525	4,4	16,6	10,602	4,76	5°	0,2
VB•W 16 04 04S	9,525	4,4	16,6	10,152	4,76	5°	0,4
VB•W 16 04 08S	9,525	4,4	16,6	9,229	4,76	5°	0,8
VB•W 16 04 12S	9,525	4,4	16,6	8,306	4,76	5°	1,2
VN•A 16 04 04S	9,525	3,81	16,6	10,152	4,76	0°	0,4
VN•A 16 04 08S	9,525	3,81	16,6	9,229	4,76	0°	0,8
VN•A 16 04 12S	9,525	3,81	16,6	8,306	4,76	0°	1,2

5.6 Insert shape S with fixing hole (inserts for milling)

See [Figure 6](#) and [Table 6](#).

NOTE For the dimensions of l_1 , see [Table 13](#).



NOTE Right-hand type is shown in the figure (R).

Figure 6


Table 6

Designation	d	d_1	l $\approx$	m	s	α_n	α'_n
SC•W 09 T3 ECR	9,525	4,4	9,525	0,543	3,97	7°	7°
SC•W 12 04 ECR	12,7	5,5	12,7	0,900	4,76	7°	7°
SP•W 09 T3 EDR	9,525	4,4	9,525	0,543	3,97	11°	15°
SP•W 12 04 EDR	12,7	5,5	12,7	0,900	4,76	11°	15°

5.7 Insert shape C with fixing hole (inserts for milling)

See [Figure 7](#) and [Table 7](#).

NOTE For the dimensions of l_1 , see [Table 13](#).



NOTE Right-hand type is shown in the figure (R).

Figure 7

Table 7

Designation	d	d_1	l $\approx$	m	s	α_n	α'_n
CC•W 09 T3 PCR	9,525	4,4	9,67	0,631	3,97	7°	7°
CC•W 12 04 PCR	12,7	5,5	12,9	0,936	4,76	7°	7°
CP•W 09 T3 PDR	9,525	4,4	9,67	0,631	3,97	11°	15°
CP•W 12 04 PDR	12,7	5,5	12,9	0,936	4,76	11°	15°

5.8 Insert shapes C, R, S, and T without fixing hole (inserts for turning)

See [Figure 8](#) and [Table 8](#).




Figure 8

Table 8

Designation	d	l $\approx$	m	m_1	m_2	s	α_n	r_ϵ
CN•N 09 03 04S	9,525	9,67	—	2,426	1,333	3,18	0°	0,4
CN•N 09 03 08S	9,525	9,67	—	2,206	1,212	3,18	0°	0,8
CN•N 09 03 12S	9,525	9,67	—	1,985	1,091	3,18	0°	1,2
CN•N 09 03 16S	9,525	9,67	—	1,764	0,970	3,18	0°	1,6
CN•N 12 04 04S	12,7	12,9	—	3,308	1,818	4,76	0°	0,4
CN•N 12 04 08S	12,7	12,9	—	3,088	1,697	4,76	0°	0,8
CN•N 12 04 12S	12,7	12,9	—	2,867	1,576	4,76	0°	1,2
CN•N 12 04 16S	12,7	12,9	—	2,646	1,454	4,76	0°	1,6
RC•N 09 03 00S	9,525	—	—	—	—	3,18	7°	—
RC•N 12 04 00S	12,7	—	—	—	—	4,76	7°	—
RN•N 09 03 00S	9,525	—	—	—	—	3,18	0°	—
RN•N 12 03 00S	12,7	—	—	—	—	3,18	0°	—
RN•N 12 04 00S	12,7	—	—	—	—	4,76	0°	—
SN•N 09 03 04S	9,525	9,525	1,808	—	—	3,18	0°	0,4
SN•N 09 03 08S	9,525	9,525	1,644	—	—	3,18	0°	0,8
SN•N 09 03 12S	9,525	9,525	1,479	—	—	3,18	0°	1,2
SN•N 09 03 16S	9,525	9,525	1,315	—	—	3,18	0°	1,6
SN•N 12 03 04S	12,7	12,7	2,466	—	—	3,18	0°	0,4
SN•N 12 03 08S	12,7	12,7	2,301	—	—	3,18	0°	0,8
SN•N 12 03 12S	12,7	12,7	2,137	—	—	3,18	0°	1,2
SN•N 12 03 16S	12,7	12,7	1,972	—	—	3,18	0°	1,6
SN•N 12 04 04S	12,7	12,7	2,466	—	—	4,76	0°	0,4
SN•N 12 04 08S	12,7	12,7	2,301	—	—	4,76	0°	0,8
SN•N 12 04 12S	12,7	12,7	2,137	—	—	4,76	0°	1,2

Table 8 — (continued)

Designation	d	l $\approx$	m	m_1	m_2	s	α_n	r_ε
SN•N 12 04 16S	12,7	12,7	1,972	—	—	4,76	0°	0,4
SP•N 09 03 04S	9,525	9,5	1,808	—	—	3,18	1°	1,6
SP•N 09 03 08S	9,525	9,5	1,644	—	—	3,18	11°	0,8
SP•N 09 03 12S	9,525	9,5	1,479	—	—	3,18	11°	1,2
SP•N 12 03 08S	12,7	12,7	2,301	—	—	3,18	11°	0,8
SP•N 12 03 12S	12,7	12,7	2,137	—	—	3,18	11°	1,2
SP•N 12 04 08S	12,7	12,7	2,301	—	—	4,76	11°	0,8
SP•N 12 04 12S	12,7	12,7	2,137	—	—	4,76	11°	1,2
SP•N 12 04 16S	12,7	12,7	1,973	—	—	4,76	11°	1,6
TB•N 06 01 02S	3,969	6,87	5,755	—	—	1,59	5°	0,2
TB•N 06 01 04S	3,969	6,87	5,557	—	—	1,59	5°	0,4
TB•N 06 01 08S	3,969	6,87	5,160	—	—	1,59	5°	0,8
TN•N 11 03 02S	6,35	11	9,322	—	—	3,18	0°	0,2
TN•N 11 03 04S	6,35	11	9,128	—	—	3,18	0°	0,4
TN•N 11 03 08S	6,35	11	8,731	—	—	3,18	0°	0,8
TN•N 11 03 12S	6,35	11	8,334	—	—	3,18	0°	1,2
TN•N 11 03 16S	6,35	11	7,937	—	—	3,18	0°	1,6
TN•N 16 04 04S	9,525	16,5	13,891	—	—	4,76	0°	0,4
TN•N 16 04 08S	9,525	16,5	13,494	—	—	4,76	0°	0,8
TN•N 16 04 12S	9,525	16,5	13,097	—	—	4,76	0°	1,2
TN•N 16 04 16S	9,525	16,5	12,700	—	—	4,76	0°	1,6
TP•N 11 03 04S	6,35	11	9,128	—	—	3,18	11°	0,4
TP•N 11 03 08S	6,35	11	8,731	—	—	3,18	11°	0,8
TP•N 11 03 12S	6,35	11	8,334	—	—	3,18	11°	1,2
TP•N 16 03 04S	9,525	16,5	13,891	—	—	3,18	11°	0,4
TP•N 16 03 08S	9,525	16,5	13,494	—	—	3,18	11°	0,8
TP•N 16 04 02S	9,525	16,5	14,089	—	—	4,76	11°	0,2
TP•N 16 04 04S	9,525	16,5	13,891	—	—	4,76	11°	0,4
TP•N 16 04 08S	9,525	16,5	13,494	—	—	4,76	11°	0,8
TP•N 16 04 12S	9,525	16,5	13,097	—	—	4,76	11°	1,2
TP•N 16 04 16S	9,525	16,5	12,700	—	—	4,76	11°	1,6

5.9 Insert shapes S and T without fixing hole (inserts for milling)

See [Figure 9](#) and [Table 9](#).




Figure 9

Table 9

Designation	d	l	m	s	α_n	α'_n
SN•N 09 03 ENR	9,525	9,525	0,543	3,18	0°	0°
SN•N 12 04 ENR	12,7	12,7	0,900	4,76	0°	0°
SP•N 09 03 EPR	9,525	9,525	0,543	3,18	11°	11°
SP•N 12 04 EPR	12,7	12,7	0,900	4,76	11°	11°
TN•N 11 03 PNR	6,35	11	1,288	3,18	0°	0°
TC•N 16 04 PCR	9,525	16,5	2,450	4,76	7°	7°
TP•N 16 04 PPR	9,525	16,5	2,450	4,76	11°	11°

5.10 Insert shapes S and T without fixing hole (inserts for milling)

See [Figure 10](#) and [Table 10](#).




Figure 10

Table 10

Designation	d	l $\approx$	m	s	α_n
SN•N 09 03 EN	9,525	9,525	0,543	3,18	0°
SN•N 12 04 EN	12,7	12,7	0,900	4,76	0°
TN•N 11 03 PN	6,35	11	1,288	3,18	0°
TN•N 16 04 PN	9,525	16,5	2,450	4,76	0°

5.11 Insert shape W with fixing hole (inserts for turning)

See [Figure 11](#) and [Table 11](#).

NOTE For the dimensions of l_1 , see [Table 13](#).



Table 11

5.12 Insert shape W without fixing hole (inserts for turning)

NOTE For the dimensions of l_1 , see [Table 13](#).



Table 12

Designation	d	l $\approx$	m	s	α_n	r_ϵ
WN•N 06 04 04	9,525	6,52	2,426	4,76	0°	0,4
WN•N 06 04 08	9,525	6,52	2,203	4,76	0°	0,8
WN•N 06 04 12	9,525	6,52	1,980	4,76	0°	1,2
WN•N 08 04 04	12,7	8,69	3,307	4,76	0°	0,4
WN•N 08 04 08	12,7	8,69	3,084	4,76	0°	0,8
WN•N 08 04 12	12,7	8,69	2,862	4,76	0°	1,2


6 Cutting edge length, l_1 , of tipped inserts

6.1 General

l_1 is defined as the length along the major cutting edge from the end of the tip to the furthest point perpendicular to the major cutting edge.

6.2 Inserts with radius

See [Figure 13](#).



a For the dimensions of l_1 , see [Table 13](#).

Figure 13

6.3 Inserts with wiper edge

See [Figure 14](#).