

International Standard



1675

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Plastics — Liquid resins — Determination of density by the pycnometer method

Plastiques — Résines liquides — Détermination de la masse volumique par la méthode du pycnomètre

Second edition — 1985-08-15

STANDARDSISO.COM : Click to view the full PDF of ISO 1675:1985

UDC 678.6/.7-498.1 : 531.756.4

Ref. No. ISO 1675-1985 (E)

Descriptors : plastics, liquid resins, tests, determination, density (mass/volume), pycnometric analysis, pycnometers.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 1675 was prepared by Technical Committee ISO/TC 61, *Plastics*.

ISO 1675 was first published in 1975. This second edition cancels and replaces the first edition, of which it constitutes a technical revision.

Plastics — Liquid resins — Determination of density by the pycnometer method

1 Scope and field of application

This International Standard specifies a method for the determination of the density of liquid resins using a pycnometer.

2 Definition

density; mass density : Mass divided by volume. (Definition taken from ISO 31/3.)

It may be expressed in grams per millilitre (g/ml).*

3 Principle

Determination of the mass at 23 °C of resin contained in a pycnometer of known volume.

NOTE — This method is easily applicable to low and medium viscosity resins. Difficulties in the procedure exist for high viscosity resins.

4 Apparatus

4.1 Pycnometer, consisting of a precision graduated flask. The height of the neck above the graduation mark shall not exceed 50 mm.

The graduated volume of the pycnometer at $23 \pm 0,1$ °C, measured by weighing the mass of distilled water contained in the pycnometer at this temperature, shall be known to within 1 part in 10 000 (see note to clause 6).

The pycnometers normally used have the characteristics given in the following table.

Volume of flask, <i>V</i>	Internal diameter of neck, <i>d</i>
ml	mm
100 ± 0,1	13 ± 1
50 ± 0,05	11 ± 1

* 1 g/ml = 1 000 kg/m³

4.2 Funnel, whose stem, the internal diameter of which shall be as large as possible, penetrates into the pycnometer exactly down to the level of the graduation mark.

4.3 Balance, accurate to 0,2 mg.

4.4 Water bath, capable of being maintained at $23 \pm 0,1$ °C.

4.5 Fine filter paper.

4.6 Transparent conical flask, with wide neck (for example Erlenmeyer), stoppered, of capacity 200 to 600 ml.

5 Procedure

5.1 Preparation of resin

Place at least 150 g of resin in the conical flask (4.6) and inspect the contents of the flask for bubbles. If any bubbles are observed, allow the stoppered flask to stand long enough for all the bubbles to dissipate before or while bringing the flask and its contents to $23 \pm 0,1$ °C by immersion in the water bath (4.4).

NOTE — To accelerate the release of bubbles, especially any adjacent to the walls of the flask, disturb or detach them using a fine wire inserted through the neck of the flask.

5.2 Measurement of density

Weigh the empty pycnometer (4.1) to the nearest 0,2 mg.

Place the pycnometer in the water-bath (4.4) and fill the pycnometer with resin using the funnel (4.2).

The following points require close attention :

- bubbles shall not be present in the resin in the pycnometer; if bubbles form, wait for them to disappear, if necessary rubbing the walls of the pycnometer with a fine metal wire, or, better still, empty the pycnometer, clean it and refill;