

INTERNATIONAL
STANDARD

ISO
17236

IULTCS/IUP 43

Second edition
2016-02-15

**Leather — Physical and mechanical
tests — Determination of extension set**

*Cuir — Essais physiques et mécaniques — Détermination de la
déformabilité*

STANDARDSISO.COM : Click to view the full PDF of ISO 17236:2016



Reference numbers
ISO 17236:2016(E)
IULTCS/IUP 43:2016(E)

© ISO 2016

STANDARDSISO.COM : Click to view the full PDF of ISO 17236:2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Sampling and sample preparation	2
6 Procedure	2
7 Expression of results	3
8 Test report	3

STANDARDSISO.COM : Click to view the full PDF of ISO 17236:2016

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

ISO 17236 was prepared by the Physical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUP Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

It is based on IUP 43 which was published in *J. Soc. Leather Tech. Chem.* **84**, p. 399, (2000) and confirmed as an official method of the IULTCS in March 2001.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This second edition cancels and replaces the first edition (ISO 17236:2002), of which it constitutes a minor revision to align item d) of Clause 8 with ISO 2419:2012.

Leather — Physical and mechanical tests — Determination of extension set

1 Scope

This International Standard specifies a method for determining the extension set of leather. It is intended for use on upholstery leather but is applicable to all flexible leathers.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 2419, *Leather — Physical and mechanical tests — Sample preparation and conditioning*

ISO 2589, *Leather — Physical and mechanical tests — Determination of thickness*

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

3 Principle

A test piece is repeatedly extended at a specified rate until the forces reach a predetermined level and the permanent extension is calculated as a percentage of the original length.

4 Apparatus

4.1 Tensile testing machine, having a force range appropriate to the specimen under test and consisting of a means of recording the force (4.1.1) and jaws that operate at a uniform speed of separation of $50 \text{ mm} \pm 5 \text{ mm/min}$.

4.1.1 Means of recording the force, to an accuracy as specified by Class 2 of ISO 7500-1.

4.1.2 Jaws, minimum length 30 mm in the direction of the applied load, designed to apply constant clamping by mechanical or pneumatic means. The texture and design of the inside faces of the jaws shall be such that at the maximum load attained in the test, the test piece does not slip at either jaw.

4.2 Thickness gauge, as specified in ISO 2589.

4.3 Press knife, the inner wall of which is a rectangle $250 \text{ mm} \pm 5 \text{ mm} \times 10,0 \text{ mm} \pm 0,5 \text{ mm}$, conforming to the requirements of ISO 2419.

4.4 Ruler, reading to 0,5 mm.

4.5 Stopwatch, reading to 1 s.

5 Sampling and sample preparation

5.1 Sample in accordance with ISO 2418.

5.2 Cut six test pieces by applying the press knife (4.3) to the grain surface. Cut three test pieces with the longer edge parallel to the backbone and three with the longer edge perpendicular to the backbone.

NOTE In the case of small skins, the number of test pieces is to be reduced because of the size of the test piece.

If there is a requirement for more than two hides or skins to be tested in one batch, then only one test piece in each direction need be taken from each hide or skin, provided that the overall total is not less than three test pieces in each direction.

5.3 Condition the test pieces in accordance with ISO 2419.

5.4 Measure the thickness in accordance with ISO 2589.

6 Procedure

6.1 Mark a line $35 \text{ mm} \pm 5 \text{ mm}$ from each short edge of the test piece with the line parallel to the short edges.

6.2 Using the ruler measure the distance, L_0 , between the two lines to the nearest 1 mm.

6.3 Set the jaws of the tensile testing machine (4.1) 200 mm apart. Clamp the test piece in the jaws such that the short edges of the test piece are parallel to the edges of the jaws, and about 25 mm of the test piece is clamped in each jaw. When the test piece is clamped its grain surface shall lie in one plane.

6.4 Run the tensile test machine until a load of $20,0 \text{ N} \pm 0,5 \text{ N}$ is reached. Immediately this load is reached stop the crosshead and keep the crosshead stopped in that position for $10 \text{ s} \pm 1 \text{ s}$.

NOTE Stopping the crosshead keeps the sample under load although relaxation of the test piece means that the load will fall slightly.

6.5 Return the crosshead to its start position as rapidly as possible.

6.6 Repeat 6.4 to 6.5 so that the test piece is subjected to a total of 5 extension cycles.

NOTE The cycling of the tensile test machine is carried out manually using the stopwatch for timing or programming the load and timing into the tensile test machine.

6.7 Remove the test piece from the tensile test machine immediately after the final load cycle (6.4). Start the stopwatch and lay the test piece on a flat surface with the lines applied as described in 6.1 uppermost. $60 \text{ s} \pm 5 \text{ s}$ after removing the test piece from the tensile tester, measure the distance, L_1 , between the lines to the nearest 1 mm.

6.8 Repeat 6.1 to 6.7 for other test pieces.

6.9 If there is slippage of the test piece at either jaw, reject the result and repeat the determination with a new test piece.