

INTERNATIONAL STANDARD

**ISO
178**

Fourth edition
2001-12-15

AMENDMENT 1
2004-02-15

Plastics — Determination of flexural properties

AMENDMENT 1: Precision statement

Plastiques — Détermination des propriétés en flexion

AMENDEMENT 1: Déclaration de fidélité

STANDARDSISO.COM : Click to view the full PDF of ISO 178:2001/Amd 1:2004



Reference number
ISO 178:2001/Amd.1:2004(E)

© ISO 2004

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 178:2001/Amd 1:2004

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 178:2001 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical properties*.

Plastics — Determination of flexural properties

AMENDMENT 1: Precision statement

Page 2, Clause 2

Correct the year of publication of ISO 3167 from 2001 to 2002.

Page 13

Replace the text of Clause 10 by the following sentence:

For precision data, see Annex B.

After Annex A, add the following new Annex B:

Annex B (informative)

Precision statement

B.1 Tables B.1 and B.2 are based on a round-robin test performed in accordance with ASTM E 691, *Standard Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method*. All materials were sampled and distributed by one source. Each “test result” was the average of five individual determinations. Each laboratory obtained and reported two test results for each material.

B.2 Table B.1 is based on a round robin involving nine laboratories and four materials and Table B.2 is based on a round-robin involving eleven laboratories and four materials.

NOTE The following explanations of r and R (see Clause B.3) are only intended to present a meaningful way of considering the *approximate* precision of this test method. The data in Tables B.1 and B.2 should not be rigorously applied to acceptance or rejection of material, as those data are specific to the round robin and may not be representative of other lots, conditions, materials or laboratories. Users of this test method should apply the principles of ASTM E 691 to generate data specific to their laboratory and materials, or between specific laboratories. The principles of Clause B.3 would then be valid for such data.

B.3 Concept of r and R in Tables B.1 and B.2: If s_r and s_R have been calculated from a large enough body of data, and for test results that were averages from testing five specimens for each test result, then:

- a) **Repeatability:** Two test results obtained within one laboratory shall be judged not equivalent if they differ by more than the r -value for that material, r being the interval representing the critical difference between two test results for the same material, obtained by the same operator using the same equipment in the same laboratory.
- b) **Reproducibility:** Two test results obtained by different laboratories shall be judged not equivalent if they differ by more than the R -value for that material, R being the interval representing the critical difference between two test results for the same material, obtained by different operators using different equipment in different laboratories.
- c) The judgments in a) and b) will have an approximately 95 % (0,95) probability of being correct.

Table B.1 — Precision data for flexural stress at a conventional deflection of 3,5 %^a

Values in megapascals

Material	Average	s_r	s_R	r	R
Polycarbonate	70,5	0,752	1,99	2,11	5,58
ABS	72,1	0,382	2,67	1,07	7,49
HDPE	20,4	0,129	0,505	0,36	1,42
GF polysulfone	156 ^a	1,65	3,13	4,62	8,75

NOTE For the meanings of the algebraic symbols used, see Table B.2.

^a For GF polysulfone, the flexural strength was measured.