

# INTERNATIONAL STANDARD

**ISO**  
**18064**

First edition  
2003-09-01

---

---

## **Thermoplastic elastomers — Nomenclature and abbreviated terms**

*Élastomères thermoplastiques — Nomenclature et termes abrégés*

STANDARDSISO.COM : Click to view the full PDF of ISO 18064:2003



Reference number  
ISO 18064:2003(E)

© ISO 2003

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 18064:2003

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

|                                                             |    |
|-------------------------------------------------------------|----|
| Foreword .....                                              | iv |
| Introduction .....                                          | v  |
| 1 Scope .....                                               | 1  |
| 2 Normative references .....                                | 1  |
| 3 Generic terms and definitions .....                       | 1  |
| 3.1 TPE .....                                               | 1  |
| 3.2 TP .....                                                | 1  |
| 4 Nomenclature system .....                                 | 2  |
| 5 Categories of thermoplastic elastomer .....               | 2  |
| 5.1 TPA .....                                               | 2  |
| 5.2 TPC .....                                               | 2  |
| 5.3 TPO .....                                               | 2  |
| 5.4 TPS .....                                               | 2  |
| 5.5 TPU .....                                               | 2  |
| 5.6 TPV .....                                               | 2  |
| 5.7 TPZ .....                                               | 2  |
| 6 Materials in each TPE category .....                      | 3  |
| 6.1 Polyamide TPEs (TPAs) .....                             | 3  |
| 6.2 Copolyester TPEs (TPCs) .....                           | 3  |
| 6.3 Olefinic TPEs (TPOs) .....                              | 3  |
| 6.4 Styrenic TPEs (TPSs) .....                              | 3  |
| 6.5 Urethane TPEs (TPUs) .....                              | 4  |
| 6.6 Dynamically vulcanized TPEs (TPVs) .....                | 4  |
| 6.7 Miscellaneous material (TPZ) .....                      | 4  |
| Annex A (informative) Formerly used abbreviated terms ..... | 5  |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18064 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*.

STANDARDSISO.COM : Click to view the full PDF of ISO 18064:2003

## Introduction

Thermoplastic elastomers combine many of the attributes and features of both vulcanized thermoset rubber and thermoplastic materials. It is, therefore, important that any system of classification and nomenclature for this rapidly expanding polymer sector should be acceptable to both the rubber and plastics industries. Neither of the existing standards for the nomenclature and abbreviated terms for rubber (ISO 1629) and for plastics (ISO 1043-1) is suitable for this purpose. The system in this International Standard has been devised to avoid any conflict of interests or ambiguity, permit the use of existing terms in the construction of abbreviations for thermoplastic elastomers, and allow for future developments or expansion.

This International Standard uses established abbreviated terms. Its aim is both to prevent the occurrence of more than one abbreviated term for a given thermoplastic elastomer term, and to prevent the interpretation of more than one meaning for a given abbreviated term. For this reason, this International Standard makes appropriate use of the terms and symbols listed in ISO 1043-1 and ISO 1629.



# Thermoplastic elastomers — Nomenclature and abbreviated terms

## 1 Scope

This International Standard establishes a nomenclature system for thermoplastic elastomers based on the chemical composition of the polymer or polymers involved. It defines symbols and abbreviated terms used to identify thermoplastic elastomers in industry, commerce and government. It is not intended to conflict with, but to supplement, existing trade names and trademarks.

NOTE 1 The name of the thermoplastic elastomer should be used in technical papers and presentations followed by the abbreviated term used to designate the elastomer in this International Standard.

NOTE 2 Annex A gives thermoplastic-elastomer abbreviated terms that have been used in the past in materials standards, technical bulletins, textbooks, patents and trade literature.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 1629, *Rubber and latices — Nomenclature*

## 3 Generic terms and definitions

### 3.1 TPE

Thermoplastic elastomer, consisting of a polymer or blend of polymers that has properties at its service temperature similar to those of vulcanized rubber but can be processed and reprocessed at elevated temperature like a thermoplastic.

NOTE Thermoplastic rubber is a commonly used term for thermoplastic elastomer.

### 3.2 TP

Prefix used to identify that the abbreviated term is for a thermoplastic elastomer.

## 4 Nomenclature system

**4.1** The prefix TP shall be followed by a letter representing each category of thermoplastic elastomer, as detailed in Clause 5.

**4.2** The abbreviated term for each category of thermoplastic elastomer shall be followed, after a hyphen, by a combination of symbols to describe a specific member of each category, as detailed in Clause 6.

## 5 Categories of thermoplastic elastomer

### 5.1 TPA

Polyamide thermoplastic elastomer, comprising a block copolymer of alternating hard and soft segments with amide chemical linkages in the hard blocks and ether and/or ester linkages in the soft blocks.

### 5.2 TPC

Copolyester thermoplastic elastomer, consisting of a block copolymer of alternating hard segments and soft segments, the chemical linkages in the main chain being ester and/or ether.

### 5.3 TPO

Olefinic thermoplastic elastomer, consisting of a blend of a polyolefin and a conventional rubber, the rubber phase in the blend having little or no crosslinking.

### 5.4 TPS

Styrenic thermoplastic elastomer, consisting of at least a triblock copolymer of styrene and a specific diene, where the two end blocks (hard blocks) are polystyrene and the internal block (soft block or blocks) is a polydiene or hydrogenated polydiene.

### 5.5 TPU

Urethane thermoplastic elastomer, consisting of a block copolymer of alternating hard and soft segments with urethane chemical linkages in the hard blocks and ether, ester or carbonate linkages or mixtures of them in the soft blocks.

### 5.6 TPV

Thermoplastic rubber vulcanizate consisting of a blend of a thermoplastic material and a conventional rubber in which the rubber has been crosslinked by the process of dynamic vulcanization during the blending and mixing step.

### 5.7 TPZ

Unclassified thermoplastic elastomer comprising any composition or structure other than those grouped in TPA, TPC, TPO, TPS, TPU and TPV.

## 6 Materials in each TPE category

### 6.1 Polyamide TPEs (TPAs)

The “TPA” group is sub-categorized into groups according to the linkages in the soft blocks. The following symbols are used:

**TPA-EE** Soft segment with both ether and ester linkages

**TPA-ES** Polyester soft segment

**TPA-ET** Polyether soft segment

### 6.2 Copolyester TPEs (TPCs)

The “TPC” group is sub-categorized into groups according to the linkages in the soft blocks. The following symbols are used:

**TPC-EE** Soft segment with ester and ether linkages

**TPC-ES** Polyester soft segment

**TPC-ET** Polyether soft segment

### 6.3 Olefinic TPEs (TPOs)

The “TPO” group varies according to the nature of the thermoplastic polyolefin being used and the rubber type.

A specific TPO is identified by a bracketed term comprising the standard abbreviation for the rubber type (see ISO 1629), a “+” sign and the standard abbreviation for the thermoplastic type (see ISO 1043-1). The thermoplastic and the rubber type shall be listed in decreasing order of abundance in the TPO.

A commercially available TPO type is described as follows:

**TPO-(EPDM+PP)** Blend of ethylene-propylene-diene terpolymer with polypropylene, with no or little crosslinking of the EPDM phase, the amount of EPDM present being greater than that of PP

### 6.4 Styrenic TPEs (TPSs)

The following symbols are used for the “TPS” group:

**TPS-SBS** Block copolymer of styrene and butadiene

**TPS-SEBS** Polystyrene-poly(ethylene-butylene)-polystyrene

**TPS-SEPS** Polystyrene-poly(ethylene-propylene)-polystyrene

**TPS-SIS** Block copolymer of styrene and isoprene

**NOTE** TPS-SEBS is a block copolymer of styrene and butadiene in which the soft block comprises a mixture of hydrogenated *cis*-1,4-polybutadiene and 1,2-polybutadiene units. TPS-SEPS is a block copolymer of styrene and isoprene in which the polyisoprene block has been hydrogenated.