
**Textiles — Quantitative chemical
analysis —**

Part 25:

**Mixtures of polyester and certain
other fibres (method using
trichloroacetic acid and chloroform)**

Textiles — Analyse chimique quantitative —

*Partie 25: Mélanges de polyester et de certaines autres fibres
(méthode à l'acide trichloracétique et au chloroforme)*



STANDARDSISO.COM : Click to view the full PDF of ISO 1833-25:2013



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	vi
1 Scope.....	1
2 Normative references.....	1
3 Principle.....	1
4 Reagents.....	1
5 Apparatus.....	1
6 Test procedure.....	2
7 Calculation and expression of results.....	2
Bibliography.....	3

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

The committee responsible for this document is ISO/TC 38, *Textiles*.

ISO 1833 consists of the following parts, under the general title *Textiles — Quantitative chemical analysis*:

- *Part 1: General principles of testing*
- *Part 2: Ternary fibre mixtures*
- *Part 3: Mixtures of acetate and certain other fibres (method using acetone)*
- *Part 4: Mixtures of certain protein and certain other fibres (method using hypochlorite)*
- *Part 5: Mixtures of viscose, cupro or modal and cotton fibres (method using sodium zincate)*
- *Part 6: Mixtures of viscose or certain types of cupro or modal or lyocell and cotton fibres (method using formic acid and zinc chloride)*
- *Part 7: Mixtures of polyamide and certain other fibres (method using formic acid)*
- *Part 8: Mixtures of acetate and triacetate fibres (method using acetone)*
- *Part 9: Mixtures of acetate and triacetate fibres (method using benzyl alcohol)*
- *Part 10: Mixtures of triacetate or polylactide and certain other fibres (method using dichloromethane)*
- *Part 11: Mixtures of cellulose and polyester fibres (method using sulfuric acid)*
- *Part 12: Mixtures of acrylic, certain modacrylics, certain chlorofibres, certain elastanes and certain other fibres (method using dimethylformamide)*
- *Part 13: Mixtures of certain chlorofibres and certain other fibres (method using carbon disulfide/acetone)*
- *Part 14: Mixtures of acetate and certain chlorofibres (method using acetic acid)*
- *Part 15: Mixtures of jute and certain animal fibres (method by determining nitrogen content)*
- *Part 16: Mixtures of polypropylene fibres and certain other fibres (method using xylene)*
- *Part 17: Mixtures of chlorofibres (homopolymers of vinyl chloride) and certain other fibres (method using sulfuric acid)*

- *Part 18: Mixtures of silk and wool or hair (method using sulfuric acid)*
- *Part 19: Mixtures of cellulose fibres and asbestos (method by heating)*
- *Part 20: Mixtures of elastane and certain other fibres (method using dimethylacetamide)*
- *Part 21: Mixtures of chlorofibres, certain modacrylics, certain elastanes, acetates, triacetates and certain other fibres (method using cyclohexanone)*
- *Part 22: Mixtures of viscose or certain types of cupro or modal or lyocell and flax fibres (method using formic acid and zinc chloride)*
- *Part 24: Mixtures of polyester and certain other fibres (method using phenol and tetrachloroethane)*
- *Part 25: Mixtures of polyester and certain other fibres (method using trichloroacetic acid and chloroform)*
- *Part 26: Mixtures of melamine and cotton or aramid fibres (method using hot formic acid)*

The following part is cancelled:

- *Part 23: Mixtures of polyethylene and polypropylene (method using cyclohexanone)*

Introduction

Chloroform is said to be harmful for operators. Safety shall be secured by strict operation according to safety regulations or precautions. However, alternative methods intended for the dissolution of polyester are included in the Bibliography.

STANDARDSISO.COM : Click to view the full PDF of ISO 1833-25:2013

Textiles — Quantitative chemical analysis —

Part 25:

Mixtures of polyester and certain other fibres (method using trichloroacetic acid and chloroform)

WARNING — This part of ISO 1833 calls for the use of substances/procedures that may be injurious to the health/environment if appropriate conditions are not observed. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety/environment at any stage.

1 Scope

This part of ISO 1833 specifies a method using trichloroacetic acid and chloroform to determine the percentage of polyester fibres after removal of non-fibrous matter, in textiles made of binary mixtures of polyester fibres with other fibres, except one type of aramid (polyamide imide), polyamide, chlorofibre and modacrylic.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1833-1, *Textiles — Quantitative chemical analysis — Part 1: General principles of testing*

3 Principle

The polyester fibre is dissolved out from a known dry mass of the mixture, with a reagent composed of trichloroacetic acid and chloroform. The residue is collected, washed, dried and weighed; its mass, corrected if necessary, is expressed as a percentage of the dry mass of the mixture. The percentage of polyester is found by difference.

4 Reagents

Use the reagents described in ISO 1833-1, together with those specified in [4.1](#), [4.2](#) and [4.3](#).

4.1 Solution of crystallized trichloroacetic acid/chloroform reagent, prepared at a mass ratio 1:1.

SAFETY PRECAUTIONS — The harmful effects of this reagent shall be borne in mind, and full precautions shall be taken during use.

4.2 Solution of 15 g of trichloroacetic acid filled up to 100 g with chloroform.

4.3 Chloroform.

5 Apparatus

Use the apparatus described in ISO 1833-1, together with that described in [5.1](#).

5.1 Conical flask, of minimum capacity of 200 ml, glass stoppered.

6 Test procedure

Follow the general procedure described in ISO 1833-1, and then proceed as follows.

- 6.1 Place the specimen in the conical flask.
- 6.2 Add 50 ml of trichloroacetic acid/chloroform reagent (4.1) per gram of specimen.
- 6.3 Stopper the conical flask and shake it vigorously.
- 6.4 Allow the flask and contents to remain for 15 min, shaking it during this time at intervals.
- 6.5 Decant the liquid through the weighed filter crucible with suction.
- 6.6 Pour 100 ml of trichloroacetic acid/chloroform reagent (4.1) into the conical flask, decant the liquid through the filter crucible, and then transfer any residual fibres to the crucible by washing out the conical flask with the trichloroacetic acid/chloroform solution (4.2) followed by chloroform (4.3).
- 6.7 Drain the crucible with suction. Do not apply suction until the washing liquor has drained under gravity.
- 6.8 Finally, drain the crucible with suction, dry the crucible and residue, cool and weigh them.
- 6.9 Check the residue under a microscope to see if the treatment completely eliminated the soluble fibre.

7 Calculation and expression of results

Calculate the results as described in the general instructions of ISO 1833-1.

The value of the correction factor of variation in mass of insoluble component in the reagent (d) is 1,02 and 1,00 for cotton and aramid, respectively.