

---

# INTERNATIONAL STANDARD



# 1969

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

---

## Three-strand polyethylene monofilament ropes

*Cordages en monofilaments de polyéthylène à trois torons*

First edition — 1976-04-01

STANDARDSISO.COM : Click to view the full PDF of ISO 1969:1976

---

UDC 677.718.06

Ref. No. ISO 1969-1976 (E)

**Descriptors** : textiles, rope, polyethylene, specifications, linear density, diameters, breaking load.

## FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard 1969 was drawn up by Technical Committee ISO/TC 38, *Textiles*. It was submitted directly to the ISO Council, in accordance with clause 6.12.1 of the Directives for the technical work of ISO.

This International Standard cancels and replaces ISO Recommendation R 1969-1971, which had been approved by the Member Bodies of the following countries :

|                     |                |                       |
|---------------------|----------------|-----------------------|
| Australia           | Greece         | South Africa, Rep. of |
| Belgium             | India          | Spain                 |
| Brazil              | Iran           | Sweden                |
| Chile               | Ireland        | Switzerland           |
| Czechoslovakia      | Israel         | Thailand              |
| Denmark             | Japan          | Turkey                |
| Egypt, Arab Rep. of | Korea, Rep. of | United Kingdom        |
| Finland             | Netherlands    | U.S.S.R.              |
| France              | Norway         |                       |

No Member Body had disapproved the Recommendation.

# Three-strand polyethylene monofilament ropes

## 1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies the essential characteristics of three-strand ropes consisting of continuous monofilaments belonging to the polyethylene group of a density of approximately 0,96.

It applies to ropes of this type of which the net mass per metre is 8,1 to 295 g and of which the nominal diameter is from 4 to 24 mm inclusive.

## 2 REFERENCES

ISO 2, *Textiles — Designation of the direction of twist in yarns and related products*.

ISO 2307, *Ropes — Determination of certain physical and mechanical properties*.

## 3 MANUFACTURE

The ropes shall be formed of strands manufactured from new material. The ropes and strands shall be continuous, without splices.

When agreed between purchaser and supplier, ropes with a net mass per metre greater than 161 g (larger than 18 mm diameter) may have a core in the strands, consisting of continuous man-made monofilaments without twist.

Polyethylene ropes, unless otherwise specified, shall be made of strands twisted together with a "Z" lay, these strands themselves being made with an "S" lay (see ISO 2).

The number of yarns, or yarns and untwisted monofilaments, shall be the same for all the strands in the rope.

## 4 REQUIRED CHARACTERISTICS AND TOLERANCES

The main characteristics of three-strand polyethylene monofilament ropes shall be as given in the table.

The pitch of these ropes shall be as given in the table except when otherwise agreed between purchaser and supplier.

## 5 METHODS OF TEST

The characteristics given in clause 4 shall be measured under the conditions indicated in ISO 2307.

## 6 PACKING

The masses invoiced should be net masses which include lashings, but not packing materials. Coil lashings should be of similar material to the rope<sup>1)</sup>.

1) The use of coil lashing of synthetic material meets this requirement.