
**Superabsorbent polymer — Sodium
polyacrylate resin for absorbing
blood —**

**Part 2:
Specifications**

*Résines super-absorbantes — Polyacrylate de sodium pour
l'absorption du sang —*

Partie 2: Spécifications



STANDARDSISO.COM : Click to view the full PDF of ISO 19699-2:2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms, definitions and abbreviated terms	1
3.1 Terms and definitions	1
3.2 Abbreviated terms	2
4 Requirements	2
5 Marking (optional)	2
6 Packaging	2
6.1 Appearance	2
6.2 Performance characteristics	3

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

A list of all parts in the ISO 19699 series can be found on the ISO website.

Introduction

The property requirements described in this document have been practically used by relevant production enterprises for several years. They have proven to be reliable with respect to common criteria of quality of superabsorbent polymer of sodium polyacrylate resin used in hygiene products (such as sanitary towels and pads) and medical products (such as tourniquets and surgery coats).

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent concerning the property requirements of residual monomers, volatile content, pH, particle size distribution, density, blood absorption capacity and blood absorption rate given in [Clause 4](#).

ISO takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has assured ISO that he/she is willing to negotiate licences under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information may be obtained from:

Jinan Haoyue Resin Co., Ltd

Bucun District, Zhangqiu City, Shandong Province

China

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. ISO shall not be held responsible for identifying any or all such patent rights.

STANDARDSISO.COM : Click to view the full PDF of ISO 19699-2:2017

Superabsorbent polymer — Sodium polyacrylate resin for absorbing blood —

Part 2: Specifications

1 Scope

This document specifies the requirements for properties, marking and packaging of superabsorbent polymer (SAP) made from sodium polyacrylate resin for absorbing blood.

This document applies to sodium polyacrylate resin, as raw material, and applies to SAP for the final products used for absorbing blood.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 17190-1, *Urine-absorbing aids for incontinence — Test methods for characterizing polymer-based absorbent materials — Part 1: Determination of pH*

ISO 17190-2, *Urine-absorbing aids for incontinence — Test methods for characterizing polymer-based absorbent materials — Part 2: Determination of amount of residual monomers*

ISO 17190-3, *Urine-absorbing aids for incontinence — Test methods for characterizing polymer-based absorbent materials — Part 3: Determination of particle size distribution by sieve fractionation*

ISO 17190-4, *Urine-absorbing aids for incontinence — Test methods for characterizing polymer-based absorbent materials — Part 4: Determination of moisture content by mass loss upon heating*

ISO 17190-9, *Urine-absorbing aids for incontinence — Test methods for characterizing polymer-based absorbent materials — Part 9: Gravimetric determination of density*

ISO 19699-1:2017, *Plastics — Superabsorbent polymer — Sodium polyacrylate resin for absorbing blood — Part 1: Test methods*

3 Terms, definitions and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 19699-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.2 Abbreviated terms

SAP-B SAP for absorption of blood

4 Requirements

The properties of SAP resin for absorption of blood shall comply with the requirements given in [Table 1](#).

In terms of physical appearance, sodium polyacrylate resin is white solid.

Table 1 — Requirements for properties

Property	Unit	Requirement		Test method
		Class I	Class II	
Amount of residual monomers	mg/kg	≤1 500	≤1 500	ISO 17190-2
Amount of volatile content	%	≤10,0	≤10,0	ISO 17190-4
pH	—	≥5,0 but ≤8,0	≥5,0 but ≤8,0	ISO 17190-1
Particle size distribution	%	≤5 (for particle size <150 µm) ≤1 (for particle size <106 µm)	≤5 (for particle size <106 µm) ≤1 (for particle size <45 µm)	ISO 17190-3
Bulk density	g/cm ³	≥0,65 but ≤0,80	≥0,30 but ≤0,90	ISO 17190-9
Simulated blood absorption capacity	g/g	≥15,0	≥15,0	ISO 19699-1:2017, 4.8
Simulated blood absorption rate	s	≤50	>50	ISO 19699-1:2017, 4.9
Whiteness	%	≥70	≥70	ISO 19699-1:2017, 4.7

For the purposes of safety concerns, the manufacturer's safety data sheet (SDS) shall be referred to.

5 Marking (optional)

The marking for the identification of sodium polyacrylate polymer for absorbing blood shall include the following information:

- a reference to this document, i.e. ISO 19699-2;
- the class of SAP-B: SAP-B, Class I or SAP-B, Class II;
- the manufacturer's name, trade mark or identification mark;
- the net weight of the resin in kilograms;
- the date of manufacture, the date of expiration, the lot number;
- the mark of waterproof and moisture-proof.

6 Packaging

6.1 Appearance

The packaging bag shall be smooth and without tear fracture.

Markings shall be clearly visible and readable.