



**International
Standard**

ISO 20263

**Microbeam analysis — Analytical
electron microscopy — Method
for the determination of interface
position in the cross-sectional
image of the layered materials**

*Analyse par microfaisceaux — Microscopie électronique
analytique — Méthode de détermination de la position
d'interface dans l'image de coupe transversale des matériaux en
couches*

**Second edition
2024-11**

STANDARDSISO.COM : Click to view the full PDF of ISO 20263:2024



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms, definitions and abbreviated terms	1
3.1 Terms and definitions	1
3.2 Abbreviated terms	4
4 Specimen preparation for cross-sectional imaging	4
4.1 General	4
4.2 Requirements for the cross-sectional specimen	5
5 Determination of an interface position	6
5.1 General	6
5.2 Preliminary considerations	6
5.2.1 Ideal model of an interface	6
5.2.2 More realistic model of an interface	6
5.2.3 Dealing with intensity fluctuations in the image	7
6 Detailed procedure for determining the position of the interface	8
6.1 General	8
6.2 Preparing cross-sectional TEM/STEM image	10
6.2.1 Preparing digitized Image	10
6.2.2 Displaying the digitized image	11
6.3 Setting the ROI	11
6.3.1 General	11
6.3.2 Classification of image	11
6.3.3 Procedure of setting the ROI	12
6.4 Acquisition of the averaged intensity profile	16
6.5 Moving-averaged processing	19
6.6 Differential processing	20
6.7 Determination of interface position	21
7 Uncertainty	21
7.1 Uncertainty accumulating from each step of the procedure	21
7.2 Uncertainty of measurement result on image analysis	22
Annex A (informative) Examples of processing the real TEM/STEM images for three image types	24
Annex B (informative) Two main applications of the method	38
Annex C (informative) Calibration of scale unit: Pixel size calibration	45
Bibliography	47

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 202, *Microbeam analysis*, Subcommittee SC 3, *Analytical electron microscopy*.

This second edition cancels and replaces the first edition (ISO 20263:2017), which has been technically revised.

The main changes are as follows:

- introduction has been revised;
- terms and sources in Clause 3 have been revised;
- [subclauses 5.2.2](#), [5.2.3](#), [6.1](#), [6.2.1](#), [6.7](#), [7.1](#), [7.2](#), [A.4.1](#), [B.2.3](#) and [B.2.4](#) have been revised;
- figures have been revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Multi-layered materials are widely used in the production of semiconductor devices, various kinds of sensors, coating films for optical element, new functional materials, etc. One of the factors used to determine the characteristics of multi-layered materials is the layer thickness, for evaluation of products and verification of the production process. In practice, measuring the total thickness and/or the thickness of each layer and checking the uniformity of thickness and/or flatness of the interface are often done using recorded images of the materials. Evaluations can be made from the cross-sectional TEM/STEM images by accurately determining the averaged interface position between two different layered materials.

In relation to the determination of the interface position in the HR atomic imaging, analysis by the multi-slice simulation (MSS) method can be applied for the target measurement, if the atomic structural models can be constructed. However, in real materials, there are a lot of cases when they cannot, such as:

- the interface between amorphous layers, or layers of amorphous substance and crystal;
- the interface recorded in low-resolution image in which the atomic columns cannot be identified:
 - for very thick single-layered material;
 - for thick multi-layered material.

This document gives the method to determine the averaged interface position using a differential processing of the accumulated intensity profile obtained from the ROI set in the cross-sectional TEM/STEM image of the multi-layered material. The thickness of the layer that can be applied ranges from a few nanometers to a few micrometers. Thus, this document is not intended for the determination of the simulated position of the layer interface analysed by the MSS method.

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 20263:2024

Microbeam analysis — Analytical electron microscopy — Method for the determination of interface position in the cross-sectional image of the layered materials

1 Scope

This document specifies a procedure for the determination of the averaged interface position between two different layered materials recorded in the cross-sectional image of the multi-layered material. This document does not apply for determining the simulated interface of the multi-layered materials expected through the multi-slice simulation (MSS) method.

This document is applicable to the cross-sectional images of multi-layered materials recorded using a transmission electron microscope (TEM) or a scanning transmission electron microscope (STEM) and cross-sectional elemental mapping images using an energy dispersive X-ray spectrometer (EDS) or an electron energy loss spectrometer (EELS). This document is also applicable to digitized images recorded on an image sensor built into a digital camera, a digital memory set in the PC or an imaging plate, where the digitalized image is obtained by converting an analogue image recorded on photographic film using an image scanner.

2 Normative references

There are no normative references in this document.

3 Terms, definitions and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1.1

cross-sectional image

TEM/STEM image of the multi-layered materials along a plane perpendicular to the stacking direction

3.1.2

differential processing

calculation of the difference between the values of adjacent pixel data in the intensity profile

3.1.3

digital camera

device that detects the image using a chip-arrayed *image sensor* (3.1.12), such as a charge-coupled device (CCD) or complementary metal-oxide semiconductor (CMOS), which converts a visual image to an electric signal

[SOURCE: ISO 29301:2023, 3.7]

3.1.4

dot pitch

distance between adjacent pixels in pixel-based devices

3.1.5

elemental mapping image

image produced by the selected signal which is attributed to a particular element, from the EDS/EELS spectrum

3.1.6

FIB thinning

site-specific thinning technique by using focused ion beam to thin a particular region of the specimen

3.1.7

filtering mask

mask to define the cut-off frequency in the reciprocal space

3.1.8

fast Fourier transformation

FFT

efficient algorithm to compute the discrete Fourier transform

[SOURCE: ISO 15932:2013, 5.4.1.1]

3.1.9

inverse fast Fourier transformation

IFFT

efficient algorithm to compute the inverse of the discrete Fourier transform

[SOURCE: ISO 15932:2013, 5.4.1.2]

3.1.10

image file format

format for saving an image as a computer file according to a predetermined rule

3.1.11

image scanner

device that converts an analogue image into a digitized image with the desired resolution

EXAMPLE There are mainly two different types of scanners: flatbed type and drum type.

[SOURCE: ISO 29301:2023, 3.17, modified — example has been added.]

3.1.12

image sensor

device, such as a charge-coupled device (CCD) array or complementary metal-oxide semiconductor (CMOS) sensor, which converts visual image information to an electric signal, built-in *digital camera* ([3.1.3](#)) or other imaging devices

3.1.13

intensity profile

signal intensity distribution along a line specified in the image

3.1.14

interface

boundary surface at the junction of two different layers of materials recorded in the *cross-sectional image* ([3.1.1](#)) of the multi-layered materials

3.1.15

ion-milling

thinning technique of sputtering the specimen with an inert gas

[SOURCE: ISO 15932:2013, 4.1]

3.1.16

imaging plate
IP

electron image detector consisting of a film with a thin active layer embedded with specifically designed phosphors

[SOURCE: ISO 29301:2023, 3.16]

3.1.17

low pass filter

filter to pass signals of frequencies lower than the cut-off frequency

3.1.18

moving average

calculation for averaging the selected dataset which is picked out from equal number of dataset on either side of a central data

3.1.19

multi-slice simulation

MSS

computer simulation method of high-resolution TEM images, which treats electrons as incoming waves and treats the interactions with matter as occurring on multiple successive single slices of the specimen

[SOURCE: ISO 15932:2013, 6.4.1, modified — “algorithm for the simulation” has been replaced by “computer simulation method”.]

3.1.20

multi-layered material

laminated material which is fabricated by alternating layers of at least two kinds of materials on the substrate

3.1.21

photographic film

sheet or a roll of thin plastic coated by photographic emulsion for recording an image

[SOURCE: ISO 29301:2023, 3.23]

3.1.22

pixel

smallest unit element that makes up the digital image

3.1.23

region of interest

ROI

sub-dataset picked out from the entire dataset for a specific purpose

3.1.24

ultra-microtome

thin sectioning instrument to prepare the specimen thin enough for TEM observation by using glass or diamond knives

3.1.25

zone axis

crystallographic direction, designated $[u \ v \ w]$, defined by the intersection of a number of crystal planes $(h_1 k_1 l_1 \dots h_p k_p l_p)$ such that all of the planes satisfy the so-called Weiss zone law; $hu + kv + lw = 0$

[SOURCE: ISO 29301:2023, 3.36]


3.2 Abbreviated terms

AEM	Analytical electron microscope/microscopy
CCD	Charge coupled device
CMOS	Complementary metal oxide semiconductor
CRT	Cathode ray tube
EDS/EDX	Energy dispersive X-ray spectrometer/spectroscopy Although "EDX" and "EDS" are interchangeable, this document uses "EDS".
EELS	Electron energy loss spectrometer/spectroscopy
FFT	Fast Fourier transformation
FIB	Focused ion beam
HREM	High-resolution transmission electron microscope/microscopy
IFFT	Inverse fast Fourier transformation
MSS	Multi-slice simulation
ROI	Region of interest
STEM	Scanning transmission electron microscope/microscopy
TEM	Transmission electron microscope/microscopy

4 Specimen preparation for cross-sectional imaging

4.1 General

To determine the interface position of the multi-layered materials stacked on a substrate, the specimen observed by TEM/STEM shall be cut into a cross-sectional thin slice perpendicular to the stacking direction of the multi-layered thin film, using the techniques of ultra-microtome, ion-milling, FIB thinning, chemical etching and so on. In order to keep the thickness information of the layered materials with an accuracy of 1 %, the cut out angle α [shown in [Figure 1, a](#)] shall be $90^\circ \pm 6^\circ$.

**Key**

- 1 substrate
- 2 multi-layered materials
- 3 direction of electron beam
- 4 thin slice of the specimen
- 5 cross-sectional TEM/STEM image
- 6 arrows indicate interface positions

Figure 1 — Specimen preparation for cross-sectional imaging

4.2 Requirements for the cross-sectional specimen

Ensure that the specimen:

- provides a good and sharp contrast and clear and straight interface for the multi-layered materials in the TEM/STEM/elemental mapping image,
- can be cleaned to remove contamination without causing mechanical/electrical damage or distortion,
- has a smooth surface on both sides and identical thickness, at least within the area used for the determination process of interface position,
- is aligned to a low-index zone axis along the electron optical axis, if the specimen region is a single crystal.

5 Determination of an interface position


5.1 General

It is important to determine the position of an interface in a layered material from its cross-sectional TEM/STEM/elemental mapping image, objectively and uniquely. In [Clause 6](#), the main scheme for the determination of the interface position, as prescribed by this document, is explained.


5.2 Preliminary considerations

5.2.1 Ideal model of an interface

Ideally, the interface between two kinds of materials, M_1 and M_2 , show straight edge [see [Figure 2 a\)](#)]. In this case, it is easy to find the interface positions (S_1 and S_2) uniquely from the intensity profile [see [Figure 2 b\)](#)] along a line (L) perpendicular to the interface.



a) Ideal interface (S_1 and S_2) model between two kinds of layers, M_1 and M_2




b) Intensity profile along an arrow line, L , in a), perpendicular to the interfaces (S_1 and S_2)

Figure 2 — Ideal interface model


5.2.2 More realistic model of an interface

In general, the interface will not be in a straight line. It typically appears as a region with a gradated intensity distribution between layers M_1 and M_2 [see [Figure 3 a\)](#)]. In this case, it is not easy to find the accurate interface position from its intensity profile which is normally s-shaped [see [Figure 3 b\)](#)]. This document defines the interface position at the steepest tilt angle in the slope. Differential processing of the intensity profile is the most suitable method to determine the interface position as defined above. [Figure 3 c\)](#) shows the differential curve of the intensity profile on in [Figure 3 b\)](#). Pixel positions on the x-axis corresponding to


the minimal value and maximal value in the curve show the interface positions (S_1 and S_2) on both sides of the layer M_2 .



a) Realistic interface (S_1 and S_2) model between two kinds of layers, M_1 and M_2



b) Intensity profile along an arrow line, L , in a), perpendicular to the interfaces (S_1 and S_2)



c) Differential curve of intensity profile

NOTE Positions of minimal and maximal value correspond to the interfaces (S_1 and S_2) defined in this document.

Figure 3 — Realistic interface model

5.2.3 Dealing with intensity fluctuations in the image

Unlike models described in 5.2.1 and 5.2.2, the actual cross-sectional TEM/STEM/elemental mapping image has a domain-like intensity fluctuation, background noise and sometimes (in the high-resolution images)

periodic modulation of the intensity due to atomic column structures. Because of this non-uniformity in the intensity in the image, follow the steps a) to g) sequentially for obtaining the desired smooth intensity profile with a plateau and well-defined slope.

NOTE 1 Details of the procedure are described in [Clause 6](#).

- a) Prepare the cross-sectional TEM/STEM/elemental mapping digital image.
- b) Set the direction of the interface parallel to the y-axis of the monitor screen.
- c) Set the ROI area in the image.
- d) Obtain the averaged intensity profile by adding up and averaging the line profiles in the direction perpendicular to the interface (parallel to the x-axis of the monitor screen) over the entire interface direction (parallel to the y-axis of the monitor screen) in the ROI.
- e) Apply “moving-average” processing to the averaged intensity profile produced by the previous step, d). This will remove small noise from the boundary region contributing to the slope of the interface.
- f) Apply differential processing to the moving-averaged intensity profile obtained in e).
- g) Determine the interface position as the pixel coordinate on the x-axis which either corresponds to the maximal or minimal value in the differential curve.

6 Detailed procedure for determining the position of the interface

6.1 General

As described in the previous clause, the interface position can be determined through the differential processing of the intensity profile in the ROI.

In the differential processing, a noise component existing in the intensity profile becomes an obstacle to find the correct interface position. Therefore, it is necessary to remove the noise components in advance through the average processing and the moving-averaged processing.

Also, in an atomic resolution image with an atomic column arrangement along the interface, the oscillated component depends on the atomic column which cannot be eliminated even in the averaged intensity profile. This is an obstacle to the extraction of the correct interface position by differential processing. Therefore, for such an image, pre-processing for obscuring the atomic column structure is essential through the processing of FFT/low pass filtering/IFFT.

[Figure 4](#) shows a flow chart of the interface position determination procedure described in [5.2.3](#). In [Clause 6](#) details of each procedure will be described.




Figure 4 — Flow chart of interface position determination procedure

6.2 Preparing cross-sectional TEM/STEM image

6.2.1 Preparing digitized Image

It is necessary to prepare a digitized cross-sectional image to determine the interface position. The bit depth of digitization of the image shall be 8 bits or more. There are four ways of digitizing the image corresponding to each image detection system shown in [Table 1](#).

Table 1 — Comparison table for image detection

Image detection system	Apparatus for digitization	Pixel size
Photographic film	Flatbed image scanner	Determined by dot pitch applied to image scanner
Imaging plate	Dedicated scanner	Determined by LASER beam diameter for readout
Image sensor (Digital camera)	Built in the digital camera	Same size as that of the image sensor
Digital memory	Built in the PC connected to the scanning device	Determined by scanning condition of electron beam

- a) Photographic film: Analogue image recorded on the photographic negative film shall be converted to a digitized image using an image scanner with dot pitch less than 20 μm .

NOTE 1 Use a flatbed image scanner because it is easy to set the transparent scale in it for pixel size calibration (Refer to ISO 29301).

- b) Imaging plate (IP): The recorded image shall be read out with a dedicated image digitizer (IP reader) connected to a PC.

- c) Image sensor: The digitized image, captured by a digital camera, shall be saved on the memory in the PC system as an image file with a reversible format.

NOTE 2 Ensure that the procedure for normalization of gain is performed to have a uniform background of the image.

- d) Digital memory: STEM and elemental mapping image, captured by the digital memory built into a PC, shall be saved as an image file with a reversible format.

Before and during the execution of the digitization procedure, ensure the following.


- The correct sensitivity setting is used for the photographic film used, to generate the negative image with proper density and contrast.
- Keep the exposure time to minimize the drift and reduce blurring in the recorded image.
- Do not use “binning” in the readout process of the magnified digital image from the digital camera.
- When using an image montage function, ensure that the seams of the image do not overlap with any of the interface of the specimen.
- For saving the digitized images, an uncompressed image file format (ESP, PICT, TIFF or Windows bitmap), or reversible (lossless) compressed image file format (GIF or PING) shall be used.
- Ethical digital imaging requires that the original uncompressed image file be stored on archival media, e.g. CD-R, without any image manipulation or processing operation. All parameters of the production and acquisition of this file and any subsequent processing steps shall be documented and reported to ensure reproducibility.

Generally, acceptable imaging operations include gamma correction, histogram stretching and brightness and contrast adjustments need not be reported. All other operations (such as Unsharp-Masking, Gaussian Blur, etc.) shall be directly identified by the author as part of the experimental methodology. However, for

diffraction data or any other image data that is used for subsequent quantification, all imaging operations shall be reported.

6.2.2 Displaying the digitized image

The digitized image used for further processing shall be orientated so that the interface is, as far as possible, parallel to the y-axis of the monitor screen. If the interface is tilted with an angle, α , to the y-axis of the monitor screen, it is necessary to measure and to record the tilting angle, α (see [Figure 5](#)).



Key

- 1 interface
- 2 y-axis of monitor screen

Figure 5 — Example of a tilted target image

6.3 Setting the ROI


6.3.1 General

This depends on the type of the image classified in [6.3.2](#).

6.3.2 Classification of image

Firstly, it is necessary to obtain an intensity profile in a direction across the interface. Ensure that the intensity profile is as smooth as possible. To do this, set the ROI in the target image in advance. Then, integrate the line profile measured across the interface, pixel by pixel, to the appropriate range along the interface. In practice, the setting procedure depends on the image type classified by image resolution and the atomic column arrangement recorded in high resolution image, as follows.

- Type 1: Low resolution images in which atomic column arrangements cannot be recognized. [Figure 6 a\)](#) shows an example.
- Type 2: High resolution images in which atomic column arranged at an angle θ to the interface [see [Figure 6 b\)](#)].
- Type 3: High resolution images in which atomic column is parallel to the interface [see [Figure 6 c\)](#)].



Key

- 1 interface position
- 2 atomic column arrangement direction


Figure 6 — Examples of classified target image

6.3.3 Procedure of setting the ROI

6.3.3.1 ROI for type 1 image

The ROI shall cover the widest possible area in the image, including the interface.

[Figure 7](#) shows examples of ROI settings for the type 1 image model. In a very low magnification image, image distortion is sometimes observed at the edges. In such case, exclude the area containing distortions from the ROI setting. [Figure 7](#) a) and b) show examples of setting the ROI when the interface is displayed in parallel to the y-axis of the monitor screen. In these cases, each side of the ROI area is parallel to the x-axis or y-axis. [Figure 7](#) c) shows an example of setting the ROI when the interface is inclined to the y-axis of the monitor screen. In this case, the ROI shall be set; one side of the ROI is parallel to the direction of the interface.



Key

- 1 region of interest (ROI)
Y y-axis of monitor screen

Figure 7 — Examples of ROI setting for type 1 image model

6.3.3.2 ROI for type 2 image

A schematic model of the type 2 image is shown in [Figure 8](#). Repetition period, R , of the atomic column arrangement along the interface can be calculated by using [Formula \(1\)](#):


$$R = s / \sin \theta = (s_x \times \cos \theta) / \sin \theta \quad (1)$$

where

- s is the atomic column spacing in layer B;
 s_x is the projected length of the atomic column spacing, s , in layer B onto the x-axis of the monitor screen;
 θ (°) is the off-angle between the interface and the atomic column arrangement in layer B.

For the type 2 image, ROI length shall be at least $(5 \times R)$ where R is the periodic length along the y-axis. However, for an image with a wider field of view, it is better to set the ROI as wide as possible. If the interface

is inclined to the y-axis, set one side of the ROI parallel to the direction of the interface (the same setting as that for the type 1 image).



Key

[broken line]	interface position
[thick solid line]	atomic column arrangement direction
[thin solid line]	auxiliary line for repetition period, R
1	layer A
2	layer B
3	atomic column in layer A
4	atomic column in layer B

Figure 8 — Examples of atomic column arrangement in the type 2 image model

6.3.3.3 ROI for type 3 image

A schematic model of the type 3 image is shown in [Figure 9 a](#)), keys 1 and 2. In this case, it is impossible to eliminate the oscillation of the intensity in the integrated intensity profile because the atomic column is aligned in the direction perpendicular to the interface. Therefore, for such an oscillatory intensity profile, it is impossible to determine the interface position because one cannot apply the last step of this procedure. In such cases, therefore, a low-pass filter shall be applied as a pre-treatment for the ROI setting.

6.3.3.3.1 Low pass filter treatment

Apply the low pass filter treatment by following the procedure below.


- a) Select 2^n (pix) $\times$ 2^n (pix) area (with edges parallel to the x-axis and y-axis) in the target image for FFT processing [region F indicated in Figure 9 a), key 3].

In order to get a clear FFT pattern, it is desirable to set $n \geq 8$ to include the largest possible area.


- b) Apply FFT processing to the region F [key 5 in Figure 9 b) shows the result of FFT processing].
- c) Set low pass filtering mask [Figure 9 c), key 6] onto the pattern generated by FFT processing to the region F. The mask has a circular opening having diameter $d_m = (0,9 \sim 0,95) \cdot d_f$ (where, d_f is the distance between primary spots) centred on the central spot, to set the circumference as close as possible to the inside of the primary spots of the FFT pattern.

NOTE Image resolution after IFFT processing is determined by diameter, d_m , of the low-pass filtering mask. Application of smaller radius makes image resolution lower than that with bigger radius.


- d) Apply an IFFT processing to the FFT pattern with low pass filtering mask. [Figure 9 d), key 7 shows the result of IFFT processing.]




a) Type 3 image model



b) FFT pattern model



c) Low pass filtering mask superimposed with FFT pattern



d) IFFT image model

Key

- 1 layer A in the type 3 image model
- 2 layer B in the type 3 image model
- 3 selected square area F for FFT processing
- 4 interface position
- 5 FFT pattern from area 3
- 6 low-pass filtering mask superimposed with FFT pattern from area 3
- 7 IFFT image
- 8 artefact region
- 9 ROI frame

The side length (l) should be 2^n pixels.


Figure 9 — Examples of type 3 image model in which atomic columns are aligned in direction perpendicular to the interface

6.3.3.3.2 Setting the ROI


Set ROI [Figure 9 d), key 9] into the IFFT image [Figure 9 d), key 7], except the artefact region [Figure 9 d), key 8] observed at the edge of the IFFT image [Figure 9 d), key 7]. If the interface is inclined to the y-axis, set the ROI so that one side of it is parallel to the direction of the interface (the same setting as that for the type 1 image).

6.4 Acquisition of the averaged intensity profile


After setting the ROI into the target image, apply the same processing for all types of images. Herein, as an example, the process is applied to the type 1 (low resolution) image [Figure 10 a)].



a) Type 1 image model having an inclined interface



b) Intensity profile



c) Averaged intensity profile

Key

- X position (pix)
- Y intensity
- 1 type 1 image model
- 2 ROI frame
- 3 intensity profile I_i along line L_i in key 2
- 4 averaged intensity profile, I_a , calculated by averaging I_i from L_0 to L_n in key 2
- 5 interface
- 6 line for intensity profile measurement
- 7 y-axis of the monitor screen

The fine broken line should be perpendicular to the interface.

Figure 10 — Examples of type 1 image model having an inclined interface to the y-axis of the monitor screen

- a) Measure and record the angle α between the interface and the y-axis of the monitor screen, shown in [Figure 10 a\)](#).
- b) Draw the straight line [L_i in [Figure 10 a\)](#)] in the direction perpendicular to the interface, in the ROI; the intensity profile, I_i , along the line L_i contains many noise components in it [[Figure 10 b\)](#), key 3].

NOTE The level of the intensity profile is equivalent to the grey level of the image acquired. The grey level is dependent on the image detection system, in most cases, with 8-bit, 12-bit or 16-bit grey scale. It is possible to obtain the intensity profile by reading the grey level of each pixel of the measurement line by using the image processing software.

- c) Acquire the averaged intensity profile, I_a , [[Figure 10 c\)](#), key 4] using [Formula \(2\)](#) through integrating procedure of the intensity profile, from I_0 to I_n , which is measured parallel to the line L_i from L_0 to L_n in the ROI.

$$I_a \equiv \frac{\sum_{i=0}^n I_i}{n+1} \quad (2)$$

where

I_i is i^{th} intensity profile along the straight line, L_i , in the ROI;

$n + 1$ is total number of pixels contained from straight line L_0 to L_n ;

I_a is the intensity profile averaged the profile from I_0 to I_n corresponding to the line $L_0 \sim L_n$ in the whole region of the ROI.

6.5 Moving-averaged processing

After the application of the procedure in 6.4, residual noise still remains in the slope of the averaged intensity profile [Figure 11 a), key 1]. To reduce the residual noise further, apply the moving-averaged processing by Formula (3).

$$I_p \equiv \frac{\sum_{j=p-n}^{p+n} I_j}{2n+1} \quad (3)$$

where


I_p is the calculated moving-averaged intensity of p^{th} pixel in the horizontal axis of the averaged intensity profile;

I_j is the intensity around the p^{th} pixel in the horizontal axis of the averaged intensity profile, to be used to calculate the moving-averaged intensity;


n is a numerical value, a positive integer, to define the range of the I_j to be used in the calculation.

NOTE Generally, the range $2 \leq n \leq 7$ is suitable.

Key 2 in Figure 11 b) shows the moving-averaged intensity profile of the averaged profile shown in key 4 in Figure 10 c), with $n = 4$ in Formula (3).



a) Slope before moving-averaged processing



b) Slope after moving-averaged processing

Key

- X position (pix)
- Y intensity
- 1 slope having residual noise in the averaged intensity profile
- 2 smooth slope after moving-averaged processing applied $n = 4$ to [Formula \(3\)](#)

Figure 11 — Noise reduction effect by moving-averaged processing

6.6 Differential processing

Apply differential processing to the moving-averaged intensity profile [see key 1 in [Figure 12 a\)](#)], by using [Formula \(4\)](#) and [Formula \(5\)](#).

$$\Delta I_k \equiv I_{k+1} - I_k \quad (4)$$

here,

$$1 \leq k \leq n_p - 1 \quad (5)$$

where


ΔI_k is the rate of intensity change of k^{th} pixel position in the horizontal axis of the moving-averaged intensity profile;

I_k is the intensity of the k^{th} pixel position in the horizontal axis of the moving-averaged intensity profile;


I_{k+1} is the intensity of the $(k+1)^{\text{th}}$ pixel position in the horizontal axis of the moving-averaged intensity profile;

n_p is the total number of pixels contained in the horizontal axis of the moving-averaged intensity profile.

By differential processing, the maximum gradient positions of the intensity change at the interface appear as distinct peaks [see key 2 in [Fig. 12 b\)](#)].



a) Intensity profile after moving-averaged processing



b) Location of interface position

Key

X position (pix)

Y1 intensity

Y2 rate of change of intensity (ΔI)1 moving-averaged result applied $n = 4$ to [Formula \(3\)](#) for key 4 in [Figure 10](#)

2 differential processing result applied to key 1

Figure 12 — Detection of interface position based on differential processing on moving-averaged result**6.7 Determination of interface position**

As defined in [5.2.2](#), the interface position is indicated by the pixel position on the horizontal axis corresponding to the steepest slope of the moving-averaged intensity profile. This means that in the resulting graph of the differential processing of the moving-averaged intensity profile, the interface position can be indicated by the position corresponding to the maximum or minimum intensity peak. For example, in key 2 in [Figure 12 b\)](#), S_1 and S_2 are both interface positions of the layered materials showing in the key 1 [Figure 10 a\)](#).

If it is difficult to decide the interface position from the differential curve because of many sub-peaks appears around the interface position, it is necessary to try again by changing the n -condition for [Formula \(3\)](#), to get smoother slope of the moving-averaged intensity profile.

Examples of processing this interface position determination procedure to the real TEM/STEM image corresponding to each of three types as defined in [6.3.2](#) are described in [Annex A](#). Two main applications using this procedure are described in [Annex B](#).

7 Uncertainty**7.1 Uncertainty accumulating from each step of the procedure**

There are the following three factors that cause uncertainty accumulated from each step of the procedure described in this document.

σ_{ROI} Uncertainty associated with the ROI setting; ROI size and its location [refer to [Figure 7](#) and key 9 in [Figure 9 d](#)].

σ_{LPF} Uncertainty associated with the low-pass filter setting; mask size [refer to key 6 in [Figure 9 c](#)].

σ_{MA} Uncertainty associated with the moving-averaging setting; pixel value for moving [refer to [Formula \(3\)](#)].

These three factors are independent. Therefore, it is necessary to measure the data under plural conditions setting for each factor. For example, repeat the measurement l times at different ROI settings, m times at different LPF settings and n times for MA settings, totally $R = l \times m \times n$ data set can be obtained. The uncertainty of each factor is expressed as follows in [Formulae \(6\)](#) to [\(8\)](#):

$$\sigma_{ROI} = \sqrt{\frac{1}{l} \sum_{i=1}^l (D_i - D_{lavg})^2}, \quad (6)$$

where

D_i is the i -th data in the different ROI settings;

D_{lavg} is the averaged value of the l -data set.

$$\sigma_{LPF} = \sqrt{\frac{1}{m} \sum_{j=1}^m (D_j - D_{mavg})^2} \quad (7)$$

where

D_j is the j -th data in the different LPF settings;

D_{mavg} is the averaged value of the m -data set.

$$\sigma_{MA} = \sqrt{\frac{1}{n} \sum_{k=1}^n (D_k - D_{navg})^2} \quad (8)$$

where

D_k is the k -th data in the different LPF settings;

D_{navg} is the averaged value of the n -data set.

The accumulated uncertainty (σ_{ACC}) of these three factors is represented as follows in [Formula \(9\)](#):

$$\sigma_{ACC}^2 = \sigma_{ROI}^2 + \sigma_{LPF}^2 + \sigma_{MA}^2 \quad (9)$$

Generally, $\sigma_{ROI} \gg \sigma_{LPF}, \sigma_{MA}$, then the $\sigma_{ACC} = \sigma_{ROI}$, in many cases.

7.2 Uncertainty of measurement result on image analysis

There are two kinds of factors that influence the measurement result for the interface position analysis.

σ_{α} Uncertainty of the tilt angle α between the interface of the layer and y-axis of the monitor screen (Refer to [Figure 5](#)).

σ_{θ} Uncertainty of the off-angle θ between the interface of the layer and the atomic column arrangement in the type 2 image (Refer to [Figure 8](#)).

According to ISO/IEC Guide 98-3 (GUM)[3], these factors are classified into the category of type A uncertainty (U_A).

The uncertainty σ_α and σ_θ shall be calculated from the results by N_1 and N_2 replicate measurements. To do this, the angle α and θ measurement described in 6.2.2 and 6.3.3.2 shall be repeated N_1 and N_2 times (three times or more), respectively.

The combined standard uncertainty, u_{c1} , of the interface position for N_1 and N_2 independent measurement can be calculated by [Formula \(10\)](#).

$$u_{c1} = \sqrt{\left(\frac{\sigma_\alpha}{\sqrt{N_1}}\right)^2 + \left(\frac{\sigma_\theta}{\sqrt{N_2}}\right)^2} \quad (10)$$

Furthermore, it is necessary to consider the uncertainty, σ_u , of the pixel size, u , when the distance between two interfaces will be measured (refer to ISO 29301:2023, 6.8.2 for pixel size measurement). When a photographic film or imaging plate is used as a recording medium, pixel size, u , can be measured referring to the method described in [Annex C](#). To get the σ_u , the pixel size, u , shall be repeatedly measured N_3 times (three times or more). Also, it is necessary to consider the uncertainty of the reference glass scale, σ_g , which is classified into the category of type B uncertainty (U_B).

In case of the distance measurement, the combined standard uncertainty u_{c2} can be calculated by [Formula \(11\)](#).

$$u_{c2} = \sqrt{\left(\frac{\sigma_\alpha}{\sqrt{N_1}}\right)^2 + \left(\frac{\sigma_\theta}{\sqrt{N_2}}\right)^2 + \left(\frac{\sigma_u}{\sqrt{N_3}}\right)^2 + \sigma_g^2} \quad (11)$$

The expanded uncertainty $U_{(p)}$ of the interface position or distance measurement for a series of measurements can be defined by [Formula \(12\)](#) and [Formula \(13\)](#), respectively.

$$U_{(1)} = k \times u_{c1} \quad (12)$$

$$U_{(2)} = k \times u_{c2} \quad (13)$$

where k is the coverage factor.

NOTE For a confidence limit of approximately 95 %, k is set to 2 and for a confidence limit of approximately 99 %, k is set to 3.

Annex A

(informative)

Examples of processing the real TEM/STEM images for three image types

A.1 General


The following examples are given for the convenience of users to understand correctly the processing procedure indicated in this document.

A.2 Processing example to type 1 image

A.2.1 Image used in a series of the processes

The low-resolution image shown in [Figure A.1](#), in which atomic column arrangements cannot be recognized, is used in a series of interface determination processes. Information on this image is as follows.

- Specimen: GaAs (10 nm)/AlGaAs (10 nm) multi-layered thin film
- Observation apparatus: TEM equipped with a CCD camera (2k × 2k pixels)



Key


- 1 ROI frame
- 2 Interface position (S_1 to S_8)
- 3 line for intensity profile measurement

The solid white line should be perpendicular to the interface.

Figure A.1 — Example of type 1 image

A.2.2 Acquisition of the averaged intensity profile


[Figure A.2](#) shows the intensity profile along line, *Li*, indicated in [Figure A.1](#). [Figure A.3](#) shows the averaged intensity profile for 450 lines in the ROI frame shown as key 1 in [Figure A.1](#).



Key

X position (pix)
Y intensity

Figure A.2 — Intensity profile for line, *Li*




Key

X position (pix)
Y averaged intensity

Figure A.3 — Averaged intensity profile for 450 lines in ROI

A.2.3 Acquisition of the moving-averaged processing

[Figure A.4](#) shows the moving-averaged intensity profile of the averaged intensity profile as shown in [Figure A.3](#). To get this profile, a numerical value of 4 was applied as the moving range, *n*, used in [Formula \(3\)](#).




Key

X position (pix)
Y moving averaged intensity

Figure A.4 — Moving averaged intensity profile, $n = 4$ applied to [Formula \(3\)](#)

A.2.4 Differential processing

[Figure A.5](#) shows the result of the differential processing on the moving-averaged intensity profile as shown in [Figure A.4](#).



Key

X position (pix)
Y rate of intensity change (ΔI)

Figure A.5 — Differential curve

A.2.5 Determination of interface position

Interface positions (S_1 to S_8) are determined as the pixel positions on the x-axis corresponding to the maximal or minimal peaks of the differential curve as shown in [Figure A.5](#). The interface positions obtained are shown below.

$S_1 =$	26 pix	$S_5 =$	212 pix
$S_2 =$	73 pix	$S_6 =$	259 pix
$S_3 =$	118 pix	$S_7 =$	304 pix
$S_4 =$	165 pix	$S_8 =$	350 pix


A.3 Processing example to type 2 image

A.3.1 Image used in a series of the processes

The high-resolution image shown in [Figure A.6](#) in which the atomic column arranged at an angle, θ , to the interface is used in a series of interface determination processes. Information on this image is as follows.

- Specimen: GaAs (10 nm)/AlGaAs (10 nm) multi-layered thin film
- Observation apparatus: STEM with digital scan
- Distance for 10 lines of atomic column: $S = 2,83$ nm
- Atomic column spacing: $a = 2,83$ nm/10 lines = 0,283 nm
- Off-angle: $\theta = 4,35^\circ$
- Repetition period: $R = a/\sin \theta = 4,18$ nm
- ROI setting: 25 nm $\times$ 25 nm

STANDARDSISO.COM : Click to view the full PDF of ISO 20263:2024



Key


- 1 ROI frame
- 2 interface position (S_1 to S_3)
- 3 atomic column arrangement direction
- 4 line for intensity profile measurement

This line should be perpendicular to the interface.

Figure A.6 — Example of Type 2 image

A.3.2 Acquisition of the averaged intensity profile


[Figure A.7](#) shows the intensity profile along line, L_i , indicated in [Figure A.6](#). [Figure A.8](#) shows the averaged intensity profile for 570 lines in the ROI frame shown as Key 1 in [Figure A.6](#).



Key

X position (pix)
Y intensity

Figure A.7 — Intensity profile for line, L_i , indicated in [Figure A.6](#)




Key

X position (pix)
Y averaged intensity

Figure A.8 — Averaged intensity profile for 570 lines in ROI

A.3.3 Acquisition of the moving-averaged processing

[Figure A.9](#) shows the moving-averaged intensity profile of the averaged intensity profile as shown in [Figure A.8](#). To get this profile, a numerical value of 4 was applied as the moving range, n , in [Formula \(3\)](#).




Key

X position (pix)
Y moving averaged intensity

Figure A.9 — Moving-averaged intensity profile, $n = 4$ applied to [Formula \(3\)](#)

A.3.4 Differential processing

[Figure A.10](#) shows the result of the differential processing on the moving-averaged intensity profile as shown in [Figure A.9](#).



Key

X position (pix)
Y rate of intensity change (ΔI)

Figure A.10 — Differential curve

A.3.5 Determination of interface position

Interface positions (S_1 to S_3) are determined as the pixel positions on the x-axis corresponding to the maximal or minimal peaks of the differential curve as shown in [Figure A.10](#). The interface positions obtained are shown below.

$S_1 = 35$ pix

$S_2 = 297$ pix


$$S_3 = 541 \text{ pix}$$

A.4 Processing example to type 3 image

A.4.1 Image used in a series of the processes

The high-resolution image shown in [Figure A.11](#), in which an atomic column arranged parallel to the interface, is used in a series of interface determination processes. Information on this image is as follows.

- Specimen: Unknown A/B/C/D/E multi-layered thin film
- Observation apparatus: TEM equipped with a CCD camera ($2k \times 2k$ pixels)
- Off-angle: $\theta = 0^\circ$ (parallel to the interface)
- FFT area setting: $2\,048 \text{ pix} \times 2\,048 \text{ pix}$ (whole area of the image)



Key

- 1 interface position (S_1 to S_6)
- 2 line for intensity profile measurement

The solid line should be perpendicular to the interface.

Figure A.11 — Example of type 3 image

[Figure A.12](#), in which intensity oscillation due to the atomic column appeared, shows the intensity profile along line, L_i , indicated in [Figure A.11](#). This intensity oscillation cannot be eliminated, even if the averaging processing over several hundred lines is done. Therefore, low-pass filtering processing is required so that there is no influence by the atomic column.




Figure A.12 — Intensity profile for line, *Li*, indicated in [Figure A.11](#)

A.4.2 Acquisition of the low pass filtering image

[Figure A.13](#) shows the FFT pattern from the whole area of the image shown in [Figure A.11](#). [Figure A.14](#) shows low pass filtering mask, superimposed to the FFT pattern, to cover clear spots in the FFT pattern. In the IFFT processing, to get the low pass filtering image shown in [Figure A.15](#), only information passing through the window at the centre of the low pass filtering mask is used, a high-frequency component related to the formation of the atomic column arrangement is interrupted.




Figure A.13 — FFT pattern processed from [Figure A.11](#)





Figure A.14 — Low-pass filtering mask superimposed to the FFT pattern

STANDARDSISO.COM : Click to view the full PDF of ISO 20263:2024




Key

- 1 ROI frame; 40 nmW × 30 nmH
- 2 artefact region

Figure A.15 — IFFT image processed with low pass filtering to the FFT pattern

A.4.3 Acquisition of the averaged intensity profile

[Figure A.16](#) shows the averaged intensity profile for 1 940 lines in the ROI frame shown as key 1 in [Figure A.15](#).




Key

X position (pix)
Y averaged intensity

Figure A.16 — Averaged intensity profile for 1 940 lines in ROI

A.4.4 Acquisition of the moving-averaged processing

[Figure A.17](#) shows the moving-averaged intensity profile of the averaged intensity profile as shown in [Figure A.16](#). To get this profile, a numerical value of 6 was applied as the moving range, n , in [Formula \(3\)](#).




Key

X position (pix)
Y moving averaged intensity

Figure A.17 — Moving-averaged intensity profile, $n = 6$, applied to [Formula \(3\)](#)

A.4.5 Differential processing

[Figure A.18](#) shows the result of the differential processing on the moving-averaged intensity profile as shown in [Figure A.17](#).

**Key**

X position (pix)

Y rate of intensity change (ΔI)**Figure A.18 — Differential curve****A.4.6 Determination of interface position**

Interface positions (S_1 to S_6) are determined as the pixel positions on the x-axis corresponding to the maximal or minimal peaks of the differential curve as shown in [Figure A.18](#). The interface positions obtained are shown below.

 $S_1 = 153$ pix $S_4 = 820$ pix $S_2 = 439$ pix $S_5 = 985$ pix $S_3 = 730$ pix $S_6 = 1\,779$ pix