
**Plastics — Epoxy resins — Determination
of electrical conductivity of aqueous
resin extracts**

*Plastiques — Résines époxy — Détermination de la conductivité
électrique des extraits aqueux de résine*

STANDARDSISO.COM : Click to view the full PDF of ISO 21318:2007



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 21318:2007

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21318 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 12, *Thermosetting materials*.

Introduction

Where epoxy resins are used as insulation for electronic devices, ionic impurities such as chloride, sodium and catalyst residues present in the epoxy resin can cause failure of the device. Instead of determining these impurities separately, a test method may be used to evaluate their contents as a whole by measuring the electrical conductivity of a resin extract obtained by extraction of the resin with water at an elevated temperature. Because of its practical usage and simplicity, this method is becoming widely used in the quality control of epoxy resins for electronic insulation applications.

STANDARDSISO.COM : Click to view the full PDF of ISO 21318:2007

Plastics — Epoxy resins — Determination of electrical conductivity of aqueous resin extracts

SAFETY STATEMENT — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory requirements.

1 Scope

This International Standard specifies a method for the determination of the electrical conductivity of an aqueous extract obtained by extraction of an epoxy resin with water at 95 °C. The method is applicable only to epoxy resins that are in the molten state at the extraction temperature (95 °C).

The method is important for epoxy resins which are used as insulation materials for electronic devices. The electrical conductivity of the extract is used as a measure of the concentration of the ionic species in the resin.

2 Materials

2.1 Water.

Use only distilled and/or deionized water, the electrical conductivity of which is below 2,0 µS/cm.

3 Apparatus

3.1 Electrical conductivity meter, accurate to 0,1 µS/cm, which can be dipped into the aqueous extract and which has a temperature-compensation function.

3.2 Graduated glass cylinders, 100 ml.

3.3 Analytical balance, accurate to 0,01 g.

3.4 Air-circulation oven, capable of maintaining a temperature of 95 °C ± 3 °C.

3.5 High-density polyethylene bottle, 100 ml (with a screw cap).

3.6 Polyethylene cup, 100 ml.

4 Procedure

4.1 Weigh a test portion of 8,00 g ± 0,05 g into a 100 ml high-density polyethylene bottle (3.5).

4.2 Add 80 ml ± 2 ml of water (2.1) to the bottle and put on the cap.

4.3 Put the bottle into the oven (3.4) which has been stabilized at 95 °C.

4.4 After 30 min, loosen the cap of the bottle to release the internal pressure in order to avoid possible bursting of the bottle. Then retighten the cap.

WARNING — Never fail to follow procedure 4.4. Wear protective gloves and a face-shield when releasing the internal pressure.

4.5 After $20 \text{ h} \pm 0,5 \text{ h}$, remove the bottle from the oven and allow to cool to room temperature.

4.6 Pour the water into a polyethylene cup (3.6), and measure the electrical conductivity using the electrical conductivity meter (3.1) at $25 \text{ }^{\circ}\text{C}$.

4.7 Carry out a blank test, following the same procedure and using the same water but without the test portion.

5 Expression of results

Calculate the electrical conductivity γ of the aqueous resin extract, expressed in microsiemens per centimetre ($\mu\text{S/cm}$), from the following equation:

$$\gamma = \gamma_{\text{S}} - \gamma_{\text{B}}$$

where

γ_{S} is the uncorrected electrical conductivity of the extract, expressed in microsiemens per centimetre ($\mu\text{S/cm}$);

γ_{B} is the electrical conductivity of the blank, expressed in microsiemens per centimetre ($\mu\text{S/cm}$).

6 Precision

Precision data were determined from a round-robin trial organized in 2002 and 2003 involving eight laboratories in Japan. Two commercial epoxy resins were tested and the results analysed in accordance with ISO 5725-2, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*.

The repeatability and reproducibility calculated from the trial are given in Table 1.

Table 1 — Precision data

Type of epoxy resin	Electrical conductivity (averaged) $\mu\text{S/cm}$	Repeatability s_r	Reproducibility s_R
BPA (bisphenol A type solid epoxy resin)	3,6	0,11	0,31
ECN (o-cresol novolac type solid epoxy resin)	1,1	0,04	0,10