

First edition
2006-10-01

AMENDMENT 1
2015-11-01

**Prosthetics — Testing of ankle-
foot devices and foot units —
Requirements and test methods**

AMENDMENT 1

*Prothèses — Essais d'articulations cheville-pied et unités de pied —
Exigences et méthodes d'essai*

AMENDEMENT 1

STANDARDSISO.COM : Click to view the full PDF of ISO 22675:2006/FD Amd 1



Reference number
ISO 22675:2006/Amd.1:2015(E)

© ISO 2015

STANDARDSISO.COM : Click to view the full PDF of ISO 22675:2006/FD Amd 1



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 168, *Prosthetics and orthotics*.

STANDARDSISO.COM : Click to view the full PDF of ISO 22675:2006/FDAmendment 1

Prosthetics — Testing of ankle-foot devices and foot units — Requirements and test methods

AMENDMENT 1

Page 8, 7.2.3

Replace 7.2.3 with the following text:

Test loading levels: P3, P4, P5, P6, P7 and P8

NOTE 1 Field experience has shown that there is a need for lower limb prostheses which sustain loads above the level covered by test loading level P5. In order to allow the structural testing of such prostheses on a uniform basis, test loading levels P6, P7 and P8 have been developed for the principal structural tests and the separate structural tests on ankle-foot devices and foot units (see Annex C).

NOTE 2 The values of the dimensions and loads of test loading levels P3, P4 and P5 are specified in separate tables in Clause 8. It is suggested that the values of the dimensions and loads specified in C.3 and [Table C.2](#) are appropriate for test loading level P6, and for P7 and P8 (pending validation), as an interim measure. Further test loading levels will be defined, if necessary.

Page 10, Table 5

Delete the NOTE and replace by the following:

For the additional test loading levels P6, P7 and P8 the test forces are specified in [Table C.1](#).

Page 11, Table 6

Delete the NOTE and replace by the following:

The total length and the segmental lengths also apply to the additional test loading levels P6, P7 and P8 specified in Annex C [see C.3 a)].

Page 12, Table 7

Delete the NOTE and replace by the following:

The specified dimensions also apply to the additional test loading levels P6, P7 and P8 specified in Annex C [see C.3 a)].

Page 12, Table 8

Delete the NOTE and replace by the following:

The specified dimensions also apply to the additional test loading levels P6, P7 and P8 specified in Annex C [see C.3 a)].

Replace Table 9 by the following:

Test procedure and test force			Unit	Test loading level (P _x) ^a and test loading condition (F _{1x} ; F _{2x})					
				P5		P4		P3	
				Heel loading, F _{1x}	Fore-foot loading, F _{2x}	Heel loading, F _{1x}	Fore-foot loading, F _{2x}	Heel loading, F _{1x}	Fore-foot loading, F _{2x}
Static test procedure	Static proof test force	F _{1sp}	N	2 227	—	2 053	—	1 601	—
		F _{2sp}		—	2 198	—	2 026	—	1 580
	Static ultimate test force	F _{1su} , lower level	N	3 340	—	3 079	—	2 401	—
		F _{2su} , lower level		—	3 297	—	3 039	—	2 369
Cyclic test procedure	1st maximum value of pulsating test force	F _{1cmax}	N	1 273	—	1 173	—	915	—
		F _{cmin}		N	850		783		611
	2nd maximum value of pulsating test force	F _{2cmax}	N	—	1 256	—	1 158	—	903
		F _{1fin} (= F _{1sp})		N	2 227	—	2 053	—	1 601
Final static test force	F _{2fin} (= F _{2sp})	—	2 198		—	2 026	—	1 580	
Prescribed number of cycles			1	2 × 10 ⁶					

NOTE The specific values of the different test forces are based on reference values described in A.2.3 and specified in Table A.1.

^a For the additional test loading level P6, P7 and P8 the values of the test forces and the prescribed number of cycles are specified in [Table C.2](#).

Replace Table 10 by the following:

Reference point	Threshold									
	Instant (Time after heel contact) ms	Interval of time ms	Rate of loading/unloading (Value relevant to test loading level)						Test force $F_c(t)$ at reference point N	
			kN/s						Symbol	Value relevant to test loading level
			P8	P7	P6	P5	P4	P3		
a	0								$F_c(t_a)$	0 0 0 0 0 0

NOTE The loading period of 600 ms corresponds to the average stance phase time of a typical walking cycle of 1 second duration. (The remaining time of 400 ms of the walking cycle corresponds to the swing phase.) Simulating this stance phase time–swing phase time–relationship in a cyclic test, a loading period of 600 ms corresponds to a test frequency $f = 1$ Hz. For other test frequencies, preferably between 0,5 Hz and 3 Hz (see 16.4.1.6 and 16.4.1.7), the time intervals between each instant after heel contact, for which rates of loading/unloading or test force are specified in this table, can easily be adapted by linear scaling.

Reference point	Threshold														
	Instant (Time after heel contact) ms	Interval of time ms	Rate of loading/unloading (Value relevant to test loading level) kN/s P8 P7 P6 P5 P4 P3						Test force $F_c(t)$ at reference point N						
									Value relevant to test loading level						
			Symbol	Value relevant to test loading level											
				P8	P7	P6	P5	P4	P3						
		115	17,8	15,4	13,3	11,1	10,2	8,0							
b	115								F_{1cmax}	2038	1760	1521	1273	1173	915
		51													
c	166								F_{1cmax}	2038	1760	1521	1273	1173	915
		103	- 6,5	- 5,6	- 4,9	- 4,1	- 3,8	- 2,9							
d	269								F_{cmin}	1361	1175	1016	850	783	611
		62													
e	331								F_{cmin}	1361	1175	1016	850	783	611
		102	6,4	5,6	4,8	4,0	3,7	2,9							
f	433								F_{2cmax}	2011	1737	1501	1256	1158	903
		51													
g	484								F_{2cmax}	2011	1737	1501	1256	1158	903
		116	-17,4	-15,0	-13,0	-10,8	- 9,9	7,9							
h	600								$F_c(t_h)$	0	0	0	0	0	0

NOTE The loading period of 600 ms corresponds to the average stance phase time of a typical walking cycle of 1 second duration. (The remaining time of 400 ms of the walking cycle corresponds to the swing phase.) Simulating this stance phase time–swing phase time–relationship in a cyclic test, a loading period of 600 ms corresponds to a test frequency $f=1$ Hz. For other test frequencies, preferably between 0,5 Hz and 3 Hz (see 16.4.1.6 and 16.4.1.7), the time intervals between each instant after heel contact, for which rates of loading/unloading or test force are specified in this table, can easily be adapted by linear scaling.

Page 44, 16.2.1.2

Replace the last sentence in the third paragraph by the following:

Make specific reference if the additional test loading level P6, P7 or P8 specified in Annex C are to be applied.

Page 47, 16.3.1.2

Replace the last sentence in the fourth paragraph by the following:

Make specific reference if the application of the additional test loading levels P6, P7 or P8 specified in Annex C is to be applied.

Page 48, 16.3.1.5

In the second sentence of the fourth paragraph replace [12.3.3 a)] by [12.3.4 a)]

Page 48, 16.3.1.8

Replace the second sentence in the fourth paragraph by the following:

Make specific reference if the application of the additional test loading levels P6, P7 or P8 specified in Annex C is to be applied.

Page 52, 16.4.1.3

Replace the second sentence in the second paragraph by the following:

Make specific reference if the application of the additional test loading levels P6, P7 or P8 specified in Annex C is to be applied.

Page 59, 18.2.1

Replace the second sentence in the first paragraph by the following:

This particularly applies to tests that are conducted at the additional test loading level P6, P7 or P8 according to Annex C (see 16.2.1.2, 16.3.1.2 and 16.4.1.3), and to the alternative static ultimate strength test according to Annex B (see 16.3.1.1, 16.3.1.5 and 16.3.1.11).

Page 63, A.1

Replace the second and third paragraph by the following:

The test loading level P5 is based on data from all amputees including a few whose body mass exceeded 100 kg. The test loading levels P6 and P7 are based on locomotion data from amputees whose body mass is less than 125 kg and 150 kg respectively, obtained from simulations and field observations; P8 is extrapolated from these two levels to amputees whose body mass is less than 175 kg. The test loading levels P4 and P3 are based on locomotion data from amputees whose body mass is less than 80 kg and 60 kg, respectively.

For the proposed additional test loading levels P6, P7 and P8 see Annex C.

Page 65, Equation (A.4)

Replace by the following:

$$D_{PT} = \sqrt{\frac{f_{T,26}^2 + u_{T,26}^2}{26}}$$

Page 66, Table A.1

Replace Table A.1 by the following:

Resultant reference forces F_{R1x} and F_{R2x} of static and maximum cyclic heel and forefoot reference loading	Related test forces F_{1x} and F_{2x} of the separate tests on ankle-foot devices and foot units specified in ISO 10328 (see Tables 11 and D.3 of ISO 10328:2006)												
	Symbol	Test loading level											
		P8		P7		P6		P5		P4		P3	
		Numerical values for heel loading (F_{1x}) and forefoot loading (F_{2x})											
		F_{1x}	F_{2x}	F_{1x}	F_{2x}	F_{1x}	F_{2x}	F_{1x}	F_{2x}	F_{1x}	F_{2x}	F_{1x}	F_{2x}
		N											
F_{R1sp}	F_{1sp}	3200	–	2900	–	2490	–	2240	–	2065	–	1610	–
F_{R2sp}	F_{2sp}	–	3200	–	2900	–	2490	–	2240	–	2065	–	1610
F_{R1su} , lower level	F_{1su} , lower level	4450	–	4100	–	3760	–	3360	–	3098	–	2415	–
F_{R2su} , lower level	F_{2su} , lower level	–	4450	–	4100	–	3760	–	3360	–	3098	–	2415
F_{R1su} , upper level	F_{1su} , upper level	5700	–	5300	–	4880	–	4480	–	4130	–	3220	–
F_{R2su} , upper level	F_{2su} , upper level	–	5700	–	5300	–	4880	–	4480	–	4130	–	3220
F_{R1cmax}	F_{1cr}	2050	–	1770	–	1530	–	1280	–	1180	–	920	–
F_{R2cmax}	F_{2cr}	–	2050	–	1770	–	1530	–	1280	–	1180	–	920
F_{R1fin}	F_{1fin}	3200	–	2900	–	2490	–	2240	–	2065	–	1610	–
F_{R2fin}	F_{2fin}	–	3200	–	2900	–	2490	–	2240	–	2065	–	1610

Page 72, Annex C

Change the Annex from informative to normative and change the title by the following:

Application of an additional test loading level P6, P7 and P8

Replace the second paragraph by the following:

In order to allow the structural testing of such prostheses on a uniform basis, additional test loading levels P6, P7 and P8 are proposed in this annex. They are derived, amongst others, from measurements of overweight prosthetic patients, normals and wobbling mass simulations.

Replace Table C.1 by the following:

Table C.1 — Test forces of the proof test of end attachments for test loading level P6, P7 and P8 (see 13.2.1)

Test procedure	End attachments for		Stabilizing test force, F_{stab} ; (F_{Rstab}) ^b	Settling test force, F_{set} ; (F_{Rset}) ^b N	Proof test force, F_{pa} ; (F_{Rpa}) ^b
	Heel loading F_1 at $\gamma = -15^\circ$	Forefoot loading F_2 at $\gamma = 20^\circ$			
All tests ^a	P8		50	1630 (1640)	6800 (6840)
		P8		1609 (1640)	6711 (6840)
	P7			1408 (1416)	6323 (6360)
		P7		1389 (1416)	6240 (6360)
	P6			1217 (1224)	5822 (5856)
		P6		1201 (1224)	5746 (5856)

^a End attachments that satisfy the stiffness requirements of the proof test of end attachments for proof test force $F_{pa} = 1,2 F_{Su}$, upper level of a test loading level specified in this table are suitable for all static and cyclic tests of this International Standard carried out at this test loading level and at all lower levels.

For sets of end attachments, individually designed to the specific requirements of the test loading conditions of the static and cyclic tests of this International Standard and/or to the specific requirements of the ankle-foot devices or foot units submitted for test, particular conditions apply (see the OPTION described in 13.2.2.1).

^b The relationship between the values of F_x and F_{Rx} (placed in parentheses) is determined by equation (A.5), using the values of α_1 and α_2 specified in A.2.3. The values of F_{Rx} are calculated from the relevant values listed in Table A.1, using the factors specified in Table 4 (see A.2.3). Which set of values applies depends on how the assembly of end attachments is placed in the test equipment (see 13.2.1.2.3).

Page 73, [Table C.2](#)

Replace [Table C.2](#) by the following:

Table C.2 — Test forces for all tests and prescribed number of cycles for the cyclic test, for test loading level P6, P7 and P8 (see 16.2, 16.3 and 16.4)

Test procedure and test load			Unit	Test loading level						
				P8		P7		P6		
				Heel loading (F_{1x}) and forefoot loading (F_{2x})						
				F_{1x}	F_{2x}	F_{1x}	F_{2x}	F_{1x}	F_{2x}	
Static test procedure	Static proof test force	F_{1sp}	N	3181	–	2883	–	2476	–	
		F_{2sp}		–	3140	–	2845	–	2443	
	Static ultimate test force	F_{1su} , lower level	N	4424	–	4076	–	3738	–	
		F_{2su} , lower level		–	4366	–	4023	–	3689	
			F_{1su} , upper level	N	5667	–	5269	–	4852	–
			F_{2su} , upper level		–	5593	–	5200	–	4788
Cyclic test procedure	1st maximum value of pulsating test force	F_{1cmax}	N	2038	–	1760	–	1521	–	
	Intermediate minimum value of pulsating test force	F_{cmin}	N	1361		1175		1016		
	2nd maximum value of pulsating test force	F_{2cmax}	N	–	2011	–	1737	–	1501	
	Final static force	F_{1fin} (= F_{1sp})	N	3181	–	2883	–	2476	–	
		F_{2fin} (= F_{2sp})		–	3140	–	2845	–	2443	
	Prescribed numbers of cycles			1	2×10^6					
NOTE The specific values of the different test forces are based on reference values, as described in A.2.2.2.										

Page 76, D.3.2.1 c)

Replace the text by the following:

- c) the test loading level to be applied, together with the corresponding values of tilting angles of the foot platform and test forces, making specific reference to the application of the additional test loading level P6, P7 or P8 specified in Annex C, if appropriate, in accordance with 16.2.1.2;