
**Rubber- or plastics-coated
fabrics — Determination of roll
characteristics —**

**Part 2:
Methods for determination of total
mass per unit area, mass per unit area
of coating and mass per unit area of
substrate**

*Supports textiles revêtus de caoutchouc ou de plastique —
Détermination des caractéristiques des rouleaux —*

*Partie 2: Méthodes de détermination de la masse surfacique totale, de
la masse surfacique du revêtement et de la masse surfacique du support*

STANDARDSISO.COM : Click to view the full PDF of ISO 2286-2:2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Determination of total mass per unit area	1
3.1 Apparatus.....	1
3.2 Preparation of test pieces.....	2
3.3 Procedure.....	2
3.4 Calculation and expression of results.....	2
3.5 Test report.....	2
4 Determination of mass per unit area of substrate	3
4.1 General.....	3
4.2 Principle.....	3
4.3 Reagent.....	3
4.4 Apparatus.....	3
4.5 Procedure.....	3
4.6 Calculation and expression of results.....	4
4.7 Test report.....	4
5 Determination of mass per unit area of coating	4
5.1 Procedure.....	4
5.2 Test report.....	4
Annex A (normative) Coating - removal methods	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword – Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products title*, Subcommittee SC 4, *Products (other than hoses)*.

This second edition cancels and replaces the first edition (ISO 2286-2:1998), which has been technically revised. The changes are as follows:

- in [3.1.1](#), the accuracy of the balance has been changed;
- in [3.2](#), the usable width of the sample has been clearly specified;
- in [3.3](#), the drying process has been changed to optional and the conditioning atmosphere has been specified more clearly;
- in [3.5](#) and [4.7](#), item b) has been added;
- in [4.5.3](#), the conditioning atmosphere has been specified more clearly.

ISO 2286 consists of the following parts, under the general title *Rubber- or plastics- coated fabrics — Determination of roll characteristics*:

- *Part 1: Methods for determination of length, width and net mass*
- *Part 2: Methods for determination of total mass per unit area, per unit area of coating and mass per unit area of substrate*
- *Part 3: Method for determination of thickness*

Introduction

The total mass per unit area of a material, the mass per unit area of the substrate cloth and the mass per unit area of the coating are quantities which define the basic quality of a coated fabric and determine many of its physical properties. The substrate cloth mass determined by these methods does not necessarily represent the mass of the substrate cloth in the uncoated state. For example, in the case of coated fabrics in which a bonding agent has been used, the substrate cloth mass determined may be substantially higher than the uncoated mass because the prescribed treatment has not removed the entire coating. This will be particularly so in cases where the substrate cloth is made from multifilament or spun-fibre yarns. Dimensional changes in the substrate cloth during processing may also occur.

STANDARDSISO.COM : Click to view the full PDF of ISO 2286-2:2016

STANDARDSISO.COM : Click to view the full PDF of ISO 2286-2:2016

Rubber- or plastics-coated fabrics — Determination of roll characteristics —

Part 2:

Methods for determination of total mass per unit area, mass per unit area of coating and mass per unit area of substrate

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This part of ISO 2286 specifies methods of determining the total mass per unit area, the mass per unit area of the coating and the mass per unit area of the substrate cloth of a rubber- or plastics-coated fabric. Methods for removing coatings of specific compositions are described in [Annex A](#).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2231:1989, *Rubber- or plastics-coated fabrics — Standard atmospheres for conditioning and testing*

3 Determination of total mass per unit area

3.1 Apparatus

3.1.1 Balance, capable of reading to 1 mg or less.

3.1.2 Means of maintaining an atmosphere with a relative humidity not greater than 10 % and a temperature of $65\text{ °C} \pm 5\text{ °C}$.

NOTE Air at 20 °C and 65 % relative humidity, when heated at constant pressure to $65\text{ °C} \pm 5\text{ °C}$, will have a relative humidity of approximately 5 %. Higher temperatures can lead to changes in some coatings.

3.1.3 Cutter, capable of cutting, from the sample of coated fabric, a test piece of area $100\text{ cm}^2 \pm 1\text{ cm}^2$.

NOTE It has been found convenient to use a circular cutter for this purpose, but square or rectangular test pieces can be used provided they are within the accuracy specified above.

3.2 Preparation of test pieces

Using the cutter (3.1.3) cut five test pieces from the sample, from positions spaced reasonably evenly and close to the diagonal across the usable width of the sample excluding 50 mm from the edge of the sample so that the full width of the coated fabric is represented.

Do not take any test pieces within 1 m of a production-manufactured roll end.

3.3 Procedure

Unless otherwise agreed between the interested parties to skip the drying process, dry the test pieces to constant mass in an atmosphere with a relative humidity not higher than 10 % at a temperature of $65\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$.

Condition the test pieces in accordance with the method of conditioning "1" in ISO 2231:1989 and, without removing them from the conditioning atmosphere, determine the mass of each to the nearest 5 mg and the surface area of each to within 1 %.

NOTE Any estimate of the mass per unit area of the coated fabric derived from the total net mass of the roll and its known length and width may be inaccurate because a complete roll of coated fabric cannot normally be conditioned to equilibrium in a standard atmosphere. Such inaccuracies are due to excesses or deficiencies in moisture regain through the complete roll.

3.4 Calculation and expression of results

For each of the five test pieces, calculate the total mass per unit area, M , in grams per square metre, using Formula (1):

$$M = \frac{m \times 10^4}{A} \quad (1)$$

where

m is the mass of the test piece, in grams;

A is the area of the test piece, in square centimetres.

Calculate the mean of the five determinations, expressing the final result to the nearest 1 g/m^2 .

Take this mean as the total mass per unit area of the material under test.

3.5 Test report

The test report shall include the following information:

- a reference to this part of ISO 2286, i.e. ISO 2286-2;
- the condition at the time of conditioning and the test;
- a complete description of the coated fabric;
- the mean value, in grams per square metre, of the total mass per unit area obtained from the five test pieces;
- details of any deviations from the procedure specified;
- the date of the determination.

4 Determination of mass per unit area of substrate

CAUTION — Some of the solvents used may be toxic, flammable or otherwise hazardous. Care in the handling of such materials must be exercised. The inhalation of vapours should be avoided. Suitable protective clothing, including gloves and goggles, should be worn when appropriate. It is recommended that a suitable eyewash be kept in a position convenient for use. Any further precautionary measures recommended by the solvent manufacturer should be followed.

4.1 General

The procedure specified for removing the coating from the substrate cloth is governed both by the nature of the coating and by the nature of the substrate, and indeed for some types of coating there will be no known method of removal. Where this is the case, it shall be reported in the test report.

4.2 Principle

The coating is removed with a stripping agent from the same test pieces as were used for the determination of the total mass per unit area. The stripped test pieces are dried, conditioned and weighed. The procedure is repeated until constant mass is reached.

4.3 Reagent

4.3.1 Suitable solvent system (stripping agent), which has no solvent or chemical action on the substrate. Particular care shall be taken if there are bonding agents or finishing treatments on the substrate which are not essentially part of the coating but which might be removed with it [e.g. bonding agents in nonwoven (bonded-fibre) fabrics, rot-proofing agents, etc.]. If it is known or suspected that such an agent has unavoidably been removed with the coating, this shall be reported in the test report.

NOTE A suitable solvent system can be an organic solvent, a mixture of organic solvents, water or an aqueous solution (see [Annex A](#)).

4.4 Apparatus

The same apparatus as described in [3.1](#) is required.

4.5 Procedure

4.5.1 Dissolve the coating from each test piece separately. In many cases, the bulk of the coating may be successfully removed mechanically after moistening the substrate with the stripping agent. Use either Soxhlet extraction where appropriate or immerse the test pieces with occasional agitation in at least three successive portions of the solvent at an appropriate temperature until the coating has apparently been completely removed. Ensure at this stage and subsequent stages that any loose threads are retained with the test pieces. If the stripping agent used is itself a solution containing non-volatile components, wash the test pieces several times in a suitable pure solvent.

4.5.2 Dry the test pieces for at least 1 h at $65\text{ °C} \pm 5\text{ °C}$, allow to stabilize by cooling in a desiccator for 15 min, and determine the mass of each to the nearest 5 mg. Extract the stripped test pieces with a further quantity of stripping agent, wash if necessary, then dry, stabilize and determine their mass as before. If the second determination differs from the first by more than 1 %, repeat the treatment until successive determinations show a difference of less than 1 %.

4.5.3 Condition the test pieces in accordance with the method of conditioning “1” in ISO 2231:1989 and determine their masses to the nearest 5 mg to obtain the substrate cloth mass per unit area.

4.6 Calculation and expression of results

For each of the five test pieces, calculate the mass per unit area of the substrate, in grams per square metre.

Calculate the mean of the five determinations, expressing the final result to the nearest 1 g/m².

Take this mean as the total mass per unit area of the material under test.

4.7 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 2286, i.e. ISO 2286-2;
- b) the condition at the time of conditioning and the test;
- c) a complete description of the coated fabric;
- d) the mean value, in grams per square metre, of the substrate mass per unit area obtained from the five test pieces;
- e) details of any deviations from the procedure specified;
- f) the date of the determination.

5 Determination of mass per unit area of coating

5.1 Procedure

Calculate the coating mass per unit area by subtracting the result obtained for the substrate mass per unit area in [Clause 4](#) from the result obtained for the total mass per unit area in [Clause 3](#).

5.2 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 2286, i.e. ISO 2286-2;
- b) a complete description of the coated fabric;
- c) the mean value, in grams per square metre, of the coating mass per unit area;
- d) details of any deviations from the procedure specified;
- e) the date of the determination.

Annex A (normative)

Coating - removal methods

A.1 General

The methods described in [A.2](#) to [A.5](#) have been found satisfactory for some of the most frequently encountered coatings.

A.2 Simple poly(vinyl chloride) compositions

CAUTION — Attention is drawn to the fact that there is a risk of an explosion occurring if the tetrahydrofuran used is evaporated to dryness, unless the precaution is taken of making sure that no peroxides are present by adding ferrous sulfate.

If the coating is continuous and on one side only, wet the substrate of each test piece with either tetrahydrofuran or butanone. Separate the bulk of the coating mechanically from the substrate. Then immerse each test piece separately in 100 ml of tetrahydrofuran or butanone and leave, with occasional agitation, for 20 min at room temperature.

Remove the stripped test pieces, together with any loose threads, from the solvent and wash them in 100 ml of acetone; then proceed in accordance with [4.5.2](#) and [4.5.3](#).

A.3 Nitrocellulose compositions

Wet the substrate of each test piece with acetone and, where possible, separate the bulk of the coating mechanically from the substrate.

Immerse each test piece separately in 100 ml of acetone in a flask fitted with a reflux condenser.

Reflux for 20 min, then replace the solvent with 100 ml of fresh acetone and reflux for another 20 min. Remove the stripped test pieces, together with any loose threads, from the solvent; then proceed in accordance with [4.5.2](#) and [4.5.3](#).

A.4 Polyurethane compositions

Immerse each test piece separately in a solution made up as follows:

propane-1,2-diol	100 parts by mass
potassium hydroxide (solid)	3 parts by mass
water	1 part by mass
<i>N</i> -methyl-2-pyrrolidone	25 parts by mass

Heat to 48 °C ± 2 °C and keep at that temperature for a period of 30 min or until the coating has been removed.

NOTE The above mixture will not attack cotton, nylon or polyester fibres, providing the maximum temperature specified, i.e. 50 °C, is not exceeded and the period of immersion in the solution is not much longer than 30 min.