
**Isoprene rubber (IR) — Non-oil-extended,
solution-polymerized types — Evaluation
procedure**

*Caoutchouc isoprène (IR) — Types polymérisés en solution et non étendus
à l'huile — Méthode d'évaluation*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 2303:2003

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Printed in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Sampling and sample preparation	2
4 Physical and chemical tests on raw rubber	2
4.1 Mooney viscosity	2
4.2 Volatile matter	2
4.3 Ash	2
5 Preparation of the test mixes for evaluation of Isoprene rubbers	2
5.1 Standard test formulation	2
5.2 Procedure	3
6 Evaluation of vulcanization characteristics by a curemeter test	5
6.1 Using an oscillating disc curemeter	5
6.2 Using a rotorless curemeter	5
7 Evaluation of tensile stress-strain properties of vulcanized test mixes	6
8 Precision	6
8.1 General	6
8.2 Precision details	6
8.3 Precision results	6
9 Test report	7
Annex A (informative) Alternative mixing method by internal mixer-mill mixing procedure	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2303 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This fourth edition cancels and replaces the third edition (ISO 2303:1990), which has been technically revised.

Annex A of this International Standard is for information only.

Isoprene rubber (IR) — Non-oil-extended, solution-polymerized types — Evaluation procedure

WARNING — Persons using this International Standard should be familiar with normal laboratory practices. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies, for general purpose non-oil-extended, solution-polymerized polyisoprene rubbers (IR):

- physical and chemical tests on raw rubbers;
- standard materials, standard test formulation, equipment and processing methods for evaluating the vulcanization characteristics.

Two mill-mixing procedures are described in this International Standard and an internal mixer-mill mixing procedure is described in annex A.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 37:1994, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 247:1990, *Rubber — Determination of ash*

ISO 248:1991, *Rubbers, raw — Determination of volatile-matter content*

ISO 289-1:1994, *Rubber, unvulcanized — Determinations using a shearing-disc viscometer — Determination of Mooney viscosity*

ISO 471:1995, *Rubber — Temperatures, humidities and times for conditioning and testing*

ISO 1795:2000, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

ISO 2393:1994, *Rubber test mixes — Preparation, mixing and vulcanization — Equipment and procedures*

ISO 3417:1991, *Rubber — Measurement of vulcanization characteristics with the oscillating disc curemeter*

ISO 6472:—¹⁾, *Rubber compounding ingredients — Abbreviations*

ISO 6502:1999, *Rubber — Guide to the use of curemeters*

ISO/TR 9272:1986, *Rubber and rubber products — Determination of precision for test method standards*

ISO 11235:1999, *Rubber compounding ingredients — Sulfenamide accelerators — Test methods*

3 Sampling and sample preparation

3.1 A laboratory sample of approximately 1,5 kg shall be taken by the method described in ISO 1795.

3.2 Preparation of the test portion shall be in accordance with ISO 1795.

4 Physical and chemical tests on raw rubber

4.1 Mooney viscosity

The Mooney viscosity shall be determined in accordance with ISO 289-1 on a test portion prepared as described in ISO 1795 (without massing).

The result shall be recorded as ML(1 + 4) at 100 °C.

4.2 Volatile matter

The volatile matter content shall be determined in accordance with ISO 248.

4.3 Ash

The ash content shall be determined in accordance with ISO 247.

5 Preparation of the test mixes for evaluation of Isoprene rubbers

5.1 Standard test formulation

The standard test formulation is given in Table 1.

The materials shall be national or International Standard reference materials. If no standard reference material is available, the materials to be used shall be agreed by the concerned parties.

1) To be published. (Revision of ISO 6472:1994)

Table 1 — Standard test formulation for evaluation of IR rubbers

Material	Parts by mass
Isoprene rubber (IR)	100,00
Stearic acid	2,00
Zinc oxide	5,00
Sulfur	2,25
Industry Reference Black (N330)	35,00
TBBS ^a	0,70
Total	144,95

^a TBBS or N-*tert*-butyl-2-benzothiazole sulfenamide in accordance with ISO 6472. This shall be supplied in powder form having an initial insoluble matter content, in accordance with ISO 11235, of less than 0,3 %. The material shall be stored at room temperature in a closed container and insoluble matter shall be checked every 6 months. If this is found to exceed 0,75 %, the material shall be discarded. TBBS may be purified by reprocessing, e.g. by recrystallization; the procedure for this is beyond the scope of this International Standard.

5.2 Procedure

5.2.1 Equipment and procedure

Equipment and procedure for the preparation, mixing and vulcanization shall be in accordance with ISO 2393.

5.2.2 Mill mixing procedures

5.2.2.1 General

Two mill mixing procedures are specified, A and B. The mixing time is shorter in method B than in method A.

The two methods do not necessarily give identical results. In laboratory cross checks or in a series of evaluations the same procedure shall be used in all cases.

In both methods the standard laboratory mill batch mass, in grams, shall be based on four times the formula mass. The surface temperature of the rolls shall be maintained at 70 °C ± 5 °C throughout the mixing.

A good rolling bank at the nip of the rolls shall be maintained during mixing. If this is not obtained with the nip settings specified in 5.2.2.2 and 5.2.2.3, small adjustments to the mill openings may be necessary.

5.2.2.2 Procedure A

	Duration (min)	Cumulative time (min)
a) Pass the rubber between the mill-rolls twice without banding, with the mill opening set at 0,5 mm for approximately 2 min and weigh the rubber.	2	2
b) Band the rubber with the mill opening set at 1,4 mm and make two 3/4 cuts from each side.	2	4

NOTE Some types of isoprene rubber go to the back roll, in which case the stearic acid should be added and after its incorporation the rubber can usually be transferred to the front roll. In addition, certain tougher types of isoprene rubber may require slightly longer breakdown before the addition of other materials in order to obtain a good rolling bank.

c) Set the mill opening to 1,7 mm and add the stearic acid. Make one 3/4 cut from each side.	2	6
d) Add the zinc oxide and the sulfur. Make two 3/4 cuts from each side.	3	9
e) Add the carbon black evenly across the mill at a uniform rate. When approximately half the black has been incorporated, open the mill to 1,9 mm and make one 3/4 cut from each side, then add the remainder of the carbon black. Be certain to add the black that has dropped into the mill pan. When all the black has been incorporated, make one 3/4 cut from each side.	13	22
f) Add the TBBS with the mill opening still at 1,9 mm. Make three 3/4 cuts from each side.	3	25
g) Cut the batch from the mill. Set the mill opening to 0,8 mm and pass the rolled batch endwise through the rolls six times.	3	28
Total time		28

- h) Sheet the batch to an approximate thickness of 6 mm and check-weigh the batch (see ISO 2393). If the mass of the batch differs from the theoretical value by more than $\begin{matrix} +0,5 \\ -1,5 \end{matrix}$ % discard the batch and re-mix. Remove sufficient material for curemeter testing.
- i) Sheet the batch to approximately 2,2 mm for preparing test slabs or to the appropriate thickness for preparing ISO ring test pieces in accordance with ISO 37.
- j) Condition the batch for 2 h to 24 h after mixing and prior to vulcanizing, if possible at standard temperature and humidity as defined in ISO 471.

5.2.2.3 Procedure B

	Duration (min)	Cumulative time (min)
a) Pass the rubber between the rolls twice without banding, with the mill opening set at $0,5 \text{ mm} \pm 0,1 \text{ mm}$, then band the rubber between the rolls with the mill opening gradually increased to 1,4 mm.	2	2
b) Add the stearic acid. Make one 3/4 cut from each side.	2	4
c) Add the sulfur and the zinc oxide. Make two 3/4 cuts from each side.	3	7
d) Add half of the carbon black. Make two 3/4 cuts from each side.	3	10
e) Add the remaining half of the carbon black and the black that has dropped into the mill pan. Make three 3/4 cuts from each side.	5	15
f) Add the TBBS. Make three 3/4 cuts from each side.	3	18
g) Cut the batch from the mill. Set the mill opening to $0,5 \text{ mm} \pm 0,1 \text{ mm}$ and pass the rolled batch endwise through the rolls six times.	2	20
Total time		20

- h) Sheet the batch to approximately 2,2 mm for preparing test slabs or to the appropriate thickness for preparing ISO ring test pieces in accordance with ISO 37.
- i) Cut the batch from the mill and check-weigh the batch (see ISO 2393). If the mass of the batch differs from the theoretical value by more than $\begin{smallmatrix} +0,5 \\ -1,5 \end{smallmatrix}$ % discard the batch and re-mix.
- j) Condition the batch for 2 h to 24 h after mixing and prior to vulcanizing if possible at standard temperature and humidity as defined in ISO 471.

6 Evaluation of vulcanization characteristics by a curemeter test

Warning — Formation of nitrosamines is possible during the cure.

6.1 Using an oscillating disc curemeter

Measure the following standard test parameters:

M_L , M_H , t_{s1} , $t'_c(50)$ and $t'_c(90)$ (see ISO 3417) using the following test conditions:

- oscillation frequency: 1,7 Hz (100 cycles per minute)
- amplitude of oscillation: 1° arc
- selectivity at M_H : to be chosen to give at least 75 % of full scale deflection

NOTE With some rubbers, 75 % may not be attainable.

- die temperature: 160 °C ± 0,3 °C
- pre-heat time: none

6.2 Using a rotorless curemeter

Measure the following standard test parameters:

F_L , F_{max} at defined time, $t'_c(50)$ and $t'_c(90)$.

in accordance with ISO 6502 using the following test conditions :

- oscillation frequency: 1,7 Hz (100 cycles per minute)
- amplitude of oscillation: 0,5° arc
- selectivity: to be chosen to give at least 75 % of full scale deflection at F_{max} .

NOTE With some rubbers, 75 % may not be attainable.

- die temperature: 160 °C ± 0,3 °C
- pre-heat time: none

7 Evaluation of tensile stress-strain properties of vulcanized test mixes

Vulcanize sheets at 135 °C for three periods chosen from a cure series of, 20 min, 30 min, 40 min and 60 min.

The three periods of cure shall be chosen to cover the undercure, optimum cure and overcure of the material under test.

Condition the vulcanized sheets for 16 h to 96 h at a standard temperature and, if possible, a standard humidity, as defined in ISO 471.

Measure the stress-strain properties in accordance with ISO 37.

8 Precision

8.1 General

Precision calculations are based on data from ASTM committee E11, E691 procedure.

NOTE References to ASTM standards have been replaced by reference to corresponding ISO standards.

The precision calculations to express repeatability and reproducibility were performed in accordance with ISO/TR 9272.

8.2 Precision details

A type 2 (interlaboratory) precision was evaluated for cure characteristics using an oscillating disc curemeter.

A sample of isoprene rubber was used in the interlaboratory programme; this was tested in five laboratories on three different days using mill mixing procedure (procedure A).

8.3 Precision results

The results of the precision calculations for repeatability and reproducibility are given in Table 2.

The symbols used in Table 2 are defined as follows:

r is the repeatability, in measurement units. This is the value below which the absolute difference between two "within-laboratory" test results may be expected to lie with a specified probability.

(r) is the relative repeatability, in percent.

The test results are obtained with the same method on nominally identical test material under the same conditions (same operator, apparatus and laboratory) and within a specified time period; unless stated otherwise, the probability is 95 %.

R is the reproducibility, in measurement units. This is the value below which the absolute difference between two "between-laboratory" test results may be expected to lie with a specified probability.

(R) is the relative reproducibility, in percent.

The test results are obtained with the same method on nominally identical test material under different conditions (different laboratories, operators and apparatus) and within a specified time period; unless stated otherwise, the probability is 95 %.

Table 2 — Type 2 Precision for various test parameters

Property	Units	Mean level ^a	Within laboratory			Between laboratories		
			S_r ^b	r	(r)	SR ^c	R	(R)
M_L	dN·m	6,05	0,15	0,40	6,61	0,36	1,01	16,69
M_H	dN·m	39,87	0,25	0,69	1,73	1,73	4,86	12,19
t_{s1}	min	3,19	0,19	0,53	16,61	0,36	1,00	31,35
$t'_{c(50)}$	min	4,97	0,07	0,20	4,02	0,14	0,39	7,85
$t'_{c(90)}$	min	7,09	0,08	0,23	3,24	0,10	0,28	3,95
^a Measured at 160 °C, 1,7 Hz, 1° amplitude arc — midpoint of range used for (r) (R) calculations. ^b Repeatability standard deviation, in measurement units. ^c Reproducibility standard deviation, in measurement units.								

9 Test report

The test report shall include the following information:

- a) reference to this International Standard i.e., ISO 2303;
- b) all details necessary for the identification of the sample;
- c) the time and temperature conditions used for the Mooney viscosity determination, and whether a massing process was used;
- d) the method used for the ash determination (method A or B of ISO 247);
- e) the standard test formulation used;
- f) the reference materials used;
- g) the mixing procedure used (method A or B);
- h) the conditioning conditions used in 5.2.2.2 j), or 5.2.2.3 j);
- i) for clause 6:
 - 1) the reference standard;
 - 2) the time for M_H ;
 - 3) the amplitude of oscillation used for the curemeter test;
- j) the vulcanization periods used in clause 7;
- k) any unusual features noted during the determination;
- l) any operation not included in this International Standard or in the International Standards to which reference is made, as well as any operation regarded as optional;
- m) the results and the units in which they have been expressed;
- n) the date of the test.

Annex A (informative)

Alternative mixing method by internal mixer-mill mixing procedure

A.1 General

A third mixing method by Internal mixing for initial and mill for final mixing can be used by agreement between the interested parties.

A.2 Procedure

A.2.1 Initial mixing procedure

	Duration (min)	Cumulative time (min)
a) Adjust the temperature of the internal mixer to achieve a final mix temperature of 170 °C in about 6 min. Close the discharge door, set the rotors at 8 rad/s (77 r/min), start the rotors and raise the ram.		
b) Load half of the rubber, all the carbon black, zinc oxide and stearic acid, then the remaining half of the rubber. Lower the ram.	0,5	0,5
c) Allow the batch to mix.	3,0	3,5
d) Raise the ram and clean the feeding hopper and the top of the ram. Lower the ram.	0,5	4,0
e) Discharge the batch when the temperature reaches 170 °C or after 6 min.	2,0	6,0
Total time (max)		6,0

- f) Immediately pass the batch three times through a laboratory mill with a mill opening of 6 mm and a temperature of 70 °C $\pm$ 5 °C. Check-weigh the batch (see ISO 2393). If the mass of the batch differs from the theoretical value by more than $\begin{smallmatrix} +0,5 \\ -1,5 \end{smallmatrix}$ % discard the batch and re-mix.
- g) Condition the batch for 2 h to 24 h after mixing and prior to vulcanizing, if possible at standard temperature and humidity as defined in ISO 471.

A.2.2 Final mill mixing procedure

A good rolling bank at the nip of the rolls shall be maintained during mixing. If this is not obtained with the nip settings specified hereunder, small adjustments to the mill openings may be necessary.

The standard laboratory mill batch mass, in grams, shall be based on twice the formulation mass.