



INTERNATIONAL STANDARD ISO 2475:1999 TECHNICAL CORRIGENDUM 1

Published 2001-06-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Chloroprene rubber (CR) — General-purpose types — Evaluation procedure

TECHNICAL CORRIGENDUM 1

Caoutchouc chloroprène (CR) — Types à usage général — Méthode d'évaluation

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to International Standard ISO 2475:1999 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

Table 1

Replace the existing table with the following:

Table 1 — Standard test formulation for evaluation of sulfur-modified chloroprene rubbers

Material	Parts by mass
Chloroprene rubber (CR), sulfur-modified	100,00
Stearic acid ^a	0,50
Magnesium oxide ^b	4,00
Carbon black ^c	25,00
Zinc oxide ^d	5,00
Total	134,50
^a See ISO 8312. ^b The surface area of the magnesium oxide shall be between 130 m²/g and 200 m²/g. Magnesium oxide will absorb water and carbon dioxide when exposed to air and this can affect its activity in compounds. Store it in a dry environment. ^c The current industry reference black (IRB), or an equivalent national or international standard reference material, shall be used. ^d Class B1a (see ISO 9298:1995, annex D).	